



SLOVENSKI STANDARD
oSIST prEN ISO 24023-2:2019
01-maj-2019

Polimerni materiali - Materiali na osnovi mehčanega polivinilklorida (PVC-P) za oblikovanje in ekstrudiranje - 2. del: Priprava preskušancev in ugotavljanje lastnosti (ISO/DIS 24023-2:2019)

Plastics - Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO/DIS 24023-2:2019)

Kunststoffe - Weichmacherhaltige Polyvinylchlorid(PVC-P)-Werkstoffe - Teil 2: Herstellung von Probekörpern und Bestimmung von Eigenschaften (ISO/DIS 24023-2:2019)

<https://standards.iteh.ai/catalog/standards/sist/6523d8c7-cc54-4f74-b505-721d0eb47304/sist-en-iso-24023-2-2020>

Plastiques - Matériaux à base de poly(chlorure de vinyle) plastifié (PVC-P) pour moulage et extrusion - Partie 2: Préparation des éprouvettes et détermination des propriétés (ISO/DIS 24023-2:2019)

Ta slovenski standard je istoveten z: prEN ISO 24023-2

ICS:

83.080.20 Plastomeri Thermoplastic materials

oSIST prEN ISO 24023-2:2019 **en,fr,de**

DRAFT INTERNATIONAL STANDARD

ISO/DIS 24023-2

ISO/TC 61/SC 9

Secretariat: **KATS**Voting begins on:
2019-03-15Voting terminates on:
2019-06-07

Plastics — Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials —

Part 2:

Preparation of test specimens and determination of properties

*Plastiques — Matériaux à base de poly(chlorure de vinyle) plastifié (PVC-P) pour moulage et extrusion —
Partie 2: Préparation des éprouvettes et détermination des propriétés*

ICS: 83.080.20

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 24023-2:2020](https://standards.iteh.ai/catalog/standards/sist/6523d8c7-cc54-4f74-b505-721d0eb47304/sist-en-iso-24023-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/6523d8c7-cc54-4f74-b505-721d0eb47304/sist-en-iso-24023-2-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 24023-2:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 24023-2:2020

<https://standards.iteh.ai/catalog/standards/sist/6523d8c7-cc54-4f74-b505-721d0eb47304/sist-en-iso-24023-2-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Preparation of test specimens	2
4.1 General.....	2
4.2 Treatment of the material before moulding.....	2
4.3 Compression moulding.....	2
5 Conditioning of test specimens	3
6 Determination of properties	3
Annex A (normative) Detailed description of the preparation of test specimens	5

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 24023-2:2020](https://standards.iteh.ai/catalog/standards/sist/6523d8c7-cc54-4f74-b505-721d0eb47304/sist-en-iso-24023-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/6523d8c7-cc54-4f74-b505-721d0eb47304/sist-en-iso-24023-2-2020>

ISO/DIS 24023-2:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This first edition cancels and replaces ISO 2898-2:2008, which has been technically revised.

The main changes compared to the previous edition are as follows:

- ISO 3167 is replaced by ISO 20753.
- IEC 60093 is replaced by the new edition of IEC 62631-3-1, IEC 62631-3-2.

A list of all parts in the ISO ##### series can be found on the ISO website.

Plastics — Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials —

Part 2: Preparation of test specimens and determination of properties

1 Scope

This part of ISO ##### specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of PVC-P moulding and extrusion materials. Requirements for handling test materials and for conditioning both the test material before moulding and the specimens before testing are given.

Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize PVC-P moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this part of ISO #####, as are the designatory properties specified in ISO #####.

In order to obtain reproducible and comparable test results, it is necessary to use the methods of preparation and conditioning, the specimen dimensions and the test procedures specified herein. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 176, *Plastics — Determination of loss of plasticizers — Activated carbon method*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 458-2, *Plastics — Determination of stiffness in torsion of flexible materials — Part 2: Application to plasticized compounds of homopolymers and copolymers of vinyl chloride*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO/DIS 24023-2:2019(E)

ISO 3451-5, *Plastics — Determination of ash — Part 5: Poly(vinyl chloride)*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

ISO. 1, *Plastics — Plasticized polyvinyl chloride) (PVC-P) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 20753, *Plastics — Test specimens*

IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials — Part 3-1: Determination of resistive properties (DC methods) — Volume resistance and volume resistivity — General method*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Preparation of test specimens**4.1 General**

It is essential that specimens are always prepared by the same procedure (compression moulding), using the same processing conditions.

The material shall be kept in moisture-proof containers until it is required for use.

4.2 Treatment of the material before moulding

Before processing, no pretreatment of the material sample is normally necessary.

4.3 Compression moulding

Before compression moulding, the material shall be plasticized using a two-roll mill under the conditions specified in [Table 1](#).

Sheet material from the mill shall be stacked, preferably with sheet orientation alternating from layer to layer, in the preheated mould. Compression- moulded sheets shall then be prepared in accordance with ISO 293, using the conditions specified in [Table 2](#).

Table 1 — Conditions for milling of material before compression moulding

Shore hardness of material	Roll surface temperature °C	Milling time ^a min	Roll surface speed m/min	Speed ratio	Roll nip width mm	Roll diameter mm	Roll length mm
Up to A 80	130 to 160	Approx. 5	Approx. 10	1:1,2	Approx. 1	e.g. 150	e.g. 300
D 35 to D 50	145 to 170	Approx. 5	Approx. 10	1:1,2	Approx. 1	e.g. 150	e.g. 300
Above D 50	160 to 175	Approx. 5	Approx. 10	1:1,2	Approx. 1	e.g. 150	e.g. 300

^a Measured from the moment when a sheet is formed.

Table 2 — Conditions for compression moulding of test specimens

Shore hardness of material	Moulding temperature °C	Average cooling rate °C/min	Demoulding temperature °C	Full pressure MPa	Full-pressure time min	Preheating pressure MPa	Preheating time min
Up to A 80	130 to 160	Not defined	Approx. 40 ^a	2 to 10	2 to 5	Approx. 0,3	Max. 5
D 35 to D 50	145 to 175	Not defined	Approx. 40 ^a	2 to 10	2 to 5	Approx. 0,3	Max. 5
Above D 50	170 to 180	Not defined	Approx. 40 ^a	2 to 10	2 to 5	Approx. 0,3	Max. 5

^a Very soft materials may require a lower temperature.

The test specimens required for the determination of the properties shall be machined from the compression-moulded sheets in accordance with ISO 2818 or stamped.

For additional details on test specimen preparation, see [Annex A](#).

5 Conditioning of test specimens

The test specimens for all determinations shall be conditioned in accordance with ISO 291 for at least 48 h at 23 °C ± 2 °C and (50 ± 10) % relative humidity.

6 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350-1 shall be applied. All tests shall be carried out in the standard atmosphere of 23 °C ± 2 °C and (50 ± 10) % relative humidity unless specifically stated otherwise in [Tables 3](#) and [4](#).

[Table 3](#) is compiled from ISO 10350-1, and the properties listed are those which are appropriate to PVC-P moulding and extrusion materials. These properties are those considered useful for comparisons of data generated for different thermoplastics.

[Table 4](#) contains those properties, not found specifically in [Table 3](#), which are in wide use or of particular significance in the practical characterization of PVC-P moulding and extrusion materials.

Table 3 — General properties and test conditions (selected from ISO 10350-1)

Property	Unit	Standard	Specimen type (dimensions in mm)	Test conditions and supplementary instructions
Mechanical properties				
Tensile stress at 50 % strain	MPa	ISO 527-1 ISO 527-2	ISO 20753 Type A2 specimen	Test speed 50 mm/min
Electrical properties				
Volume resistivity	Ω·m	IEC 62631-3-1	≥ 100 × ≥ 100 × (1±0,5)	Voltage 100 V
Other properties				
Density ^a	kg/m ³	ISO 1183-1	At least 1 g	Method A or B Report the result to two decimal places

^a Designatory property.

ISO/DIS 24023-2:2019(E)

Table 4 — Additional properties and test conditions of particular utility to PVC-P moulding and extrusion materials

Property	Unit	Standard	Specimen type (dimensions in mm)	Test conditions and supplementary instructions
Mechanical properties				
Tensile stress at 100 % elongation	MPa	ISO 527-1 ISO 527-2	Type 1BA specimen Thickness 2 mm	Test speed 500 mm/min
Shore A or D hardness ^a	—	ISO 868	Disc of diameter 50 mm or square 50 mm × 50 mm specimen Thickness 4 mm or 6 mm (type A: 6mm only)	Force applied to specimen 50 N Take reading after 15 s ± 1 s Use Shore D if Shore A hardness ≥ 85
Thermal properties				
Torsional stiffness as a function of temperature ^a	°C	ISO 458-2	60 mm × 60 mm × 2 mm For very flexible compounds, use a 60 mm × 60 mm × 4 mm specimen at high temperatures of test.	The values of the torsional stiffness are plotted as a function of temperature. The two temperatures at which the stiffness in torsion has values of 300 MPa and 4,1 MPa are TST 300 and TST 4,1, respectively. For ISO #####-1, TST = 300.
Other properties				
Sulfated ash	% (by mass)	ISO 3451-5	Pellets	Method B
Loss of plasticizers	% (by mass)	ISO 176	Disc of diameter 50 mm and thickness 1 mm	Method B
^a Designatory property.				

<https://standards.iteh.ai/catalog/standards/sist/6523d8c7-cc54-4f74-b505-721d0eb47304/sist-en-iso-24023-2-2020>