

SLOVENSKI STANDARD
oSIST prEN ISO 24026-2:2019
01-junij-2019

Polimerni materiali - Materiali na osnovi polimetilmetakrilata (PMMA) za oblikovanje in ekstrudiranje - 2. del: Priprava preskušancev in ugotavljanje lastnosti (ISO/DIS 24026-2:2019)

Plastics - Poly(methyl methacrylate) (PMMA) moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO/DIS 24026-2:2019)

Kunststoffe - Polymethylmethacrylat (PMMA)-Werkstoffe - Teil 2: Herstellung von Probekörpern und Bestimmung von Eigenschaften (ISO/DIS 24026-2:2019)

Plastiques - Matériaux à base de poly(méthacrylate de méthyle) (PMMA) pour moulage et extrusion - Partie 2: Préparation des éprouvettes et détermination des propriétés (ISO/DIS 24026-2:2019)

Ta slovenski standard je istoveten z: prEN ISO 24026-2

ICS:

83.080.20 Plastomeri Thermoplastic materials

oSIST prEN ISO 24026-2:2019 **en,fr,de**

DRAFT INTERNATIONAL STANDARD

ISO/DIS 24026-2

ISO/TC 61/SC 9

Secretariat: **KATS**Voting begins on:
2019-03-25Voting terminates on:
2019-06-17

Plastics — Poly(methyl methacrylate) (PMMA) moulding and extrusion materials —

Part 2:

Preparation of test specimens and determination of properties

*Plastiques — Poly(méthacrylate de méthyle) (PMMA) pour moulage et extrusion —**Partie 2: Préparation des éprouvettes et détermination des propriétés*

ICS: 83.080.20

iTeh STANDARD PREVIEW
(standards.iteh.ai)[SIST EN ISO 24026-2:2020](https://standards.iteh.ai/catalog/standards/sist/dfb8a4bc-6a44-4a9d-a4ea-7bf54be99cb9/sist-en-iso-24026-2-2020)<https://standards.iteh.ai/catalog/standards/sist/dfb8a4bc-6a44-4a9d-a4ea-7bf54be99cb9/sist-en-iso-24026-2-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 24026-2:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 24026-2:2020

<https://standards.iteh.ai/catalog/standards/sist/dfb8a4bc-6a44-4a9d-a4ea-7bf54be99cb9/sist-en-iso-24026-2-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Preparation of test specimens	2
4.1 General.....	2
4.2 Treatment of the material before moulding.....	2
4.3 Moulding of specimens.....	3
4.3.1 General requirements.....	3
4.3.2 Melt temperature.....	3
4.3.3 Mould temperature.....	4
4.3.4 Average melt velocity.....	4
4.3.5 Hold pressure.....	4
4.3.6 Cooling time.....	4
5 Conditioning of test specimens	4
6 Determination of properties	4

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 24026-2:2020

<https://standards.iteh.ai/catalog/standards/sist/dfb8a4bc-6a44-4a9d-a4ea-7bf54be99cb9/sist-en-iso-24026-2-2020>

ISO/DIS 24026-2:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This first edition of ISO XXXXX-2 cancels and replaces ISO 24026-2:2001, which has been technically revised. <https://standards.iteh.ai/catalog/standards/sist/dfb8a4bc-6a44-4a9d-a4ea-7bf54be99cb9/sist-en-iso-24026-2-2020>

ISO XXXXX consists of the following parts, under the general title *Plastics — Poly(methyl methacrylate) (PMMA) moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

A list of all parts in the ISO XXXXX series can be found on the ISO website.

Plastics — Poly(methyl methacrylate) (PMMA) moulding and extrusion materials —

Part 2: Preparation of test specimens and determination of properties

1 Scope

1.1 This part of ISO XXXXX specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of Poly(methyl methacrylate)PMMA moulding and extrusion materials. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given here.

1.2 Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize Poly(methyl methacrylate) moulding and extrusion materials are listed.

1.3 The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this document, as are the designatory properties specified in ISO XXXXX-1.

1.4 In order to obtain reproducible and comparable test results, it is necessary to use the methods of specimen preparation and conditioning, the specimen dimensions and the test procedures specified in this document. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 175, *Plastics — Methods of test for the determination of the effects of immersion in liquid chemicals*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 180, *Plastics — Determination of Izod impact strength*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO/DIS 24026-2:2019(E)

ISO 489, *Plastics — Determination of refractive index*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 604, *Plastics — Determination of compressive properties*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1628-6, *Plastics — Determination of viscosity number and limiting viscosity number — Part 6: Methyl methacrylate polymers*

ISO 2039-1, *Plastics — Determination of hardness — Part 1: Ball indentation method*

ISO 2039-2, *Plastics — Determination of hardness — Part 2: Rockwell hardness*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 6721-2, *Plastics — Determination of dynamic mechanical properties — Part 2: Torsion-pendulum method*

ISO 24026-1, *Plastics — Poly(methyl methacrylate) (PMMA) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

ISO 13468-1, *Plastics — Determination of the total luminous transmittance of transparent materials — Part 1: Single-beam instrument*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Preparation of test specimens

4.1 General

It is essential that specimens always be prepared by the same procedure (injection moulding), using the same processing conditions.

4.2 Treatment of the material before moulding

Before processing, the moisture content of the material sample shall not exceed 0,05% by mass. If the moisture level exceeds this limit, the sample shall be dried in accordance with the manufacturer's instructions until the moisture content no longer exceeds the limit.

4.3 Moulding of specimens

4.3.1 General requirements

The specimens shall be prepared by injection moulding in accordance with ISO 294-1, using the conditions specified in [4.3.2](#) to [4.3.6](#).

4.3.2 Melt temperature

4.3.2.1 General

PMMA moulding compounds are designated using a code-number representing the value of the Vicat softening temperature (VST), a code-number representing the value of the melt mass-flow rate (MFR) and, optionally, a code-number representing the value of the viscosity number (VN). For details of this designation system, in particular the code-numbers used, see ISO 24026-1. In those cases where the designation only includes code-numbers for VST and MFR, the melt temperature used for moulding test specimens may be determined from the MFR code-number (see [4.3.2.2](#)). If the code-number for VN is also used in the designation, the melt temperature may also be determined from the VST and VN code-numbers (see [4.3.2.3](#)). It should be noted that, for moulding compounds with MFR values lying between 1 g/10 min (code-number 015) and 16 g/10 min (code-number 120), there is little difference in the melt temperatures calculated from the MFR code-number and those calculated from the VST and VN code-numbers. However, for moulding compounds outside this range, the melt temperature shall be determined only from the VST and VN code-numbers.

When preparing specimens, the melt temperature shall be kept constant to within ± 3 °C.

4.3.2.2 Melt temperature determined from MFR code-number

Select the appropriate melt temperature from Table 1.

Table 1 — Melt temperature as function of MFR code-number

MFR code-number	Melt temperature °C
005	270
015	260
030	250
060	240
120	230
240	220

EXAMPLE

Moulding-compound designation: ISO 24026-PMMA,MLN,108-030

Melt temperature = 250°C

4.3.2.3 Melt temperature determined from VST and VN code-numbers

Calculate the melt temperature, in degrees Celsius, from the equation

$$\text{Melt temperature} = \text{VST code-number} + 130 + a_{\text{VN}}$$

where a_{VN} is a number which depends on the VN code-number as shown in [Table 3](#).

ISO/DIS 24026-2:2019(E)

Table 2 — Value of a_{VN} as a function of VN code-number

VN code-number	a_{VN}
43	0
53	10
63	20
73	30
83	40
93	50

EXAMPLE

Moulding-compound designation: ISO 24026-PMMA,MLN,108-030-53

Melt temperature = $108+130+10=248^{\circ}\text{C}$

4.3.3 Mould temperature

Calculate the mould temperature, in degrees Celsius, from the equation

Mould temperature = VST code-number -40

The mould temperature shall be kept constant to within $\pm 3^{\circ}\text{C}$.

EXAMPLE

Moulding-compound designation: ISO 24026-PMMA,MLN,108-030-53

Mould temperature = 68°C

4.3.4 Average melt velocity

Set the injection pressure to given an average melt velocity of $200\text{ mm/s} \pm 100\text{ mm/s}$.

4.3.5 Hold pressure

Set the hold pressure to a value such that test specimens with only very slight sink marks are obtained.

4.3.6 Cooling time

Use a cooling time of $50\text{s} \pm 5\text{s}$.

5 Conditioning of test specimens

Test specimens shall be conditioned in an oven for 16 h at a temperature of (VST code-number-25) $^{\circ}\text{C}$. The conditioning temperature shall be kept constant to within $\pm 3^{\circ}\text{C}$.

After conditioning in the oven, the specimens shall be further conditioned for at least 24 h at $(23 \pm 2)^{\circ}\text{C}$ and $(50 \pm 10)\%$ relative humidity, except for specimens to be used for the determination of certain thermal and "other" properties, as given in [table 2](#) and [3](#), which, after conditioning in the oven, shall be allowed to cool for at least 1 h at $(23 \pm 2)^{\circ}\text{C}$ in a desiccator. Testing shall be performed immediately after the specimens are removed from the desiccator.

6 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350-1 shall be applied. All tests shall be carried out in the standard