

**SLOVENSKI STANDARD
SIST EN ISO 21304-2:2021****01-marec-2021****Nadomešča:****SIST EN ISO 11542-2:2000****SIST EN ISO 11542-2:2000/AC:2009**

Polimerni materiali - Materiali na osnovi polietilena z ultra visoko molsko maso (PE-UHMW) za oblikovanje in ekstrudiranje - 2. del: Priprava preskušancev in ugotavljanje lastnosti (ISO 21304-2:2021)

Plastics - Ultra-high-molecular-weight polyethylene (PE-UHMW) moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO 21304-2:2021)

(standards.iteh.ai)

Kunststoffe - Ultrahochmolekulare Polyethylen (PE-UHMW)-Werkstoffe - Teil 2: Herstellung von Probekörpern und Bestimmung von Eigenschaften (ISO 21304-2:2021)

<https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021>

Plastiques - Matériaux à base de polyéthylène à très haute masse moléculaire (PE-UHMW) pour moulage et extrusion - Partie 2: Préparation des éprouvettes et détermination des propriétés (ISO 21304-2:2021)

Ta slovenski standard je istoveten z: EN ISO 21304-2:2021

ICS:

83.080.20

Plastomeri

Thermoplastic materials

SIST EN ISO 21304-2:2021**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 21304-2:2021](https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021>

EUROPEAN STANDARD

EN ISO 21304-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2021

ICS 83.080.20

Supersedes EN ISO 11542-2:1998

English Version

Plastics - Ultra-high-molecular-weight polyethylene (PE-UHMW) moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO 21304-2:2021)

Plastiques - Matériaux à base de polyéthylène à très haute masse moléculaire (PE-UHMW) pour moulage et extrusion - Partie 2: Préparation des éprouvettes et détermination des propriétés (ISO 21304-2:2021)

Kunststoffe - Ultrahochmolekulare Polyethylen (PE-UHMW)-Werkstoffe - Teil 2: Herstellung von Probekörpern und Bestimmung von Eigenschaften (ISO 21304-2:2021)

This European Standard was approved by CEN on 9 January 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 21304-2:2021](https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021)
<https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021>

European foreword

This document (EN ISO 21304-2:2021) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2021, and conflicting national standards shall be withdrawn at the latest by July 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11542-2:1998.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 21304-2:2021 has been approved by CEN as EN ISO 21304-2:2021 without any modification.

[SIST EN ISO 21304-2:2021
https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021](https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 21304-2:2021](https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021>

INTERNATIONAL
STANDARD

ISO
21304-2

First edition
2021-01

Plastics — Ultra-high-molecular-weight polyethylene (PE-UHMW) moulding and extrusion materials —

**Part 2:
Preparation of test specimens and
determination of properties**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Plastiques — Matériaux à base de polyéthylène à très haute masse moléculaire (PE-UHMW) pour moulage et extrusion —

Partie 2: Préparation des éprouvettes et détermination des propriétés

<https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021>



Reference number
ISO 21304-2:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 21304-2:2021](https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	3
4 Preparation of test specimens.....	3
4.1 Treatment of the material before moulding.....	3
4.2 Compression moulding.....	3
5 Conditioning of test specimens.....	4
6 Determination of properties.....	4
Annex A (normative) Method for determining the melt volume-flow rate of PE-UHMW materials... 8	8
Annex B (normative) Method for determining the elongational stress of PE-UHMW moulding materials.....	11
Annex C (normative) Method for determining the Charpy double-notched impact strength of PE-UHMW moulding material.....	17
Bibliography.....	20

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 21304-2:2021](https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/e0330f3c-5429-49f0-aa6f-1c8c007d4f28/sist-en-iso-21304-2-2021>

ISO 21304-2:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition of ISO 21304-2 cancels and replaces ISO 11542-2:1998, which has been technically revised. It also incorporates the Technical Corrigendum ISO 11542-2:1998/Cor 1:2007.

The main changes compared to the previous edition are as follows:

- updated the normative references to the latest version;
- added terms and definitions (see [Clause 3](#));
- revised the contents and structures of [Table 2](#) and [Table 3](#) according to the revised ISO 10350-1;
- added new [Annex A](#);
- revised the masses of weights used to load specimen in [Table B.1](#) (former Table A.1);
- revised [Figure B.1](#), [Figure B.2](#), [Figure B.3](#) and [Figure C.1](#) (former Figures A.1, A.2, A.3 and B.1).

A list of all parts in the ISO 21304 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Ultra-high-molecular-weight polyethylene (PE-UHMW) moulding and extrusion materials —

Part 2: Preparation of test specimens and determination of properties

1 Scope

This document specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of PE-UHMW moulding and extrusion materials. It gives the requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing.

This document gives the procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made. Properties and test methods which are suitable and necessary to characterize PE-UHMW moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for or of particular significance to these moulding and extrusion materials are also included in this document, as are the designatory properties specified in ISO 21304-1. This document specifies the materials with MFR less than 0,1 g/10 min at 190 °C/21,6 kg based on ISO 17855-1.

The methods of preparation and conditioning, the specimen dimensions and the test procedures specified in this document are used in order to obtain reproducible and comparable test results. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-1, *Plastics — Determination of temperature of deflection under load — Part 1: General test method*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 21304-2:2021(E)

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastics composites*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 1628-3, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 3: Polyethylenes and polypropylenes*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 8256, *Plastics — Determination of tensile-impact strength*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and step height*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 15527, *Plastics — Compression-moulded sheets of polyethylene (PE-UHMW, PE-HD) — Requirements and test methods*

ISO 20753, *Plastics — Test specimens*

ISO 21304-1, *Plastics — Ultra-high-molecular-weight polyethylene (PE-UHMW) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*

ISO/IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*

IEC 62631-2-1, *Dielectric and resistive properties of solid insulating materials-Part 2-1:Relative permittivity and dissipation factor-Technical frequencies (0,1 Hz to 10 MHz)-AC Methods*

IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials — Part 3-1: Determination of resistive properties (DC methods) — Volume resistance and volume resistivity — General method*