

SLOVENSKI STANDARD SIST EN IEC 61788-23:2021

01-december-2021

Nadomešča:

SIST EN IEC 61788-23:2018

Superprevodnost - 23. del: Meritve deleža preostale upornosti - Razmerje preostale upornosti niobijskih superprevodnikov (IEC 61788-23:2021)

Superconductivity - Part 23: Residual resistance ratio measurement - Residual resistance ratio of cavity-grade Nb superconductors (IEC 61788-23:2021)

Supraleitfähigkeit - Teil 23 Messung des Restwiderstandsverhältnisses - Restwiderstandsverhältnis von hochreinen Nb Supraleitern für Kavitäten (IEC 61788-23:2021) (standards.iteh.ai)

Supraconductivité - Partie 23: Mesurage du rapport de résistance résiduelle - Rapport de résistance résiduelle des supraconducteurs de Nb à cavités (IEC 61788-23:2021)

Ta slovenski standard je istoveten z: EN IEC 61788-23:2021

ICS:

17.220.20 Merjenje električnih in Measurement of electrical

magnetnih veličin and magnetic quantities

29.050 Superprevodnost in prevodni Superconductivity and

materiali conducting materials

SIST EN IEC 61788-23:2021 en

SIST EN IEC 61788-23:2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN IEC 61788-23:2021

https://standards.iteh.ai/catalog/standards/sist/3615cdc7-1807-4539-ad51-b80fb3797d1f/sist-en-iec-61788-23-2021

EUROPEAN STANDARD NORME EUROPÉENNE **EN IEC 61788-23**

EUROPÄISCHE NORM

October 2021

ICS 17.220; 29.050

Supersedes EN IEC 61788-23:2018 and all of its amendments and corrigenda (if any)

English Version

Superconductivity - Part 23: Residual resistance ratio measurement - Residual resistance ratio of cavity-grade Nb superconductors (IEC 61788-23:2021)

Supraconductivité - Partie 23: Mesurage du rapport de résistance résiduelle - Rapport de résistance résiduelle des supraconducteurs de Nb à cavités (IEC 61788-23:2021)

Supraleitfähigkeit - Teil 23: Messung des Restwiderstandsverhältnisses - Restwiderstandsverhältnis von hochreinen Nb Supraleitern für Kavitäten (IEC 61788-23:2021)

This European Standard was approved by CENELEC on 2021-09-27. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member II Q a r Q S . I L Q

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions. dards iteh avcatalog/standards/sist/3615cdc/-180/-4539-ad51-

b80fb3797d1f/sist-en-iec-61788-23-2021

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN IEC 61788-23:2021 (E)

European foreword

The text of document 90/478/FDIS, future edition 2 of IEC 61788-23, prepared by IEC/TC 90 "Superconductivity" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 61788-23:2021.

The following dates are fixed:

- latest date by which the document has to be implemented at national (dop) 2022-06-27 level by publication of an identical national standard or by endorsement
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2024-09-27

This document supersedes EN IEC 61788-23:2018 and all of its amendments and corrigenda (if any).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national committee. A complete listing of these bodies can be found on the CENELEC website.

iTeh STANDARD PREVIEW Endorsement notice (standards.iteh.ai)

The text of the International Standard IEC 61788-23:2021 was approved by CENELEC as a European Standard without any modification. 80fb3797d1f/sist-en-icc-61788-23-2021

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 61788-4 NOTE Harmonized as EN IEC 61788-4 IEC 61788-10 NOTE Harmonized as EN 61788-10

EN IEC 61788-23:2021 (E)

Annex ZA

(normative)

Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

PublicationYearTitleEN/HDYearIEC 60050-815-International Electrotechnical Vocabulary ---Part 815: Superconductivity

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN IEC 61788-23:2021 https://standards.iteh.ai/catalog/standards/sist/3615cdc7-1807-4539-ad51-b80fb3797d1f/sist-en-iec-61788-23-2021 SIST EN IEC 61788-23:2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN IEC 61788-23:2021

https://standards.iteh.ai/catalog/standards/sist/3615cdc7-1807-4539-ad51-b80fb3797d1f/sist-en-iec-61788-23-2021



IEC 61788-23

Edition 2.0 2021-08

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Superconductivity Teh STANDARD PREVIEW

Part 23: Residual resistance ratio measurement – Residual resistance ratio of cavity-grade Nb superconductors

SIST EN IEC 61788-23:2021

Supraconductivité//standards.iteh.ai/catalog/standards/sist/3615cdc7-1807-4539-ad51-

Partie 23: Mesurage du rapport de résistance résiduelle – Rapport de résistance résiduelle des supraconducteurs de Nb à cavités

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

ICS 17.220; 29.050 ISBN 978-2-8322-1011-5

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREW	ORD	4
INTROD	UCTION	6
1 Sco	pe	7
2 Nor	mative references	7
3 Terr	ms and definitions	7
4 Prin	ciple	8
5 Mea	asurement apparatus	9
5.1	Mandrel or base plate	9
5.2	Cryostat and support of mandrel or base plate	9
6 Spe	cimen preparation	10
7 Data	a acquisition and analysis	11
7.1	Data acquisition hardware	11
7.2	Resistance (R ₁) at room temperature	11
7.3	Residual resistance (R_2) just above the superconducting transition	11
7.4	Validation of the residual resistance measurement	13
7.5	Residual resistance ratio	13
8 Unc	ertainty of the test method A.N.D.A.R.D. P.R.E.V.I.E.W.	13
9 Tes	t report	13
9.1	t report(standards.iteh.ai) General	13
9.2	Test informationSIST EN IEC 61788-23 2021	13
9.3	Specimentinformationtch.ai/catalog/standards/sist/3615cdc7-1807-4539-ad51	
9.4	Test conditions b80fb3797d1f/sist-en-iec-61788-23-2021	
9.5	RRR value	
	(informative) Additional information relating to the measurement of RRR	
A.1	Considerations for specimens and apparatus	
A.2	Considerations for specimen mounting orientation	16
A.3	Alternative methods for increasing temperature of specimen above superconducting transition temperature	
A.3.		
	2 Heater method	
A.3.		
A.4	Other test methods	
A.4. A.4.		_
A.4. A.4.		
A.4.	·	
A.4.	•	
A.4.		
Annex B	(informative) Uncertainty considerations	19
B.1	Overview	19
B.2	Definitions	19
B.3	Consideration of the uncertainty concept	20
B.4	Uncertainty evaluation example for IEC TC 90 standards	22
	(informative) Uncertainty evaluation for resistance ratio measurement of Nb	24

– 3 –

IEC 61788-23:2021 © IEC 2021

C.1 Evaluation of uncertainty	24
C.1.1 Room temperature measurement uncertainty	24
C.1.2 Cryogenic measurement uncertainty	25
C.1.3 Estimation of uncertainty for typical experimental conditions	27
C.2 Inter-laboratory comparison summary	28
Bibliography	29
Figure 1 – Relationship between temperature and resistance near the superconducting transition	8
Figure A.1 – Determination of the value of R_2 from a resistance versus time plot	
Figure C.1 – Graphical description of the uncertainty of regression related to the measurement of R_2	27
Table B.1 – Output signals from two nominally identical extensometers	20
Table B.2 – Mean values of two output signals	20
Table B.3 – Experimental standard deviations of two output signals	21
Table B.4 – Standard uncertainties of two output signals	21
Table B.5 – Coefficients of variation of two output signals	21
Table C.1 – Uncertainty of measured parameters Table C.2 – RRR values obtained by inter-laboratory comparison using liquid helium	27 28
(standards.iteh.ai)	

SIST EN IEC 61788-23:2021 https://standards.iteh.ai/catalog/standards/sist/3615cdc7-1807-4539-ad51b80fb3797d1f/sist-en-iec-61788-23-2021

– 4 –

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY -

Part 23: Residual resistance ratio measurement – Residual resistance ratio of cavity-grade Nb superconductors

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity; independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 61788-23 has been prepared by IEC technical committee 90: Superconductivity. It is an International Standard.

This second edition cancels and replaces the first edition published in 2018. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) The scope of this standard was modified to restrict the range of residual resistance ratio to that encountered by providers of material for superconducting radio-frequency cavities.
- b) The references to technical material were updated and corrected.

IEC 61788-23:2021 © IEC 2021

- 5 -

The text of this International Standard is based on the following documents:

FDIS	Report on voting
90/478/FDIS	90/482/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

A list of all parts in the IEC 61788 series, published under the general title Superconductivity. can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed, iTeh STANDARD PREVIEW
- withdrawn.
- replaced by a revised edition, or and ards.iteh.ai)
- amended.

SIST EN IEC 61788-23:2021

https://standards.iteh.ai/catalog/standards/sist/3615cdc7-1807-4539-ad51b80fb3797d1f/sist-en-iec-61788-23-2021

IMPORTANT - The 'color inside' logo on the cover page of this publication indicates that it contains colors which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a color printer.

IEC 61788-23:2021 © IEC 2021

INTRODUCTION

High-purity niobium is the chief material used to make superconducting radio-frequency cavities. Similar grades of niobium may be used in the manufacture of superconducting wire. Procurement of raw materials and quality assurance of delivered products often use the residual resistance ratio (RRR) to specify or assess the purity of a metal. RRR is defined for non-superconducting metals as the ratio of electrical resistance measured at room temperature (293 K) to the resistance measured for the same specimen at low temperature (~4,2 K). The low-temperature value is often called the residual resistance. Higher purity is associated with higher values of RRR.

Niobium presents special problems due to its transformation to a superconducting state at \sim 9 K, so DC electrical resistance is effectively zero below this temperature. The definition above would then yield an infinite value for RRR. This document describes a test method to determine the residual resistance value by using a plot of the resistance to temperature as the test specimen is gradually warmed through the superconducting transition in the absence of an applied magnetic field. This results in a determination of the residual resistance at just above superconducting transition, \sim 10 K, from which RRR is subsequently determined.

International Standards also exist to determine the RRR of superconducting wires. In contrast to superconducting wires, which are usually a composite of a superconducting material and a non-superconducting material and the RRR value is representative of only the non-superconducting component, here the entire specimen is composed of superconducting niobium. Frequently, niobium is procured as a sheet, bar, tube, or rod, and not as a wire. For such forms, test specimens will likely be a few millimetres in the dimensions transverse to electric current flow. This difference is significant when making electrical resistance measurements, since niobium samples will likely be much longer than that for the same length-to-diameter ratio as a wire, and higher electrical current may be required to produce sufficient voltage signals. Guidance for sample dimensions and electrical connections is provided in Annex A. Test apparatus should also take into consideration aspects such as the orientation of a test specimen relative to the liquid helium surface, accessibility through ports on common liquid helium dewars, design of current contacts, and minimization of thermal gradients over long specimen lengths. These aspects distinguish this document from similar wire standards.

Other test methods have been used to determine RRR. Some methods use a measurement at a temperature other than 293 K for the high resistance value. Some methods use extrapolations at 4,2 K in the absence of an applied magnetic field for the low resistance value. Other methods use an applied magnetic field to suppress superconductivity at 4,2 K. A comparison between this document and some other test methods is presented in Annex A. Note that systematic differences of up to 10 % are produced by these other methods, which is larger than the target uncertainty of this document. It is therefore important to apply this document or the appropriate corrections listed in Annex A according to the test method used.

Whenever possible, this test method should be transferred to vendors and collaborators who also perform RRR measurements. To promote consistency, the results of inter-laboratory comparisons are described in Clause C.2.

- 6 -