

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
2589

IUP 4

IULTCS

Voting begins on:
2015-10-22

Voting terminates on:
2015-12-22

**Leather — Physical and mechanical
tests — Determination of thickness**

Cuir — Essais physiques et mécaniques — Détermination de l'épaisseur

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2c27fd84-a925-4efd-8efc-0a39023eb931/iso-2589-2016>

Please see the administrative notes on page iii

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference numbers
ISO/FDIS 2589:2015(E)
IUP 4:2015(E)

© ISO 2015

ISO/CEN PARALLEL PROCESSING

This final draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO-lead** mode of collaboration as defined in the Vienna Agreement. The final draft was established on the basis of comments received during a parallel enquiry on the draft.

This final draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel two-month approval vote in ISO and formal vote in CEN.

Positive votes shall not be accompanied by comments.

Negative votes shall be accompanied by the relevant technical reasons.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2c27fd84-a925-4efd-8efc-0a39023cb931/iso-2589-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Sampling and sample preparation	2
6 Procedure	2
7 Expression of results	2
8 Test report	2

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2c27fd84-a925-4efd-8efc-0a39023cb931/iso-2589-2016>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 2589 was prepared by the Physical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUP Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

It is based on IUP 4 originally published in *J. Soc. Leather Trades Chemists* **42**, p. 387, (1958) and declared an official method of the IULTCS in 1959. An updated version was published in *J. Soc. Leather Tech. Chem.* **82**, p. 225, (1998) and a further revision published in *J. Soc. Leather Tech. Chem.* **84**, p. 311, (2000) and reconfirmed as an official method in March 2001. This latest revision now includes the number of test measurements to be taken.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This third edition cancels and replaces the second edition (ISO 2589:2002), of which it constitutes a minor revision to align item c) of Clause 8 with ISO 2419:2012.

Leather — Physical and mechanical tests — Determination of thickness

1 Scope

This International Standard specifies a method for determining the thickness of leather. The method is applicable to all types of leather of any tannage. The measurement is valid for both the whole leather and a test sample.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

3 Principle

The leather is placed in a gauge under a specified load for a specified time and the thickness read directly.

4 Apparatus

4.1 Test machine, including the following:

4.1.1 Gauge, graduated to read to 0,01 mm directly with an accuracy of $\pm 0,02$ mm over the whole scale length.

4.1.2 Anvil, comprising the flat horizontal surface of a cylinder of diameter 10,00 mm \pm 0,05 mm projecting 3,0 mm \pm 0,1 mm above the surface of a concentric flat circular platform of diameter 50,0 mm \pm 0,2 mm.

NOTE The circular platform of 50 mm diameter helps to support medium weight leathers which otherwise presents a convex surface to the presser foot. The anvil is raised 3 mm above the platform so that errors are avoided in measurements on heavy leathers which are not flat.

4.1.3 Presser foot, having a flat circular surface of diameter 10,0 mm \pm 0,05 mm, coaxial with the anvil and capable of movement normal to the face of the anvil. The contacting surfaces of the anvil and presser foot shall be dead weight loaded with 393 g \pm 10 g. Movements of the presser foot shall give a direct reading of the movement on the gauge (4.1.1).

NOTE The loads and dimensions quoted in 4.1.3 give a pressure of 49,1 kPa (500 g/cm²).

4.1.4 Rigid stand, to hold the gauge (4.1.1), anvil (4.1.2) and presser foot (4.1.3).

5 Sampling and sample preparation

5.1 Official sample in accordance with ISO 2418. Five measurements to be taken, distributed across the sample.

5.2 Sample prepared for other tests. Three measurements to be taken, distributed across the sample.

5.3 Sample of unknown origin. Five measurements to be taken, distributed across the sample.

5.4 For very heavy, firm leathers, a smaller sample is recommended to avoid curvature. Three measurements to be taken, distributed across the sample.

5.5 For whole hides, five measurements for each location should be taken. Condition all samples in accordance with ISO 2419.

6 Procedure

Place the apparatus on a flat, horizontal surface. Place the sample in the gauge grain side up if this can be identified. If the grain cannot be identified place the sample in the gauge with either surface upwards. Apply the load gently and record the thickness $5\text{ s} \pm 1\text{ s}$ after full loading is reached.

7 Expression of results

The results shall be expressed as the arithmetic mean and range to the nearest 0,01 mm.

8 Test report

The test report shall include the following:

- a) a reference to this International Standard, i.e. ISO 2589;
- b) the results obtained expressed to the nearest 0,01 mm;
- c) the standard atmosphere used for conditioning and testing as given in ISO 2419;
- d) any deviations from the method specified in this International Standard;
- e) full details for identification of the sample.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2c27fd84-a925-4efd-8efc-0a39023cb931/iso-2589-2016>

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/2c27fd84-a925-4efd-8efc-0a39023cb931/iso-2589-2016>