

---

---

**Qualification testing of welders for  
underwater welding —**

**Part 1:  
Hyperbaric wet welding**

*Épreuve de qualification des soudeurs pour le soudage sous l'eau —*

*Partie 1: Soudage hyperbare en pleine eau*

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

[ISO 15618-1:2016](https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016)

<https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 15618-1:2016

<https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Symbols and abbreviations</b> .....	<b>2</b>
4.1 General.....	2
4.2 Test piece.....	2
4.3 Filler materials and fluxes.....	3
4.4 Miscellaneous.....	3
<b>5 Essential variables for qualification testing</b> .....	<b>3</b>
5.1 General.....	3
5.2 Welding processes.....	3
5.3 Joint types (butt and fillet welds).....	4
5.4 Material groups.....	4
5.5 Filler materials and fluxes.....	4
5.6 Dimensions.....	4
5.7 Welding positions.....	5
5.8 Hyperbaric environment.....	5
5.9 Visibility.....	5
<b>6 Range of qualification (standards.iteh.ai)</b> .....	<b>5</b>
6.1 General.....	5
6.2 Welding process.....	5
6.3 Joint types.....	6
6.4 Material groups.....	6
6.5 Filler materials.....	7
6.6 Dimensions.....	7
6.7 Welding positions.....	7
6.8 Hyperbaric environment.....	7
<b>7 Examination and testing</b> .....	<b>9</b>
7.1 General.....	9
7.2 Witnessing.....	9
7.3 Shapes and dimensions of test pieces.....	9
7.4 Welder-diver qualification test criteria.....	11
7.5 Test methods.....	11
7.6 Test pieces and test specimens.....	12
7.6.1 General.....	12
7.6.2 Butt welds in plate and pipe.....	12
7.6.3 Fillet welds on plate and pipe.....	13
7.7 Test report.....	15
<b>8 Acceptance requirements for test pieces</b> .....	<b>15</b>
<b>9 Re-tests</b> .....	<b>15</b>
<b>10 Period and confirmation of validity</b> .....	<b>15</b>
<b>11 Revalidation of welder-diver qualification</b> .....	<b>16</b>
<b>12 Welder-diver qualification test certificate</b> .....	<b>16</b>
<b>13 Designation</b> .....	<b>16</b>
<b>Annex A (informative) Welder-diver qualification test certificate for hyperbaric wet welding</b> .....	<b>18</b>
<b>Annex B (informative) Job knowledge</b> .....	<b>20</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 15618-1:2016](https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016)

<https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html)

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*, Subcommittee SC 11, *Qualification requirements for welding and allied processes personnel*.

This second edition cancels and replaces the first edition (ISO 15618-1:2001), which has been technically revised.

ISO 15618 consists of the following parts, under the general title *Qualification testing of welders for underwater welding*:

- *Part 1: Hyperbaric wet welding*
- *Part 2: Diver-welders and welding operators for hyperbaric dry welding*

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 11 via your national standards body. A complete listing of these bodies can be found at [www.iso.org](http://www.iso.org).

## **Introduction**

This part of ISO 15618 covers the principles to be observed in the qualification testing of welder-diver performance for the fusion welding of steels in a hyperbaric wet environment.

The ability of the welder-diver to follow verbal or written instructions and testing of his skill are therefore important factors in ensuring the quality of the welded product.

Testing of skill to this part of ISO 15618 depends on welding methods in which uniform rules and test conditions are complied with, and standard test pieces are used.

The principle of this part of ISO 15618 is that a qualification test qualifies a welder-diver not only for the conditions used in the test, but also for all other conditions which are considered easier to weld in accordance with this part of ISO 15618. It is presumed that the welder-diver has received training and/or has industrial practice within the range of qualification.

This part of ISO 15618 is intended to provide the basis for the mutual recognition by examining bodies for qualification relating to the welder-diver's competence in the various fields of application. Tests are to be carried out in accordance with this part of ISO 15618 unless additional tests are specified by the relevant application standard when these should be applied.

The welder-diver's skill and job knowledge continue to be approved only if the welder-diver is working with reasonable continuity on welding work within the extent of qualification.

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

[ISO 15618-1:2016](https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016)

<https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016>

# Qualification testing of welders for underwater welding —

## Part 1: Hyperbaric wet welding

### 1 Scope

This part of ISO 15618 specifies essential requirements, ranges of qualification, test conditions, acceptance requirements and certification for the qualification testing of welder-diver performance.

This part of ISO 15618 is applicable for hyperbaric wet welding on steel.

The recommended format for the certificate of qualification testing is given in [Annex A](#).

During the qualification test, the welder-diver may be required to show adequate job knowledge of the welding processes, materials and safety requirements for which he is to be qualified. Information on these aspects is given in [Annex B](#).

The welding processes referred to in this part of ISO 15618 include those fusion welding processes which are designated as manual or partly mechanised welding. It does not cover fully mechanised and fully automatic processes (see [5.2](#)).

This part of ISO 15618 applies to all new qualifications from the date of issue.

However, this part of ISO 15618 does not invalidate previous welder-diver qualifications made to former national standards or specifications, providing the intent of the technical requirements is satisfied and the previous qualifications are relevant to the application and production work on which they are employed.

The certificate of qualification testing is issued under the sole responsibility of the examiner or examining body.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers*

ISO 5173, *Destructive tests on welds in metallic materials — Bend tests*

ISO 5817, *Welding — Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) — Quality levels for imperfections*

ISO 6947, *Welding and allied processes — Welding positions*

ISO 9017, *Destructive tests on welds in metallic materials — Fracture test*

ISO 15609-1, *Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 1: Arc welding*

ISO 17636 (all parts), *Non-destructive testing of welds — Radiographic testing*

ISO 17637, *Non-destructive testing of welds — Visual testing of fusion-welded joints*

## ISO 15618-1:2016(E)

ISO 17639, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds*

ISO 17640, *Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment*

ISO/TR 15608, *Welding — Guidelines for a metallic materials grouping system*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 15609-1 and the following apply.

#### 3.1 welder-diver

person who performs the welding under hyperbaric conditions

#### 3.2 hyperbaric wet welding

process of welding in a wet environment in excess of surface pressure with no mechanical barrier between the arc and the water

#### 3.3 examiner

person appointed to verify compliance with the applicable standard

Note 1 to entry: A certified examiner or certified bodies according to national or international standards/regulations.

Note 2 to entry: In certain cases, an external independent examiner can be required.

[SOURCE: ISO/TR 25901:2007, 2.119, modified — Note 1 to entry added.]

<https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016>

#### 3.4 examining body

organization appointed to verify compliance with the applicable standard

Note 1 to entry: In certain cases, an external independent examining body can be required.

[SOURCE: ISO/TR 25901:2007, 2.120]

### 4 Symbols and abbreviations

#### 4.1 General

Where the full wording is not used, the following symbols and abbreviations shall be used when completing the test certificate (see [Annex A](#)).

#### 4.2 Test piece

<i>a</i>	design/throat thickness
BW	butt weld
<i>D</i>	outside pipe diameter
FW	fillet weld
P	plate
<i>s</i>	penetration depth



<i>t</i>	material thickness of test piece (plate or wall thickness)
T	pipe
<i>z</i>	leg length of fillet weld

#### 4.3 Filler materials and fluxes

A	acid covering
B	basic covering or electrode core — basic
R	rutile covering
RA	rutile — acid covering
RB	rutile basic covering
RC	rutile cellulosic covering
RR	rutile thick covering
Z	electrode core

Other filler materials and fluxes may be used by agreement.

#### 4.4 Miscellaneous

bs	welding from both sides
gg	back gouging or back grinding of welds
mb	welding with backing material
ml	multi-layer
sl	single-layer
ss	single-side welding
wd	water depth
sw	salt water
fw	fresh water
as	aqueous solution

iteh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 15618-1:2016

<https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016>

## 5 Essential variables for qualification testing

### 5.1 General

The criteria specified in this clause shall be examined in order to identify the ability of the welder-diver in these areas. Each criterion is considered to be a significant factor in the qualification testing. The welder-diver qualification test shall be carried out on standard test pieces.

Welder-divers shall be qualified according to a welding procedure specification (see ISO 15609-1).

### 5.2 Welding processes

Welding processes are defined in ISO/TR 25901-3 and reference numbers of welding processes for symbolic representation are listed in ISO 4063.

This part of ISO 15618 covers the following welding processes applicable in hyperbaric wet environment:

- 111 manual metal arc welding (metal arc welding with covered electrode);
- 114 self-shielded tubular-cored arc welding.

Other fusion welding processes may be used by agreement.

### 5.3 Joint types (butt and fillet welds)

Test pieces shall be produced for butt weld (BW) and fillet weld (FW) in plates (P) or pipes<sup>1)</sup> (T) for qualification tests in accordance with [7.3](#).

### 5.4 Material groups

The designation of steel groups of material as defined in ISO/TR 15608 shall apply.

This part of ISO 15618 primarily applies to the following material groups according to ISO/TR 15608: 1 and 8.

Other steel groups may be used by agreement.

### 5.5 Filler materials and fluxes

In most qualification tests, the filler metal is similar to the parent metal. When a welder-diver test has been carried out using a filler material/flux combination suitable for a certain material group, this test will only confer qualification of the welder-diver to use those consumables (filler material/flux combination) for other materials from the same material group.

Only electrodes designed for hyperbaric wet welding shall be used.

NOTE Certified filler materials for wet welding according to national/international standards may apply.

If there is no national/international standard for wet welding filler material available, the filler material shall be qualified according to a customer approved WPS for hyperbaric wet welding.

ITeT STANDARD PREVIEW  
(standards.iteh.ai)

### 5.6 Dimensions

The welder-diver qualification test shall be based on the thickness of the material (i.e. plate thickness or wall thickness of pipe) and pipe diameters which the welder-diver will use in production. A range of qualification is listed for each of the ranges of plate thickness and pipe wall thickness or pipe diameter as specified in [Tables 1](#) and [2](#).

The thicknesses and diameters given in [Table 1](#) and [2](#) are nominal values and not intended to be measured precisely.

---

1) The word “pipe”, alone or in combination, is used to mean “pipe”, “tube” or “hollow section”.

**Table 1 — Test piece thickness (plate or pipe) and range of qualification**

Test piece thickness, $t$ mm	Range of qualification for butt welds	Range of qualification for fillet welds
$t < 6$	$\geq t$ (max. 6 mm)	$\geq t$ (max. 6 mm)
$6 \leq t < 12$	$0,8 t$ to $2 t$ (min. 6 mm)	$\geq 6$ mm
$t \geq 12$	$0,5 t$ to $1,5 t$	

**Table 2 — Test piece diameter and range of qualification**

Test piece diameter, $D^a$ mm	Range of qualification
$D \leq 100$	$0,7 D$ to $2 D$
$100 < D \leq 300$	$0,5 D$ to $2 D$ (min. 75 mm)
$D > 300$	$>0,5 D$

<sup>a</sup> For structural hollow sections, " $D$ " is the dimension of the smallest side.

## 5.7 Welding positions

The welding positions shall be as detailed in ISO 6947.

## 5.8 Hyperbaric environment

The welder-diver qualification test shall be carried out under actual or simulated hyperbaric conditions in fresh water (fw) or salt water (sw). The type of water (fw or sw) is a non-essential variable.

For other aqueous solutions, the welder-diver shall be qualified based on a welding procedure specification (see ISO 15609-1).

<https://standards.iteh.ai/catalog/standards/sist/cc89b483-75ff-4f0a-859f-4948e3a76345/iso-15618-1-2016>

## 5.9 Visibility

The visibility during the qualification test shall be equal to or greater than 300 mm.

If the visibility under water during production is less than 300 mm, an additional onsite confirmation test weld shall be performed. The confirmation test weld (fillet weld or butt weld) shall be agreed between the contracting parties and shall meet the visual inspection criteria of this part of ISO 15618.

If the qualification test is performed with a visibility less than 300 mm, the welder-diver is qualified for the actual visibility and greater.

## 6 Range of qualification

### 6.1 General

The range of qualification for each type of test is given in the relevant subclauses and tables. In these tables, the range of qualification is indicated in the same horizontal line.

### 6.2 Welding process

Each test approves one welding process. A change of welding process requires a new qualification test.

### 6.3 Joint types

Depending on the test piece, the range of welds for which the welder-diver is approved is shown in [Table 3](#). The following additional criteria are applicable:

- a) butt welds qualify fillet welds but not vice versa;
- b) welds on pipes qualify welds on plates;
- c) qualification for welds in plates cover welds on pipes having an outside diameter  $\geq 600$  mm in the qualified welding position and joint type;
- d) butt welds made from one side with backing qualify welds from both sides with back gouging and vice versa;
- e) fillet welds made from one side qualify fillet welds from both sides;
- f) butt welds in pipes qualify branch joints with an angle  $\geq 60^\circ$ . The range of qualification is based on the outside diameter of the branch.

For applications where the type of weld cannot be qualified by means of either a butt or fillet, or for branch connections of less than  $60^\circ$ , a specific test piece should be used to qualify the welder-diver, when specified (e.g. by the product standard).

**Table 3 — Range of qualification for tests (details of weld type)**

Details of weld type	Range of qualification			
	Butt welds		Fillet welds	
	welded from one side (ss) with backing (mb)	welded from both sides (bs) with back gouging (gg)	plate	pipe
<b>Butt welds</b>	welded from one side (ss) with backing (mb)	x	x	x <sup>a</sup>
	welded from both sides (bs) with back gouging (gg)	x	x	x
<b>Fillet welds</b>	plate	—	x	x <sup>a</sup>
	pipe	—	x	x

<sup>a</sup> See [6.3 c](#)).

x Indicates those welds for which the welder-diver is approved.

— Indicates that for what the welder-diver is not approved.

### 6.4 Material groups

According to the material group of the test piece specified in [5.4](#), the welder-diver is only approved for this material group.

For any other steel group, the welder-diver shall be qualified based on a welding procedure specification (see ISO 15609-1).