



Standard Specification for Cured-In-Place Thermosetting Resin Sewer Pipe¹

This standard is issued under the fixed designation D 5813; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers cured-in-place thermosetting resin pipe (CIPP), 4 through 132-in. (100 through 3353-mm) equivalent diameter, for use in gravity flow systems for conveying sanitary sewage, storm water, and certain industrial wastes. This specification is suited for the evaluation and testing of materials used in the rehabilitation of existing pipes by the installation and cure of a resin-impregnated fabric liner.

1.2 The values given in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

NOTE 1—There are no ISO standards covering the primary subject matter of this specification.

1.3 The following safety hazards caveat pertains only to the test methods portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:* <http://www.astm.org/catalog/standards/sist/fb9817ac>
- D 543 Test Method for Resistance of Plastics to Chemical Reagents²
 - D 638 Test Method for Tensile Properties of Plastics²
 - D 695 Test Method for Compressive Properties of Rigid Plastics²
 - D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastic and Electrical Insulating Materials²
 - D 883 Terminology Relating to Plastics²
 - D 1600 Terminology for Abbreviated Terms Relating to Plastics²
 - D 1682 Test Methods for Breaking Load and Elongation of Textile Fabric³

¹ This specification is under the jurisdiction of ASTM Committee D-20 on Plastics and is under the direct responsibility of Subcommittee D20.23 on Reinforced Plastic Piping Systems and Chemical Equipment.

Current edition approved Oct. 10, 1995. Published December 1995.

² *Annual Book of ASTM Standards*, Vol 08.01.

³ Discontinued; see 1991 *Annual Book of ASTM Standards*, Vol 07.01.

D 3039/D3039M Test Method for Tensile Properties of Fiber-Resin Composites⁴

D 3567 Practice for Determining Dimensions of “Fiber-glass” (Glass-Fiber-Thermosetting Resin) Pipe and Fittings⁵

D 3681 Test Method for Chemical Resistance of “Fiber-glass” (Glass-Fiber Reinforced Thermosetting Resin) Pipe in a Deflected Condition⁵

D 4814 Specification for Automotive Spark—Ignition Engine Fuel⁶

F 412 Terminology Relating to Plastic Piping Systems⁵

F 1216 Practice for Rehabilitation of Existing Pipelines and Conduits by the Inversion and Curing of a Resin-Impregnated Tube⁵

3. Terminology

3.1 *General*—Definitions are in accordance with Terminologies D 883 and F 412. Abbreviations are in accordance with Terminology D 1600, unless otherwise indicated.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *cured-in-place pipe (CIPP)*—hollow cylinder consisting of a fabric with cured (cross-linked) thermoset resin; interior or exterior plastic tube coatings, or both, may be included; this pipe is formed within and takes the shape of an existing conduit.

3.2.2 *delamination*—separation of coating or layers of the CIPP, or both.

3.2.3 *dry spot*—a fabric area of the finished CIPP which is deficient or devoid of resin.

3.2.4 *fabric tube*—a flexible material formed into a tubular shape which during the installation process is saturated with resin and holds the resin in place during the cure.

3.2.5 *fully deteriorated pipe*—the original pipe is not structurally sound and cannot support soil and live loads or is expected to reach this condition over the design life of the rehabilitated pipe.

3.2.6 *lift*—a portion of the CIPP that has pulled away from the existing conduit wall and formed a reverse (inward) curvature of the CIPP relative to the existing conduit.

⁴ *Annual Book of ASTM Standards*, Vol 15.03.

⁵ *Annual Book of ASTM Standards*, Vol 08.04.

⁶ *Annual Book of ASTM Standards*, Vol 05.03.

3.2.7 *partially deteriorated pipe*—the original pipe can support the soil and live loads throughout the design life of the rehabilitated pipe. The soil adjacent to the existing pipe must provide adequate side support. The pipe may have longitudinal cracks and some distortion of the diameter.

3.2.8 *qualification test*—one or more tests used to prove the design of a product; not a routine quality control test.

3.2.9 *quality assurance test*—one or more tests used to verify the physical properties of the CIPP.

3.2.10 *quality control test*—one or more tests used by the manufacturer of the tube during manufacture or assembly.

3.2.11 *tube coating*—a plastic coating on the outside or inside surface, or both, of the fabric tube.

4. Classification

4.1 Types of CIPP:

4.1.1 *Type I*—Designed to provide chemical resistance and prevent exfiltration.

4.1.2 *Type II*—Installed in a partially deteriorated existing pipe and is designed to provide chemical resistance, prevent exfiltration and infiltration, and support the external hydrostatic loads due to groundwater only (and internal vacuum, where applicable), since the soil and live loads can be supported by the original conduit.

4.1.3 *Type III*—Installed in a fully deteriorated existing pipe and designed to provide chemical resistance, prevent exfiltration and infiltration, and support all external hydraulic, soil, and live loads acting on the original conduit.

4.2 Grades of CIPP:

4.2.1 *Grade 1*—Thermosetting polyester resin.

4.2.2 *Grade 2*—Thermosetting epoxy resin.

NOTE 2—For the purposes of this specification, polyester includes vinyl ester resins.

NOTE 3—The purchaser should determine or consult the manufacturer for the proper type and grade pipe to be used under the installation and operation conditions that will exist for the project in which the pipe is to be used.

5. Materials and Manufacture

5.1 *General*—The resins, fabric tube, tube coatings, fillers, and other materials, when combined as a composite structure, shall produce a pipe that meets the requirements of this specification.

5.2 *CIPP Wall Composition*—The wall shall consist of a fabric tube and tube coating filled with a thermosetting (cross-linked) resin, and if used, a filler.

5.2.1 *Resin*—A thermosetting polyester or epoxy resin.

5.2.2 *Fabric Tube*—This tube shall consist of one or more layers of fabric that are compatible with the resin system used and are capable of supporting and carrying resin. The tube should be capable of withstanding installation procedures and curing temperatures. Longitudinal and circumferential joints between multiple layers of a tube should be staggered to not overlap. The tube shall be fabricated to fit its final in-place position in the original conduit, with allowance for stretch as recommended by the tube manufacturer.

5.2.2.1 *Tube Coating*—The inside or outside surface, or both, of the fabric tube may be coated with a plastic flexible material that is compatible with the tube and the resin system

used. The coating shall allow visual inspection of the proper impregnation of the tube fabric with resin.

5.2.3 *Filler*—An additive which alters the thixotropic or physical properties, or both, of a resin, and when incorporated into the CIPP will not detrimentally affect its ability to meet the requirements of this specification.

6. Requirements

6.1 *Fabric Tube Strength*—The fabric tube, as a quality control test, when tested in accordance with 8.4 shall have a minimum tensile strength of 750 psi (5 MPa) in both the longitudinal and transverse directions.

6.2 *Workmanship*—After installation, Types I, II, and III CIPP shall be free of dry spots, lifts, delamination of any CIPP layers or tube coating. If any of these conditions are present, repair the CIPP in these areas with materials compatible with the resin system and fabric tube and in a manner acceptable to the purchaser, or replace the CIPP so that it meets the requirements of these specifications.

6.3 Dimensions:

6.3.1 *Pipe Diameters*—Due to diametric shrinkage of the CIPP during cure, the minimum allowable outside diameter of Types I, II, and III CIPP should be 98 % of the inside diameter of the host or mold pipe used for sampling, when measured in accordance with 8.1.1.

6.3.2 *Lengths*—Types I, II, and III CIPP shall be designed to extend the full length of the existing pipe between the access points after installation and curing, unless otherwise required. The cured CIPP may be cut to project beyond the ends of the existing pipe as required by the owner.

6.3.3 *Wall Thickness*—The average wall thickness of Types I, II, and III CIPP shall not be less than the specified thickness. The minimum wall thickness at any point shall not be less than 87.5 % of the specified thickness when measured in accordance with 8.1.2.

6.4 Chemical Resistance Requirements:

6.4.1 Types I, II, and III specimens of each grade and class for use in sanitary sewer applications shall be evaluated in a laminate form by qualification test in accordance with 8.2.1. The specimens shall be capable of exposure to the solutions in Table 1 at a temperature of $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) with a percentage retention of flexural modulus of elasticity, when tested in accordance with 8.3, of at least 80 % after one-year exposure. Flexural properties after exposure to the chemical solution shall be based on the dimensions of the specimen after exposure.

6.4.2 Types I, II, and III CIPP specimens of each grade and class used shall be evaluated by qualification test in accordance

TABLE 1 Minimum Chemical Resistance Requirements for Typical Municipal Sewer Applications

Chemical Solution	Concentration, %
Nitric acid	1
Sulfuric acid	5
ASTM Fuel C ^A	100
Vegetable oil (cottonseed, corn, or mineral oil)	100
Detergent ^B	0.1
Soap ^B	0.1

^AIn accordance with Specification D 4814.

^BIn accordance with Test Method D 543.