



SLOVENSKI STANDARD

SIST ISO 12219-9:2019

01-december-2019

Notranji zrak v cestnih vozilih - 9. del: Določevanje emisij hlapnih organskih spojin iz notranjih delov vozila - Metoda vzorčenja s plinskimi vrečami

Interior air of road vehicles - Part 9: Determination of the emissions of volatile organic compounds from vehicle interior parts - Large bag method

iTeh STANDARD PREVIEW

Air intérieur des véhicules routiers - Partie 9: Détermination des émissions de composés organiques volatils des parties et matériaux intérieurs des véhicules - Méthode du grand sac

[SIST ISO 12219-9:2019](https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019)

[https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-](https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019)

Ta slovenski standard je istoveten z: [ISO 12219-9:2019](https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019)

ICS:

13.040.20	Kakovost okoljskega zraka	Ambient atmospheres
43.020	Cestna vozila na splošno	Road vehicles in general

SIST ISO 12219-9:2019

en,fr

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 12219-9:2019](https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019)

<https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019>

INTERNATIONAL
STANDARD

ISO
12219-9

First edition
2019-04

Interior air of road vehicles —

Part 9:

**Determination of the emissions of
volatile organic compounds from
vehicle interior parts — Large bag
method**

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Air intérieur des véhicules routiers —

*Partie 9: Détermination des émissions de composés organiques
volatils des parties et matériaux intérieurs des véhicules — Méthode
du grand sac*

<https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019>



Reference number
ISO 12219-9:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 12219-9:2019

<https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus and materials	2
5.1 General.....	2
5.2 Large sampling bag.....	3
5.2.1 General.....	3
5.2.2 Material.....	3
5.2.3 Air tightness.....	3
5.2.4 Bag blank concentration.....	3
5.3 Purity of the filling gas.....	3
5.4 Thermostatic oven.....	3
5.5 Pumps.....	4
5.6 Integrating flow meter or gas meter.....	4
6 Test conditions	4
6.1 General.....	4
6.2 Vehicle interior parts.....	4
6.3 Storage period and storage conditions.....	4
6.4 Heating temperature.....	5
6.5 Heating time.....	5
6.6 Gas amount to be filled in a sampling bag.....	5
7 Verification of test conditions	5
7.1 Monitoring of test conditions.....	5
7.2 Recovery rate.....	5
8 Test method	5
8.1 Test equipment.....	5
8.2 Preparation for testing.....	6
8.2.1 Heated cleaning of sampling bag.....	6
8.2.2 Preparation of large sampling bags.....	6
8.3 Emission test.....	6
8.4 Gas sampling.....	7
9 Analysis procedures	7
9.1 Analysis of VOC.....	7
9.2 Analysis of formaldehyde and other carbonyl compounds.....	8
10 Calculation of sampling bag values	8
11 Test report	8
12 Quality assurance/quality control (QA/QC)	11
Annex A (informative) Summary for heated cleaning process for large sampling bags	12
Annex B (informative) Supplement on test report and recovery rate	13
Bibliography	15

ISO 12219-9:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 146, *Air quality*, Subcommittee SC 6, *Indoor air*.

A list of all parts in the ISO 12219 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Volatile organic compounds (VOCs) are widely used in industry and can be emitted by many every-day products and materials. They have attracted much attention in recent years because of their impact on cabin air quality. After homes and workplaces, people spend a lot of time in their vehicles. It is important to determine the material emissions of interior parts and to reduce them to an acceptable level. Therefore, it is important to get comprehensive and reliable information about the types of organic compounds in the interior air of vehicles and also their concentrations.

This document outlines the sampling bag test method of volatile organic compounds (VOC), formaldehyde and other carbonyl compounds which diffuse from vehicle interior parts into the air inside road vehicles.

Measuring VOC from vehicle interior parts can be performed in several ways and the approach selected depends upon the desired outcome and the material type. For example, to obtain diffusion data from complete assemblies (e.g. instrument panel, seat, etc.), chambers/bags that have sufficient volume to house the complete assembly are employed. Meanwhile, to obtain diffusion data from representative samples of homogeneous vehicle interior materials, micro-scale chamber method can be chosen.

Each measurement method such as bag/micro-scale chamber/small-chamber sampling offers a complementary approach.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 12219-9:2019](https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019)

<https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 12219-9:2019](https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019)

<https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-38cd7601c087/sist-iso-12219-9-2019>

Interior air of road vehicles —

Part 9:

Determination of the emissions of volatile organic compounds from vehicle interior parts — Large bag method

1 Scope

This document specifies a large bag sampling method for measuring volatile organic compounds (VOCs), formaldehyde and other carbonyl compounds which are emitted from vehicle interior parts into the air inside road vehicles. This method is intended for evaluation of large new vehicle interior parts, and complete assemblies. This is a screening method to compare similar car components under similar test conditions on a routine basis.

Evaluating VOC emissions of vehicle interior parts is an important aspect of the vehicle indoor air quality.

This document is complementary to existing standards and provides test laboratories and the manufacturing industry with a cost-effective evaluation of vehicle interior parts. This method is only applicable to newly manufactured vehicle parts. This method is applicable to all types of vehicles, and vehicle products which are used as parts in the interior of vehicles.

2 Normative references

SIST ISO 12219-9:2019

<https://standards.iteh.ai/catalog/standards/sist/9d05ed7a-21a0-498b-a050-352a0b005120/iso-12219-9-2019>

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16000-3, *Indoor air — Part 3: Determination of formaldehyde and other carbonyl compounds in indoor air and test chamber air — Active sampling method*

ISO 16000-6, *Indoor air — Part 6: Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA sorbent, thermal desorption and gas chromatography using MS or MS-FID*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

vehicle interior part

part which is used in the interior of a vehicle including related materials such as adhesives and coating materials

[SOURCE: ISO 12219-2:2012, 3.1]

ISO 12219-9:2019(E)**3.2****sampling bag value**

concentration increment of a subject gas component due to the diffusion of VOCs, formaldehyde and other carbonyl compounds from a *vehicle interior part* (3.1), multiplied by the total amount of the gas filled in the sampling bag

[SOURCE: ISO 12219-2:2012, 3.2 modified — “vehicle interior part” replaces “test specimen”.]

3.3**volatile organic compound****VOC**

organic compound eluting between and including n-hexane and n-hexadecane on a gas chromatographic column specified as a 5 % phenyl 95 % methyl polysiloxane capillary column

3.4**total volatile organic compound****TVOC**

sum of volatile organic compounds, sampled on Tenax TA®, which elute between and including n-hexane and n-hexadecane on a non-polar capillary column, detected with a flame ionization detector (TVOC-FID) or mass spectrometric detector (TVOC-MS), and quantified by converting the total area of the chromatogram in that analytical window to a nominal mass using the chromatographic response factor for toluene (toluene equivalents)

[SOURCE: ISO 16000-6:2011, 3.4, modified — Note has been deleted.]

iTeh STANDARD PREVIEW (standards.iteh.ai)

4 Principle

The test method specified in this document describes a procedure for calculating sampling bag values of VOC, formaldehyde and other carbonyl compounds which can diffuse from vehicle interior parts.

Vehicle interior parts put in a sampling bag are heated at a specified temperature, and then a fraction of the gas in the sampling bag is collected to measure the test concentrations. By comparing the test concentrations with the corresponding bag blank concentrations, the sampling bag values of VOC, formaldehyde and other carbonyl compounds diffusing from vehicle interior parts can be calculated (see [Clause 10](#)).

The analytical part of the overall measurement procedure is based on the use of sorbent tubes with subsequent thermal desorption and gas chromatographic analysis for VOCs (according to ISO 16000-6) and the use of 2,4-dinitrophenylhydrazine (DNPH) sorbent tubes, followed by high performance liquid chromatography (HPLC) analysis with ultraviolet absorption for the determination of formaldehyde and other carbonyl compounds (according to ISO 16000-3).

The specified analytical procedure is valid for the determination of volatile organic compounds (VOCs) ranging in concentration from sub- $\mu\text{g}/\text{m}^3$ to several mg/m^3 . The method is applicable to the measurement of non-polar and slightly polar VOCs ranging in volatility from n-C₆ to n-C₁₆.

The specified analytical procedure for formaldehyde and other carbonyl compounds is valid for the determination of carbonyls within the concentration range of approximately $1 \mu\text{g}/\text{m}^3$ to $1 \text{mg}/\text{m}^3$.

5 Apparatus and materials**5.1 General**

Test apparatus and materials necessary for determining the sampling bag values of VOC, formaldehyde and other carbonyl compounds diffusing from vehicle interior parts are mainly as follows:

- sampling bag;
- nitrogen gas or air (filling gas);

- thermostatic oven;
- pumps;
- integrating flow meter;
- analytical equipment is described in ISO 16000-3 and ISO 16000-6.

5.2 Large sampling bag

5.2.1 General

Large sampling bags used in this document shall be in accordance with [5.2.2](#), [5.2.3](#), [5.2.4](#) and [7.2](#).

They shall be low-emitting, low-permeable and low-sorption plastic bags having a capacity of 20 l to 2 000 l used for measuring VOC, formaldehyde and other carbonyl compounds which can emit from vehicle interior parts. The size of the bag depends on the size of the part and is to be agreed upon between the parties.

5.2.2 Material

Though no specification is set for the material of a sampling bag, the recommended materials are fluorinated resin [vinyl fluoride (PVF), polyvinylidene fluoride (PVDF), 4 ethylene fluoride - 6 propylene fluoride copolymer (FEP)], ethylene-vinyl alcohol copolymer (EVOH). Large sample bags made of just a single layer of polyethylene terephthalate (PET) or polyolefins (PEHD) can have high permeation through the bag material. Total film thickness should be above 20 microns.

5.2.3 Air tightness

The large sampling bag shall be sealed airtight using a sealing material such as a tape that will not affect the test or by the heat seal method so that the gases inside are not mixed with any uncontrolled outside air.

5.2.4 Bag blank concentration

The bag blank concentration generated by heating a large sampling bag filled with only nitrogen or air shall be at such a low level as to not affect the test. Each target VOC, collecting 1 l on the sampling tube, shall have a value less than 20 ng collected on each tube and for formaldehyde and/or any other carbonyl compound, collecting 3 l on the DNPH cartridge, shall have a value less than 200 ng collected on each cartridge.

Users should be aware that TVOC bag blank values from bags vary significantly depending on material, age, cleaning procedure and analytical process. Report specific bag cleaning parameters and all analytical conditions and calculation methods in order to interpret TVOC report values.

5.3 Purity of the filling gas

For the nitrogen gas or air filled in a large sampling bag, use a high purity gas containing as few impurities as possible so that the concentration of any contained VOC, formaldehyde and other carbonyl compounds will not affect the diffusion test. It is recommended to use nitrogen gas of a purity of 99,999 % or more.

5.4 Thermostatic oven

To control the temperature, use a thermostatic chamber capable of uniform temperature control.

The thermostatic chamber into which a sampling bag is set shall be capable of controlling the temperature distribution accuracy of ± 2 °C.