



SLOVENSKI STANDARD
oSIST prEN 15080-12:2022
01-oktober-2022

Razširjena uporaba rezultatov požarne odpornosti - 12. del: Nosilni zidovi

Extended application of results from fire resistance tests - Part 12: Loadbearing masonry walls

Erweiterter Anwendungsbereich der Ergebnisse von Feuerwiderstandsprüfungen - Teil 12: Tragende Mauerwerkswände

Application étendue des résultats des essais de résistance au feu - Partie 12: Murs porteurs en maçonnerie

<https://standards.iteh.ai/catalog/standards/sist/e96d2a6b-2ba3-4774-8ebf-41e0-700000000000/osist-pr-en-15080-12-2022>

Ta slovenski standard je istoveten z: prEN 15080-12

ICS:

13.220.50	Požarna odpornost gradbenih materialov in elementov	Fire-resistance of building materials and elements
91.060.10	Stene. Predelne stene. Fasade	Walls. Partitions. Facades

oSIST prEN 15080-12:2022

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 15080-12

July 2022

ICS 13.220.50; 91.060.10

Will supersede EN 15080-12:2011

English Version

Extended application of results from fire resistance tests - Part 12: Loadbearing masonry walls

Application étendue des résultats des essais de
résistance au feu - Partie 12: Murs porteurs en
maçonnerie

Erweiterter Anwendungsbereich der Ergebnisse von
Feuerwiderstandsprüfungen - Teil 12: Tragende
Mauerwerkswände

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 127.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 General principles	5
4.1 General	5
4.2 Classifications	6
4.3 Necessary additional information	6
5 Rules for extended application	7
5.1 Units	7
Table 1 – Ranges of unit compressive strength for extrapolation	9
5.2 Masonry mortars and joints	9
5.3 Plaster, rendering or external covering	10
5.4 Load Level	10
5.5 Geometrical parameters	11
6 Report of the extended application analysis	11
Annex A (informative) Recommendations for the installation	12
A.1 Connection systems for REI walls	12
A.2 Recesses and chases	12
Bibliography	13

European foreword

This document (prEN 15080-12:2022) has been prepared by Technical Committee CEN/TC 127 “Fire safety in buildings”, the secretariat of which is held by BSI.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 15080-12:2011.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of 89/106/EEC.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 15080-12:2022](https://standards.iteh.ai/catalog/standards/sist/e96d2a6b-2ba3-4774-8ebf-4e8bcc2d1ab8/osist-pren-15080-12-2022)

<https://standards.iteh.ai/catalog/standards/sist/e96d2a6b-2ba3-4774-8ebf-4e8bcc2d1ab8/osist-pren-15080-12-2022>

prEN 15080-12:2022 (E)**1 Scope**

This document provides guidance, and where appropriate defines procedures, for variations of certain parameters and factors associated with the design of internal and external loadbearing walls that have been tested, see EN 1365-1.

Data from historic standard fire resistance tests may be used as supporting information.

Manufactured stone masonry units (see EN 771-5) and natural stone units (see EN 771-6) are not covered.

This document is not valid for reinforced masonry.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 771-1, *Specification for masonry units — Part 1: Clay masonry units*

EN 771-3, *Specification for masonry units — Part 3: Aggregate concrete masonry units (Dense and light-weight aggregates)*

EN 772-1, *Methods of test for masonry units — Part 1: Determination of compressive strength*

EN 998-1:2010, *Specification for mortar for masonry — Part 1: Rendering and plastering mortar*

EN 1363-1, *Fire resistance tests - Part 1: General requirements*

EN 1363-2, *Fire resistance tests - Part 2: Alternative and additional procedures*

EN 1365-1, *Fire resistance tests for loadbearing elements - Part 1: Walls*

EN 1996-1-1, *Eurocode 6 - Design of masonry structures - Part 1-1: General rules for reinforced and unreinforced masonry structures*

EN 1996-1-2:2005, *Eurocode 6 - Design of masonry structures - Part 1-2: General rules - Structural fire design*

EN 1996-2, *Eurocode 6 - Design of masonry structures - Part 2: Design considerations, selection of materials and execution of masonry*

EN 1996-3:2006, *Eurocode 6 - Design of masonry structures - Part 3: Simplified calculation methods for unreinforced masonry structures*

EN 13501-2, *Fire classification of construction products and building elements - Part 2: Classification using data from fire resistance tests, excluding ventilation services*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1996-1-2:2005 and the following apply.

3.1

unfilled perpend joint

vertical plain joint or joint with tongue and groove, not filled with mortar or adhesive

3.2

utilisation factor

relation between the applied load on the test specimen and the design resistance in the fire situation $N_{Rd,fi}$
w

Note 1 to entry: For design resistance see EN 1996-1-1 or EN 1996-3.

3.3

historical data

test data generated by fire resistance tests that have been undertaken by a Notified Test Laboratory

Note 1 to entry: This is in accordance with European and/or former and in accordance with standards.

Note 2 to entry: Previously existing test data are acceptable even though the test may not have been carried out using the plate thermometer as long as the necessary additional information, (see 4.3) is available. This data can only be used as described in this European Standard.

Note 3 to entry The temperature-time curve used is based on the one specified in EN 1363-1, which is also defined in ISO 834.

3.5

moisture content of units

difference between the density of the units at the beginning of the fire test and the gross dry density of the units, related to the gross dry density of the units, in percent by mass

4 General principles

4.1 General

(1) The fire behaviour of load bearing masonry mainly depends on:

- the masonry unit material - clay, calcium silicate, autoclaved aerated concrete, dense/lightweight aggregate concrete;
- the type of unit - solid or hollow (type of holes, percentage and direction of holes), shell and web thickness;
- the unit dimensions;
- the unit gross density;
- the unit compressive strength;
- the type of mortar - general purpose, thin layer or lightweight mortar;
- the type of perpend joint – filled or unfilled perpend joint, especially for unplastered walls;

prEN 15080-12:2022 (E)

- the use of finishes;
- the geometrical slenderness of the wall as defined in EN 1996-1-1;
- the level of the applied load;
- eccentricities;
- fire exposure of separating/non separating elements.

(2) For the determination of values by consideration of test results, the interpretation of any existing fire test results have to be based on the requirements for the relevant test method from EN 1363-1, EN 1363-2, EN 1364-1, EN 1365-1 or EN 1365-4 respectively.

(3) For the evaluation of use of previously existing data, differences between the test methods, have to be considered.

NOTE Differences to be considered are for example material properties, specimen dimensions, utilization factor based on maximum loading, eccentricities, etc.

(4) To establish the extended application, the rules given in Clause 5 shall be followed for each of the given parameters.

(5) Extrapolations exceeding the rules of this European Standard are possible, provided that tests give evidence to do so. Such extrapolations have to be specified in the report, see Clause 6.

4.2 Classifications

(1) All the given rules are always valid for the same classification.

(2) Extrapolation is possible for different wall thicknesses and geometries, different unit densities, compressive strengths, perforation patterns and sizes, different types of masonry mortar, different types of external covering, different load levels and eccentricities.

(3) An extrapolation for higher fire resistances or from REI tests to REI-M or R is not possible.

NOTE 1 In some cases, there are different extended application rules given for the classifications R, REI and REI-M.

NOTE 2 In addition, the rules given in this document for REI tests also apply for RE and REW tests.

4.3 Necessary additional information

For the classification according to these extended application rules additional information on material properties and additional measurements during the test procedure according to EN 1363-1, EN 1363-2, EN 1364-1, EN 1365-1, EN 1365-4 or historic standard fire test methods are necessary:

- measurement of the deflection of the test specimen at least in mid height, to allow for an extrapolation for height, see 5.5 (1);
- gross density, compressive strength and moisture content of the units;
- percentage of voids, web and shell thickness (parallel and perpendicular to the wall surface, if applicable) and combined thickness (at least for webs and shells perpendicular to the wall surface) for perforated units;

- gross density and compressive strength of the masonry mortar;
- thickness of unfilled perpend joints in unplastered or unrendered walls;
- thickness and type of plaster or render in rendered walls;
- gross density and moisture content of the plaster;
- type and thickness of applied thermal insulation material (if applicable);
- gross density and moisture of the insulation material (if applicable);
- measurement of applied load on the test specimens;
- determination of the utilization factor μ_0 / α_{fi} , applied standard for the determination of the utilization factor in the next report, f.e. EN 1996-1-1 (with national annex, if applicable).

The measurement of the temperature within the test specimen at least in mid-height across the wall thickness is advised to allow for a future calculation of fire resistances according to EN 1996-1-2. Thermocouples should be placed at least in depths of 10 mm, 30 mm and 50 mm from the exposed side and then every 50 mm.

5 Rules for extended application

5.1 Units

- (1) Extrapolations are only possible within the same type of material – e.g. tests on clay unit masonry with units according to EN 771-1 can only be used for extrapolations for clay unit masonry. For lightweight aggregate concrete units according to EN 771-3 extrapolations are only possible within lightweight aggregate concrete units.
- (2) The test results are valid for the tested type of unit. If solid units, i.e. group 1 units according to EN 1996-1-1 are tested, the results are only valid for group 1 units with the same or a smaller percentage of voids.
- (3) For vertically perforated units, the test results can be applied for units with the same or a smaller percentage of voids. If the difference between the tested percentage of voids and the upper limit of the group in EN 1996-1-1 is less than 5 % of the overall surface of the unit, test results are valid for all percentages of voids within that group. The tested percentage of voids can be rounded up to the next multiple of 5 %.
- (4) For vertically perforated units, the test results can be applied for units with the same or a higher thickness of webs and shells.
- (5) For vertically perforated units, the test results can be applied for units with the same or higher values of the combined thickness. The value of the combined thickness can be rounded down to the next multiple of 10 mm/m.
- (6) For horizontal perforated units, the test results can be applied for units with the same or a higher thickness of webs and shells and for the same or higher values of the combined thickness. The value of the combined thickness can be rounded down to the next multiple of 10 mm/m.
- (7) Test results for vertically perforated units can be applied for solid units without perforations.

prEN 15080-12:2022 (E)

- (8) For the classification REI and R the test results are valid for the tested size of the unit and units larger in height, length and width.
- (9) For units with a length between 200 mm and 1000 mm, test results for a unit length from that range are valid for the whole range of unit lengths between 200 mm and 1000 mm.
- (10) For the classification REI-M, test results are valid for the tested length and width and units larger in length and width. It is not possible to extrapolate from tests on masonry walls with unit heights equal or smaller than 250 mm to units with greater heights.
- (11) For tested wall thicknesses up to 140 mm, the test results are valid for masonry with units with the same or a higher declared value of the gross density of the units within the following ranges.
- unit density between 300 kg/m³ and 999 kg/m³: Tested density and densities up to 800 kg/m³ higher than the tested density up to a maximum gross dry density of 1600 kg/m³.
 - unit density between 1000 kg/m³ and 2600 kg/m³: Tested density and densities up to 600 kg/m³ higher than the tested density up to a maximum gross dry density of 2600 kg/m³.

NOTE 1 Extrapolations for lightweight aggregate concrete units are limited to net dry densities 20 % higher than tested.

- (12) For wall thicknesses greater than 140 mm, the test results are valid for masonry units with a higher declared value of the gross density of units.

NOTE 2 Extrapolations for lightweight aggregate concrete units are limited to net dry densities 20 % higher than tested.

- (13) The tested density can be rounded down within the following ranges:

- for unit densities between 300 kg/m³ and 999 kg/m³ to the next multiple of 50 kg/m³;
- for unit densities between 1000 kg/m³ and 2600 kg/m³ to the next multiple of 200 kg/m³.

- (14) The test results are valid for masonry with the same or a higher declared value of the compressive strength of units tested according to EN 772-1 within the ranges given in Table 1 and with the same or lower utilization factor. The tested compressive strength can be rounded down to:

- the next multiple of 1 N/mm² for compressive strengths up to 7 N/mm²;
- the next multiple of 2 N/mm² for compressive strengths between 7,1 N/mm² and 16 N/mm²;
- the next multiple of 5 N/mm² for compressive strengths greater than 16,1 N/mm².