

Designation: A 242/A 242M – 03a Designation: A 242/A 242M – 04 (Reapproved a 2

# Standard Specification for High-Strength Low-Alloy Structural Steel<sup>1</sup>

This standard is issued under the fixed designation A 242/A 242M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (\$\varepsilon\$) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

## 1. Scope \*

1.1 This specification covers high-strength low-alloy structural steel shapes, plates, and bars for welded, riveted, or bolted construction intended primarily for use as structural members where savings in weight [mass] or added durability are important. The atmospheric corrosion resistance of the steel in most environments is substantially better than that of carbon structural steels with or without copper addition. When properly exposed to the atmosphere, this steel can be used bare (unpainted) for many applications (see Note 1). This specification is limited to material up to 4 in. [100 mm], inclusive, in thickness.

Note 1—For methods of estimating the atmospheric corrosion resistance of low-alloy steels, see Guide G 101.

- 1.2 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification A 6/A 6M/A6M for information on weldability.
- 1.3 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.
- 1.4 For structural products produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A 6/A 6M apply.

# 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling G 101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

#### 3. General Requirements for Delivery

- 3.1 Structural products furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M/A6M, for the specific structural product ordered, unless a conflict exists, in which case this specification shall prevail.
- 3.2 Coils are excluded from qualification to this specification until they are processed into a finished structural product. Structural products produced from coil means structural products that have been cut to individual lengths from a coil. The processor directly controls, or is responsible for, the operations involved in the processing of a coil into a finished structural product. Such operations include decoiling, leveling or straightening, hot-forming or cold-forming (if applicable), cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

Note 2—For structural products produced from coil and furnished without heat treatment or with stress relieving only, two test results are to be reported for each qualifying coil. Additional requirements regarding structural products produced from coil are described in Specification A 6/A 6M.

#### 4. Materials and Manufacture

4.1 The steel shall be semi-killed or killed.

## 5. Chemical Composition

5.1 The heat analysis shall conform to the requirements prescribed in <del>Table 1</del>Table 2.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel; Steel and Related Alloys; Alloys and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, Stock and Ships.

Current edition approved May 10, 2003. April 1, 2009. Published July 2003. May 2009. Originally approved in 1941. Last previous edition approved in 2003 as A242/A242M—03. A 242/A 242M—04<sup>£1</sup>.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards, Vol 01.04-volume information, refer to the standard's Document Summary page on the ASTM website.