

SLOVENSKI STANDARD SIST EN 1996-1-1:2022

01-junij-2022

Nadomešča:

SIST EN 1996-1-1:2006+A1:2013

Evrokod 6 - Projektiranje zidanih konstrukcij - 1-1. del: Splošna pravila za armirano in nearmirano zidovje

Eurocode 6 - Design of masonry structures - Part 1-1: General rules for reinforced and unreinforced masonry structures

Eurocode 6 - Bemessung und Konstruktion von Mauerwerksbauten - Teil 1-1: Allgemeine Regeln für bewehrtes und unbewehrtes Mauerwerk

Eurocode 6 - Calcul des ouvrages en maçonnerie Partie 11. Règles générales pour ouvrages en maçonnerie armée et non armée

SIST EN 1996-1-1:2022

Ta slovenski standard je istoveten z: EN 1996-1-1:2022

ICS:

91.010.30 Tehnični vidiki Technical aspects

91.080.30 Zidane konstrukcije Masonry

SIST EN 1996-1-1:2022 en,fr,de

SIST EN 1996-1-1:2022

iTeh STANDARD **PREVIEW** (standards.iteh.ai)

<u>SIST EN 1996-1-1:2022</u> https://standards.iteh.ai/catalog/standards/sist/13775edffb3d-4dda-90c5-728d058bcde5/sist-en-1996-1-1-2022

EUROPEAN STANDARD NORME EUROPÉENNE **EUROPÄISCHE NORM**

EN 1996-1-1

April 2022

ICS 91.010.30; 91.080.30

Supersedes EN 1996-1-1:2005+A1:2012

English Version

Eurocode 6 - Design of masonry structures - Part 1-1: General rules for reinforced and unreinforced masonry structures

Eurocode 6 : Calcul des ouvrages en maçonnerie -Partie 1-1: Règles générales pour ouvrages en maçonnerie armée et non armée

Eurocode 6 - Bemessung und Konstruktion von Mauerwerksbauten - Teil 1-1: Allgemeine Regeln für bewehrtes und unbewehrtes Mauerwerk

This European Standard was approved by CEN on 3 January 2022.

This European Standard was corrected and reissued by the CEN-CENELEC Management Centre on 20 April 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

COII	itents	Page
	pean foreword	
Intro	duction	_
1	Scope	
2	Normative references	8
3	Terms, definitions and symbols	10
3.1	Terms and definitions	
3.2	Symbols	
4	Basis of design	
4.1 4.2	General rulesPrinciples of limit state design	
4.2 4.3	Basic variables	
4.4	Verification by the partial factor method	
4.5	Design assisted by testing	
5	Materials	25
5.1	Masonry units	25
5.2	Mortar	27
5.3	Concrete infill ITEN STANDARD	
5.4 5.5	Steel reinforcementPREVIEW	
5.5 5.6		
5.7	Ancillary components	29
5.8	Deformation properties of masonry	38
6	Durability SIST EN 1996-1-1:2022	41
6.1	General https://standards.iteh.ai/catalog/standards/sist/13775edf- Classification of environmental conditions	41
6.2		
6.3	Durability of masonry	
6.4	Masonry below ground	
7	Structural analysis	
7.1 7.2	GeneralStructural behaviour in accidental situations (other than fire)	
7.2 7.3	Imperfections	
7.4	Second order effects	
7.5	Analysis of structural members	46
8	Ultimate limit states	58
8.1	General	
8.2	Verification of unreinforced masonry walls subjected to mainly vertical loading	58
8.3	Verification of unreinforced masonry walls subjected to combined vertical and horizontal loading in the plane of the wall	64
8.4	Verification of unreinforced masonry walls subjected to mainly lateral loading	
8.5	Verification of unreinforced masonry walls subjected to combined vertical and	
0 -	lateral loading	
8.6 8.7	TiesVerification of reinforced masonry members subjected to bending, bending and	69
U. /	axial loading, or axial loading	70

3.8	Verification of reinforced masonry members subjected to shear loading	79
3.9	Prestressed masonry	
3.10	Confined masonry	83
9	Serviceability limit states	86
9.1	General	
9.2	Unreinforced masonry walls	
9.3	Reinforced masonry members	
9.4	Prestressed masonry members	
9.5	Confined masonry members	
9.6	Walls subjected to concentrated loads	87
10	Detailing	
10.1	Masonry details	
10.2	Reinforcement details	
10.3	Prestressing details	
10.4	Confined masonry details	
10.5	Connection of walls	
10.6	Chases and recesses on walls Damp proof courses	
10.7 10.8	Thermal and long term movement	
	Execution iTeh STANDARD	99
11	Execution AND	99
11.1	General Design of structural members K. E. V. L. E. V. E	99
11.2	Design of structural members	99
11.3	Loading of masonry	99
Annex		
4.1	Use of this Informative Annex SIST EN 1996-1-1:2022 Scope and field of application hear/catalog/standards/sist/137775edf	. 100
4.2	Scope and field of application	. 100
4.3	General fb3d-4dda-90c5-728d058bcde5/sist-en-1996-1-1-2022	100
	B (informative) Method for calculating the second order effect	
B.1	Use of this Informative Annex	. 102
B.2	Scope and field of application	. 102
B.3	Total moment including second order effects	. 102
Annex	C (informative) Simplified methods for calculating the out-of-plane eccentricity of	
IIIIICA	loading on walls	. 104
C. 1	Use of this Informative Annex	
C.2	Scope and field of application	
C.3	Eccentricity with reinforced concrete floors	
C. 4	Eccentricity with timber floors	. 109
Annex	D (informative) Bending moment coefficients, α_2 , in single leaf laterally loaded wall	
	panels	. 111
D.1	Use of this Informative Annex	
D.2	Scope and field of application	. 111

Annex	E (informative) Limiting height and length to thickness ratios for unreinforced walls and walls with only bed joint reinforcement under the serviceability limit state	.118
E.1	Use of this Informative Annex	118
E.2	Scope and field of application	118
E.3	Limiting height and length to thickness ratios	118
Annex	F (informative) Capacity reduction factor for slenderness and eccentricity	.121
F.1	Use of this Informative Annex	121
F.2	Scope and field of application	121
F.3	Reduction factor $\Phi_{\rm m}$ for masonry walls subjected to mainly vertical loading (expressed as a function of eccentricity)	.121
F.4	Reduction factor $\Phi_{\rm M}$ for masonry walls subjected to combined vertical and lateral loading (expressed as a function of normal load ratio)	.122
Annex	G (informative) Adjustment of lateral load for walls supported on three or four edges subjected to out-of-plane horizontal loading and vertical loading	.125
G.1	Use of this Informative Annex	125
G.2	Scope and field of application	
G.3	Calculation of the reduction factor for the lateral load	125
Annex	H (informative) Reinforced masonry members subjected to shear loading: enhancement of the design shear strength of masonry, $f_{\rm vd}$	
H.1	Use of this Informative Annex	126
H.2	Use of this Informative Annex Carrol and Field of application. Scope and field of application.	126
Н.3	Calculation of the design shear strength of masonry, f _{vd}	126
Annex	I (informative) A design method for complex shaped members subjected to mainly vertical loading	
I.1	Use of this Informative Annex	
I.2	Scope and field of application	127
I.3	Design of complex shaped members	128
Annex	J (informative) Method for walls under combined lateral and vertical loading taking buckling due to vertical loading and flexural strength into account	.133
J.1	Use of this Informative Annex	133
J.2	Scope and field of application	133
J.3	Verifications	133
Annex	K (informative) Mean material properties	134
K.1	Use of this Informative Annex	134
K.2	Scope and field of application	134
К.3	Mechanical properties of masonry	
K.4	Deformation properties of masonry	136
Biblio	graphy	137

European foreword

This document (EN 1996-1-1:2022) has been prepared by Technical Committee CEN/TC 250 "Structural Eurocodes", the secretariat of which is held by BSI. CEN/TC 250 is responsible for all Structural Eurocodes and has been assigned responsibility for structural and geotechnical design matters by CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2027, and conflicting national standards shall be withdrawn at the latest by March 2028.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1996-1-1:2005+A1:2012.

The first generation of EN Eurocodes was published between 2002 and 2007. This document forms part of the second generation of the Eurocodes, which have been prepared under a Mandate M/515 given to CEN by the European Commission and the European Free Trade Association.

The Eurocodes have been drafted to be used in conjunction with relevant execution, material, product and test standards, and to identify requirements for execution, materials, products and testing that are relied upon by the Eurocodes:

The main changes compared to the previous edition are listed below:

- improvement of the verification of combined loading; (Standards.iteh.ai)
- improvement of the capacity reduction factor for slenderness and eccentricity;
- addition of the out-of-plane shear friction coefficient. 022
 - https://standards.iteh.ai/catalog/standards/sist/13775edf-
- addition of rules for confined masonry 058bcde5/sist-en-1996-1-1-2022
- addition of informative annexes for complex shapes and mean material properties.

The Eurocodes recognize the responsibility of each Member State and have safeguarded their right to determine values related to regulatory safety matters at national level through the use of National Annexes.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

0 Introduction

0.1 Introduction to the Eurocodes

The Structural Eurocodes comprise the following standards generally consisting of a number of Parts:

- EN 1990 Eurocode: Basis of structural and geotechnical design
- EN 1991 Eurocode 1: Actions on structures
- EN 1992 Eurocode 2: Design of concrete structures
- EN 1993 Eurocode 3: Design of steel structures
- EN 1994 Eurocode 4: Design of composite steel and concrete structures
- EN 1995 Eurocode 5: Design of timber structures
- EN 1996 Eurocode 6: Design of masonry structures
- EN 1997 Eurocode 7: Geotechnical design
- EN 1998 Eurocode 8: Design of structures for earthquake resistance
- EN 1999 Eurocode 9: Design of aluminium structures

The Eurocodes are intended for use by designers, clients, manufacturers, constructors, relevant authorities (in exercising their duties in accordance with national or international regulations), educators, soft-ware developers, and committees drafting standards for related product, testing and execution standards.

SIST EN 1996-1-1:2022

NOTE Some aspects of design are most appropriately specified by relevant authorities or, where not specified, can be agreed on a project-specific basis between relevant parties such as designers and clients. The Eurocodes identify such aspects making explicit reference to relevant authorities and relevant parties.

0.2 Introduction to EN 1996 Eurocode 6

EN 1996 Eurocode 6 standards apply to the design of building and civil engineering works, or parts thereof, in unreinforced, reinforced, prestressed and confined masonry.

EN 1996 (all parts) deal only with the requirements for resistance, serviceability and durability of structures. Other requirements, for example, concerning thermal or sound insulation, are not considered.

EN 1996 (all parts) do not cover the specific requirements of seismic design. Provisions related to such requirements are given in EN 1998 (all parts), which complements, and is consistent with EN 1996 (all parts).

EN 1996 (all parts) do not cover numerical values of the actions on building and civil engineering works to be taken into account in the design. They are provided in EN 1991(all parts).

0.3 Introduction to EN 1996-1-1

For the design of new structures, EN 1996-1-1 is intended to be used, for direct application, together with the other Eurocodes where applicable.

0.4 Verbal forms used in the Eurocodes

The verb "shall" expresses a requirement strictly to be followed and from which no deviation is permitted in order to comply with the Eurocodes.

The verb "should" expresses a highly recommended choice or course of action. Subject to national regulation and/or any relevant contractual provisions, alternative approaches could be used/adopted where technically justified.

The verb "may" expresses a course of action permissible within the limits of the Eurocodes.

The verb "can" expresses possibility and capability; it is used for statements of fact and clarification of concepts.

0.5 National Annex for EN 1996-1-1

National choice is allowed in this standard where explicitly stated within notes. National choice includes the selection of values for Nationally Determined Parameters (NDPs).

The national standard implementing EN 1996-1-1 can have a National Annex containing all national choices to be used for the design of buildings and civil engineering works to be constructed in the relevant country.

When no national choice is given, the default choice given in this standard is to be used.

When no national choice is made and no default is given in this standard, the choice can be specified by a relevant authority or, where not specified, agreed for a specific project by appropriate parties.

National choice is allowed in EN 1996-1-1 through notes to the following:

4.4.4(2)	5.2.2(2) 5.7.2.1(2) 5.7.2.1(2)	.2(1) 5.7.1.3(2)	
5.7.2.1(1)	5.7.2.1(2) 5.7.2.	5.7.4(4) – 3 choices	S
5.8.2(3)	5.8.4(3) SIST EN 1996-1-1:20	6.3.3(3)	
7.5.1.4(4)	https://8.3.1(2) s.iteh.ai/catalog/s8.10.	3:1(2)st/13775edf- 10.1.2(2)	
10.5.2.2(2)	fb3d-41d5.203(2)728d058bcde5/f0.6.	.2(1) ⁹⁹⁶⁻¹⁻¹⁻²⁰²² 10.6.3(1)	

National choice is allowed in EN 1996-1-1 on the application of the following informative annexes:

Annex A	Annex B	Annex C	Annex D
Annex E	Annex F	Annex G	Annex H
Annex I	Annex J	Annex K	

The National Annex can contain, directly or by reference, non-contradictory complementary information for ease of implementation, provided it does not alter any provisions of the Eurocodes.

Scope 1

Scope of EN 1996-1-1

- (1) The basis for the design of building and civil engineering works in masonry is given in this document, which deals with unreinforced masonry, reinforced masonry and confined masonry. Principles for the design of prestressed masonry are also given.
- (2) This document is not valid for masonry elements with a plan area of less than 0,04 m².
- (3) Reinforced masonry and confined masonry built with Group 4 units and subjected to mainly vertical loading are not covered by this document.
- (4) This document gives detailed rules which are mainly applicable to ordinary buildings. The applicability of these rules can be limited, for practical reasons or due to simplifications; any limits of applicability are given in the text where necessary.
- (5) Execution is covered to the extent that is necessary to indicate the quality of the construction materials and products that are to be used and the standard of workmanship on site needed to comply with the assumptions made in the design rules.
- (6) For those types of structures not covered entirely, for new structural uses for established materials, for new materials, or where actions and other influences outside normal experience have to be resisted, the provisions given in this document can be applied, but with possible need for supplements.
- (7) This document does not cover: **iTeh ST**
- resistance to fire (which is dealt with in EN 1996-1-2);
- particular aspects of special types of building (for example, dynamic effects on tall buildings);
- standards.iten.ai particular aspects of special types of civil engineering works (such as masonry bridges, dams, chimneys or liquid-retaining structures); T EN 1996-1-1:2022
- particular aspects of special types of structures (such as arches or domes) 75 edf-

- fb3d-4dda-90c5-728d058bcde5/sist-en-1996-1-1-2022 masonry where gypsum, with or without cement, mortars are used;
- masonry where the units are not laid in a regular pattern of courses (rubble masonry);
- masonry reinforced with other materials than steel.

1.2 Assumptions

(1) The assumptions of EN 1990 apply to this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

See the Bibliography for a list of other documents cited that are not normative references, including those referenced as recommendations (i.e. in 'should' clauses), permissions ('may' clauses), possibilities ('can' clauses), and in notes.

EN 206, Concrete. Specification, performance, production and conformity

EN 771-1, Specification for masonry units - Part 1: Clay masonry units

- EN 771-2, Specification for masonry units Part 2: Calcium silicate masonry units
- EN 771-3, Specification for masonry units Part 3: Aggregate concrete masonry units (Dense and lightweight aggregates)
- EN 771-4, Specification for masonry units Part 4: Autoclaved aerated concrete masonry units
- EN 771-5, Specification for masonry units Part 5: Manufactured stone masonry units
- EN 771-6, Specification for masonry units Part 6: Natural stone masonry units
- EN 845-1, Specification for ancillary components for masonry Part 1: Ties, tension straps, hangers and brackets
- EN 845-2, Specification for ancillary components for masonry Part 2: Lintels
- EN 845-3, Specification for ancillary components for masonry Part 3: Bed joint reinforcement of steel meshwork
- EN 998-1, Specification for mortar for masonry Part 1: Rendering and plastering mortar
- EN 998-2, Specification for mortar for masonry Part 2: Masonry mortar
- EN 1015-11, Methods of test for mortar for masonry Part 11: Determination of flexural and compressive strength of hardened mortar
- EN 1052-1, Methods of test for masonry Part 1: Determination of compressive strength
- EN 1052-2, Methods of test for masonry Part 2: Determination of flexural strength
- EN 1052-3, Methods of test for masonry Part 3: Determination of initial shear strength
- EN 1052-4, Methods of test for masonry Part 4: Determination of shear strength including damp proof course
- EN 1052-5, Methods of test for masonry Part 5: Determination of bond strength by the bond wrench method
- EN 1990, Eurocode Basis of structural and geotechnical design
- EN 1991 (all parts), Eurocode 1 Actions on structures
- EN 1992-1-1, Eurocode 2: Design of concrete structures Part 1-1: General rules Rules for buildings, bridges and civil engineering structures
- EN 1996-2, Eurocode 6 Design of masonry structures Part 2: Design considerations, selection of materials and execution of masonry

Terms, definitions and symbols 3

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1990 and the following apply.

3.1.1 Terms relating to masonry

3.1.1.1

masonry

assemblage of masonry units joined together with mortar

3.1.1.2

unreinforced masonry

masonry not containing sufficient reinforcement so as to be considered as reinforced masonry

3.1.1.3

reinforced masonry

masonry in which bars of reinforcing steel or bed joint reinforcement are embedded in mortar or concrete so that all the materials act together in resisting action effects

3.1.1.4

prestressed masonry

masonry in which internal compressive stresses have been intentionally induced by tensioned prestressing steel PREVIEW

3.1.1.5

confined masonry

standards.iteh.ai)

masonry provided with reinforced concrete or reinforced masonry confining elements in the vertical (tiecolumn) and horizontal (tie-beam) direction, so that all materials act compositely in resisting action effects

https://standards.iteh.ai/catalog/standards/sist/13775edffb3d-4dda-90c5-728d058bcde5/sist-en-1996-1-1-2022

3.1.1.6

masonry bond

disposition of units in masonry in a regular pattern to achieve common action

3.1.2 Terms relating to strength of masonry

3.1.2.1

characteristic strength of masonry

value of the strength of masonry having a prescribed probability of 5 % of not being attained in a hypothetically unlimited test series

This value generally corresponds to a specified fractile of the assumed statistical distribution of the particular property of the material or product in a test series.

3.1.2.2

compressive strength of masonry

strength of masonry in compression without the effects of platen restraint, slenderness or eccentricity of loading

3.1.2.3

shear strength of masonry

strength of masonry in shear

3.1.2.4

flexural strength of masonry

out-of-plane strength of masonry in bending

3.1.2.5

anchorage bond strength

bond strength, per unit surface area, between reinforcement and concrete or mortar, when the reinforcement is subjected to tensile or compressive forces

3.1.2.6

adhesion

effect of mortar developing a tensile and shear resistance at the contact surface of masonry units

3.1.3 Terms relating to masonry units

3.1.3.1

masonry unit

preformed component, intended for use in masonry construction

3.1.3.2

group 1, 1S, 2, 3 and 4 masonry units

group designations for masonry units, including geometrical requirements, such as the percentage size and orientation of holes in the units when laid

3.1.3.3

PREVIEW

bed face

top or bottom surface of a masonry unit when laid as intended

3.1.3.4

frog

SIST EN 1996-1-1:2022

depression, formed during manufacture, in one or both bed faces of a masonry unit

fb3d-4dda-90c5-728d058bcde5/sist-en-1996-1-1-2022

3.1.3.5

hole

formed void which may or may not pass completely through a masonry unit

3.1.3.6

griphole

formed void in a masonry unit to enable it to be more readily grasped and lifted with one or both hands or by machine

3.1.3.7

web

solid material between the holes in a masonry unit

3.1.3.8

shell

peripheral material between a hole and the face of a masonry unit

3.1.3.9

gross area

area of a cross-section through the unit without reduction for the area of holes, voids and re-entrants

3.1.3.10

compressive strength of masonry units

mean compressive strength of a specified number of masonry units

3.1.3.11

normalized compressive strength of masonry units

compressive strength of masonry units converted to the air-dried compressive strength of an equivalent 100 mm wide x 100 mm high masonry unit (see EN 771-1 to EN 771-6)

3.1.4 Terms relating to concrete infill

3.1.4.1

concrete infill

concrete used to fill pre-formed cavities or voids in masonry

3.1.5 Terms relating to reinforcement

3.1.5.1

reinforcing steel

steel reinforcement bars for use in masonry

3.1.5.2

bed joint reinforcement

reinforcing steel that is prefabricated for building into a bed joint

3.1.5.3

steel wires, bars or strands for use in masonry dards.iteh.ai)

3.1.6 Terms relating to ancillary components $_{EN\ 1996-1-1:2022}$

3.1.6.1

https://standards.iteh.ai/catalog/standards/sist/13775edffb3d-4dda-90c5-728d058bcde5/sist-en-1996-1-1-2022

damp proof course

layer of sheeting, masonry units or other material used in masonry to resist the passage of water

3.1.6.2

wall tie

device for connecting one leaf to another leaf or to a framed structure or backing wall

3.1.6.3

strap

device for connecting masonry members to other adjacent components, such as floors and roofs

3.1.6.4

composite lintel

lintel comprising a prefabricated part and a complementary element of in-situ masonry, above, acting together

3.1.7 Terms relating to mortar joints

3.1.7.1

bed joint

mortar layer between the bed faces of masonry units

3.1.7.2

perpend joint (head joint)

mortar joint perpendicular to the bed joint and to the face of the wall

3.1.7.3

longitudinal joint

vertical mortar joint within the thickness of a wall, parallel to the face of the wall

3.1.7.4

thin layer joint

joint made with thin layer mortar

3.1.7.5

jointing

process of finishing a mortar joint as the work proceeds

3.1.7.6

pointing

process of filling and finishing mortar joints where the surface of the joint has been raked out or left open for pointing

3.1.8 Terms relating to mortar

"iTeh STANDARD

3.1.8.1

masonry mortar

mixture of one or more inorganic binders, aggregates and water, and sometimes additions and/or admixtures, for bedding, jointing and pointing of masonry

3.1.8.2

general purpose masonry mortar<u>SIST EN 1996-1-1:2022</u>

masonry mortar without special characteristics log/standards/sist/13775edf-

fb3d-4dda-90c5-728d058bcde5/sist-en-1996-1-1-2022

3.1.8.3

thin layer masonry mortar

designed masonry mortar with a maximum aggregate size less than or equal to a prescribed figure

3.1.8.4

lightweight masonry mortar

designed masonry mortar with a dry hardened density equal to or below $1\,300~{\rm kg/m^3}$ according to EN 998-2

3.1.8.5

designed masonry mortar

mortar whose composition and manufacturing method is chosen in order to achieve specified properties (performance concept)

3.1.8.6

prescribed masonry mortar

mortar made in predetermined proportions, the properties of which are assumed from the stated proportions of the constituents (recipe concept)

3.1.8.7

factory made masonry mortar

mortar batched and mixed in a factory