
INTERNATIONAL STANDARD



2114

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Plastics — Unsaturated polyester resins — Determination of acid value

Matières plastiques — Résines de polyesters non saturés — Détermination de l'indice d'acide

First edition — 1974-11-01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2114:1974

<https://standards.iteh.ai/catalog/standards/sist/2cd4c246-0179-40fc-86da-cb17b8b58ba3/iso-2114-1974>

UDC 678.674.543.24

Ref. No. ISO 2114-1974 (E)

Descriptors : plastics, polyester resins, unsaturated chains, chemical analysis, determination of content, acidity.

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2114 was drawn up by Technical Committee ISO/TC 61, *Plastics*.

It has been approved by the Member Bodies of the following countries :

ISO 2114:1974		
Australia	Greece	Portugal
Austria	Hungary	Romania
Belgium	India	South Africa, Rep. of
Canada	Israel	Spain
Chile	Japan	Sweden
Czechoslovakia	Korea, Rep. of	United Kingdom
Egypt, Arab Rep. of	Netherlands	U.S.A.
France	New Zealand	U.S.S.R.
Germany	Poland	

No Member Body expressed disapproval of the document.

Plastics — Unsaturated polyester resins — Determination of acid value

1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies a method of determining the acid value of unsaturated polyester resins. In some cases, notably when free anhydrides are present, a somewhat lower than theoretical acid value is found, due to the formation of acid esters which precipitate and are, therefore, not determined.

2 DEFINITION

acid value: The number of milligrams of potassium hydroxide (KOH) required to neutralize 1 g of the test product under the test conditions.

3 PRINCIPLE

A weighed quantity of resin is dissolved in a mixture of solvents and the resin solution is titrated with a standardized ethanolic solution of potassium hydroxide, using a suitable indicator.

The number of milligrams of potassium hydroxide used to neutralize 1 g of resin is calculated.

4 REAGENTS

4.1 Solvent mixture, composed of 2 parts of toluene and 1 part of absolute ethanol.

4.2 Thymol blue, 0,1 % indicator solution in absolute ethanol.

4.3 Potassium hydroxide, 0,1 N standard volumetric solution in absolute ethanol.

The solution must be anhydrous and as free from carbon dioxide as possible.

If required :

4.4 Acetone, containing less than 0,1 % of water.

5 APPARATUS

5.1 Conical flask, capacity 250 ml, with a large neck.

5.2 Burette, capacity 25 ml, graduated in 0,05 ml divisions.

5.3 Magnetic stirrer.

5.4 Source of nitrogen gas.

5.5 Pipette, capacity 50 ml.

6 PROCEDURE

Weigh, to the nearest 1 mg, 0,5 to 3 g of the resin into the flask (5.1), the quantity depending on the expected acid value.

Add 50 ml of the solvent mixture (4.1), using the pipette.

Shake until the resin has completely dissolved, warming if necessary on a water bath with a condenser on the flask. If the solubility is poor, or if solution is incomplete in about 5 min, prepare another solution by dissolving another test portion in a mixture of 50 ml of the solvent mixture (4.1) and 25 ml of acetone (4.4). Record this change in procedure in the test report.

Cool the solution to room temperature.

Add 5 drops of thymol blue solution (4.2). Place the flask on the magnetic stirrer and bubble into the solution a stream of nitrogen.

Titrate with the potassium hydroxide solution (4.3) from the burette (5.2) to the point where the colour remains blue for 20 to 30 s. Record the volume, V_1 , of KOH solution (4.3) used, in millilitres.

Carry out a blank determination using 50 ml of the solvent mixture (4.1) (or 50 ml of the solvent mixture (4.1) and 25 ml of acetone (4.4) as described above) and titrate to obtain the same blue coloration as obtained when the resin was present. Record the volume, V_2 , of KOH solution (4.3) used, in millilitres.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2114:1974
<https://standards.iteh.ai/catalog/standards/sist/2cd4c246-0179-40fc-86da-cb17b8b58ba3/iso-2114-1974>

7 CALCULATION AND EXPRESSION OF RESULTS

7.1 Calculation

Calculate, for each test, the acid value, Av, from the formula

$$56,1 \frac{(V_1 - V_2) \times T}{m}$$

where

m is the mass, in grams, of the test portion;

V_1 is the volume, in millilitres, of KOH solution (4.3) used to neutralize the resin solution;

V_2 is the volume, in millilitres, of KOH solution (4.3) used in the blank determination;

T is the normality of the KOH solution (4.3) (about 0,1).

7.2 Expression of results

Take as the result the mean of at least two determinations, rounded to the nearest whole number.

8 TEST REPORT

The test report shall include the following particulars :

- a) reference to this International Standard;
- b) the individual results and their mean;
- c) the solvent used for solution preparation, i.e. toluene/ethanol or toluene/ethanol/acetone;
- d) any special features noted during the determination;
- e) any operations not specified in this International Standard and all incidents that may have affected the results.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 2114:1974](https://standards.iteh.ai/catalog/standards/sist/2cd4c246-0179-40fc-86da-eb17b8b58ba3/iso-2114-1974)

<https://standards.iteh.ai/catalog/standards/sist/2cd4c246-0179-40fc-86da-eb17b8b58ba3/iso-2114-1974>