

---

---

**High yield strength steel plates and  
wide flats for cold forming — Delivery  
conditions**

*Produits plats en acier à haute limite d'élasticité pour formage à  
froid — Conditions de livraison*

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ISO 6930:2019](https://standards.iteh.ai/catalog/standards/iso/adca1211-65c3-4c4d-b262-6b83a93fe042/iso-6930-2019)

<https://standards.iteh.ai/catalog/standards/iso/adca1211-65c3-4c4d-b262-6b83a93fe042/iso-6930-2019>



iTeh Standards  
(<https://standards.itih.ai>)  
Document Preview

ISO 6930:2019

<https://standards.itih.ai/catalog/standards/iso/adca1211-65c3-4c4d-b262-6b83a93fe042/iso-6930-2019>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	v
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Dimensions and tolerances</b> .....	<b>2</b>
4.1 General .....	2
4.2 Mandatory information .....	2
<b>5 Classification and designation</b> .....	<b>2</b>
5.1 Classification .....	2
5.2 Designation .....	3
5.3 Using <a href="#">Annexes A, B and C</a> .....	3
<b>6 Technical requirements</b> .....	<b>3</b>
6.1 Steelmaking process .....	3
6.2 Method of deoxidation .....	3
6.3 Production process .....	3
6.4 Delivery condition .....	3
6.5 Chemical composition .....	3
6.5.1 Heat analysis .....	3
6.5.2 Product analysis tolerances .....	3
6.6 Dimensions tolerances and surface condition .....	4
6.7 Internal soundness .....	4
<b>7 Mechanical properties</b> .....	<b>4</b>
7.1 Tensile properties .....	4
7.2 Impact properties .....	4
7.3 Technical properties .....	4
7.3.1 Weldability .....	4
7.3.2 Bending and cold-edging ability .....	4
<b>8 Inspection and testing</b> .....	<b>5</b>
8.1 General .....	5
8.2 Test unit .....	5
8.2.1 Product analysis .....	5
8.2.2 Mechanical properties .....	5
8.3 Position and orientation of sample .....	5
8.4 Preparation .....	5
8.4.1 Tensile test pieces .....	5
8.4.2 Impact test pieces .....	5
8.5 Testing .....	6
8.5.1 Tensile Test .....	6
8.5.2 Impact test .....	6
8.5.3 Bend test .....	6
8.5.4 Product analysis .....	6
8.6 Retests .....	6
<b>9 Inspection documents</b> .....	<b>7</b>
<b>10 Sorting and reprocessing</b> .....	<b>7</b>
<b>11 Marking</b> .....	<b>7</b>
<b>Annex A (normative) Chemical composition and mechanical properties of normalized and normalized rolled steels for steel grades S260NC, S315NC, S355NC and S420NC</b> .....	<b>8</b>

<b>Annex B (normative) Chemical composition and mechanical properties of thermomechanically rolled steels for steel grades S315MC, S355MC, S420MC, S460MC, S500MC, S550MC, S600MC, S650MC, S700MC, S900MC and S960MC</b> .....	<b>10</b>
<b>Annex C (normative) Chemical composition and mechanical properties for steel grades S345, S415, S485, S550 and S690</b> .....	<b>12</b>
<b>Bibliography</b> .....	<b>14</b>

**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

[ISO 6930:2019](https://standards.itih.ai/catalog/standards/iso/adca1211-65c3-4c4d-b262-6b83a93fe042/iso-6930-2019)

<https://standards.itih.ai/catalog/standards/iso/adca1211-65c3-4c4d-b262-6b83a93fe042/iso-6930-2019>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 3, *Steels for structural purposes*.

This second edition cancels and replaces ISO 6930-1:2001 and ISO 6930-2:2004, which have been technically revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).



# High yield strength steel plates and wide flats for cold forming — Delivery conditions

## 1 Scope

This document specifies the requirements for weldable high yield strength plates and wide flats for cold forming.

It does not apply to weldable structural steels, whether or not of special quality, which are covered by other International Standards, namely:

- structural steels: ISO 630 (all parts);
- high yield strength flat steel products: ISO 4950-1, ISO 4950-2 and ISO 4950-3;
- hot-rolled steel sheet of higher yield strength with improved formability: ISO 5951;
- sheet and strip: refer to ISO/TC 17, *Steel*, SC 12, *Continuous mill flat rolled products*;
- tubular products; refer to ISO/TC 5, *Ferrous metal pipes and metallic fittings*, SC 1, *Steel tubes*.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method*

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 404, *Steel and steel products — General technical delivery requirements*

ISO 2566-1, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels*

ISO 4885, *Ferrous materials — Heat treatments — Vocabulary*

ISO 4948-1, *Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition*

ISO 4948-2, *Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics*

ISO/TS 4949, *Steel names based on letter symbols*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 6929, *Steel products — Vocabulary*

ISO 7438, *Metallic materials — Bend test*

ISO 7452, *Hot-rolled steel plates — Tolerances on dimensions and shape*

ISO 7788, *Steel — Surface finish of hot-rolled plates and wide flats — Delivery requirements*

ISO 9034, *Hot-rolled structural steel wide flats — Tolerances on dimensions and shape*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

ISO 17577, *Steel — Ultrasonic testing of steel flat products of thickness equal to or greater than 6 mm*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6929 and ISO 4885 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1 wide flat

flat product of width over 150 mm up to and including 1 250 mm and thickness generally over 4 mm, supplied in lengths, i.e. not coiled, and the edges are square, i.e. hot-rolled on all four sides (or in box passes)

### 4 Dimensions and tolerances

#### 4.1 General

This document applies to plates and wide-flats, hot-rolled on reversing mills, of a thickness  $\leq 20$  mm for grades specified in [Annexes A](#) and [B](#) and of a thickness between 4 mm and 50 mm (inclusive) for grades specified in [Annex C](#).

#### 4.2 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) the quantity required;
- b) the type of product;
- c) the nominal dimensions and tolerances on dimensions and shape of the product;
- d) the number of this document, i.e. ISO 6930;
- e) the steel name (grade);
- f) all required options;
- g) inspection document to be issued.

### 5 Classification and designation

#### 5.1 Classification

The steel grades specified in this document shall be classified as non-alloy or alloy quality steels in accordance with ISO 4948-1, ISO 4948-2 and ISO/TS 4949 depending on the steel-grade chemical composition and heat treatment condition.



## 5.2 Designation

Designation shall be carried out in accordance with ISO/TS 4949.

This document specifies twenty (20) steel grades.

Grades S260NC, S315NC, S355NC, and S420NC are specified in [Annex A](#).

Grades S315MC, S355MC, S420MC, S460MC, S500MC, S550MC, S600MC, S650MC, S700MC, S900MC and S960MC are specified in [Annex B](#).

Grades S345, S415, S485, S550 and S690 are specified in [Annex C](#).

## 5.3 Using [Annexes A, B and C](#)

The requirements of [Annexes A, B and C](#) shall be regarded separately. Each is independent of the other without combining in any way.

## 6 Technical requirements

### 6.1 Steelmaking process

Unless otherwise specified at the time of the order, the steelmaking process is left to the discretion of the manufacturer. On request, the purchaser shall be informed of the steelmaking process to be used.

### 6.2 Method of deoxidation

The steels shall be fully killed and have a fine grain practice containing sufficient amounts of nitrogen binding elements.

### 6.3 Production process

Unless otherwise specified at the time of the order, the production process is left to the discretion of the manufacturer.

### 6.4 Delivery condition

Products of grades S260NC, S315NC, S355NC and S420NC are supplied in the normalized or normalized rolled delivery condition.

Products of grades S315MC, S355MC, S420MC, S460MC, S500MC, S550MC, S600MC, S650MC, S700MC, S900MC and S960MC are supplied in the thermomechanically rolled delivery condition.

Plates and wide flats shown in [Annex C](#) are supplied in the as-rolled, normalized, or thermomechanically rolled delivery condition.

### 6.5 Chemical composition

#### 6.5.1 Heat analysis

The chemical composition in % mass fraction determined by heat analysis shall conform to the values specified in [Tables A.1, B.1](#) or [C.1](#)

#### 6.5.2 Product analysis tolerances

If requested by the purchaser at the time of the order, a product analysis shall be carried out.

The permissible deviations for the product analysis in relation to the heat analysis of grades S260NC, S315NC, S355NC and S420NC shall conform to the values given in [Table A.2](#).

The permissible deviations for the product analysis in relation to the heat analysis of grades S315MC, S355MC, and S420MC, S460MC, 500MC, S550MC, S600MC, S650MC, S700MC, S900MC and S960MC shall conform to the values given in [Table B.2](#).

The product analysis of grades S345, S415, S485, S550 and S690 shall conform to the values given in [Table C.2](#).

### 6.6 Dimensions tolerances and surface condition

Product dimensions tolerances and surface condition shall be in accordance with ISO 7452, ISO 7788 and ISO 9034.

### 6.7 Internal soundness

By agreement, ultrasonic requirements together with the conditions of their verification shall be specified at the time of the order in accordance with ISO 17577.

## 7 Mechanical properties

### 7.1 Tensile properties

The tensile properties at room temperature shall conform to the values specified in [Tables A.3](#), [B.3](#) or [C.3](#).

### 7.2 Impact properties

If agreed upon at the time of order, the impact energy value shall be verified for products with nominal thickness  $\geq 6$  mm at  $-20$  °C and shall meet a minimum average value of 40 J, or at  $-40$  °C and shall meet a minimum average value of 27 J based on full size (10 mm  $\times$  10 mm) test piece (see [8.4.2](#)). If the thickness is not sufficient for the preparation of full-size impact test pieces, test pieces of smaller thickness shall be taken and the applicable values shall be decreased proportionally.

This subclause is only applicable to [Annexes A](#) and [B](#).

### 7.3 Technical properties

#### 7.3.1 Weldability

The steels are weldable by all the appropriate processes when following the rules of technology.

A maximum value of the carbon equivalent value (CEV) based on the heat analysis can be agreed upon at the time of enquiry and order. The CEV shall be determined using [Formula \(1\)](#):

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15} \quad (1)$$

#### 7.3.2 Bending and cold-edging ability

The products of steel grades according to [Annexes A](#) and [B](#) are suitable for cold forming.

Mandatory bending radii at 180° values are in [Tables A.3](#) and [B.3](#).

As an option, other bending radii according to [Table B.4](#) can be agreed at the time of the order.