



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 20337:2019**  
**01-september-2019**

---

**Z vlakni ojačeni kompozitni polimerni materiali - Metoda strižnega preskusa z uporabo strižnega okvira za ugotavljanje odziva na ravninsko strižno/natezno obremenitev in strižnega modula (ISO 20337:2018)**

Fibre-reinforced plastic composites - Shear test method using a shear frame for the determination of the in-plane shear stress/shear strain response and shear modulus (ISO 20337:2018)

Faserverstärkte Kunststoffe - Schubversuch mittels Schubrahmen zur Ermittlung der Schubspannungs-/Schubverformungskurve und des Schubmoduls in der Lagenebene (ISO 20337:2018)

<https://standards.iteh.ai/catalog/standards/sist/87591009-b941-4d09-8959-655023e0457/sist-pr-en-20337-2019>

Composites plastiques renforcés de fibres - Méthode d'essai de cisaillement à l'aide d'un châssis de cisaillement pour la détermination de la contrainte de cisaillement /déformation au cisaillement dans le plan et du module de cisaillement (ISO 20337:2018)

**Ta slovenski standard je istoveten z: prEN ISO 20337**

---

**ICS:**

83.120            Ojačani polimeri            Reinforced plastics

**oSIST prEN ISO 20337:2019**            **en,fr,de**



INTERNATIONAL  
STANDARD

ISO  
20337

First edition  
2018-11

---

---

**Fibre-reinforced plastic composites —  
Shear test method using a shear frame  
for the determination of the in-plane  
shear stress/shear strain response  
and shear modulus**

*Composites plastiques renforcés de fibres — Méthode d'essai  
de cisaillement à l'aide d'un châssis de cisaillement pour la  
détermination de la contrainte de cisaillement /déformation au  
cisaillement dans le plan et du module de cisaillement*

SIST EN ISO 20337:2019

<https://standards.iteh.ai/catalog/standards/sist/87591009-b941-4d09-8959-655032ec04f7/sist-en-iso-20337-2019>



Reference number  
ISO 20337:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 20337:2019  
<https://standards.iteh.ai/catalog/standards/sist/87591009-b941-4d09-8959-655032ec04f7/sist-en-iso-20337-2019>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Test apparatus</b> .....	<b>3</b>
5.1 Tensile test machine.....	3
5.1.1 General.....	3
5.1.2 Test speeds.....	3
5.1.3 Force indicator.....	3
5.2 Shear frame.....	3
5.3 Strain measurement.....	5
5.4 Micrometer.....	6
<b>6 Test specimens</b> .....	<b>6</b>
6.1 Shape and dimensions.....	6
6.2 Preparation of test specimens.....	7
6.3 Inspection of the test specimens.....	8
6.4 Number of test specimens.....	8
6.5 Conditioning of test specimens.....	8
<b>7 Procedure</b> .....	<b>8</b>
7.1 Test atmosphere.....	8
7.2 Determination of the test specimen thickness.....	8
7.3 Test speed.....	8
7.4 Data collection.....	8
7.5 Test termination.....	8
7.6 Failure mode.....	9
<b>8 Calculation and expression of results</b> .....	<b>10</b>
<b>9 Test report</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>12</b>

## ISO 20337:2018(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

SIST EN ISO 20337:2019

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

The test method described in this document uses a shear frame fixture in order to introduce a pure shear loading throughout the free area of the test specimens. The edges of the test specimens are uniformly clamped during the test procedure avoiding fibre rotation and load re-distribution effects. This allows for the ultimate shear strength of high shear-elongation materials to be obtained even at shear strains higher than 5 % which is a limitation when using ISO 14129 or other standards regarding in-plane shear test methods for fibre reinforced plastic composites.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN ISO 20337:2019](https://standards.iteh.ai/catalog/standards/sist/87591009-b941-4d09-8959-655032ec04f7/sist-en-iso-20337-2019)

<https://standards.iteh.ai/catalog/standards/sist/87591009-b941-4d09-8959-655032ec04f7/sist-en-iso-20337-2019>





# Fibre-reinforced plastic composites — Shear test method using a shear frame for the determination of the in-plane shear stress/shear strain response and shear modulus

## 1 Scope

This document specifies a method using a shear test apparatus for measuring the in-plane shear stress/shear strain response, shear modulus and shear strength of continuous-fibre-reinforced plastic composite materials with fibre orientations of 0° and 0°/90°.

This method is applicable to thermoset and thermoplastic matrix laminates made from unidirectional layers/non-woven fabrics and/or fabrics including unidirectional fabrics, with the fibres oriented at 0° and 0°/90° to the specimen axis, where the lay-up is symmetrical and balanced about the specimen mid-plane.

The method is suitable for determining shear properties in both the linear and nonlinear load-deformation range even at shear strains greater than 5 %.

Short and long fibre-reinforced plastic composites can also be tested using this document.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 1268 (all parts), *Fibre-reinforced plastics — Methods of producing test plates*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 2602, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 12781-1, *Geometrical product specifications (GPS) — Flatness — Part 1: Vocabulary and parameters of flatness*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### plane

plane spanned by coordinate axes 1 and 2

Note 1 to entry: See [Figure 2](#).

**ISO 20337:2018(E)****3.2  
in-plane shear stress**

$\tau_{12}$   
stress obtained by dividing the instantaneous tensile load acting on the shear frame by the specimen cross-sectional area

Note 1 to entry: See also [8.1](#).

Note 2 to entry: The in-plane shear stress is expressed in MPa.

**3.3  
in-plane shear strength**

$\tau_{12M}$   
maximum value for the shear stress

Note 1 to entry: See also [8.2](#).

Note 2 to entry: The in-plane shear strength is expressed in MPa.

**3.4  
shear strain**

$\gamma_{12}$   
sum of the individual components of the total shear strain of the test specimen

Note 1 to entry: See also [8.3](#).

**3.5  
in-plane shear modulus**

in-plane chord modulus

$G_{12}$   
shear stress difference  $\tau''_{12}$  and  $\tau'_{12}$  divided by the corresponding shear strain difference  $\gamma''_{12} = 0,005$  and  $\gamma'_{12} = 0,001$

Note 1 to entry: See also [8.4](#) and [Figure 4](#).

Note 2 to entry: The in-plane shear modulus is expressed in MPa.

**3.6  
direction of coordinate axis 1**

<test specimen> direction parallel to the loading axis of the test machine

Note 1 to entry: The fibres oriented at an angle of  $0^\circ$  are in this direction.

Note 2 to entry: See [Figure 2](#) and [Figure 3](#).

**3.7  
direction of coordinate axis 2**

<test specimen> direction orthogonal to the loading axis of the test machine

Note 1 to entry: The fibres oriented at an angle of  $90^\circ$  are in this direction.

Note 2 to entry: See [Figure 2](#) and [Figure 3](#).

**4 Principle**

A square test specimen with recessed corners and reinforcing fibres oriented at  $0^\circ$  and  $0^\circ/90^\circ$  to the specimen axis is held in a shear frame and subjected to pure shear loading. In order to determine the shear modulus and the shear strength, the tensile load acting on the shear frame and the associated shear strain are measured.

In this method, a test specimen is put in a state of pure shear, thus enabling testing to be carried out without interference by superimposed shear and other stresses, and, as a consequence, ensuring that the material characteristics are determined in a reproducible manner.

The test specimen is gripped along all its sides by a device exerting uniform, reproducible pressure and that is equipped with a follower mechanism enabling a constant gripping force to be maintained. The test specimens have no free edges, and therefore there are no load re-distribution effects which might otherwise affect the test results. Because the maximum shear stress occurs in the central portion of the test specimen, no invalid test results owing to material failure of the specimen at the edges where it is gripped are obtained.

## 5 Test apparatus

### 5.1 Tensile test machine

#### 5.1.1 General

The tensile test machine shall comply with ISO 7500-1 and meet the specifications given in [5.1.2](#) and [5.1.3](#).

#### 5.1.2 Test speeds

The testing machine shall be capable of maintaining the test speeds as specified in [Table 1](#).

**Table 1 — Recommended test speeds**

Test speed $v$ mm/min	Tolerance %
0,125	±20
0,25	
0,5	
1	
2	
4	
10	
20	±10
50	
100	
200	
300	
500	

#### 5.1.3 Force indicator

The force measurement system shall comply with class 1 as defined in ISO 7500-1.

### 5.2 Shear frame

The specimen is placed inside two identical halves of a shear frame and is held in place by means of a clamping device which controls the grip on the specimen in its plane along all its sides and ensures that this clamping force is applied to the specimen in a uniform and reproducible manner throughout the test. The kinematic principle of the shear frame, deforming the square test specimen into a rhombic specimen when an axial force is applied, is shown in [Figure 1](#).