
Pločevina za pokrivanje streh in oblaganje sten - Specifikacija za samonosilne proizvode iz jeklene, aluminijeve pločevine ali pločevine iz nerjavnega jekla - 1. del: Jeklo

Roofing and cladding products from metal sheet - Specification for self-supporting products of steel, aluminium or stainless steel sheet - Part 1: Steel

Dachdeckungs- und Wandbekleidungsprodukte aus Metallblech - Spezifikation für selbsttragende Dachdeckungsprodukte aus Stahlblech, Aluminiumblech oder nichtrostendem Stahlblech - Teil 1: Stahl

Produits de couverture et de bardage en tôle métallique - Spécification pour les produits autoportants en tôle d'acier, d'aluminium ou d'acier inoxydable - Partie 1 : Acier

Ta slovenski standard je istoveten z: prEN 508-1

ICS:

| | | |
|-----------|--|---------------------------------------|
| 77.140.50 | Ploščati jekleni izdelki in polizdelki | Flat steel products and semi-products |
| 91.060.20 | Strehe | Roofs |

oSIST prEN 508-1:2020 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 508-1:2020](#)

<https://standards.iteh.ai/catalog/standards/sist/d9480a43-d43a-4825-a8bc-a797104ae1c4/osist-pren-508-1-2020>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 508-1

April 2020

ICS 91.060.20

Will supersede EN 508-1:2014

English Version

Roofing and cladding products from metal sheet - Specification for self-supporting products of steel, aluminium or stainless steel sheet - Part 1: Steel

Produits de couverture et de bardage en tôle
métallique - Spécification pour les produits
autoportants en tôle d'acier, d'aluminium ou d'acier
inoxydable - Partie 1 : Acier

Dachdeckungs- und Wandbekleidungsprodukte aus
Metallblech - Spezifikation für selbsttragende
Dachdeckungsprodukte aus Stahlblech,
Aluminiumblech oder nichtrostendem Stahlblech - Teil
1: Stahl

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 128.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

| Contents | Page |
|--|-------------|
| European foreword..... | 3 |
| Introduction | 4 |
| 1 Scope | 5 |
| 2 Normative references | 5 |
| 3 Terms, definitions, symbols and abbreviations | 6 |
| 3.1 General | 6 |
| 3.2 Material definitions | 6 |
| 3.3 Profile definitions | 7 |
| 3.4 Product geometry | 9 |
| 3.5 Symbols and abbreviations | 12 |
| 4 Requirements | 13 |
| 4.1 General | 13 |
| 4.2 Materials | 13 |
| 4.3 Products | 15 |
| 5 Test methods | 17 |
| 5.1 Material properties | 17 |
| 5.2 Mechanical properties | 17 |
| 6 Designation | 17 |
| 7 Marking, labelling and packaging | 17 |
| 7.1 Marking and labelling | 17 |
| 7.2 Packaging and special ordering conditions | 18 |
| 7.3 Transport, storage and handling | 18 |
| Annex A (informative) Aluminium coated steel sheet (type A) | 19 |
| Annex B (normative) Multilayer coated steel sheet | 21 |
| Annex C (informative) Metallic coatings | 23 |
| Annex D (normative) Dimensional tolerances | 26 |
| Bibliography | 45 |

European foreword

This document (prEN 508-1:2020) has been prepared by Technical Committee CEN/TC 128 “Roof covering products for discontinuous laying and products for wall cladding”, the secretariat of which is held by NBN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 508-1:2014.

In comparison with EN 508-1:2014 the following technical changes have been made:

- the scope of the document has been extended to cladding products;
- a reference has been added to ZM (hot dip zinc-magnesium) coating;
- a bending requirement has been added;
- three grades have been added 390, 420 and 450;
- minimum nominal coating masses have been added for exterior applications.

These changes or additions can be found in the following Clauses and subclauses: Clause 1; 3.2.4; 3.2.6; 3.2.7; 3.5; 4.1; 4.2.1; 4.2.2; 4.2.3; 4.3.1; 4.3.3.1 and Annex C.

EN 508 Roofing products from metal sheet - Specification for self-supporting products of steel, aluminium or stainless steel sheet consists of the following parts:

- Part 1: Steel; <https://standards.iteh.ai/catalog/standards/sist/d9480a43-d43a-4825-a8bc-a797104ae1c4/osist-pren-508-1-2020>
- Part 2: Aluminium;
- Part 3: Stainless steel.

Introduction

Figure 1 indicates the position of this document in the CEN framework of standards concerning roofing and cladding products of metal sheet.




Figure 1 — Framework of standards

In this document, the performance of the product has been defined in terms of calculation and a number of type tests.

The performance of a roof constructed with these products depends not only on the properties of the product as required by this document, but also on the design, construction and performance of the roof as a whole in relation to the environment and conditions of use.

1 Scope

This part of EN 508 specifies requirements for self-supporting roofing, covering, wall cladding, lining, liner tray and tile products for discontinuous laying made from metallic coated steel sheet with or without additional organic coatings. Sheets intended to be used with insulation and membranes are also covered.

This document establishes general characteristics, definitions, classifications and labelling for the products, together with requirements for the materials from which the products can be manufactured. It is intended to be used either by manufacturers to ensure that their products comply with the requirements or by purchasers to verify that the products comply when purchased before they are despatched from the factory. It specifies the requirements for products which enable them to meet all normal service conditions.

This document applies to all discontinuously laid self-supporting external profiled sheets for roofing covering, wall cladding, lining, and liner trays, with the exception of tiles with a surface area less than 1 m² and produced by stamping. These profiled sheets are designed to keep wind, rain and snow out of the building and to transfer any resultant loads and infrequent maintenance loads to the structure.

This document does not cover products for structural purposes, i.e. it does cover products used in constructions of structural Class III (according to EN 1993-1-3), it does not cover products used in constructions of structural Classes I and II (according to EN 1993-1-3) intended to contribute to the global or partial stability of the building structure by providing racking resistance or resistance to permanent static loads (excluding self-weight of the metal sheet).

No requirements for supporting construction, design of roof, cladding, lining, tile system and execution of connections and flashings are included.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10143, *Continuously hot-dip coated steel sheet and strip - Tolerances on dimensions and shape*

EN 10169:2010+A1:2012, *Continuously organic coated (coil coated) steel flat products - Technical delivery conditions*

EN 10346, *Continuously hot-dip coated steel flat products for cold forming - Technical delivery conditions*

EN 14782, *Self-supporting metal sheet for roofing, external cladding and internal lining - Product specification and requirements*

EN ISO 6270-1, *Paints and varnishes - Determination of resistance to humidity – Part 1: Condensation (single-sided exposure) (ISO 6270-1)*

EN ISO 6988, *Metallic and other non-organic coatings - Sulfur dioxide test with general condensation of moisture (ISO 6988)*

EN ISO 9227, *Corrosion tests in artificial atmospheres - Salt spray tests (ISO 9227)*

3 Terms, definitions, symbols and abbreviations

3.1 General

For the purposes of this document, the terms and definitions given in EN 10169:2010+A1:2012 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1.1

self-supporting product

product which will, by virtue of its material and shape, support all applied loadings (e.g. snow, wind, foot traffic, insulation, membrane) and transmit these loadings to spaced structural supports

3.2 Material definitions

3.2.1

hot-dip zinc coated steel sheet (type Z)

product obtained by continuously hot-dip zinc coating cold reduced strips of either low carbon steel for cold forming or steel of structural quality

Note 1 to entry: see EN 10346.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.2.2

hot-dip zinc-aluminum coated steel sheet (type ZA)

product obtained by continuously hot-dip coating cold reduced strips of low carbon steel for cold forming or steel of structural quality on a production line using an alloy consisting of zinc and approximately 5 % aluminium (nominal percentage by mass)

Note 1 to entry: see EN 10346.

3.2.3

hot-dip aluminum-zinc alloy coated steel sheet (type AZ)

product obtained by continuously hot-dip coating cold reduced strips of low carbon steel for cold forming or steel of structural quality on a production line using an alloy consisting of:

- 55 % aluminium (nominal percentage by mass);
- 1,6 % silicon (nominal percentage by mass);
- and the balance zinc

Note 1 to entry: see EN 10346.

3.2.4

hot dip zinc-magnesium coated steel sheet (type ZM)

product obtained by continuously hot-dip coating cold reduced strips of low carbon steel for cold forming or steel of structural quality on a production line using an alloy of zinc-aluminium-magnesium

Note 1 to entry: The composition of the molten coating alloy is a sum of aluminium and magnesium from 1,5 % to 8 %, containing a minimum of 0,2 % magnesium and the balance zinc.

Note 2 to entry: For information on chemical composition and density, the manufacturer may be asked for advice.

Note 3 to entry: see EN 10346

Note 4 to entry: The corrosion performance depends on the ZM composition

3.2.5

hot-dip aluminium coated steel sheet (type A)

product obtained by continuously hot-dip aluminium coating cold reduced strips of low carbon steel for cold forming steel or steel of structural quality on a production line

Note 1 to entry: See Annex A.

3.2.6

organic coated steel sheet

product obtained by factory application of paint by roller or spray processes, or factory application of laminated organic film, on substrates of type Z, type ZA, type AZ, type ZM, or type A coated steel sheet

Note 1 to entry: EN 10169:2010+A1:2012 refers to this type of coated steel.

3.2.7

multilayer coated steel sheet

product obtained by continuously coating on both sides hot-dip metal coated (type Z, type ZA, type AZ, type ZM, or type A) cold reduced strips of low carbon steel for cold forming or steel of structural quality with one or multiple applications of thermoplastic asphalt compounds (minimum thickness 1,5 mm) and subsequent lamination of a metal foil with or without decorative painting

Note 1 to entry: See Annex B.

3.3 Profile definitions

3.3.1

trapezoidal profiled sheet

self-supporting sheet which is designed to allow it to be side and end lapped, the crowns of which may be rounded and, in addition, the crowns, webs and valleys may be stiffened

Note 1 to entry: See Figures 2, 3, 4 and 5.



Figure 2 — Part of typical trapezoidal profile



Figure 3 — Part of typical trapezoidal profile with rounded crowns




Figure 4 — Part of typical trapezoidal profile with stiffened crown and web

prEN 508-1:2020 (E)





Figure 5 — Part of typical trapezoidal profile with stiffened valley

3.3.2

sinusoidal profiled sheet

self-supporting sheet which is designed to allow it to be side and end lapped, comprising a series of arc shaped crowns and valleys interconnected with tangential webs

Note 1 to entry: See Figure 6.

**Key**

- 1 depth
- 2 pitch

Figure 6 — Part of typical sinusoidal profiled sheet

iTeh STANDARD PREVIEW

(standards.iteh.ai)

3.3.3

standing seam and concealed fix sheet

self-supporting sheet profiled in such a way that the fixings are hidden within the construction and are not exposed to the weather

<https://standards.iteh.ai/catalog/standards/sist/d9480a43-d43a-4825-a8bc-a797104ee1c4/osist-pr-en-508-1-2020>

Note 1 to entry: The profile shape is designed to allow the formation of side laps on site.

Note 2 to entry: As these types of roof covering products are used in proprietary roofing or cladding systems, no structural requirements are given within this part of EN 508.

Note 3 to entry: See Figures 7 and 8.

Note 4 to entry: These products are normally designed by testing.



Figure 7 — Typical standing seam profile




Figure 8 — Typical concealed fix profile

3.3.4 tile profiles

parts of typical tile profiled sheets that can allow the sheet to be side and/or end lapped

Note 1 to entry: The tile profile may include transverse steps.

Note 2 to entry: As these types of roof covering or cladding products are used in proprietary systems no structural requirements are given within this part of EN 508.

Note 3 to entry: See Figure 9 a), b) and c).

Note 4 to entry: These products are normally designed by testing.




Figure 9 — Typical tile profiles

3.4 Product geometry

(standards.iteh.ai)

NOTE The names for various parts of typical trapezoidal profiled sheets are given in Figure 10 and 11, with additional definitions for sinusoidal profiles in Figure 12 and tile profiles in Figure 13.

prEN 508-1:2020 (E)






Figure 10 — Definitions of the parts of typical trapezoidal profiled sheets



Key

- 1 bend radius
- 2 end lap
- 3 web angle
- 4 overlap
- 5 underlap
- 6 side lap in principle the same on tiles

Figure 11 — Definitions of the parts of typical trapezoidal profiled sheets



Key

- 1 depth
- 2 pitch

Figure 12 — Definitions of the parts of typical sinusoidal profiled sheets