



Designation: D 5868 – 01

Standard Test Method for Lap Shear Adhesion for Fiber Reinforced Plastic (FRP) Bonding¹

This standard is issued under the fixed designation D 5868; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes a lap shear test for use in measuring the bonding characteristics of adhesives for joining fiber reinforced plastics to themselves and to metals. The method is applicable to random and fiber oriented FRP.

1.2 This test method is intended to complement Test Method D 1002 and extend the application to single-lap shear adhesive joints of fiber-reinforced plastic (FRP) adherends. This test method is useful for generating comparative apparent shear strength data for joints made from a number of FRP materials, providing a means by which FRP surface treatments may be compared.

1.3 The values stated in inch-pound units are to be regarded as the standard. The SI values in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*
D 1002 Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading (Metal-to-Metal)²
D 2093 Practice for Preparation of Surfaces of Plastics Prior to Adhesive Bonding²
D 3163 Test Method for Determining the Strength of Adhesively Bonded Rigid Plastic Lap-Shear Joints in Shear by Tension Loading²
D 4896 Guide for Use of Adhesive-Bonded Single Lap-Joint Specimen Test Results²
D 907 Terminology of Adhesives²
D 5573 Practice for Classifying Failure Modes in Fiber-Reinforced-Plastic (FRP) Joints²

¹ This test method is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.40 on Adhesives for Plastics.

Current edition approved March 10, 2001. Published May 2001. Originally published as D 5868 - 95. Last previous edition D 5868 - 95.

² *Annual Book of ASTM Standards*, Vol 15.06.

E 4 Practices for Force Verification of Testing Machines³

2.2 *SAE Standard:*

SAE J1525 Lap Shear Test for Automotive-Type Adhesives for Fiber Reinforced Plastic (FRP) Bonding⁴

3. Terminology

3.1 Adhesive terminology for this test method is covered in Terminology D 907.

4. Summary of Test Method

4.1 This test method describes a procedure for the testing of lap shear bond strengths, using composite materials not recommended in Test Method D 3163 such as FRP.

5. Significance and Use

5.1 Due to the increased use of adhesively-bonded FRP as a result of the inherent advantages afforded by bonded rather than mechanically-fastened joints (particularly the alleviation of stress risers and stress cracking), there is a need for tests by which joints of various FRP substrates and adhesives may be compared. This test method is intended to meet such a need.

5.2 Additional information on significance and use may be found in Guide D 4896.

6. Interference

6.1 Apparent shear strength may be affected by substrate properties, such as moisture absorption and strength.

7. Apparatus

7.1 *Testing Machine*, conforming to the requirements and having the capabilities of the machine in Practices E 4 with self-aligning grips capable of securely grasping the specimen throughout the test without allowing the specimen to slip.

8. Procedure

8.1 *Test Substrate:*

8.1.1 *Substrates*—Fiber reinforced plastic (FRP) as specified, with metal composition (heat treat, temper, and condition) and roughness as specified when bonding FRP to metal.

³ *Annual Book of ASTM Standards*, Vol 03.01.

⁴ Available from the Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096-0001.