



Designation: D 5870 – 95

Standard Practice for Calculating Property Retention Index of Plastics¹

This standard is issued under the fixed designation D 5870; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers procedures for the calculation of a property retention index (PRI) of thermoplastic and thermoset plastics after exposure to thermal aging, natural or artificial accelerated weathering, or chemical exposures.

1.2 This practice is not intended to establish a fixed procedure for conducting the exposure test, but it is intended to provide a set of specific procedures used to calculate the retention index of a characteristic property of the material after it has been exposed. Selection of the specific exposure test conditions depends on the material being tested and the property being measured. It is up to the user to determine which exposure test conditions are most relevant to the specific material and the service condition being used. The exposure test used must be conducted according to conditions described in specific exposure standards.

1.3 This practice does not describe procedures for sampling the materials to be tested. These procedures are described in the standards and specifications applicable to the material being evaluated.

1.4 The procedure used to calculate the PRI depends on whether the test used to characterize the materials being exposed is destructive or nondestructive. The PRI can be useful in describing short-term mechanical, electrical, and other properties of plastics at specified temperatures after the materials have been subjected to an exposure test.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO standard. ISO DIS 11248 is significantly different since it pertains only to thermosetting resins.

2. Referenced Documents

2.1 ASTM Standards:

D 543 Test Method for Resistance of Plastics to Chemical Reagents²

D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing²

D 883 Terminology Relating to Plastics²

D 1435 Practice for Outdoor Weathering of Plastics²

D 1499 Practice for Operating Light- and Water-Exposure Apparatus (Carbon-Arc Type) for Exposure of Plastics²

D 1898 Practice for Sampling of Plastics²

D 2565 Practice for Operating Xenon Arc-Type Light Exposure Apparatus With and Without Water for Exposure of Plastics³

D 3045 Practice for Heat Aging of Plastics Without Load³

D 4329 Practice for Operating Light- and Water-Exposure Apparatus (Fluorescent UV-Condensation Type) for Exposure of Plastics⁴

D 4364 Practice for Performing Accelerated Outdoor Weathering of Plastics Using Concentrated Natural Sunlight⁴

D 4459 Practice for Operating an Accelerated Lightfastness Xenon-Arc-Type (Water Cooled) Light-Exposure Apparatus for the Exposure of Plastics for Indoor Applications⁴

D 4674 Test Method for Accelerated Testing for Color Stability of Plastics Exposed to Indoor Fluorescent Lighting and Window-Filtered Daylight⁴

G 113 Terminology Relating to Natural and Artificial Weathering Test of Nonmetallic Materials⁵

2.2 ISO Standards:⁶

ISO 291 Plastics—Standard Atmospheres for Conditioning and Testing

ISO 877 Plastics—Methods of Exposure to Direct Weathering, to Weathering Using Glass Filtered Daylight, and to Intensified Weathering by Daylight Using Fresnel Mirrors

ISO 4892 Plastics—Methods of Exposure to Laboratory Light Sources Part 1: General Guidance, Part 2: Xenon Arc Exposures, Part 3: Fluorescent UV Exposures, and Part 4: Filtered Open Flame Carbon Arc Exposures

ISO DIS 11248 Plastics—Thermosetting Molding Materials, Evaluation of Short-Term Performance at Elevated Temperatures

¹ This practice is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.50 on Durability of Plastics.

Current edition approved December 10, 1995. Published February 1996.

² *Annual Book of ASTM Standards*, Vol 08.01.

³ *Annual Book of ASTM Standards*, Vol 08.02.

⁴ *Annual Book of ASTM Standards*, Vol 08.03.

⁵ *Annual Book of ASTM Standards*, Vol 14.02.

⁶ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

3. Terminology

3.1 *Definitions:* The terminology given in Terminologies D 883 and G 113 is applicable to this practice.

4. Significance and Use

4.1 The property retention index (PRI) determined by this practice is intended primarily to provide relative durability performance information on materials for design engineers. It is up to the user to ensure that appropriate sampling procedures are used for the selection of specimens to be exposed so that the PRI data obtained is actually representative of the material being evaluated.

4.2 The PRI obtained depends on the material being tested, property being evaluated, and exposure condition used. A PRI obtained for one property will probably not be the same as the PRI for a different property of the same material, even if the same exposure test is used.

4.3 Plastics exposed to a combination of environmental and thermal treatments may undergo a change in functional performance. Any laboratory-accelerated aging procedure, especially those that use only a single stress, may not realistically indicate the changes a plastic may undergo in actual use conditions. This practice provides a means for expressing the changes in properties as a function of time exposed in a wide variety of tests. The PRI data obtained is best used for comparing the performance of materials subjected to the same exposure test simultaneously.

4.3.1 Both laboratory-accelerated and outdoor exposure testing can be highly variable, and the PRI data will be influenced by this variability. For example, PRI data from outdoor exposures can vary depending on the exposure location and the time of year when the exposure is conducted. Variability in laboratory-accelerated exposure tests can result in large differences in PRI data from two laboratories running supposedly identical tests. PRI data obtained from exposure to laboratory-accelerated tests cannot be used to predict the PRI for exposure to natural weathering or actual use conditions unless there is a sufficient amount of data from both types of exposure to allow valid statistical comparisons.

4.4 A number of different exposure techniques can be used to provide information on the effects of environmental stresses such as light, heat, and water on plastics (see Practices D 1435, D 1499, D 2565, D 4329, D 4364, and D 4459; Test Method D 4674; and ISO 4892 and 877). When it is desirable to evaluate the effects of heat alone, exposures should be conducted in accordance with Practice D 3045. When it is desirable to evaluate the effects of chemical exposures, the exposures should be conducted in accordance with Test Method D 543.

4.5 There are a number of factors influencing the physical properties and the retention of these properties after exposure. In addition to a complete description of the exposure test conditions used, the following information shall be included in any report referencing this practice: (1) complete description of the material tested, including the type, source, manufacturer's code number, form, and previous history; (2) methods of preparation for the material and individual test specimens; (3) procedure used for specimen conditioning prior to and after

exposure; (4) complete description of the environment in which the physical properties were determined (for example, temperature and relative humidity); (5) complete description of the procedure used to determine the physical properties tested, including the rate at which specimens were tested, if applicable; (6) if applicable, void content of the specimens tested and the method used to measure void content.

NOTE 2—It is not the intent of this practice to require users to divulge proprietary information regarding composition. To avoid divulging proprietary information, generic descriptions may be used to provide information on material composition.

4.6 When destructive tests are used to determine a physical or chemical change, or both, which occurs as a result of exposure, the amount of change is expressed as a function of the value obtained for the material tested at a specified test environment (for example, temperature and humidity). The exposed and reference specimens are measured at the same time in the specified test environment.

4.7 When nondestructive tests are used to determine a physical or chemical change, or both, which occurs as a result of exposure, the amount of change is expressed as a function of the value obtained on the specimens prior to exposure. Property measurement tests on the specimens before and after exposure shall be conducted at the same conditions (for example, temperature and humidity).

4.8 The property or properties to be measured may be specified in an ASTM, ISO, or other appropriate standard for the material being tested, or by any prior agreement between interested parties. If the method used to measure the property being evaluated is not described in an ASTM, ISO, or other appropriate standard, a description of the test method shall be included in the report of test results.

4.9 It is realized that a material cannot be tested without specifying the method of preparation. To have any meaning in comparative testing, specimens of each material being evaluated by these test procedures should be prepared or molded from the same lot under identical processing conditions and randomized prior to testing at the conditions desired. It must be realized that lot-to-lot variation in the material may cause additional variability in results.

NOTE 3—For those plastics with a T_g greater than ambient, the slow collapse of free volume, with attendant significant changes in mechanical properties such as fatigue resistance, impact resistance, yield stress, and vapor transmission, etc. will be accelerated at elevated temperatures below the T_g but will be reversed at temperatures above the T_g . Therefore, incubation at elevated temperatures in the T_g range may be erratically susceptible to oven fluctuation effects.

4.10 The results depend on which side of the test specimen is exposed with some tests. In bending tests, for example, different results are obtained according to whether the exposed surface or the unexposed surface of the test specimen is placed under tension. Care must be taken to ensure that all specimens being exposed have the same orientation in the test fixture used to hold the specimens during exposure. In addition, the results also depend on the orientation of test specimens during the procedure used to measure the property being monitored. This is especially true with impact tests. During the procedure used