



SLOVENSKI STANDARD
oSIST prEN ISO 17636-1:2021
01-junij-2021

**Neporušitveno preskušanje zvarnih spojev - Radiografske preiskave - 1. del:
Tehnike z rentgenskimi in gama žarki z uporabo filmov (ISO/DIS 17636-1:2021)**

Non-destructive testing of welds - Radiographic testing - Part 1: X- and gamma-ray techniques with film (ISO/DIS 17636-1:2021)

Zerstörungsfreie Prüfung von Schweißverbindungen - Durchstrahlungsprüfung - Teil 1: Röntgen- und Gammastrahlungstechniken mit Filmen (ISO/DIS 17636-1:2021)

Contrôle non destructif des assemblages soudés - Contrôle par radiographie - Partie 1: Techniques par rayons X ou gamma à l'aide de film (ISO/DIS 17636-1:2021)

<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-13094e3149d8/osist-pr-en-iso-17636-1-2021>

Ta slovenski standard je istoveten z: prEN ISO 17636-1

ICS:

25.160.40 Varjeni spoji in vari Welded joints and welds

oSIST prEN ISO 17636-1:2021 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 17636-1:2021](https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 17636-1

ISO/TC 44/SC 5

Secretariat: AFNOR

Voting begins on:
2021-04-16Voting terminates on:
2021-07-09

Non-destructive testing of welds — Radiographic testing — Part 1: X- and gamma-ray techniques with film

*Contrôle non destructif des assemblages soudés — Contrôle par radiographie —
Partie 1: Techniques par rayons X ou gamma à l'aide de film*

ICS: 25.160.40

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 17636-1:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 17636-1:2021](https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
Introduction	vii
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	3
5 Classification of radiographic techniques	3
6 General preparations and requirements	4
6.1 Protection against ionizing radiation.....	4
6.2 Surface preparation and stage of manufacture.....	4
6.3 Location of the weld in the radiograph.....	4
6.4 Identification of radiographs.....	4
6.5 Marking.....	4
6.6 Overlap of films.....	4
6.7 Types and positions of image quality indicators.....	5
6.8 Evaluation of image quality.....	5
6.9 Minimum image quality values.....	6
6.10 Personnel qualification.....	6
7 Recommended techniques for making radiographs	6
7.1 General.....	6
7.2 Test arrangements.....	7
7.2.1 General.....	7
7.2.2 Radiation source located in front of the object and with the film at the opposite side (see Figure 1).....	7
7.2.3 Radiation source located outside the object and film inside (see Figures 2 to 4).....	8
7.2.4 Radiation source centrally located inside the object and with the film outside (see Figures 5 to 7).....	9
7.2.5 Radiation source located off-centre inside the object and film outside (see Figures 8 to 10).....	9
7.2.6 Elliptical technique (see Figure 11).....	10
7.2.7 Perpendicular technique (see Figure 12).....	11
7.2.8 Radiation source located outside the object and film on the other side (see Figures 13 to 18).....	11
7.2.9 Technique for different material thicknesses (see Figure 19).....	13
7.3 Choice of tube voltage and radiation source.....	13
7.3.1 X-ray devices up to 1 000 kV.....	13
7.3.2 Other radiation sources.....	14
7.3.3 Film systems and metal screens.....	15
7.4 Alignment of beam.....	17
7.5 Reduction of scattered radiation.....	17
7.5.1 Metal filters and collimators.....	17
7.5.2 Interception of backscattered radiation.....	17
7.6 Source-to-object distance.....	18
7.7 Maximum area for a single exposure.....	20
7.8 Density of radiograph.....	20
7.9 Processing.....	21
7.10 Film viewing conditions.....	21
8 Test report	21
Annex A (normative) Number of exposures which give an acceptable examination of a circumferential butt weld	23

ISO/DIS 17636-1:2021(E)

Annex B (normative) Minimum image quality values	28
Annex C (informative) The maximum tube voltages of Figure 20	35
Bibliography	36

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 17636-1:2021](https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021)
<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44 *Welding and allied processes*, Subcommittee SC 5 *Testing and inspection of welds*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces ISO 17636-1:2013, which has been technically revised.

The main changes compared to the previous edition are as follows:

- the normative references have been updated;
- the figures have been updated;
- in [6.9](#) the lower thickness limit for Se-75 applications has been deleted;
- in [7.3.2](#) the lower thickness limit for Se-75 by agreement of contracting parties has been deleted;
- Update of references to the [Figures 1](#) to [19](#) in the whole document;
- in [6.7](#) the usage of ASTM wires and other IQIs by agreement of contracting parties has been added;
- Clarification for measurement of optical density in the weld root;
- Clarification for IQI usage for DWDI technique;
- Addition of the acceptance of shorter wire visibility than 10 mm for pipes with an external diameter < 50 mm in [6.7 a](#));
- the document has been editorially revised.

A list of all parts in the ISO 17636 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO/DIS 17636-1:2021(E)

Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 17636-1:2021](https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021)
<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021>

Introduction

This document specifies fundamental techniques of radiography with the objective of enabling satisfactory and repeatable results. The techniques are based on generally recognized practice and fundamental theory of the subject, inspection of fusion welded joints with industrial radiographic films.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 17636-1:2021](https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 17636-1:2021](https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-d3094c3149d8/osist-pren-iso-17636-1-2021>

Non-destructive testing of welds — Radiographic testing —

Part 1: X- and gamma-ray techniques with film

1 Scope

This document specifies techniques of radiographic examination of fusion welded joints in metallic materials using industrial radiographic film techniques.

This document applies to the joints of plates and pipes. Besides its conventional meaning, “pipe” as used in this document it covers other cylindrical bodies such as tubes, penstocks, boiler drums, and pressure vessels.

NOTE This document complies with most requirements of ISO 5579 [1].

This document does not specify acceptance levels for any of the indications found on the radiographs.

If contracting parties apply lower test criteria, it is possible that the quality achieved is significantly lower than when this document is strictly applied.

2 Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5576, *Non-destructive testing — Industrial X-ray and gamma-ray radiology — Vocabulary*

ISO 5580, *Non-destructive testing — Industrial radiographic illuminators — Minimum requirements*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 11699-1, *Non-destructive testing — Industrial radiographic film — Part 1: Classification of film systems for industrial radiography*

ISO 11699-2, *Non-destructive testing — Industrial radiographic films — Part 2: Control of film processing by means of reference values*

ISO 19232-1, *Non-destructive testing — Image quality of radiographs — Part 1: Determination of the image quality value using wire-type image quality indicators*

ISO 19232-2, *Non-destructive testing — Image quality of radiographs — Part 2: Determination of the image quality value using step/hole-type image quality indicators*

EN 12543 (all parts), *Non-destructive testing — Characteristics of focal spots in industrial X-ray systems for use in non-destructive testing*

EN 12679, *Non-destructive testing — Determination of the size of industrial radiographic sources — Radiographic method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5576 and the following apply.

ISO/DIS 17636-1:2021(E)

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1**nominal thickness***t*

nominal thickness of the parent material only where manufacturing tolerances do not have to be taken into account

3.2**penetration thickness change** Δt

change of penetrated thickness relative to the nominal thickness due to beam angle

3.3**penetrated thickness***w*

thickness of material in the direction of the radiation beam calculated on the basis of the nominal thicknesses of all penetrated walls

3.4**object-to-film distance***b*

distance between the radiation side of the radiographed part of the test object and the film surface measured along the central axis of the radiation beam

3.5**source size***d*

size of the radiation source or focal spot size

oSIST prEN ISO 17636-1:2021
<https://standards.iteh.ai/catalog/standards/sist/ed782a03-c9f9-4c11-9d4f-1399-2149d8/osist-pr-en-iso-17636-1-2021>

Note 1 to entry: See EN 12679 or EN 12543.

3.6**source-to-film distance**

SFD

distance between the source of radiation and the film measured in the direction of the beam

Note 1 to entry: $SFD = f + b$

where

f source-to-object distance

b object-to-film distance

3.7**source-to-object distance***f(SOD)*

distance between the source of radiation and the source side of the test object measured along the central axis of the radiation beam

3.8**external diameter***D_e*

nominal external diameter of the pipe

3.9**Region of Interest**

RoI

minimum area which should be visible on the radiograph and contains the weld and the heat affected zone (HAZ) on both sides

3.10**Area of Interest**

AoI

minimum area which should be visible on the radiograph and contains the weld, the heat affected zone HAZ on both sides and all IQIs

4 Symbols and abbreviated terms

For the purposes of this document, the symbols given in [Table 1](#) apply.

Table 1 — Symbols and terms

Symbol	Term
b	object-to-film distance
b'	object-to-film distance perpendicular to test object
D_e	external diameter
d	source size
f	source-to-object distance
f'	source-to-object distance perpendicular to test object
f_{\min}	minimum source-to-object distance
t	nominal thickness
Δt	penetration thickness change
w	penetrated thickness
F	film
IQI	image quality indicator
S	radiation source
SFD	source-to-film distance

NOTE Object-to-film distance (OFD) is equivalent to b .

Object-to-detector distance (ODD) as used in part 2 is equivalent to b .

The source-to-detector-distance (SDD) as used in digital radiography is equivalent to SFD.

The source-to-object distance (SOD) is equivalent to f .

5 Classification of radiographic techniques

The radiographic techniques are divided into two classes:

- Class A: basic techniques;
- Class B: improved techniques.

Class B techniques are used when class A might be insufficiently sensitive.

Radiographic techniques providing higher sensitivity than class B are possible and may be agreed between the contracting parties by specification of all appropriate test parameters.

The choice of radiographic technique shall be agreed between the contracting parties.