



SLOVENSKI STANDARD
oSIST prEN ISO 3262-20:2020

01-marec-2020

Polnila - Specifikacije in preskusne metode - 20. del: Pirogeni silicijev dioksid (kremenčev dim) (ISO/DIS 3262-20:2020)

Extenders - Specifications and methods of test - Part 20: Fumed silica (ISO/DIS 3262-20:2020)

Füllstoffe für Beschichtungsstoffe - Anforderungen und Prüfverfahren - Teil 20: Pyrogenes Siliciumdioxid (ISO/DIS 3262-20:2020)

Matières de charge - Spécifications et méthodes d'essai - Partie 20: Silice pyrogénée (ISO/DIS 3262-20:2020)

[kSIST PrEN ISO 3262-20:2021](https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427e1e94190b/ksist-pr-en-iso-3262-20-2020)

<https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427e1e94190b/ksist-pr-en-iso-3262-20-2020>

Ta slovenski standard je istoveten z: prEN ISO 3262-20

ICS:

87.060.10 Pigmenti in polnila Pigments and extenders

oSIST prEN ISO 3262-20:2020 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[kSIST FprEN ISO 3262-20:2021](https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-fpren-iso-3262-20-2021)

<https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-fpren-iso-3262-20-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 3262-20

ISO/TC 256

Secretariat: DIN

Voting begins on:
2020-01-31Voting terminates on:
2020-04-24

Extenders — Specifications and methods of test —

Part 20: Fumed silica

*Matières de charge pour peintures — Spécifications et méthodes d'essai —**Partie 20: Silice pyrogénée*

ICS: 87.060.10

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 3262-20:2021](https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-fpren-iso-3262-20-2021)<https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-fpren-iso-3262-20-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 3262-20:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 3262-20:2021](https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-fpren-iso-3262-20-2021)

<https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-fpren-iso-3262-20-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Requirements and test methods.....	2
5 Sampling.....	2
6 Determination of silica content.....	2
6.1 Principle.....	2
6.2 Reagents.....	3
6.3 Apparatus.....	3
6.4 Procedure.....	3
6.5 Expression of results.....	4
6.6 Precision.....	4
7 Determination of aluminium oxide, titanium (IV) oxide and iron (III) oxide contents by spectrometry.....	4
7.1 Principle.....	4
7.2 Reagents and materials.....	4
7.3 Apparatus.....	5
7.4 Procedure.....	6
7.5 Expression of results.....	8
7.6 Precision.....	8
8 Determination of carbon content.....	9
8.1 Principle.....	9
8.2 Reagents and materials.....	9
8.3 Apparatus.....	9
8.4 Procedure.....	10
8.5 Expression of results.....	10
8.6 Precision.....	10
9 Determination of chloride content.....	11
9.1 Principle.....	11
9.2 Reagents.....	11
9.3 Apparatus.....	11
9.4 Procedure.....	11
9.5 Expression of results.....	12
9.6 Precision.....	12
10 Test report.....	12

ISO/DIS 3262-20:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuff and extenders*.

This second edition cancels and replaces the first edition (ISO 3262-20:2000), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the main title has been changed from "Extenders for paints" to "Extenders";
- in [Table 1](#) carbon content has been revised and organic surface has been refined;
- in [6.3.4](#) magnesium perchlorate has been changed to an example for a desiccant;
- in [8.2.3](#) suitable examples for carbon steel have been added;
- the text has been editorially revised and the normative references have been updated.

A list of all parts in the ISO 3262 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Extenders — Specifications and methods of test —

Part 20: Fumed silica

1 Scope

This document specifies requirements and corresponding methods of test for fumed silica.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 degrees C*

ISO 787-9, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 787-11, *General methods of test for pigments and extenders — Part 11: Determination of tamped volume and apparent density after tamping*

ISO 787-18, *General methods of test for pigments and extenders — Part 18: Determination of residue on sieve — Mechanical flushing procedure*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3262-1, *Extenders for paints — Specifications and methods of test — Part 1: Introduction and general test methods*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 3819, *Laboratory glassware — Beakers*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 18451-1, *Pigments, dyestuffs and extenders — Terminology — Part 1: General terms*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18451-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

fumed silica

amorphous silica produced from silicon halides by high-temperature flame hydrolysis

ISO/DIS 3262-20:2020(E)

4 Requirements and test methods

For fumed silica complying with this document, the essential requirements are specified in [Table 1](#) and the conditional requirements are listed in [Table 2](#).

Table 1 — Essential requirements

Characteristic	Unit	Requirement		Test method
		Grade A	Grade B	
Silica content, min.	% (mass fraction)	99,8		Clause 6
Oxide content		max. 0,05		Clause 7
— Al ₂ O ₃		max. 0,03		
— TiO ₂		max. 0,003		
— Fe ₂ O ₃				
Carbon content ^a		< 0,3	≥ 0,3 ^b	Clause 8
Chloride content		max. 0,025		Clause 9
Organic surface treatment or surface coating	—	No	Yes	Clause 8
Residue on 45 µm sieve	% (mass fraction)	max. 0,05	Not applicable	ISO 787-18
Matter volatile at 105 °C	% (mass fraction)	max. 3	max. 1	ISO 787-2
Loss on ignition	% (mass fraction)	max. 2,5	max. 10	ISO 3262-1
pH value of aqueous suspension	—	3,6 to 4,5	3,4 to 8 ^c	ISO 787-9
^a The carbon content is also part of the loss on ignition. https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-pr-en-iso-3262-20-2021				
^b Usually does not exceed 15 %. https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-pr-en-iso-3262-20-2021				
^c Use a 1:1 (mass fraction) mixture of water and methanol. https://standards.iteh.ai/catalog/standards/sist/74fc8897-a970-4fea-8a7a-427a1e9410ab/ksist-pr-en-iso-3262-20-2021				

Table 2 — Conditional requirements

Characteristic	Unit	Requirement		Test method
		Grade A	Grade B	
Apparent density after tamping	g/ml	To be agreed between the interested parties		ISO 787-11
Specific surface area	m ² /g			To be agreed between the interested parties

5 Sampling

Take a representative sample of the product to be tested according to ISO 15528.

6 Determination of silica content

6.1 Principle

A test portion is ignited, weighed and treated with sulphuric acid and hydrofluoric acid. The silicon tetrafluoride thus formed is evaporated off and the silica content is calculated from the impurities is not required.

6.2 Reagents

Use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

6.2.1 Sulfuric acid, diluted 1 + 1.

Add 1 part by volume of concentrated sulphuric acid, approximately 96 % (mass fraction) $\rho \approx 1,84$ g/ml, slowly to 1 part by volume of water.

6.2.2 Hydrofluoric acid, concentrated, approximately 40 % (mass fraction) $\rho \approx 1,13$ g/ml.

6.3 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following:

6.3.1 Platinum dish.

6.3.2 Muffle furnace, capable of being maintained at $(1\ 000 \pm 20)$ °C.

6.3.3 Infrared evaporator.

6.3.4 Desiccator, containing for example magnesium perchlorate as desiccant.

6.4 Procedure

(standards.iteh.ai)

6.4.1 Number of determinations

Carry out the determination in duplicate.

6.4.2 Test portion

Weigh, to the nearest 0,2 mg, approximately 1 g (m_0) of the sample (see [Clause 5](#)) into the tared platinum dish ([6.3.1](#)).

6.4.3 Determination

Ignite the test portion in the muffle furnace ([6.3.2](#)) at $(1\ 000 \pm 20)$ °C to constant mass (this should take approximately 2 h) and allow to cool in the desiccator ([6.3.4](#)). Weigh the test portion again (m_1).

Wet the ignited test portion in the platinum dish with 2 ml to 3 ml of water, add 1 ml of sulphuric acid ([6.2.1](#)) and 15 ml of hydrofluoric acid ([6.2.2](#)) and evaporate to a syrup on the infrared evaporator ([6.3.3](#)), taking care to avoid loss by spitting. Allow to cool and wash the sides down with small quantities of water. Then add a further 10 ml of hydrofluoric acid and evaporate to dryness. If the evaporation of the silicon tetrafluoride is not complete, add a further 10 ml of hydrofluoric acid and evaporate to dryness again.

Heat the residue until white fumes are no longer evolved, then ignite for 30 min in the muffle furnace at $(1\ 000 \pm 20)$ °C. Remove from the furnace, allow to cool in the desiccator and weigh to the nearest 0,2 mg (m_2).