

INTERNATIONAL
STANDARD

ISO
20977

First edition
2018-12

**Liming materials — Determination of
size distribution by dry and wet sieving**

*Amendements minéraux basiques — Détermination de la distribution
granulométrique par tamisage à sec ou à l'état humide*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 20977:2018](#)

<https://standards.iteh.ai/catalog/standards/iso/3f1c2d4a-8d61-494a-b456-28d91303671e/iso-20977-2018>



Reference number
ISO 20977:2018(E)

© ISO 2018

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 20977:2018](#)

<https://standards.iteh.ai/catalog/standards/iso/3f1c2d4a-8d61-494a-b456-28d91303671e/iso-20977-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
4.1 Suitable methods	1
4.2 Method A (dry sieving)	4
4.3 Method B (wet sieving)	4
5 Apparatus	4
6 Sampling	4
7 Procedure	5
7.1 Test portion	5
7.2 Method A (dry sieving)	5
7.2.1 Preparation of test portions	5
7.2.2 Determination	5
7.3 Method B (wet sieving)	5
7.3.1 General	5
7.3.2 Determination	6
8 Expression of results	6
8.1 Method A	6
8.2 Method B	7
9 Precision	7
9.1 General	7
9.2 Repeatability	7
9.3 Reproducibility	8
10 Test report	8
Annex A (informative) Results of an interlaboratory trial to determine the size distribution by dry and wet sieving	9
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 134, *Fertilizers, soil conditioners and beneficial substances*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

<https://standards.iteh.ai/catalog/standards/iso/3f1c2d4a-8d61-494a-b456-28d91303671e/iso-20977-2018>

Introduction

The dry sieving of powdered material containing individual particles can be carried out quite easily. This simple, quick and cheap method enables the determination of the particle size of water-soluble materials. Therefore, the dry sieving method should always be used first. However, the sieve apertures can become blocked by sample particles, a phenomenon known as blinding. Blinding is mainly caused by caking and the production of electrostatic charges, particularly on sieves with small apertures. Dry sieving of very wet material can also lead to blinding. These difficulties are not encountered with the wet sieving method, which is applicable to any kind of material such as powders (dry or wet), paste-like products or granules except those containing water-soluble constituents.

In order to ensure the comparability of results, all masses of size fractions are expressed as dry matter.

This document is based on EN 12948:2002.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ISO 20977:2018](#)

<https://standards.iteh.ai/catalog/standards/iso/3f1c2d4a-8d61-494a-b456-28d91303671e/iso-20977-2018>

Liming materials — Determination of size distribution by dry and wet sieving

1 Scope

This document specifies two methods for the determination of the particle size distribution of liming materials.

Method A (the dry sieving method) is applicable to all liming materials except wet and paste-like products. Method A is not applicable if blinding, caking, electrostatic charges or agglomeration occur after drying.

Method B (the wet sieving method) is applicable to products which are susceptible to blinding, caking, electrostatic charges or agglomeration after drying. Method B can be used to determine the primary particle size distribution of granulated products. Method B is not applicable to burnt lime and liming materials containing water-soluble constituents.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 8397:1988, *Solid fertilizers and soil conditioners — Test sieving*

<https://standards.iec.org/catalog/standards/iso/311c2d4a-8d61-494a-b436-28d91303671e/iso-20977-2018>

ISO 14820-1, *Fertilizers and liming materials — Sampling and sample preparation — Part 1: Sampling*

EN 12048, *Solid fertilisers and liming materials — Determination of moisture content — Gravimetric method by drying at (105 ± 2) °C*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

4.1 Suitable methods

[Table 1](#) gives the recommended methods for different liming materials.

In case of different options, see remarks.

Table 1 — Suitable methods for size distribution determination

Material type	Presentation	Moisture	Water soluble	Size range on the market	Suitable method(s)			Remarks
Limestone/ dolomite	Powder/ Defined/ Granulated/ Suspension/ Screened	Dry/Wet	Yes/No/ Partially		Dry sieving (method A)	Wet sieving (method B)	Laser diffraction (not standard- ized)	
	Powder	Dry	No	0/10 µm to 0/63 µm	—	—	x	
	Powder	Dry	No	0/63 µm to 0/100 µm	x	—	x	
	Powder	Dry	No	0/100 µm to 0/5 mm	x	optional	—	
	Powder	Wet	No	0/100 µm to 0/5 mm	optional	x	—	after drying for dry sieving as received for wet sieving
	Defined	Dry	No	100 µm/x to y/5 mm	x	optional	—	
	Granulated	Dry	No	2/7 mm	x	—	—	before breakdown
	Granulated	Dry	No	0/63 µm to 0/1 mm (el- ementary particles)	x	optional 1	optional 2	1 and 2: after breakdown 2: up to 200 µm
	Suspension	Wet	No	0/10 µm to 0/250 µm	optional	—	x	fraction coarser than 100 µm as received
Chalk (soft material)	Powder	Wet	No	0/5 mm to 0/ 50 mm	—	x	—	
Burnt lime	Powder	Dry	Partially	0/1 mm to 0/1 mm	x	optional	—	
Hydrated lime	Powder	Dry	Partially	0/1 mm to 0/3 mm	—	—	—	
BOF slags (blast oxy- gen furnace)	Suspension	Wet	Partially	1/x mm to y/8 mm	x	—	—	optional in alcohol no need
BOF slags (blast oxy- gen furnace)	Powder	Dry	Partially	0/50 µm to 0/200 µm	x	—	—	optional in alcohol after drying
				up to 4 mm	x	—	—	

Key

x: preferred method

optional: may be used

—: not applicable

Table 1 (continued)

Material type	Presentation	Moisture	Water soluble	Size range on the market	Suitable method(s)			Remarks
	Powder/ Defined/ Granulated/ Suspension/ Screened	Dry/Wet	Yes/No/ Partially		Dry sieving (method A)	Wet sieving (method B)	Laser diffraction (not standard- ized)	
Sugar factory lime	Powder	Dry	No	very fine particles	x	—	x	
	Powder	Wet	No	very fine particles	x	—	x	after drying
Suspension	Wet	No	very fine particles	—	—	—	x	
	Powder	Dry	Partially	up to 5 mm	x	—	—	
Ashes	Powder	Wet	Partially	up to 5 mm after preliminary sieving	x	—	—	after drying
	Granulated	Dry	Partially	2/7 mm	x	—	—	

Key

x: preferred method
optional: may be used
—: not applicable

In some countries, very fine materials (finer than 50 µm) can be found (such as calcium carbonate suspensions).

For such products, measurement by sieving is not suitable:

Fine particles block the sieve holes and the results cannot be considered as representative.

In this situation, only the laser granulometry measurement is suitable.

However, this measurement is not standardized because the results (xx percent passing yy mm) depend on a material matrix and on a device calculation algorithm which is specific to each device provider. Usually, for laser granulometry, particles are dispersed in water. When the product is totally or partially water soluble, alcohol should be used but in such a case (as burnt or hydrated lime), the agricultural product reactivity is much better than for insoluble products (carbonates) and fineness generally does not matter.

4.2 Method A (dry sieving)

Dry sieving of a liming material with one or more test sieves by hand or using a mechanical sieving machine.

4.3 Method B (wet sieving)

Dispersion of agglomerated or granulated liming materials with tap water.

Wet sieving of the dispersed liming materials under continuous water spraying by hand or using a mechanical sieving machine. Drying of the different fractions retained on the sieves.

(<https://standards.iteh.ai>)

5 Apparatus

Document Preview

Usual laboratory apparatus and, in particular, the following.

5.1 **Balance**, capable of weighing to the nearest 0,01 g.

<https://standards.iteh.ai/catalog/standards/iso/311c2d4a-8d61-494a-b456-28d91303671e/iso-20977-2018>

5.2 **Mechanical shaker (sieving machine)**, capable of imparting both horizontal and vertical motion to material inside a stack of sieves, fitted with a lid with a water intake and a receiver with a water outlet when used for method B.

Hand sieving may be carried out instead of mechanical sieving.

5.3 **Stainless steel woven wire test sieves**, conforming to ISO 3310-1 and of nominal aperture sizes covering the granulometry range of the product.

5.4 **Stopwatch.**

5.5 **Soft brush.**

5.6 **Oven**, capable of being controlled at $(105 \pm 2) ^\circ\text{C}$.

6 Sampling

Sample the liming material in accordance with ISO 14820-1.