



**SLOVENSKI STANDARD**  
**kSIST-TP FprCEN ISO/TR 16178:2021**

**01-september-2021**

---

**Obuvala - Nevarne snovi, ki so lahko prisotne v obuvalih in njihovih sestavnih delih - Seznam kritičnih kemičnih snovi (ISO/PRF TR 16178:2021)**

Footwear - Critical substances potentially present in footwear and footwear components - Lists of critical chemical substances (ISO/PRF TR 16178:2021)

Schuhe - Möglicherweise in Schuhen und Schuhbestandteilen vorhandene kritische Substanzen (ISO/PRF TR 16178:2021)

Chaussures - Substances critiques potentiellement présentes dans la chaussure et les composants de chaussures - Listes des substances chimiques critiques (ISO/PRF TR 16178:2021)

**iteh STANDARD PREVIEW**  
(standards.iteh.ai)  
[kSIST-TP FprCEN ISO/TR 16178:2021](https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcfe8db4dc979000/ksist-tp-fprcen-iso-tr-16178-2021)  
<https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcfe8db4dc979000/ksist-tp-fprcen-iso-tr-16178-2021>

**Ta slovenski standard je istoveten z: prCEN ISO/TR 16178**

---

**ICS:**

61.060          Obuvala          Footwear

**kSIST-TP FprCEN ISO/TR 16178:2021          en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[KSIST-TP FprCEN ISO/TR 16178:2021](https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcf-edb4dc979000/ksist-tp-fprcen-iso-tr-16178-2021)

<https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcf-edb4dc979000/ksist-tp-fprcen-iso-tr-16178-2021>

TECHNICAL  
REPORT

ISO/TR  
16178

Third edition

---

---

**Footwear — Critical substances  
potentially present in footwear and  
footwear components — Lists of  
critical chemical substances**

*Chaussures — Substances critiques potentiellement présentes dans la  
chaussure et les composants de chaussures — Listes des substances  
chimiques critiques*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ksIST-TP FprCEN ISO/TR 16178:2021](https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcf-edb4dc979000/ksist-tp-fprcen-iso-tr-16178-2021)

[https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcf-  
edb4dc979000/ksist-tp-fprcen-iso-tr-16178-2021](https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcf-edb4dc979000/ksist-tp-fprcen-iso-tr-16178-2021)

**PROOF / ÉPREUVE**

---

---



Reference number  
ISO/TR 16178:2021(E)

© ISO 2021

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST-TP FprCEN ISO/TR 16178:2021](https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcf-edb4dc979000/ksist-tp-fprcen-iso-tr-16178-2021)

<https://standards.iteh.ai/catalog/standards/sist/94af19fe-bd33-4c9a-adcf-edb4dc979000/ksist-tp-fprcen-iso-tr-16178-2021>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Presence of chemicals in footwear materials</b> .....	<b>2</b>
<b>5 Critical substances potentially present in footwear and footwear components</b> .....	<b>8</b>
5.1 Acrylonitrile.....	8
5.1.1 General.....	8
5.1.2 Potential risks.....	8
5.1.3 Test methods.....	8
5.2 Alkylphenols and Alkylphenol ethoxylates (NP, OP, NPEO, OPEO).....	8
5.2.1 General.....	8
5.2.2 Potential risks.....	9
5.2.3 Test methods.....	9
5.3 Aromatic amines.....	10
5.3.1 General.....	10
5.3.2 Potential risks.....	11
5.3.3 Test methods.....	11
5.4 Benzene.....	11
5.4.1 General.....	11
5.4.2 Potential risks.....	11
5.4.3 Test methods.....	11
5.5 Biocides.....	12
5.5.1 Orthophenylphenol.....	12
5.5.2 2-(thiocyanatomethylthio)-1,3-benzothiazole (TCMTB).....	12
5.5.3 2-octylisothiazol-3(2H)-one (OIT).....	13
5.5.4 4-Chloro-3-methylphenol (CMK).....	13
5.5.5 Triclosan.....	14
5.6 Bisphenol.....	15
5.6.1 General.....	15
5.6.2 Potential risks.....	15
5.6.3 Test methods.....	15
5.7 Cadmium – Cd.....	15
5.8 Chlorinated paraffins.....	15
5.8.1 General.....	15
5.8.2 Potential risks.....	16
5.8.3 Test methods.....	16
5.9 Chlorobenzenes and chlorotoluenes.....	16
5.9.1 General.....	16
5.9.2 Potential risks.....	17
5.9.3 Test methods.....	17
5.10 Chromium and Chromium VI.....	17
5.11 Colophony.....	18
5.11.1 General.....	18
5.11.2 Potential risks.....	18
5.11.3 Test methods.....	18
5.12 Dimethylformamide.....	18
5.12.1 General.....	18
5.12.2 Potential risks.....	19
5.12.3 Test methods.....	19
5.13 Dimethylfumarate (DMFU).....	19
5.13.1 General.....	19
5.13.2 Potential risks.....	19

## ISO/TR 16178:2021(E)

5.13.3	Test methods	20
5.14	Disperses dyes	20
5.14.1	General	20
5.14.2	Potential risks	21
5.14.3	Test methods	21
5.15	Flame retardants	21
5.15.1	General	21
5.15.2	Potential risks	22
5.15.3	Test methods	22
5.16	Formaldehyde	22
5.16.1	General	22
5.16.2	Potential risks	22
5.16.3	Test methods	23
5.17	Heavy metals	23
5.17.1	General	23
5.17.2	List of heavy metals	23
5.17.3	Potential risks	23
5.17.4	Test methods	25
5.17.5	Special cases	25
5.18	Mercaptobenzothiazole	26
5.18.1	General	26
5.18.2	Potential risks	26
5.18.3	Test methods	27
5.19	N-ethylphenylamine	27
5.19.1	General	27
5.19.2	Potential risks	27
5.19.3	Test methods	27
5.20	N methyl-2-pyrrolidone (NMP)	27
5.20.1	General	27
5.20.2	Potential risks	27
5.20.3	Test methods	28
5.21	N,N-dimethylacetamide	28
5.21.1	General	28
5.21.2	Potential risks	28
5.21.3	Test methods	28
5.22	Nickel – Ni	28
5.23	Nitrosamines	28
5.23.1	General	28
5.23.2	Potential risks	29
5.23.3	Test methods	29
5.24	Organotins compounds	29
5.24.1	General	29
5.24.2	Potential risks	30
5.24.3	Test methods	30
5.25	PAHs (Polycyclic aromatic hydrocarbons)	30
5.25.1	General	30
5.25.2	Potential risks	31
5.25.3	Test methods	31
5.26	Paraphenylene diamine	31
5.26.1	General	31
5.26.2	Potential risks	32
5.26.3	Test methods	32
5.27	Pesticides	32
5.27.1	General	32
5.27.2	Potential risks	32
5.27.3	Test methods	33
5.28	Perfluorinated and polyfluorinated chemicals-PFC	33
5.28.1	Different substances	33

STANDARD PREVIEW  
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/94af19e-bd33-4e9a-adeb-444de979000/ksist-tp-fprcen-iso-tr-16178-2021>

5.28.2	Potential risks	36
5.29	pH	36
5.29.1	General	36
5.29.2	Potential risks	36
5.29.3	Test methods	36
5.30	Phenol	36
5.30.1	General	36
5.30.2	Potential risks	37
5.30.3	Test methods	37
5.31	Phenyl mercury	37
5.31.1	General	37
5.31.2	Potential risks	37
5.31.3	Test methods	38
5.32	Phthalates	38
5.32.1	General	38
5.32.2	Potential risks	39
5.32.3	Test methods	39
5.33	Polychlorophenols	40
5.33.1	General	40
5.33.2	Potential risks	41
5.33.3	Test methods	41
5.34	Paratertiary butyl phenol formaldehyde (PTBF)	41
5.34.1	General	41
5.34.2	Potential risks	41
5.34.3	Test methods	42
5.35	Quinoline	42
5.35.1	General	42
5.35.2	Potential risks	42
5.35.3	Test methods	42
5.36	Thiuram and thiocarbamate	42
5.36.1	General	42
5.36.2	Potential risks	43
5.36.3	Test methods	43
5.37	Volatile organic compounds (VOC)	43
5.37.1	General	43
5.37.2	Potential risks	43
5.37.3	Test methods	43
<b>Bibliography</b>		<b>45</b>

## ISO/TR 16178:2021(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 216, *Footwear*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO/TR 16178:2012), which has been technically revised.

The main changes compared to the previous edition are as follows:

- new [Table 1](#) including a new system of grading;
- withdrawn substances:
  - proteins in latex, substances destroying ozone layer, polychlorobiphenyls, polychloroprene, vinyl chloride;
- added substances:
  - benzene, bisphenol, NMP, DMAC, phenyl mercury, quinoline, VOC;
- biocides are grouped together (CMK, OIT, OPP, TCMTB);
- Annex A is now in ISO 21061<sup>[67]</sup>;
- Annex B is now [Clause 4](#);
- bibliography, updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).



# Footwear — Critical substances potentially present in footwear and footwear components — Lists of critical chemical substances

## 1 Scope

This document defines lists of critical chemical substances potentially present in footwear and footwear components.

This document describes the critical chemical substances, their potential risks of innocuousness, in which materials they could be found, and which test method(s) can be used to quantify them.

The test methods listed indicate the state of the art. For some substances, a test method is not available.

This document is applicable to any kind of footwear and footwear components.

## 2 Normative references

There are no normative references in this document.

iTech STANDARD PREVIEW

## 3 Terms and definitions (standards.iteh.ai)

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **allergen**

substance that is capable of inducing an allergic reaction

### 3.2

#### **allergy**

immunologically mediated response to certain specific substances (allergens)

Note 1 to entry: Type-1 allergy (respiratory allergy) is mediated by IgE antibodies, can cause asthma, rhinitis, urticaria. Type-4 allergy (dermal allergy) is mediated by T-cells, can cause dermatitis.

### 3.3

#### **limit of detection**

value from which a substance is considered as detectable

Note 1 to entry: This means that the signal associated to the substance is three times bigger than the background noise signal. The limit of detection is determined experimentally by the laboratory for each substance.

### 3.4

#### **critical substances**

chemical substance that can be found in footwear or footwear components and can have an effect on the wearer and/or environmental impact due to its chemical reactivity

Note 1 to entry: The effects caused by critical substances vary. It can be carcinogenic or mutagenic effects, allergy, reaction to toxics, etc.

## ISO/TR 16178:2021(E)

### 3.4.1

#### critical substances category 1

substances with proven dangerous effect on the wearer

Note 1 to entry: These substances are widely restricted by national regulation in several countries.

### 3.4.2

#### critical substances category 2

substances with dangerous effect on the wearer

Note 1 to entry: These substances are restricted by national regulation in a limited number of countries.

### 3.4.3

#### critical substances category 3

substances that are highly suspected to have an effect on the wearer

Note 1 to entry: These substances might not be restricted by regulation at the time of publication but they are frequently requested by the market stakeholders.

### 3.4.4

#### critical substances category 4

substances that are suspected to have an effect on the wearer

Note 1 to entry: These substances might not be restricted by regulation. Substances known to have an allergenic effect on the wearer are included in category 4 for reference.

## 4 Presence of chemicals in footwear materials

A number of chemicals are present in footwear materials. [Table 1](#) lists the following:

- a) in which materials they are supposed to be. The possible materials potentially used in the footwear industry are given in ISO 21061-1:2017, Annex C;
- b) a list of critical chemicals, (see [Clause 5](#) for information);
- c) test methods that can be used to quantify them (see Bibliography);
- d) the potential risks associated with their use, assessed by the use of the critical substances' category scale
  - 1) stand for "critical substances category 1";
  - 2) stand for "critical substances category 2";
  - 3) stand for "critical substances category 3";
  - 4) stand for "critical substances category 4".

For composite materials, the tests should be conducted on the entire component.

EXAMPLE 1 Coated textile (cotton + PVC coating). Test on PVC and test on cellulosic natural fibres should be done.

EXAMPLE 2 Mixed textile (PES + cotton). Test on cellulosic natural textile and test on PES textile should be done.

Table 1 — Critical chemicals potentially present in footwear and footwear components

Substance (see Annex B)	Test method	Leather			Synthetic material								Natural material				Miscellaneous					
		Leather	Coated leather	Leather board	PVC	EVA	Rubber	PU - TPU elastane	PE-T PP	Polyester	Polyamide	Chloride fibre	Polyacrylic	Latex	Cellulosic natu- ral textile	Proteinic natu- ral textile	Wood - cork	Adhesives	Metal hardware	Prints for textile	Cellulose	
Acrylonitrile						4						4						4				
Alkylphenols( OP, NP) and Alkylpheno- lethoxylates, (OPEO, NPEO)	ISO 18254-1	3	3	3																		
Alkylphenols( OP, NP) and Alkylpheno- lethoxylates, (OPEO, NPEO)	ISO 18218-1 ISO 18218-2 ISO 21084								2	2	2	2		2	2					2		
AZO - arylamines	ISO 17234-1	1	1	1																		
When 4-aminoa- zobenzene is sus- pected	ISO 17234-2	1	1	1																		
AZO - arylamines	ISO 14362-1								1	1	1	1		1	1						1	
When 4-aminoa- zobenzene is sus- pected	ISO 14362-3								1	1	1	1		1	1						1	
Benzene									1	1	1	1		1	1			2				
Biocides (TCMTB, OIT, CMK)	ISO 13365 (all parts)	4	4	4					4	4	4	4		4	4							4
Biocides (OPP)	ISO 13365 (all parts)	2	2	2										2	2							2
Biocides (triclosan)	EN 17134	2	2	2					2	2	2	2		2	2			2				2
Bisphenol		2	2	2																		
Cadmium	EN 1122		1																			1
Chlorinated paraffin's (Short chained [C10-C13])	ISO 18219	2	2	2					2	2	2	2		2	2							2

Table 1 (continued)

Substance (see Annex B)	Test method	Leather			Synthetic material								Natural material				Miscellaneous									
		Leather	Coated leather	Leather board	PVC	EVA	Rubber	PU - TPU elastane	PE-T PP	Polyester	Polyamide	Chloride fibre	Polyacrylic	Latex	Cellulosic natu- ral textile	Proteinic natu- ral textile	Wood - cork	Adhesives	Metal hardware	Prints for textile	Cellulose					
Chlorinated paraffin's (Middle chained [C14-C17])	ISO 18219	3	3	3			3			3	3	3		3	3					3						
	EN 17137								2																	
Chlorobenzene and chlorotoluene Chlorobenzene and chlorotoluene (tetra- chlorotoluene, trichlorotoluene, achlo- rotoluene)	EN 17137									2	2	2	2	2	2											
	ISO 17075-1 ISO 17075-2	1	1	1																						
Chromium VI	ISO 10195	3	3	3																						
Chromium VI With ageing																										
Colophony																							4			
Dimethylformamide (DMF)	ISO/TS 16189		2																							
Dimethylfumarate (DMFU)	ISO/TS 16186	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1		
Disperses dyes and dyestuffs	ISO 16373-2 ISO 16373-3																									
Flame retard- ant (Phosphorated and brominat- ed) Only for product claim- ing FR properties	ISO 17881-1 ISO 17881-2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1		
Formaldehyde	ISO 17226-1 ISO 17226-2	2	2	2																						
Formaldehyde	EN 120 EN 717-3																								2	
Formaldehyde	ISO 27587																									3
Formaldehyde	ISO 14184-1																									1

Table 1 (continued)

Substance (see Annex B)	Test method	Leather			Synthetic material							Natural material				Miscellaneous							
		Leather	Coated leather	Leather board	PVC	EVA	Rubber	PU - TPU elastane	PE-T PP	Polyester	Polyamide	Chloride fibre	Polyacrylic	Latex	Cellulosic natu- ral textile	Proteinic natu- ral textile	Wood - cork	Adhesives	Metal hardware	Prints for textile	Cellulose		
Extractible (Sb - As - Cd - Cr - Co - Cu - Ni - Hg - Zn)	ISO 17072-1	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	
	EN 16711-2																						
E x t r a c t i b l e Footwear for children less than 36 months	ISO 17072-1	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2
	EN 16711-2																						
Heavy metals (Sb - As - Cd - Cr - Co - Cu - Ni - Hg - Zn - Ba - Se)	ISO 17072-2	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3
	EN 16711-1																						
Total content (Sb - As - Cd (leather and textile) - Cr - Co - Cu - Ni - Hg - Zn)	ISO 17072-2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
	EN 16711-1																						
Lead	ISO 17072-2																						
EN 16711-1																							
Mercaptobenzothiazole																							
N-ethylphenyl-amine																							
N methyl pyrrolidone	ISO 19070				2																		
N,N-dimethylacetamide (DMAC)																							
Nickel	EN 1811 (with or with- out EN 12472)																						
	Skin contact																						
Nitrosamines	Footwear for children less than 36 months																						
	ISO 19577																						
Organotin compounds (TBT, TPT)	ISO 19577																						
	ISO/TS 16179	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1

Table 1 (continued)

Substance (see Annex B)	Test method	Leather			Synthetic material										Natural material					Miscellaneous			
		Leather	Coated leather	Leather board	PVC	EVA	Rubber	PU - TPU elastane	PE-T PP	Polyester	Polyamide	Chloride fibre	Polyacrylic	Latex	Cellulosic natu- ral textile	Proteinic natu- ral textile	Wood - cork	Adhesives	Metal hardware	Prints for textile	Cellulose		
Organotin compounds (DBT, DOT)	ISO/TS 16179	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2
Organotin compounds (others),	ISO/TS 16179	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3
PAH - polycyclic aromatic hydrocarbons	ISO/TS 16190	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Paraphenylenediamine																							
Pesticides	ISO 22517	3	3	3																			
PFCs perfluorinated compounds (PFOS/ PFOA)	CEN TS 15968																						
PFCs perfluorinated compounds	ISO 23702-1	1	1	1																			
pH	ISO 4045	2	2	2																			
pH	ISO 3071																						
Phenol	ISO 20536	4	4	4																			
Phenyl mercury																							
Phthalates	Footwear for children less than 14 years																						
		ISO/TS 16181	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Phthalates	ISO 14389																						
Polychlorophenol (PCP pentachlorophenol)	ISO 17070	1	1	1																			
Polychlorophenol TeCP	ISO 17070	2	2	2																			
Polychlorophenol TriCP - DiCP	ISO 17070	3	3	3																			
Polychlorophenol (PCP pentachlorophenol)	CEN/TR 14823																						
Polychlorophenol (PCP pentachlorophenol)	XP G 08-015																						
Polychlorophenol TeCP	XP G 08-015																						
Polychlorophenol TriCP - DiCP - MoCP	XP G 08-015																						

Table 1 (continued)

Substance (see Annex B)	Test method	Leather			Synthetic material										Natural material				Miscellaneous			
		Leather	Coated leather	Leather board	PVC	EVA	Rubber	PU - TPU elastane	PE-T PP	Polyester	Polyamide	Chloride fibre	Polyacrylic	Latex	Cellulosic natu- ral textile	Proteinic natu- ral textile	Wood - cork	Adhesives	Metal hardware	Prints for textile	Cellulose	
PTBF Parateritary butyl phenol for- maldehyde																		4				
quinoline							2	2	2	2			2									
Thiuram and Thiocarbamate							4															
Volatile organic compounds			4				4	4	4	4												4