



Designation: ~~D7377-08~~ Designation: D 7377 - 09

# Standard Practice for ~~Evaluating the Water Wash-Off Resistance of Traffic~~ ~~Paints~~ Evaluating the Water Wash-Off Resistance of Traffic Paints using a Water Faucet<sup>1</sup>

This standard is issued under the fixed designation D 7377; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1A newly applied traffic paint film may be exposed to rain of varying intensities shortly after application. This practice was designed to determine the relative water wash-off resistance of an applied traffic paint film under controlled conditions. This test can be used to compare conventional and fast-dry traffic paints and the binders used in them for their relative ability to withstand rain soon after application on roadway surfaces.

1.1 A traffic paint film freshly applied to a roadway, air strip, or parking lot may be exposed to rain of varying intensities shortly after application. This practice was designed to determine the relative water wash-off resistance of an applied traffic paint film under controlled laboratory conditions using a water faucet to simulate a heavy rain. This laboratory practice can also be used to compare conventional and fast-dry waterborne traffic paints and the effects of binders and other components in traffic for their relative ability to withstand a heavy rain soon after application.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

D 562 Test Method for Consistency of Paints Measuring Krebs Unit (KU) Viscosity Using a Stormer-Type Viscometer

D 711 Test Method for No-Pick-Up Time of Traffic Paint

D 823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels

D 1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers

D 1212 Test Methods for Measurement of Wet Film Thickness of Organic Coatings

D 4414 Practice for Measurement of Wet Film Thickness by Notch Gages [a-927b-177a617c42c7/astm-d7377-09](https://standards.iteh.ai/a-927b-177a617c42c7/astm-d7377-09)

## 3. Terminology

### 3.1 Definitions:

3.1.1 *conventional waterborne traffic paint, n*—an aqueous traffic paint that uses a conventional (non-fast-dry) latex binder.

3.1.1.1 *Discussion*—~~Typical no-pick-up dry times for conventional traffic paints are 20 to 45 min.~~ Typical no-pick-up dry times for conventional traffic paints by Test Method D 711 are 20 to 45 min. These paints are often used for zone marking of parking lots and garages.

3.1.2 *durable fast-dry waterborne traffic paint, n*—an aqueous traffic paint that uses a ~~third-generation~~ durable fast-dry latex binder.

3.1.2.1 *Discussion*—Air or airless spray application on roadways is typically 0.65 mm (25 mils) wet or about 0.41 mm (16 mils) dry. The range of application for durable waterborne paints is 0.56 to 0.89 mm (22 to 35 mils) wet, but sometimes ~~the~~ durable paints are also striped at standard line thickness. Typical no-pick-up dry times by Test Method D 711 for durable paints applied at standard line thickness are 5 to 8 min.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.44 on Traffic Coatings.

Current edition approved Feb. June 1, 2008-2009. Published March 2008-July 2009. Originally approved in 2007. Last previous edition approved in 2007-2008 as D 7377 - 07g.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.3 *effective water wash-off dry time, n*— the traffic paint dry time required for no visible loss of coating when conducting the water- wash<sub>off</sub> Standard Practice.

3.1.4 *fast-dry waterborne traffic paint, n*— an aqueous traffic paint that uses a fast-dry traffic latex binder.

3.1.4.1 *Discussion*—~~Typical no-pick-up dry times for fast-dry traffic paints are <10 min.—These paints are sometimes also referred to as fast-hardening since they still may contain a substantial amount of moisture even though they feel dry. Typical no-pick-up dry times by Test Method D 711 for fast-dry traffic paints are <10 min.~~

3.1.5 *standard line fast-dry waterborne traffic paint, n*—an aqueous traffic paint that uses a ~~first or second generation standard~~ fast-dry latex binder.

3.1.5.1 *Discussion*—~~Air or airless spray application on roadways is typically 0.38 mm (15 mils) wet or about .223 mm (9 mils) dry.—Air or airless spray application on roadways is typically 0.38 mm (15 mils) wet or about .223 mm (9 mils) dry. Typical no-pick-up dry times for standard line traffic paints by Test Method D 711 are 5 to 8 min.~~

3.1.6 *waterborne traffic paint, n*—an aqueous traffic paint (usually white or yellow) containing either a conventional or fast-dry latex binder.

3.1.7 *water wash-off resistance, n*—the resistance of a traffic paint line to partial or complete wash-out during a rain.

#### 4. Summary of Practice

4.1 This standard practice involves preparing a series of uniform thickness films of traffic paint on standard substrates. The films are allowed to dry over different time periods, and then each paint film is subsequently tested with the water-wash-off test to determine the relative amount of coating remaining at the end of the wash off period.

#### 5. Significance and Use

5.1 After waterborne traffic paints are applied to a road, airstrip, or parking lot pavement, it is important that ~~they~~ the paint films be sufficiently hardened, coalesced, or cured so they will not be removed by rain. This practice can be used to determine the relative performance of binders and other components within traffic paint for their effect on the water-wash off resistance of the coating. Some key elements of the coating that may affect water-wash-off performance are the quality and type of latex binder, the dry time of the coating (often conducted by Test Method D 711), pigment volume concentration (PVC), and the relative water sensitivity of additives (for example, pigment dispersants, and surfactants) in the coating.

#### 6. Apparatus and Equipment

6.1 *Paddle Type Viscometer*, to measure viscosity (in Krebs units) of the traffic paint prior to application.

6.2 *Conditioned Room*, at  $23 \pm 2^\circ\text{C}$  ( $73.5 \pm 3.5^\circ\text{F}$ ) and  $50 \pm 5\%$  relative humidity for film draw-downs and film drying.

6.3

6.2 *Conditioning Room*, to provide a constant standard environment of  $23 \pm 2^\circ\text{C}$  ( $73.5 \pm 3.5^\circ\text{F}$ ) and  $50 \pm 5\%$  relative humidity during film draw-downs and film drying.

6.3 *Conditioning Chamber*, convenient to provide a constant standard high humidity environment of  $23 \pm 2^\circ\text{C}$  ( $73.5 \pm 3.5^\circ\text{F}$ ) and  $90 \pm 3\%$  relative humidity during film draw-downs and film drying.

6.4 *Graduated Cylinder*, to determine and adjust water flow rate from faucet.

6.5 *Humidity Gauge*, to record relative humidity during the drying period.

6.4

6.6 *Thermometers*, to record the air and water temperatures.

6.5

6.7 *Spatula*, to mix the paint prior to application.

6.6

6.8 *Glass Plates*, for film draw-downs (see also option for charts in 6.7.6.9).

6.7

6.9 *Draw-Down Chart*, preferred option for film draw-downs. Black Scrub Test Panels are preferred and can be cut in half to give two test panels of 16.5 by 21.6 cm (6½ by 8½ in.) size. Use of these charts instead of a glass plate allows for a permanent record of the test results.

6.8

6.10 *Film Applicator (15 cm (6 in.)) width*, to obtain 0.38 mm (15 mil) wet thickness for standard traffic paints or 0.64 mm (25 mil) wet thickness for durable traffic paints.

6.9

6.11 *Wet Film Gauge*, to measure wet film thickness.

6.10 *Sink with combined hot and cold tap water faucet*, to apply water stream to the test panel for the running water method.

6.11 *Water Sprayer (hand pumped type spray bottle or adjustable nozzle garden-type sprayer)*, to provide a water spray to the test panel for the alternative water spray method.

6.12 *Sink with combined hot and cold tap water faucet*, to apply water stream onto test panel film during the water wash-off testing.

6.13 *Lab Jack*, to support the applied paint film, and to control distance from the water nozzle.