



Designation: D4904 – 99 (Reapproved 2009)

## Standard Practice for Cooling of Analytical Solutions<sup>1</sup>

This standard is issued under the fixed designation D4904; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice covers a standard procedure for the cooling of analytical solutions such as those prepared Practices **D4901**, **D4905**, or **D6405**. The tannin analysis results for an analytical solution are to some extent dependent on the conditions of the cooling of that solution.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**D4901 Practice for Preparation of Solution of Liquid Vegetable Tannin Extracts**

**D4905 Practice for Preparation of Solution of Solid, Pasty and Powdered Vegetable Tannin Extracts**

**D6405 Practice for Extraction of Tannins from Raw and Spent Materials**

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee **D31** on Leather and is the direct responsibility of Subcommittee **D31.01** on Vegetable Leather. This practice has been adapted from and is a replacement for Method **A12A12** of the Official Methods of the American Leather Chemists Association.

Current edition approved April 1, 2009. Published July 2009. Originally approved in 1989. Last previous edition approved in 2004 as D4904 – 99 (2004). DOI: 10.1520/D4904-99R09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *ALCA Methods:*

**A12 Cooling of Analytical Solutions**<sup>3</sup>

### 3. Summary of Practice

3.1 This practice specifies a procedure to follow in cooling to standard or room temperature the hot analytical solutions prepared from tanning materials for Practices **D4901**, **D4905**, or **D6405**.

### 4. Significance and Use

4.1 The solubility of extracts is influenced by temperature. The analytical solutions prepared from tanning extracts are dissolved or diluted in hot water. It is necessary to exercise caution in cooling these solutions and to do so in such a way as to avoid chilling, under-cooling, or uneven cooling of the solutions.

### 5. Specimen

5.1 The specimen shall be the 1-L or 2-L solutions prepared under Practices **D4901**, **D4905**, or **D6405**.

### 6. Procedure

6.1 The prepared solutions shall be protected from drafts and shall be allowed to stand overnight in an ambient temperature of not less than 23°C, nor more than 28°C. After their temperature has been adjusted, the solutions shall be made up to the mark with distilled water at 23°C. Where a constant temperature room is available, the solutions, suitably protected from drafts, may be cooled therein with advantage. In this case, the room shall be so controlled that solutions in flasks, exposed therein, shall remain at 24°C.

<sup>3</sup> Official Methods of the American Leather Chemists Association. Available from the American Leather Chemists Association, University of Cincinnati, P.O. Box 210014, Cincinnati, OH 45221-0014.