

INTERNATIONAL STANDARD

ISO
12984

Second edition
2018-02

Carbonaceous materials used in the production of aluminium — Calcined coke — Determination of particle size distribution

*Produits carbonés utilisés pour la production de l'aluminium — Coke
calciné — Détermination de la granulométrie*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 12984:2018](#)

<https://standards.iteh.ai/catalog/standards/iso/fe9794e0-1d22-45e9-85d4-7e64b60a6875/iso-12984-2018>



Reference number
ISO 12984:2018(E)

© ISO 2018

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 12984:2018](#)

<https://standards.iteh.ai/catalog/standards/iso/fe9794e0-1d22-45e9-85d4-7e64b60a6875/iso-12984-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
6 Sampling and preparation of test portion	2
7 Procedure	2
8 Expression of results	3
9 Precision	4
9.1 Repeatability	4
9.2 Reproducibility	4
10 Test report	4

iTeh Standards

(<https://standards.iteh.ai>)

Document Preview

[ISO 12984:2018](#)

<https://standards.iteh.ai/catalog/standards/iso/fe9794e0-1d22-45e9-85d4-7e64b60a6875/iso-12984-2018>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

This document was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

This second edition cancels and replaces the first edition, ISO 12984:2000, of which it constitutes a minor revision.

[ISO 12984:2018](http://www.iso.org/iso/12984:2018)

<https://standards.iteh.ai/catalog/standards/iso/fe9794e0-1d22-45e9-85d4-7e64b60a6875/iso-12984-2018>

Carbonaceous materials used in the production of aluminium — Calcined coke — Determination of particle size distribution

1 Scope

This document specifies a method for the determination of the particle size distribution of a sample of coke having a typical size distribution as normally produced by calcination of delayed petroleum coke. The same procedure is applicable to consignments of calcined anthracite. This document does not apply to fractions of carbon material prepared by sieving and crushing or to filter fines.

This method is applicable to the determination of particle sizes ranging from 0,25 mm to 16 mm, as the sum of the percentages of the size distribution above and below this range is typically less than 10 %. This document does not apply to determining particle sizes below 0,25 mm where a specific test for dust is used.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 6375, *Carbonaceous materials for the production of aluminium — Coke for electrodes — Sampling*
<https://standards.iec.ch/catalog/standards/iso/ie9794e0-1d22-45e9-85d4-7e64b60a6873/iso-12984-2018>

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

A sample of coke is subjected to a process of particle size analysis by dry sieve testing. The results are expressed in terms of the measured percentage by mass of the coke remaining on sieves of different sized openings between 16 mm and 0,25 mm, or alternatively in terms of calculated cumulative percentages for the different sized openings.

5 Apparatus

5.1 Wire cloth test sieves, of the following opening sizes: 16 mm, 8 mm, 4 mm, 2 mm, 1 mm, 0,5 mm and 0,25 mm.

The diameter of the sieves shall not be less than 200 mm and preferably 400 mm. The height shall be a minimum of 30 mm. The sieves shall comply with ISO 565 and ISO 3310-1.

All specified sieves shall be used to prevent any one sieve overloading.

5.2 Batch-type sieve shaker, which oscillates the particles in short time periods with minimal particle breakage. Shaking by hand is not appropriate.

5.3 Balances, capable of weighing the mass of one sieve plus the mass of the sample, such that the sample weighing error is less than 0,1 %.

5.4 Drying oven, for temperatures up to 120 °C, and **drying dishes**, made from stainless steel, aluminium or another suitable material.

6 Sampling and preparation of test portion

6.1 Take a representative sample of the coke load in accordance with ISO 6375.

NOTE The sample is normally split between the supplier and the customer and 4 kg of the material is used for the size analysis in each laboratory (see ISO 6375:1980, 7.2).

Care should be taken to ensure that the particle sizes are not altered during sampling and sample preparation, including drying.

6.2 Take a test portion from the representative sample in accordance with the quantities in [Table 1](#).

NOTE The test portion size is a function of sieve size to avoid overloading the sieves.

Table 1 — Relationship between sieve size and test portion size

Sieve diameter mm	Test portion g
200	500 ± 100
300	1 000 ± 200
400	2 000 ± 400

Take the amount shown in [Table 1](#) from the representative sample (see [5.1](#)) using one of the methods of sample division described in ISO 6375.

7 Procedure

- Dry the test portion at a temperature of 110 °C for 12 h or until consecutive weighing at 5 min intervals show less than 1 % loss in mass.
- Determine the mass by weighing the test portion to an accuracy of 0,1 %.
- Inspect the sieves and if blinding of the apertures is observed clean them with a stiff bristle or soft metal sieve brush.
- Assemble the sieves in a nest in descending order of size and fit to the receiver.