
**Textiles — Method for determination
of alkylphenols (AP)**

Textiles — Méthode de détermination de la teneur en alkylphénols (AP)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 21084:2019

<https://standards.iteh.ai/catalog/standards/sist/e8e2b94d-74d9-4dcc-a384-43476d911d48/iso-21084-2019>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 21084:2019

<https://standards.iteh.ai/catalog/standards/sist/e8e2b94d-74d9-4dcc-a384-43476d911d48/iso-21084-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
6.1 General	2
6.2 Apparatus and auxiliaries for preparing the sample	2
6.3 Chromatographic equipment	2
7 Procedure	2
7.1 Standard preparation	2
7.2 Sample preparation	2
7.3 Sample extraction	3
7.4 Sample analysis	3
8 Calculation and calibration	3
8.1 Calibration curve	3
8.2 External calibration	3
8.3 Calculation of each AP in sample	4
8.4 Reliability of the method	4
9 Test report	4
Annex A (informative) Examples of chromatographic condition — GC-MS/MS	5
Annex B (informative) Examples of chromatographic condition — LC-MS/MS and LC-FLD	8
Annex C (informative) Reliability of the method	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Textiles — Method for determination of alkylphenols (AP)

WARNING — This document calls for the use of substances/procedures that may be injurious to the health/environment if appropriate conditions are not observed. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety/environment at any stage.

1 Scope

This document specifies the method for the determination of extractable alkylphenols (AP) without derivatization step in textile and textile products.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>
<https://standards.iteh.ai/catalog/standards/sist/e8e2b94d-74d9-4dcc-a384-43476d911d48/iso-21084-2019>

4 Principle

The test specimen is cut into small pieces, transferred to a sample vial and treated with methanol in ultrasonic water bath. The extract is filtered and collected. Subsequently, the collected extract is analysed by gas chromatograph with mass selective detector (GC-MS), liquid chromatograph with mass selective detector (LC-MS) or liquid chromatograph with fluorescence detector (LC-FLD).

5 Reagents

Unless otherwise specified, analytical grade chemicals shall be used.

- 5.1 **4-n-Octylphenol**, CAS No.1806-26-4.
- 5.2 **4-tert-Octylphenol**, CAS No.140-66-9.
- 5.3 **4-n-Nonylphenol**, CAS No.104-40-5.
- 5.4 **4-Nonylphenol**, CAS No. 84852-15-3.
- 5.5 **Methanol**, (HPLC grade).
- 5.6 **Acetone**.
- 5.7 **Acetonitrile**, (HPLC grade).

5.8 Water, (HPLC grade).

6 Apparatus

6.1 General

Clean all glassware by rinsing with acetone (5.6) prior to use.

6.2 Apparatus and auxiliaries for preparing the sample

6.2.1 Standard laboratory equipment and the following.

6.2.2 Analytical balance with resolution of 0,01 g (for test specimen preparation).

6.2.3 Analytical balance with resolution of 0,001 g (for standard preparation).

6.2.4 Glass vial with screw cap (e.g. 40 ml).

6.2.5 Ultrasonic water bath [to be set up at (70 ± 5) °C].

6.2.6 Disposable syringe and membrane filter (with pore size of 0,45 µm or less).

6.2.7 Glass vial with septum cap (for chromatographic instrument).

6.3 Chromatographic equipment

6.3.1 Gas chromatograph with mass selective detector (GC-MS), or

6.3.2 Liquid chromatograph with mass selective detector (LC-MS), or

6.3.3 Liquid chromatograph with fluorescence detector (LC-FLD).

6.3.4 Capillary column for gas chromatograph, (5 %-phenyl)-methylpolysiloxane phase, non-polar, bonded and cross-linked, low bleed.

6.3.5 C18 reverse phase column for liquid chromatograph.

7 Procedure

7.1 Standard preparation

Octylphenols and nonylphenols are weighed accurately with analytical balance (6.2.3) and dissolved with methanol (5.5) containing 1 000 mg/l for stock solution. The stock solution can be preserved in the dark at less than 4°C.

7.2 Sample preparation

The test specimen is cut into pieces with 5 mm × 5 mm and pieces are mixed homogeneously. The specimen is weighed 1 g to the nearest 0,01 g with analytical balance (6.2.2) and put into the 40 ml glass vial (6.2.4) for extraction.

7.3 Sample extraction

10 ml of methanol (5.5) are added to glass vial (6.2.4) for extraction. If sample is not sufficiently immersed in the extraction solvent, add more methanol and record the final volume for calculation of each AP described in 8.3. Then the sample vial is sonicated for extraction in ultrasonic water bath (6.2.5) at 70 °C for 60 min. Subsequently, the extract is cooled down to room temperature, approximately 1 ml to 2 ml of extract is filtered into sample vial (6.2.7) using disposable syringe equipped with membrane filter (6.2.6). The sample vial is closed with cap immediately for further analysis.

In general, samples are examined without concentration, but the instrumental equipment of the laboratories may vary, the concentration procedure of extract is applicable for lower detection on limit.

7.4 Sample analysis

Qualitative and quantitative analysis of alkylphenols is performed by using GC-MS, LC-MS or LC-FLD.

Guidelines for suitable chromatographic conditions are given in Annex A for GC-MS/MS and in Annex B for LC-MS/MS and LC-FLD.

In case of positive results using GC-MS method, the results shall be confirmed using LC techniques.

NOTE False-positive results using GC-MS method could be caused by decomposition of tris(nonylphenyl) phosphate (TNPP) due to high injection temperature.

8 Calculation and calibration

8.1 Calibration curve

Prepare a calibration curve of the response against the known standard concentration. From the calibration curve, the concentration of the AP (alkylphenols, octylphenols and nonylphenols) in mg/l (C_S) is determined.

NOTE Concentration ranges for the calibration standards are subject to change upon the need of each laboratory and equipment used.

For quantification, the calibration curve shall have a correlation coefficient greater than 0,995 (R^2 greater than 0,990).

8.2 External calibration

The concentration of each AP in sample extract solution is calculated in mg/l according to Formula (1):

$$C_S = \frac{A_S}{A_C} \times C_C \quad (1)$$

where

C_S is the concentration of each AP in sample extract solution, in mg/l;

C_C is the concentration of each AP in calibration solution, in mg/l;

A_S is the area response of each AP in sample extract solution;

A_C is the area response of each AP in calibration solution.

8.3 Calculation of each AP in sample

The AP level is calculated as mass portion, X_i , in mg/kg of the specimen according to [Formula \(2\)](#):

$$X_i = \frac{C_S \times V \times DF}{M} \quad (2)$$

where

X_i is the concentration of each AP in sample, in mg/kg;

C_S is the concentration of each AP and calculated according to [Formula \(1\)](#), in mg/l;

V is the final volume of extract solution, in ml;

M is the mass of test specimen, in g;

DF is the dilution factor.

8.4 Reliability of the method

The reliability of the method is given in [Annex C](#).

9 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 21084:2019;
- b) identification of sample and the date of analysis;
- c) detection method and quantification method;
- d) the result of each AP (nonylphenols and octylphenols are reported individually);
- e) details of any deviation from the procedure specified and of all circumstances that may have influenced the results.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 21084:2019
<https://standards.iteh.ai/catalog/standards/sist/e8e2b94d-74d9-4dcc-a384-4246c111d48/iso-21084-2019>

Annex A (informative)

Examples of chromatographic condition — GC-MS/MS

A.1 Preliminary remark

As the instrumental equipment of the laboratories may vary, no generally applicable instructions can be provided for chromatographic analyses. The following parameters have been successfully tested and used.

A.2 Gas chromatographic conditions

A.2.1 GC-MS/MS condition

Capillary column: HP-5MS, length 35 m, inside diameter 0,25 mm, film thickness 0,25 µm

Injector mode: Splitless

Injector temperature: 250 °C

Injection volume: 1 µl

Carrier gas: Helium (rate: 1,0 ml/min)

Collision gas: Nitrogen (rate: 1,5 ml/min)

Oven program: 80 °C (0 min), 80 °C to 230 °C (7 °C/min), 230 °C (2 min)

Detection: Tandem mass spectrometer (MS/MS)

Acquisition mode: MRM mode, see [Table A.1](#) for MRM condition.

Table A.1 — MRM condition in GC-MS/MS

Compounds	m/z [Q1]	m/z [Q3]	Collision energy (eV)
4-tert-Octylphenol	135	107	10
	135	77	30
4-n-Octylphenol	107	77	20
	107	51	40
4-n-Nonylphenol	107	77	20
	107	51	40
4-Nonylphenol	107	77	20
	121	77	20
	135	77	30
	149	107	10
	163	107	20
	191	107	20

See examples in [Figure A.1](#) and [Figure A.2](#).