
**Ships and marine technology —
Butterfly valves for use in low
temperature applications — Design
and testing requirements**

*Navires et technologie maritime — Robinets à papillon destinés aux
applications à basse température — Exigences de conception et d'essai*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 21159:2018

<https://standards.iteh.ai/catalog/standards/iso/7acf56bd-bae0-429f-b145-36248082b83c/iso-21159-2018>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 21159:2018

<https://standards.iteh.ai/catalog/standards/iso/7acf56bd-bae0-429f-b145-36248082b83c/iso-21159-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Pressure-temperature rating	3
5 Structure	3
5.1 General.....	3
5.1.1 Structure.....	3
5.1.2 Materials.....	4
5.2 Design and materials of the body.....	4
5.2.1 Design.....	4
5.2.2 Materials.....	4
5.2.3 Manufacturing.....	4
5.3 Design and materials of the extended bonnet.....	5
5.3.1 Design.....	5
5.3.2 Materials.....	5
5.4 Design and materials of the disc.....	5
5.4.1 Design.....	5
5.4.2 Materials.....	5
5.5 Design and materials of the stem.....	5
5.5.1 Design.....	5
5.5.2 Materials.....	6
5.6 Stem sealing.....	6
5.7 Design and materials of the seat.....	6
5.7.1 Design.....	6
5.7.2 Bore materials.....	6
5.8 Design and materials of the connection.....	7
5.8.1 Design.....	7
5.8.2 Materials.....	7
5.9 Requirements of operating device and actuators.....	7
5.10 Surface treatment.....	7
5.11 Welding and heat treatment.....	8
5.11.1 Welding.....	8
5.11.2 Heat treatment.....	8
5.12 Repair welding.....	8
6 Test and inspection	8
6.1 General.....	8
6.2 Material test.....	8
6.3 Non-destructive inspection.....	8
6.3.1 General.....	8
6.3.2 Radiographic testing (RT).....	9
6.3.3 Dye penetrant testing (PT).....	9
6.3.4 Ultrasonic Testing (UT).....	9
6.3.5 Retest.....	10
6.3.6 Submission of inspection results.....	10
6.4 Dimension check.....	10
6.5 Visual inspection.....	10
6.6 Heat treatment inspection.....	10
6.7 Operating tests.....	10
6.8 Pressure test.....	10
6.8.1 Pressure test in ambient temperature.....	10
6.8.2 Test procedure and method.....	11

6.9	Fire-resistance test (if necessary)	11
6.10	Anti-static testing	11
6.11	Cryogenic tests	11
6.11.1	General	11
6.11.2	Scope of tests	12
6.11.3	Test procedure	12
6.11.4	Submission of test results	13
7	Marking	13
Annex A (informative) Examples of butterfly valve construction		14

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 21159:2018](https://standards.iteh.ai/catalog/standards/iso/7acf56bd-bae0-429f-b145-36248082b83c/iso-21159-2018)

<https://standards.iteh.ai/catalog/standards/iso/7acf56bd-bae0-429f-b145-36248082b83c/iso-21159-2018>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 8, *Ships and marine technology*, Subcommittee SC 3, *Piping and machinery*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

<https://standards.iteh.ai/catalog/standards/iso/7acf56bd-bae0-429f-b145-36248082b83c/iso-21159-2018>

Ships and marine technology — Butterfly valves for use in low temperature applications — Design and testing requirements

1 Scope

This document specifies requirements for design, manufacture, and test methods of cryogenic butterfly valves in order to have an excellent quality leakage stability in a very low temperature service (–196 °C to 80 °C).

It is applicable to valves of nominal sizes: DN: 80, 100, 150, 200, 250, 300, 350, 400, 450, 500, 550, 600 corresponding to nominal pipe size (NPS): 3, 4, 6, 8, 10, 12, 14, 16, 18, 20, 22, 24.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5208, *Industrial valves — Pressure testing of metallic valves*

ISO 5209, *General purpose industrial valves — Marking*

ISO 5211, *Industrial valves — Part-turn actuator attachments*

ISO 28921-1, *Industrial valves — Isolating valves for low-temperature applications — Part 1: Design, manufacturing and production testing*

ISO 10497, *Testing of valves — Fire type-testing requirements*

API 609, *Butterfly Valves: Double flanged, lug and wafer-type*

ASME B 16.5, *Pipe Flanges and Flanged Fittings*

ASME B 16.10, *Face-to-Face and End-to-End Dimensions of Valves*

ASME B 16.25, *Buttwelding Ends*

ASME B16.34:2007, *Valves — Flanged, Threaded, and Welding End*

SEC ASME V, *Non-destructive Examination*

SEC ASME VIII, *Pressure vessels*

ASTM A182/A182M, *Forged or Rolled Alloy-Steel Pipe Flanges, Forged Fittings and Valves and Parts for High-temperature Service*

ASTM A193/A193M, *Standard Specification for Alloy-Steel and Stainless Steel Bolting for High Temperature or High Pressure Service and Other Special Purpose Applications*

ASTM A194/A194M, *Carbon and Alloy Steel Nuts and Bolts for High-Pressure and High-Temperature Service*

ASTM A276, *Standard Specification for Stainless Steel Bars and Shapes*

ASTM A312/A312M, *Standard Specification for Seamless, Welded, and Heavily Cold Worked Austenitic Stainless Steel Pipes*

ASTM A320/A320M, *Alloys-Steel Bolting material for Low-Temperature service*

ASTM A351/A351M, *Casting, Austenitic, Austenitic -Ferritic (Duplex), for Pressure-Containing Parts*

ASTM E186, *Reference Radiographs for Heavy-Walled (2 to 4 1/2-in) Steel Castings*

ASTM E446, *Reference Radiographs for Steel Castings up to 2in. in Thickness*

MSS SP-44. *Steel pipeline flanges*

MSS-SP-55. *Quality Standard for steel Castings for Valves, Flanges and Fittings and other Piping Components (Visual Method)*

3 Terms and definitions

For the purpose of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 nominal diameter

DN

alphanumeric designation of size for components of a pipe-work system, used for reference purposes, comprising the letters DN followed by a dimensionless whole number which is indirectly related to the physical size, in millimetres, of the bore or outside diameter of the end connections

Note 1 to entry: The number following the letters DN does not represent a measure value and shall not be used for calculation purposes except where specified in the relevant standard.

Note 2 to entry: In those standards which use the DN designation system, any relationship between DN and component dimensions shall be given, e.g. DN/OD or DN/ID.

3.2 nominal pressure

PN

numerical designation relating to pressure that is a convenient round number for reference purposes

Note 1 to entry: It is intended that all equipment of the same nominal size (DN) designated by the same PN number shall have the same mating dimensions appropriate to the type of end connections. The permissible working pressure depends upon materials, design and working temperature and has to be selected from the pressure/temperature rating tables in corresponding standards.

3.3 nominal pipe size

NPS

alphanumeric designation of size that is common for components used in a piping system, used for reference purposes, comprising the letters NPS followed by a dimensionless number having an indirect correspondence to the physical size of the bore or outside diameter of the component end connections.

Note 1 to entry: The dimensionless number may be used as a size identifier without the prefix NPS. The dimensionless number does not represent a measurable value and is not used for calculation purposes.

Note 2 to entry: Prefix NPS usage is applicable to components bearing Class designations according to ISO 7268.

3.4 class

alphanumeric designation, used for reference purposes, related to a combination of mechanical and dimensional characteristics of a component of a pipe-work system, comprising the word “class” followed by a dimensionless whole number

4 Pressure-temperature rating

4.1 The types of typical fluid are shown in [Table 1](#).

Table 1 — Types of typical fluid

Fluid	Temperature (in atmospheric pressure)	Liquid density (density)
LNG (Liquefied natural gas)	–163 °C to –88 °C	(434 to 478) kg/m ³
NG (Natural gas)	–160 °C to –65 °C	(0,7 to 0,89) kg/m ³
LN2 (Liquefied nitrogen)	–196 °C	804 kg/m ³
N2 (Nitrogen)	–196 °C to –65 °C	1,184 kg/m ³

4.2 The valve shall be designed to operate without failure or leakage at the extreme temperature and pressure ranges expected in service. The maximum working pressure and design temperature are shown in [Table 2](#).

Table 2 — Maximum working pressure

PN	Class	Maximum working pressure MPa(psi)	Note
20	150	2,0(290)	in ambient temperature
50	300	5,2(750)	

NOTE The piping design condition including, but not limited to, working pressure, service temperature and fluid is provided by the purchasers.

4.3 The manufacturers and purchasers may reach an agreement when Class exceeds 300.

4.4 Design temperature should be between –196 °C and 80 °C.

5 Structure

5.1 General

5.1.1 Structure

Butterfly valves can be divided into two types, with maintenance holes and without maintenance holes. For butterfly valves with maintenance holes, the disc or seat sealing shall be removable from the maintenance hole without removing the valve from the pipe. The butterfly valve is extended bonnet type. The end connection of the body is welding ends type or flanged ends type. A wheel or levers is used to apply the turning torque or thrust to open or close the valve. The butterfly valve may be either soft-seated or metal-seated. Configuration and functions of the butterfly valve are shown in this document. If there are some differences from this document, the manufacturers can make a decision after reaching an agreement with the purchasers. General examples of the structure of the valve are shown in [Annex A](#).

5.1.2 Materials

Throughout this document, materials are specified for each of the various parts of the valve. In lieu of the materials specified, other materials may be used provided they are manufactured by the same process as the materials specified, such as forging, casting, bar, or seamless pipe. In addition, the material shall be suitable for the operating temperatures and pressure of the valve and the metal materials shall have mechanical properties, including low temperature impact resistance, and resistance to corrosion equal to or better than the material specified for the specific valve part.

5.2 Design and materials of the body

5.2.1 Design

The body should be casting integrally, in case the valve contains suitably located lugs which have sufficient strength to support the valve lift and valve support legs, they cannot affect the connection bolts.

5.2.2 Materials

Materials are shown in [Table 3](#). Materials for 'welding ends' type valves may be used for 'flange ends' type material.

Table 3 — Materials by manufacturing method

Manufacturing method	Materials	
	Flange ends type	Welding ends type
Casting	ASTM A351 CF8M	ASTM A351 CF3M

5.2.3 Manufacturing

The valve shall be manufactured according to the following requirements except when there are purchaser's special orders.

- a) Face-to-face and end-to-end dimensions of flange ends type shall satisfy ASME B16.10. Face-to-face and end-to-end dimensions of welding ends type shall reach an agreement between purchasers and manufacturers.
- b) The minimum wall thickness shall be equal to or thicker than the values shown in ASME B16.34:2007 6.1.
- c) The end connection of the body shall be manufactured as specified below:
 - 1) butt welding ends:
 - according to the wall thickness of connected pipes which is given by the purchasers, manufactured according to ASME B16.25; and
 - the butt welding ends may add a short stub if specified in the order. The wall thickness shall conform to the requirements of purchasers;
 - 2) flange ends type:
 - NPS 24(DN 600) and under, except NPS22(DN550): to be manufactured in accordance with ASME B16.5; and
 - NPS 22(DN 550): to be manufactured in accordance with MSS SP-44.