



SLOVENSKI STANDARD
oSIST prEN ISO 12696:2021
01-april-2021

Katodna zaščita jekla v betonu (ISO/DIS 12696:2021)

Cathodic protection of steel in concrete (ISO/DIS 12696:2021)

Kathodischer Korrosionsschutz von Stahl in Beton (ISO/DIS 12696:2021)

Protection cathodique de l'acier dans le béton (ISO/DIS 12696:2021)

Ta slovenski standard je istoveten z: prEN ISO 12696

[oSIST prEN ISO 12696:2021](https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021)

<https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021>

ICS:

77.060	Korozija kovin	Corrosion of metals
77.140.15	Jekla za armiranje betona	Steels for reinforcement of concrete
91.080.40	Betonske konstrukcije	Concrete structures

oSIST prEN ISO 12696:2021

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 12696:2021](https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021)

<https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 12696

ISO/TC 156

Secretariat: SAC

Voting begins on:
2021-02-15Voting terminates on:
2021-05-10

Cathodic protection of steel in concrete

Protection cathodique de l'acier dans le béton

ICS: 77.140.15; 77.060

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 12696:2021](https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021)
<https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 12696:2021(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 General	3
4.1 Quality management systems.....	3
4.2 Persons.....	3
4.3 Design.....	3
5 Structure assessment and repair	4
5.1 General.....	4
5.2 Records.....	4
5.3 Visual inspection and delamination survey.....	4
5.4 Chloride analysis.....	4
5.5 Carbonation depth measurement.....	4
5.6 Concrete cover and reinforcement location.....	5
5.7 Reinforcement electrical continuity.....	5
5.8 Steel/concrete potential.....	5
5.9 Concrete electrical resistivity.....	5
5.10 Repair.....	6
5.10.1 General.....	6
5.10.2 Concrete removal.....	6
5.10.3 Reinforcement preparation.....	6
5.10.4 Concrete reinstatement.....	6
5.11 Cementitious overlay.....	7
5.12 New structures.....	7
6 Cathodic protection system components	8
6.1 General.....	8
6.2 Anode systems.....	8
6.2.1 General.....	8
6.2.2 Conductive coating anode systems.....	9
6.2.3 Activated titanium anode systems.....	10
6.2.4 Titania ceramic anodes.....	11
6.2.5 Conductive cementitious anodes.....	11
6.2.6 Embedded galvanic anodes.....	11
6.2.7 Surface-mounted galvanic anodes.....	12
6.2.8 Buried and immersed anodes.....	12
6.3 Monitoring sensors.....	14
6.3.1 General.....	14
6.3.2 Portable reference electrodes.....	14
6.3.3 Other sensors.....	15
6.4 Monitoring instrumentation.....	15
6.4.1 General.....	15
6.4.2 Digital meters.....	16
6.4.3 Data loggers.....	16
6.5 Data management system.....	17
6.6 Direct current cables.....	17
6.7 Junction boxes.....	18
6.8 Power supplies.....	19
6.9 Transformer-rectifiers.....	19
7 Installation procedures	20
7.1 Electrical continuity.....	20

ISO/DIS 12696:2021(E)

7.2	Performance monitoring system.....	21
7.3	Connections to steel in concrete.....	22
7.4	Concrete repairs associated with the cathodic protection components.....	22
7.5	Surface preparation for anode installation.....	22
7.6	Anode installation.....	22
7.7	Connections to the anode system.....	23
7.8	Anode overlay, surface sealant or decorative coating application.....	23
7.9	Electrical installation.....	24
7.10	Testing during installation.....	24
8	Commissioning.....	25
8.1	Visual inspection.....	25
8.2	Pre-energizing measurements.....	25
8.3	Initial energizing of impressed current systems.....	26
8.4	Initial adjustment of impressed current systems.....	26
8.5	Initial performance assessment.....	26
8.6	Criteria of protection: Interpretation of performance assessment data.....	28
9	System records and documentation.....	29
9.1	Quality and test records.....	29
9.2	Installation and commissioning report.....	29
9.3	Operation and maintenance manual.....	29
10	Operation and maintenance.....	30
10.1	Intervals and procedures.....	30
10.2	System review.....	31
10.3	System review report.....	31
Annex A (informative)	Principles of cathodic protection and its application to steel in concrete.....	32
Annex B (informative)	Design Process.....	40
Annex C (informative)	Notes on anode systems.....	47
Annex D (informative)	Notes on reference electrodes.....	52
Bibliography		56

iTech STANDARD PREVIEW

(standards.iteh.ai)

oSIST prEN ISO 12696:2021
<https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-fc92e3191000/iso-12696-2021>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys* and CEN/TC 219, *Cathodic protection of steel in concrete*.

This third edition cancels and replaces the second edition (ISO 12696:2016), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [3.1](#) “steel surface ratio” has been added;
- [8.6](#) has been revised;
- [Annex A](#) has been revised: the figures in [Annex A](#) has been updated; [A.7](#) has been moved to the new [Annex D](#) and a new [Clause A.7](#) “Benefits of Cathodic Protection Current when Criteria in [8.6](#) are not fully met” has been added;
- [Annex B](#) has been revised completely;
- New [Annex D](#);
- [C.5](#) “Hybrid anodes” has been added;
- The references in the whole document has been revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO/DIS 12696:2021(E)

Introduction

This document applies to cathodic protection of steel in concrete, with the concrete atmospherically exposed, buried or immersed.

Because the criteria of protection for steel in buried or immersed concrete are those applicable to cathodic protection of steel in atmospherically exposed concrete, this revision of EN 12696:2016 incorporates cathodic protection of steel in buried and immersed concrete. The provision of cathodic protection current can often be more economically provided to steel in buried and immersed concrete by using buried or immersed anode systems detailed in International Standards for buried and immersed steel structures, rather than the anode systems that are suitable for applications to steel in atmospherically exposed concrete. Therefore, reference is made to other International Standards in this respect while the cathodic protection performance criteria for steel in concrete are defined in this document for all exposures.

There are other electrochemical treatments intended to provide corrosion control for steel in concrete. These techniques include re-alkalization and chloride extraction and are not incorporated into this document. EN 14038-1:2016 and prEN 14038-2:2019 have been published.

Cathodic protection of steel in concrete is a technique that has been demonstrated to be successful in appropriate applications in providing cost effective long-term corrosion control for steel in concrete. It is a technique that requires specific design calculations and definition of installation procedures in order to be successfully implemented. This document does not represent a design code for cathodic protection of steel in concrete, but represents a performance standard for which it is anticipated, in order to comply with this document, a detailed design and specification for materials, installation, commissioning and operation will be prepared by expert and experienced persons.

[oSIST prEN ISO 12696:2021
https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021](https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021)

Cathodic protection of steel in concrete

1 Scope

This document specifies performance requirements for cathodic protection of steel in cement-based concrete, in both new and existing structures. It covers building and civil engineering structures, including carbon steel reinforcement and prestressed reinforcement embedded in the concrete. It is applicable to uncoated steel reinforcement and to organic-coated steel reinforcement. It is not applicable to carbon fibre reinforced concrete.

This document applies to steel embedded in atmospherically exposed, buried, immersed and tidal elements of buildings or structures.

This document applies only to the applications of cathodic protection to steel in concrete which are designed with the intention to, and can be demonstrated to, meet the Criteria of Protection as defined in 8.6. This requires the provision of sufficient performance monitoring systems as defined in 6.3 to all parts of the structure intended to be protected, in order to assess the extent to which the Criteria in 8.6 are met.

This may exclude from the Scope of this document galvanic anodes or systems applied into patch repairs to reduce the effects of 'incipient anodes'. This may also exclude from the Scope of this document any form of cathodic protection systems or other electrochemical treatments that either cannot meet the requirements of 8.6 or are not provided with the performance monitoring systems (see 6.3) that are necessary to assess whether the Criteria of Protection as defined in 8.6 are met.

NOTE 1 [Annex A](#) gives guidance on the principles of cathodic protection and its application to steel in concrete.

NOTE 2 This document, while not specifically intended to address cathodic protection of steel in any electrolyte except concrete, can be applied to cathodic protection of steel in other cementitious materials such as are found, for example, in early 20th century steel-framed masonry, brick and terracotta clad buildings. In such applications, additional considerations specific to these structures are required in respect of design, materials and installation of cathodic protection; however, the requirements of this document can be applied to these systems.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies

EN 1504 (all parts), *Products and systems for the protection and repair of concrete structures — Definitions, requirements, quality control and evaluation of conformity*

EN 14629, *Products and systems for the protection and repair of concrete structures — Test methods — Determination of chloride content in hardened concrete*

EN 14630, *Products and systems for the protection and repair of concrete structures — Test methods — Determination of carbonation depth in hardened concrete by the phenolphthalein method*

ISO 15257, *Cathodic protection — Competence levels of cathodic protection persons — Basis for a certification scheme*

IEC 60502-1, *Power cables with extruded insulation and their accessories for rated voltages from 1 kV ($U_m = 1,2$ kV) to 30 kV ($U_m = 36$ kV) — Part 1: Cables for rated voltages of 1 kV ($U_m = 1,2$ kV) and 3 kV ($U_m = 3,6$ kV)*

ISO/DIS 12696:2021(E)

IEC 60529, *Degrees of protection provided by enclosures (IP Code)*

IEC 61140, *Protection against electric shock — Common aspects for installation and equipment*

IEC 61558-1, *Safety of power transformers, power supplies, reactors and similar products — Part 1: General requirements and tests*

IEC 61558-2-1, *Safety of power transformers, power supplies, reactors and similar products — Part 2-1: Particular requirements and tests for separating transformers and power supplies incorporating separating transformers for general applications*

IEC 61558-2-2, *Safety of power transformers, power supplies, reactors and similar products — Part 2-2: Particular requirements and tests for control transformers and power supplies incorporating control transformers*

IEC 61558-2-4, *Safety of transformers, reactors, power supply units and similar products for supply voltages up to 1 100 V — Part 2-4: Particular requirements and tests for isolating transformers and power supply units incorporating isolating transformers*

IEC 61558-2-13, *Safety of transformers, reactors, power supply units and similar products for supply voltages up to 1 100 V — Part 2-13: Particular requirements and tests for auto transformers and power supply units incorporating auto transformers*

IEC 61558-2-16, *Safety of transformers, reactors, power supply units and similar products for voltages up to 1 100 V — Part 2-16: Particular requirements and tests for switch mode power supply units and transformers for switch mode power supply units*

IEC 62262, *Degrees of protection provided by enclosures for electrical equipment against external mechanical impacts (IK code)*

ITeH STANDARD PREVIEW
(standards.iteh.ai)

3 Terms and definitions

oSIST prEN ISO 12696:2021

[https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-](https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pr-en-iso-12696-2021)

[e40545fb21cc/osist-pr-en-iso-12696-2021](https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pr-en-iso-12696-2021)

For the purposes of this document, the terms and definitions given in ISO 8044 and EN 1504 (all parts) and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 steel surface ratio

ratio of surface area of steel to surface area of concrete

3.2 zone

part of a cathodic protection system

Note 1 to entry: Anode systems can be divided into separate zones to supply current to a fully continuous reinforcement mesh. Alternatively, a single anode zone can supply current to separate, electrically isolated, zones within the reinforcement system. Zones can comprise an individual anode zone for each reinforcement zone or exposure condition. As the current provision to each of the zones in each of these alternatives can be separately measured, all of them are generically called “cathodic protection zones” and specifically “anode zones” or “cathode zones”.

3.3 humectant

hygroscopic material, i.e. a substance that promotes the retention of moisture

Note 1 to entry: It can be applied to the surface of a galvanic anode to keep the concrete-anode interface moist.

4 General

4.1 Quality management systems

The design, the installation, the energizing, the commissioning and the long-term operation of all of the elements of cathodic protection systems for steel in concrete shall be fully documented, see [Annex B](#).

NOTE ISO 9000 constitutes a suitable quality management systems standard which can be utilized.

Each element of the work shall be undertaken in accordance with a fully documented quality plan.

Each stage of the design shall be checked and the checking shall be documented.

Each stage of the installation, energizing, commissioning and operation shall be the subject of appropriate visual, mechanical and/or electrical testing, and all testing shall be documented.

All test instrumentation shall have valid calibration certificates traceable to National or International standards concerning calibration.

The documentation shall constitute part of the permanent records for the works.

4.2 Persons

Each aspect of the cathodic protection system design, installation, testing of the installation, energizing, commissioning and long-term operational control shall be under the supervision of persons with appropriate qualifications, training, expertise and experience in the particular element of the work for which they are responsible.

NOTE Cathodic protection of steel in concrete is a specialist multidiscipline activity. Expertise is required in the fields of electrochemistry, concrete technology, civil and/or structural engineering and cathodic protection engineering.

Persons who undertake the design, supervision of installation, commissioning, supervision of operation, measurements, monitoring and supervision of maintenance of cathodic protection systems shall have the appropriate level of competence for the tasks undertaken. ISO 15257 specifies a suitable method which may be utilized for assessing the competence of cathodic protection persons.

The competence of cathodic protection persons to the appropriate level for tasks undertaken should be demonstrated by certification in accordance with ISO 15257 or by another equivalent prequalification procedure.

4.3 Design

This document does not represent a design code, but is a performance standard.

Cathodic protection systems for steel in concrete shall be the subject of detailed design.

The design shall, as a minimum, include and document the following:

- a) detailed calculations;
- b) detailed installation drawings;
- c) detailed material and equipment specifications;
- d) detailed method statements or specifications for installation, testing, energizing, commissioning and operation;
- e) structures containing prestressing shall be assessed for their susceptibility to hydrogen embrittlement and for risk of stray currents.

ISO/DIS 12696:2021(E)

[Annex B](#) provides guidance for the detailed design which shall be undertaken by persons who meet the requirements of [4.2](#). If ISO 15257 is used to demonstrate their competence, they shall be certificated to Level 4 or above in the Sector 'Reinforced concrete structures'.

5 Structure assessment and repair

5.1 General

For cathodic protection (or cathodic prevention) of new structures, see [5.12](#).

The assessment of an existing structure, including its material condition, its structural integrity and whether and how to repair it, shall be performed in accordance with EN 1504 (all parts).

When cathodic protection is proposed as the repair/protection method, or part of it, for a structure, additional investigation shall be undertaken in order to

- a) confirm the suitability of cathodic protection and
- b) provide system-design input information (for further information see [Annex B](#)).

These investigations shall include, but shall not be limited to those in [5.2](#) to [5.10](#).

5.2 Records

All available drawings, specifications, records and notes shall be reviewed to assess the location, quantity, nature (e.g. normal, galvanized, epoxy-coated, prestressed) and continuity of the reinforcement and any additional steel, the constituents and quality of the concrete.

The available information shall be confirmed and supplemented by site survey and laboratory tests, as specified in [5.3](#) to [5.8](#).

<https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021>

5.3 Visual inspection and delamination survey

Visual survey data shall be collected to ascertain the type, causes and extent of defects, and any features of the structure or its surrounding environment, which could influence the application and effectiveness of cathodic protection. Areas which have been previously repaired, and the repair methods and materials, shall be identified.

All areas of the structure which require to be cathodically protected shall be checked for delamination of the concrete cover.

Defects, such as cracks, honeycombing or poor construction joints, which could permit significant water penetration, and which could in turn impair the effectiveness or durability of the cathodic protection system, shall be recorded.

Where necessary, the inspection and survey of buried or immersed elements will be facilitated by excavation and or cofferdams.

5.4 Chloride analysis

If required, values and distributions of the chloride content of the concrete shall be determined in accordance with EN 14629.

5.5 Carbonation depth measurement

If required, distribution of carbonation depths shall be measured in accordance with EN 14630.

5.6 Concrete cover and reinforcement location

Concrete cover distribution and embedded steel and reinforcement size and position measurements shall be carried out in order to assess whether the anode/cathode spacing will be adequate for the particular anode system envisaged, and to identify dense regions of steel or reinforcement which may require high current density. Shielding of the steel to be protected, caused by embedded metal meshes, metal fibres or plates, plastic sheets or non-conductive repair materials, which could impair the efficiency of cathodic protection, shall be assessed. Possible short-circuits between reinforcing steel and impressed current anodes shall be assessed.

For buried or immersed structures or zones, the concrete cover may be less significant if the anode system is to comprise anodes buried or immersed and located some distance from the structure.

5.7 Reinforcement electrical continuity

Drawings of reinforcement and other steel elements shall be checked for size, distribution, laps and continuity. The last shall then be proven on site by measuring the electrical resistance and/or potential difference between bars in locations remote from each other across the structure. Testing shall be as specified in 7.1 for the purpose of confirming cathodic protection feasibility and providing design information. This shall include at least an assessment of the following on a representative basis:

- a) electrical continuity between elements of the structure within each zone of the cathodic protection system;
- b) electrical continuity of reinforcement within elements of the structure;
- c) electrical continuity of metallic items, other than reinforcement, to the reinforcement itself.

At the subsequent repair and installation stage, reinforcement and other steel size, distribution, laps and electrical continuity shall be further checked in accordance with the methods, and to the extent specified in 7.1.

<https://standards.iteh.ai/catalog/standards/sist/e3764fe6-b9b4-4ab4-9bb5-e40545fb21cc/osist-pren-iso-12696-2021>

5.8 Steel/concrete potential

Representative areas, both damaged and apparently undamaged, shall be surveyed for reinforcing steel corrosion activity, using portable reference electrodes conforming to 6.3.2. Measurements shall be taken, preferably on an orthogonal grid, at a maximum spacing of 500 mm.

NOTE 1 It is not necessary to carry out a steel/concrete potential survey of the entire structure. It is appropriate to survey, in more detail, those areas where reference electrodes are planned to be permanently installed, in order to place them in most anodic and other suitable locations.

Continuity of the reinforcement and any other steel within any steel/concrete potential survey area is essential and shall be checked, using the method in 7.1 before the steel/concrete potential survey.

Measurements in any areas identified as delaminated, in the survey specified in 5.3, should be interpreted with caution, because delamination can produce readings inconsistent with the level of corrosion of the reinforcement or other embedded steel.

NOTE 2 [12], [13] and [14] provide guidance with respect to steel/concrete potential measurements and interpretation.

5.9 Concrete electrical resistivity

The impact of variations in concrete resistivity on the cathodic protection system shall be considered. There is no firm guidance on limits of electrical resistivity with respect to cathodic protection, but the designer shall consider whether full protection can be achieved where required for the ranges of concrete resistivity found on the structure.

NOTE [14] and [15] provide guidance with respect to concrete electrical resistivity measurements and interpretation.

ISO/DIS 12696:2021(E)

5.10 Repair

5.10.1 General

All operations comprising repair shall be performed in accordance with EN 1504 (all parts), except where stated otherwise in this subclause.

NOTE Installation of cathodic protection to an existing structure can be associated with other forms of repair work, such as strengthening, patching or coating, as determined in accordance with EN 1504 (all parts). In this subclause, the term “repair” signifies reinstatement of the damaged/deteriorated concrete to provide an uninterrupted path for the flow of cathodic protection current prior to the installation of cathodic protection, as well as reinstatement at locations where concrete has been removed to provide access to reinforcement and other steel, to install cable connections and monitoring sensors, etc.

5.10.2 Concrete removal

Any repair material detrimental to the performance of the CP system shall be broken out.

For example, predominantly epoxy-based repair materials will have very high resistivity values and may shield reinforcement within or behind them from cathodic protection. Concrete reinforced with metallic fibres may have very low electrical resistivity and the fibres may form an electrical short-circuit path between the anode and the steel.

For impressed-current cathodic protection systems, any tying wire, nails or other metal components visible on the concrete, that might contact the anode system or might be too close to the anode for optimum anode/cathode spacing, shall be cut back and the concrete shall be repaired.

NOTE Any metallic objects electrically isolated from the cathodic protection cathode circuit can corrode and can require to be electrically bonded to the reinforcement or removed.

The removal of physically sound chloride-contaminated or carbonated concrete prior to applying cathodic protection is not necessary.

5.10.3 Reinforcement preparation

Any loose corrosion product particles shall be removed from the exposed reinforcement or other steel to ensure good contact between the steel and the repair material, but there is no need to clean the reinforcement or other steel, to be embedded in concrete, to bright metal. However, the designer shall consider the impacts of any significant corrosion products on the steel surface on the bonding of concrete repairs to the reinforcement.

NOTE Retained corrosion products are likely to be high in chlorides. If these coincide with voids in the concrete repairs these areas are likely to continue to corrode.

The designer shall consider the effect of primers or coatings used as part of the repair system, having consideration for the possible shielding of CP current from the steel to which, or behind which, the primers or coatings are applied.

5.10.4 Concrete reinstatement

Concrete reinstatement shall be in accordance with EN 1504 (all parts), except where stated in this subclause.

Concrete shall be reinstated using cementitious materials. Repair materials containing metal (either fibre or powder) shall not be used. The electrical resistivity characteristics and mechanical properties of the repair materials shall be compatible with the original concrete. Proprietary curing membranes shall not be used prior to subsequent anode installation over the repair area. Alternative curing methods shall be used.

The electrical resistivity of concrete repair materials shall be similar to that of the parent concrete.

NOTE Typically, these repair materials will have an electrical resistivity within the range approximately half to twice that of the parent concrete when measured under the same conditions as the parent concrete. However, the electrical resistivity of the parent concrete will be that of an aged material (age > 20 years), whereas the electrical resistivity of the repair material will reflect the properties at a relatively young age; it is anticipated that there will be a significant ageing effect over time. Also, measurements made in the laboratory on prisms will not represent the conditions of the structure. A good quality repair made with materials known to be compatible with cathodic protection installations has been found to be more important than arbitrary resistivity limits.

5.11 Cementitious overlay

For cathodic protection systems employing anode systems as outlined in 6.2.2.2, following repair as specified in 5.10, and anode installation in accordance with 7.5, 7.6 and 7.7, a cementitious overlay shall be applied over appropriate types of installed anode. All cementitious materials and application methods shall be in accordance with EN 1504 (all parts). The average bond strength between the existing concrete and overlay shall be greater than 1,5 MPa and the minimum shall be greater than 1,0 MPa.

If the substrate concrete cohesive strength fails at lower values than 1,5 MPa average and 1,0 MPa minimum, the use of a cementitious overlay may be inappropriate.

Overlay application may be combined with concrete repair.

The electrical resistivity of anode overlays may significantly exceed that of the parent concrete subject to the anode within the overlay being able to pass its design current at the design voltage, in an overlay of this resistivity, in all atmospheric and exposure conditions applicable to the structure.

The selected material, thickness and placement method shall be compatible with each other, with the anode material and the exposure of the structure. Curing membranes shall be removed from the parent concrete/substrate or shall have sufficiently degraded to avoid adversely influencing the performance of the cathodic protection system.

The potential between the anode and reinforcement/steel (cathode) shall be monitored to detect short-circuits.

5.12 New structures

In the case of a new structure, if cathodic protection as a preventive system (Cathodic Prevention) is to be included in the original construction, the following issues shall be assessed in the design, specification and construction procedures, in addition to the requirements of the remainder of this document and of the standards governing the design and construction of the new structure:

- a) provision and checking of reinforcing steel electrical continuity, in accordance with 7.1;
- b) adequate securing and protection of monitoring sensors and all cables and their connections, to avoid damage or disturbance during concrete placement and vibration;
- c) connection, location or insulation of other metallic fixtures, fixings or other items, so as to avoid undesirable influences from the cathodic prevention system;
- d) in the case of anodes cast into the concrete structure, provision of sufficient rigid insulating spacers and attachments to secure the anodes in position and prevent the creation of short-circuits during concrete placement and vibration. Monitoring of potential between anode and reinforcement/steel (cathode) shall be used to detect any short-circuits during concrete placement.