



**Designation: B 779—96 Designation: B 779 – 03 (Reapproved 2009)**

## Standard Specification for Shaped Wire Compact Concentric-Lay-Stranded Aluminum Conductors, Steel-Reinforced (ACSR/TW)<sup>1</sup>

This standard is issued under the fixed designation B 779; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers shaped wire compact concentric-lay-stranded aluminum conductor, steel-reinforced (ACSR/TW) and its component wires for use as overhead electrical conductors (Explanatory Note 1 and Note 2).

~~1.2 The values stated in inch-pound units are to be regarded as the standard with the exception of temperature, density, and resistivity. The SI equivalents of inch-pound units may be approximate.~~

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—ACSR/TW is designed to increase the aluminum area for a given diameter of conductor by the use of trapezoidally shaped wires (TW). The conductors consist of a central core of round steel wire(s) surrounded by two or more layers of trapezoidal aluminum 1350-H19 wires. Different strandings of the same size of conductor are identified by type, which is the approximate ratio of steel area to aluminum area expressed in percent (Table 1, Table 2 and Table 3). For the purpose of this specification, the sizes listed in Table 1 and Table 2 are tabulated on the basis of the finished conductor having an area or outside diameter equal to that of specific sizes of standard ACSR so as to facilitate conductor selection.

NOTE 2—The aluminum and temper designations conform to ANSI Standard H 35.1. Aluminum 1350 corresponds to Unified Numbering System (UNS) A91350 in accordance with Practice E 527.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

~~B 230/B 230M Specification for Aluminum 1350-H19 1350H19 Wire for Electrical Purposes~~

~~B 232/B 232M Specification for Concentric-Lay-Stranded Aluminum Conductors, Coated-Steel-Reinforced (ACSR)~~

~~B 263 Test Method for Determination of Cross-Sectional Area of Stranded Conductors~~

~~B 341/B 341M Specification for Aluminum-Coated (Aluminized) Steel Core Wire for Aluminum Conductors, Steel Reinforced (ACSR/AZ)~~

~~B 354 Terminology Relating to Uninsulated Metallic Electrical Conductors~~

~~B 498 Specification for Zinc-Coated (Galvanized) Steel Core Wire for Aluminum Conductors, Steel Reinforced (ACSR)<sup>2</sup>~~

~~498/B 498M Specification for Zinc-Coated (Galvanized) Steel Core Wire for Use in Overhead Electrical Conductors~~

~~B 500 Specification for Metallic Coated Stranded Steel Core for Aluminum Conductors, Steel Reinforced (ACSR)<sup>2</sup>—500/~~

~~B 500M Specification for Metallic Coated Stranded Steel Core for Use in Overhead Electrical Conductors~~

~~B 502 Specification for Aluminum-Clad Steel Core Wire for Aluminum Conductors, Aluminum-Clad Steel Reinforced~~

~~B 549 Specification for Concentric-Lay-Stranded Aluminum Conductors, Aluminum-Clad Steel Reinforced (ACSR/AW)~~

~~B 606 Specification for High-Strength Zinc-Coated (Galvanized) Steel Core Wire for Aluminum and Aluminum-Alloy Conductors, Steel Reinforced~~

~~B 802/B 802M Specification for Zinc-5%—Zinc5 % Aluminum-Mischmetal Alloy-Coated Steel Core Wire for Aluminum Conductors, Steel Reinforced (ACSR)~~

~~B 803 Specification for High-Strength Zinc-5% Aluminum-Mischmetal Alloy-Coated Steel Core Wire for Aluminum and Aluminum-Alloy Conductors, Steel Reinforced<sup>2</sup>—Specification for High-Strength Zinc5 % Aluminum-Mischmetal Alloy-Coated Steel Core Wire for Use in Overhead Electrical Conductors~~

~~E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications~~

~~E 527 Practice for Numbering Metals and Alloys (UNS)—Practice for Numbering Metals and Alloys in the Unified Numbering~~

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B-4 on Electrical Conductors and is the direct responsibility of Subcommittee B01.07 on Conductors of Light Metals.

Current edition approved March 10, 1996. Published May 1996. Originally published as B779-87. Last previous edition B779-91.

Current edition approved April 1, 2009. Published May 2009. Originally approved in 1987. Last previous edition approved in 2003 as B 779 – 03.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* Vol 02.03 volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Construction Requirements for Shaped Wire Compact Concentric-Lay-Stranded Aluminum Conductors, Coated Steel Reinforced Size to Have Area Equal to ACSR, Class AA**

ACSR/TW Conductor Size		Size and Stranding of ACSR with Equal Area		Number of Aluminum Wires	Number of Layers	Steel Core Stranding		Mass per Unit Length, <sup>A</sup> lb/1000 ft	Rated Strength, 1000 lb <sup>B</sup>	Nominal Outside Diameter, in.
kcmil	Type	kcmil	Stranding			Number of Wires	Diameter, in.			
336.4	6	336.4	18/1	14	2	1	0.1367	365	8.6	0.63
477.0	13	477.0	24/7	18	2	7	0.0940	613	17.2	0.78
477.0	16	477.0	26/7	18	2	7	0.1053	655	19.4	0.79
556.5	13	556.5	24/7	18	2	7	0.1015	715	20.0	0.84
556.5	16	556.5	26/7	20	2	7	0.1138	765	22.6	0.85
636.0	3	636.0	36/1	27	3	1	0.1329	646	13.5	0.85
636.0	13	636.0	24/7	18	2	7	0.1085	816	22.9	0.89
636.0	16	636.0	26/7	20	2	7	0.1216	874	25.4	0.91
795.0	7	795.0	45/7	17	2	7	0.0886	892	21.0	0.96
795.0	10	795.0	22/7	18	2	7	0.1108	975	25.9	0.98
795.0	13	795.0	54/7	20	2	7	0.1213	1021	28.2	0.99
795.0	16	795.0	26/7	20	2	7	0.1360	1092	31.8	1.01
954.0	5	954.0	42/7	30	3	7	0.0837	1029	23.7	1.05
954.0	7	954.0	45/7	32	3	7	0.0971	1075	25.9	1.06
954.0	13	954.0	54/7	20	2	7	0.1329	1226	33.5	1.08
1033.5	5	1033.5	42/7	30	3	7	0.0871	1115	25.7	1.09
1033.5	7	1033.5	45/7	32	3	7	0.1010	1165	28.1	1.10
1033.5	13	1033.5	54/7	21	2	7	0.1363	1327	36.3	1.13
1113.0	5	1113.0	42/7	30	3	7	0.0904	1201	27.5	1.13
1113.0	7	1113.0	45/7	33	3	7	0.1049	1254	30.3	1.14
1113.0	13	1113.0	54/19	38	3	19	0.0862	1429	39.1	1.19
1192.5	5	1192.5	42/7	30	3	7	0.0936	1286	29.5	1.17
1192.5	7	1192.5	45/7	33	3	7	0.1085	1343	32.4	1.18
1192.5	13	1192.5	54/19	38	3	19	0.0892	1530	41.9	1.22
1272.0	5	1272.0	42/7	30	3	7	0.0967	1372	31.4	1.20
1272.0	7	1272.0	45/7	35	3	7	0.1121	1433	34.6	1.22
1272.0	13	1272.0	54/19	39	3	19	0.0921	1632	44.1	1.26
1351.5	7	1351.5	45/7	35	3	7	0.1155	1522	36.7	1.26
1351.5	13	1351.5	54/19	39	3	19	0.0949	1734	46.8	1.30
1431.0	7	1431.0	45/7	36	3	7	0.1189	1613	38.9	1.29
1431.0	13	1431.0	54/19	39	3	19	0.0977	1836	49.6	1.34
1590.0	7	1590.0	45/7	36	3	7	0.1253	1792	42.2	1.36
1590.0	13	1590.0	54/19	42	3	19	0.1030	2040	55.1	1.41
1780.0	8	1780.0	84/19	37	3	19	0.0874	2063	50.7	1.45
2156.0	8	2156.0	84/19	64	4	19	0.0961	2515	61.1	1.61

<sup>A</sup> Mass per unit length is based on Class A zinc-coated steel.

<sup>B</sup> Rated strengths were calculated in accordance with 9.1 using steel stresses at 1 % for Class A coating in accordance with Specification B 498/B 498M (1 kip = 1000 lbf = 4.448 kN).

## System (UNS)

### 2.2 Other Documents:

ANSI H35.1 American National Standard Alloy and Temper Designation Systems for Aluminum<sup>3</sup>

NBS Handbook 100—Copper Wire Tables of the National Bureau of Standards<sup>4</sup>

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 ACSR/TW covered by this specification has five types of coated core wire and one type of aluminum-clad core wire which are designated by abbreviations as follows (Explanatory Note 2):

3.1.1.1 ACSR/TW/AW—ACSR/TW using aluminum-clad steel wire (Specification B 502).

3.1.1.2 ACSR/TW/AZ—ACSR/TW using aluminum-coated (aluminized) steel wire (Specification B 341/B 341M).

3.1.1.3 ACSR/TW/GA—ACSR/TW using Class A zinc-coated steel wire (Specification B 498/B 498M).

3.1.1.4 ACSR/TW/GB—ACSR/TW using Class B zinc-coated steel wire (Specification B 498/B 498M).

3.1.1.5 ACSR/TW/GC—ACSR / TW using Class C zinc-coated steel wire (Specification B 498/B 498M).

3.1.1.6 ACSR/TW/HS—ACSR/TW using extra high-strength steel wire (Specification B 606).

3.1.1.7 ACSR/TW/MA—ACSR/TW using Class A zinc-5 % aluminum-mischmetal alloy-coated steel core wire (Specification B 802/B 802M).

<sup>3</sup> Annual Book of ASTM Standards, Vol 14.02.

<sup>3</sup> Available from American National Standards Institute, 11 West 42nd Street, New York, NY 10036.

<sup>4</sup> Annual Book of ASTM Standards, Vol 01.01.

<sup>4</sup> Available from National Technical Information Service, 5285 Port Royal Road, Springfield, VA 22161.

**TABLE 2 Construction Requirements for Shaped Wire Compact Concentric-Lay-Stranded Aluminum Conductors, Coated Steel Reinforced Sized to Have Diameter Equal to ACSR, Class AA**

Code Word <sup>a</sup>	ACSR/TW Conductor Size		Size and Stranding of ACSR with Equal Diameter		Number of Aluminum Wires	Number of Layers	Steel Core Stranding		Mass per Unit Length, <sup>kg</sup> lb/1000 ft	Rated Strength, 1000 lb <sup>⊥</sup> ⊃	Nominal Outside Diameter, in. ⊥
	kcml <sup>⊥</sup>	Type	kcml <sup>⊥</sup>	Stranding			Number of Wires	Diameter, in. ⊥			
Monongahela/TW	495.1	6	336.4	18/1	14	2	1	0.1520	441	10.2	0.68
	571.7	13	477.0	24/7	18	2	7	0.1030	735	20.6	0.85
Mohawk/TW	565.3	16	477.0	26/7	20	2	7	0.1146	776	22.9	0.86
	666.6	13	556.5	24/7	20	2	7	0.1111	856	24.0	0.91
Mystic/TW	664.8	16	556.5	26/7	20	2	7	0.1244	913	26.6	0.93
Oswego/TW	768.2	13	636.0	24/7	20	2	7	0.1195	988	27.7	0.98
Maumee/TW	762.8	16	636.0	26/7	20	2	7	0.1331	1047	30.5	0.99
Wabash/TW	768.9	13	636.0	24/7	27	3	7	0.1520	1079	31.6	0.99
	957.2	7	795.0	45/7	32	3	7	0.0973	1241	34.0	1.09
Kettle/TW	946.7	10	795.0	22/7	35	3	7	0.1154	1241	34.0	1.09
Fraser/TW	966.2	13	795.0	24/7	21	2	7	0.1338	1318	37.0	1.11
Columbia/TW	959.6	16	795.0	26/7	22	2	7	0.1493	1318	37.0	1.11
Suwannee/TW	1168.1	5	954.0	42/7	30	3	7	0.0926	1260	28.9	1.16
	1158.0	7	954.0	45/7	33	3	7	0.1078	1308	31.6	1.17
Cheyenne/TW	1158.4	13	954.0	24/7	25	2	7	0.1467	1489	39.6	1.20
Genesee/TW	1272.0	5	1033.5	42/7	30	3	7	0.0967	1372	31.4	1.20
	1257.1	7	1033.5	45/7	35	3	7	0.1115	1417	34.2	1.21
Catawba/TW	1233.6	13	1033.5	24/7	38	3	7	0.0910	1586	42.9	1.25
Nelson/TW	1372.5	5	1113.0	42/7	30	3	7	0.1004	1481	33.4	1.25
Yukon/TW	1359.7	7	1113.0	45/7	36	3	7	0.1159	1530	36.9	1.26
	1334.6	13	1113.0	24/7	39	3	7	0.0944	1713	46.3	1.29
Truckee/TW	1467.8	5	1192.5	42/7	33	3	7	0.1041	1585	36.8	1.29
	1455.3	7	1192.5	45/7	36	3	7	0.1200	1640	39.2	1.30
Mackenzie/TW	1433.6	13	1192.5	24/7	39	3	7	0.0978	1840	49.7	1.34
Thames/TW	1569.0	5	1272.0	42/7	33	3	7	0.1074	1693	38.2	1.33
St. Croix/TW	1557.4	7	1272.0	45/7	36	3	7	0.1244	1755	41.9	1.35
Miramichi/TW	1533.3	13	1272.0	24/7	39	3	7	0.1012	1968	53.2	1.38
Merrimack/TW	1657.4	5	1351.5	42/7	36	3	7	0.1280	1868	44.0	1.39
Platte/TW	1622.0	7	1351.5	45/7	39	3	7	0.1064	2107	57.5	1.42
Potomac/TW		13		54/19	39	3	19				
Rio Grande/TW		13		54/19	39	3	19				
Schuylkill/TW		13		45/7	36	3	7				
Pecos/TW		13		54/19	39	3	19				