
Kemikalije, ki se uporabljajo za pripravo pitne vode – Anionski in neionski poliakrilamidi

Chemicals used for treatment of water intended for human consumption - Anionic and non-ionic polyacrylamides

Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch - Anionische und nicht-ionische Polyacrylamide

Produits chimiques utilisés pour le traitement de l'eau destinée à la consommation humaine - Polyacrylamides anioniques et non-ioniques

<https://standards.iteh.ai/catalog/standards/sist/40fe99ff-37d9-481f-ac61-22ce00dad5fa/sist-en-1407-1999>

Ta slovenski standard je istoveten z: EN 1407:1998

ICS:

13.060.20	Pitna voda	Drinking water
71.100.80	Kemikalije za čiščenje vode	Chemicals for purification of water

SIST EN 1407:1999**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1407:1999

<https://standards.iteh.ai/catalog/standards/sist/40fe99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999>

EUROPEAN STANDARD

EN 1407

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 1998

ICS 71.100.80

Descriptors: potable water, water treatment, chemical compounds, acrylic acids, description, physical properties, chemical properties, impurities, toxic substances, tests, labelling, storage, information, warning notices

English version

Chemicals used for treatment of water intended for human consumption - Anionic and non-ionic polyacrylamides

Produits chimiques utilisés pour le traitement de l'eau destinée à la consommation humaine - Polyacrylamides anioniques et non-ioniques

Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch - Anionische und nicht-ionische Polyacrylamide

This European Standard was approved by CEN on 23 March 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1407:1999

<https://standards.iteh.ai/catalog/standards/sist/40c99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword	3
Introduction	4
1 Scope	4
2 Normative references	4
3 Description	5
3.1 Identification	5
3.2 Commercial form	7
3.3 Physical properties.....	7
3.4 Chemical properties	8
4 Purity criteria	8
4.1 Composition of commercial product	8
4.2 Impurities and main by-products	9
4.3 Toxic substances	9
5 Test methods	9
5.1 Sampling	9
5.2 Analyses	9
6 Labelling - Transportation - Storage	15
6.1 Means of delivery	15
6.2 Risk and safety labelling in accordance with the EU Directives	15
6.3 Transportation regulations and labelling	15
6.4 Marking	15
6.5 Storage	15
Annex A (informative) General information on anionic and non-ionic polyacrylamides	16
Annex B (informative) Bibliography	19

iTeh STANDARD PREVIEW (standards.itech.ai)

[SIST EN 1407:1999](https://standards.itech.ai/catalog/standards/sist/40fe99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999)

<https://standards.itech.ai/catalog/standards/sist/40fe99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999>



Foreword

This European Standard has been prepared by Technical Committee CEN/TC 164 "Water supply", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1998, and conflicting national standards shall be withdrawn at the latest by October 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1407:1999

<https://standards.iteh.ai/catalog/standards/sist/40fe99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999>

Introduction

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by this standard :

- 1) this standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA ;
- 2) it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

1 Scope

This European Standard is applicable to anionic and non-ionic polyacrylamides used for treatment of water intended for human consumption. It describes the characteristics of anionic and non-ionic polyacrylamides and specifies the requirements and the corresponding test methods for anionic and non-ionic polyacrylamides.

Annex A gives some information on origin, use and handling of anionic and non-ionic polyacrylamides.

Annex B lists the bibliography.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN ISO 3696	Water for analytical laboratory use - Specification and test methods (ISO 3696:1987)
ISO 3165	Sampling of chemical products for industrial use - Safety in sampling
ISO 6206	Chemical products for industrial use - Sampling - Vocabulary
ISO 8213	Chemical products for industrial use - Sampling techniques - Solid chemical products in the form of particles varying from powders to coarse lumps

3 Description

3.1 Identification

3.1.1 Chemical names

Copolymer of acrylamide and acrylic acid salt, or homopolymer of acrylamide.

3.1.2 Synonyms or common names

Anionic polyacrylamide or non-ionic polyacrylamide.


NOTE : The more general terms : "anionic (or non-ionic) polymer", "anionic polyelectrolyte" and "anionic (or non-ionic) flocculant" are used but can also cover other chemicals referred to in other European Standards.

3.1.3 Relative molecular mass


Typically in the range of 1 million to 20 million.

3.1.4 Empirical formulae

Non-ionic polyacrylamide :



Anionic polyacrylamide :



where :

A is a positive ion ;

x and y are variable depending on the product.


ITEH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1407:1999


<https://standards.iteh.ai/catalog/standards/sist/40fe99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999>

3.1.5 Chemical formulae

Anionic polyacrylamide :



Non-ionic polyacrylamide :



where :

A is a positive ion ;

x and y are variable depending on the product.

3.1.6 CAS Registry Numbers ¹⁾

The following is a list of CAS Registry Numbers for typical anionic or non-ionic polyacrylamides :

25085-02-3

9003-05-8

9003-04-7

SIST EN 1407:1999

<https://standards.iteh.ai/catalog/standards/sist/40fe99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999>

¹⁾ Chemical Abstracts Service Registry Number.

3.1.7 EINECS reference ²⁾

The conformity of polymers to EINECS is assessed on the basis of the monomers of which they are composed. Thus, EINECS reference numbers do not exist for polymers.

3.2 Commercial form

Anionic or non-ionic polyacrylamides as specified in this standard are available as solids containing a small amount of residual moisture.

3.3 Physical properties

3.3.1 Appearance

The product is a white or off-white solid in the form of granule, flake or powder.

3.3.2 Density

The bulk density of the product is typically in the range 0,6 g/cm³ to 0,9 g/cm³.

3.3.3 Solubility

The product is soluble in cold water. Its solubility is limited only by viscosity, with a gel being formed at concentrations of approximately 20 g/l and above.

3.3.4 Vapour pressure

Not applicable.

3.3.5 Boiling point at 100 kPa

Not applicable.

3.3.6 Melting point

The product decomposes at approximately 200 °C.

<https://standards.iteh.ai/catalog/standards/sist/40fe99ff-37f9-481f-ae61-22ce00dad5fa/sist-en-1407-1999>

3.3.7 Specific heat

Not applicable.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

²⁾ European Inventory of Existing Commercial Chemical Substances.

Page 8
EN 1407:1998

3.3.8 Viscosity dynamic

Not applicable.

3.3.9 Critical temperature

Not applicable.

3.3.10 Critical pressure

Not applicable.

3.3.11 Physical hardness

Not applicable.

3.4 Chemical properties

Anionic and non-ionic polyacrylamides are non-hazardous materials and not intrinsically reactive. However, in common with many other organic compounds, a strong exothermic reaction will occur if they are brought into contact in the dry state with a strong acid or strong oxidizing agent.

NOTE : In dilute solution there can be a reaction with, or destruction by, some of the disinfection and oxidizing agents used in water treatment.

4 Purity criteria

Limits have been given for impurities and toxic substances where these are likely to be present in significant quantities from the current production process and raw materials. If a change in the production process or raw materials leads to significant quantities of other impurities or by-products being present, this shall be notified to the user.

4.1 Composition of commercial product

The following requirement shall apply to anionic or non-ionic polyacrylamide : The anionic or non-ionic polyacrylamide shall be free of any visible extraneous matter.

NOTE : Various parameters can be checked as part of assessment of product quality (see 5.2.2).

ITC STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1407:1999

22ce00dad5fa/sist-en-1407-1999

4.2 Impurities and main by-products

The product shall contain no more than 250 mg of acrylamide monomer per kilogram of product (as derived from a reference dose of 0,4 mg/l).

Based on the raw materials and manufacturing process (see A.1), there are no significant concentration of additional reactants or by-products which are relevant to the application of these products in drinking water treatment.

4.3 Toxic substances

NOTE : For the purpose of this standard, "toxic substances" are those defined in the EU Directive 80/778/EEC of 15 July 1980 (see B.1).

Toxic substances as defined above are not relevant at a reference dose of 0,4 mg/l.

5 Test methods

5.1 Sampling

Sampling shall be in accordance with ISO 8213 and the recommendations given in ISO 3165 and ISO 6206 shall be followed.

A representative sample of the solid product, of sufficient mass, shall be obtained immediately after manufacture or from a newly opened package(s). The sample shall be clearly labelled with product name/code, batch number, type of container(s) sampled and date sampled. Reference samples shall be retained for the storage life of the product as claimed by the manufacturer/supplier.

5.2 Analyses

5.2.1 General

Unless otherwise specified, all reagents shall be of recognized analytical grade. The water used shall conform to grade 2 specified in EN ISO 3696.

iTeh STANDARD PREVIEW

5.2.2 Main product **(standards.iteh.ai)**

If additional requirements are agreed between the customer and the manufacturer/supplier, the latter shall provide the necessary test methods, if requested, so that the customer can carry out his own quality checks.

A certificate of analysis shall be provided by the manufacturer/supplier if requested.