
**Plastics piping systems for renovation
of underground non-pressure
drainage and sewerage networks —**

**Part 3:
Lining with close-fit pipes**

*Systèmes de canalisations en plastique pour la rénovation des réseaux
de branchements et de collecteurs d'assainissement enterrés sans
pression —*

Partie 3: Tubage par tuyau continu sans espace annulaire

ISO 11296-3:2018

<https://standards.iteh.ai/catalog/standards/iso/e4e46859-ac74-4655-9b12-0ac3cdf810d5/iso-11296-3-2018>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 11296-3:2018

<https://standards.iteh.ai/catalog/standards/iso/c4e46859-ac74-4655-9b12-0ac3cdf810d5/iso-11296-3-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
3.1 General	2
3.2 Techniques	2
3.3 Characteristics	2
3.4 Materials	2
3.5 Product stages	2
3.6 Service conditions	2
3.7 Joints	3
4 Symbols and abbreviated terms	3
5 Pipes at the “M” stage	3
5.1 Materials	3
5.1.1 General	3
5.1.2 Distinction between PVC-U types	3
5.1.3 Virgin material	3
5.1.4 Reprocessable material and recyclable material	3
5.2 General characteristics	4
5.2.1 Appearance	4
5.2.2 Colour	4
5.3 Material characteristics	4
5.4 Geometric characteristics	5
5.5 Mechanical characteristics	5
5.6 Physical characteristics	5
5.7 Jointing	5
5.8 Marking	6
6 Fittings at the “M” stage	6
7 Ancillary components	6
8 Fitness for purpose of the installed lining system at the “I” stage	6
8.1 Materials	6
8.2 General characteristics	6
8.3 Material characteristics	6
8.4 Geometric characteristics	6
8.5 Mechanical characteristics	8
8.6 Physical characteristics	9
8.7 Additional characteristics	9
8.8 Sampling	9
9 Installation practice	9
9.1 Preparatory work	9
9.2 Storage, handling and transport of pipes and fittings	9
9.3 Equipment	9
9.3.1 Butt fusion equipment and debanding equipment	9
9.3.2 Reduction equipment	10
9.3.3 Pipe skids/rollers	10
9.3.4 Winching and rod-pulling equipment	10
9.3.5 Pipe entry guides	10
9.3.6 Reforming equipment	10
9.3.7 Electrofusion equipment	10
9.3.8 Inspection equipment	11

9.3.9	Lifting equipment.....	11
9.4	Installation.....	11
9.5	Process-related inspection and testing.....	12
9.6	Lining termination.....	12
9.7	Reconnection to existing manholes and laterals.....	12
9.8	Documentation	12
9.9	Final inspection and testing.....	12
Annex A (normative) Factory-folded heat-reverted polyethylene (PE) pipe — Determination of memory ability		13
Bibliography		15

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 11296-3:2018](https://standards.iteh.ai/catalog/standards/iso/e4e46859-ac74-4655-9b12-0ac3cdf810d5/iso-11296-3-2018)

<https://standards.iteh.ai/catalog/standards/iso/e4e46859-ac74-4655-9b12-0ac3cdf810d5/iso-11296-3-2018>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 8, *Rehabilitation of pipeline systems*.

This second edition cancels and replaces the first edition (ISO 11296-3:2009) which has been technically revised. It also incorporates the Corrigendum ISO 11296-3:2009/Cor 1:2011.

The main changes compared to the previous edition are as follows:

- [Clauses 3, 5, 6, 8](#) and [9](#) have been technically revised;
- the previous Annex B has been deleted.

A list of all parts in the ISO 11296 series can be found on the ISO website.

Introduction

This document is a part of a system standard for plastics piping systems of various materials used for renovation of existing pipelines in a specified application area. System standards for renovation dealing with the following applications are either available or in preparation:

- ISO 11296, *Plastics piping systems for renovation of underground non-pressure drainage and sewerage networks* (this series);
- ISO 11297, *Plastics piping systems for renovation of underground drainage and sewerage networks under pressure*;
- ISO 11298, *Plastics piping systems for renovation of underground water supply networks*;
- ISO 11299, *Plastics piping systems for renovation of underground gas supply networks*.

These system standards are distinguished from system standards for conventionally installed plastics piping systems by the requirement to verify certain characteristics in the “as installed” condition, after site processing. This is in addition to verification of characteristics of plastics piping systems “as manufactured”.

Each of the system standards comprises a:

- *Part 1: General*

and all applicable renovation technique family-related parts, which for non-pressure drainage and sewerage networks include or potentially include the following:

- *Part 2: Lining with continuous pipes*
- *Part 3: Lining with close-fit pipes* (this document)
- *Part 4: Lining with cured-in-place pipes*
- *Part 5: Lining with discrete pipes*
- *Part 7: Lining with spirally-wound pipes*
- *Part 8: Lining with pipe segments*
- *Part 9: Lining with rigidly anchored plastics inner layer*
- *Part 10: Lining with sprayed polymeric materials*

The requirements for any given renovation technique family are specified in Part 1, applied in conjunction with the relevant other part. For example, both ISO 11296-1 and this document together specify the requirements relating to lining with close-fit pipes. For complementary information, see ISO 11295. Not all technique families are pertinent to every area of application and this is reflected in the part numbers included in each system standard.

A consistent structure of clause headings has been adopted for all parts to facilitate direct comparisons across renovation technique families.

[Figure 1](#) shows the common part and clause structure and the relationship between ISO 11296 and system standards for other applications.




Figure 1 — Format of the renovation system standards

Plastics piping systems for renovation of underground non-pressure drainage and sewerage networks —

Part 3: Lining with close-fit pipes

1 Scope

This document, in conjunction with ISO 11296-1, specifies requirements and test methods for close-fit lining systems used for the renovation of underground non-pressure drainage and sewerage networks.

It applies to pipes and fittings made of polyethylene (PE) or unplasticized poly(vinyl chloride) (PVC-U) as manufactured, as well to the installed lining system with its associated joints.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 2507-1, *Thermoplastics pipes and fittings — Vicat softening temperature — Part 1: General test method*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 4435, *Plastics piping systems for non-pressure underground drainage and sewerage — Unplasticized poly(vinyl chloride) (PVC-U)*

ISO 6259-1, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method*

ISO 8772, *Plastics piping systems for non-pressure underground drainage and sewerage — Polyethylene (PE)*

ISO 9852, *Unplasticized poly(vinyl chloride) (PVC-U) pipes — Dichloromethane resistance at specified temperature (DCMT) — Test method*

ISO 9967, *Thermoplastics pipes — Determination of creep ratio*

ISO 9969, *Thermoplastics pipes — Determination of ring stiffness*

ISO 11296-1:2018, *Plastics piping systems for renovation of underground non-pressure drainage and sewerage networks — Part 1: General*

ISO 12176-1, *Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 1: Butt fusion*

ISO 12176-2, *Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 1: Electrofusion*

ISO 13953, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint*

ISO 18373-1:2007, *Rigid PVC pipes — Differential scanning calorimetry (DSC) method — Part 1: Measurement of the processing temperature*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 11296-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1 General

3.1.1

close fit

situation of the outside of the installed liner relative to the inside of the existing pipeline, which may either be an interference fit or include a small annular gap resulting from shrinkage and tolerances only

3.1.2

close-fit pipe

continuous lining pipe of thermoplastic material reshaped or otherwise expanded after insertion to achieve a close fit to the existing pipeline

3.2 Techniques

No additional definitions apply.

3.3 Characteristics

3.3.1

MFR

melt mass-flow rate

rate of extrusion of a molten resin through a die of specified length and diameter under prescribed conditions of temperature, load and piston position in the cylinder of an extrusion plastometer, the rate being determined as the mass extruded over a specified time

Note 1 to entry: MFR is expressed in units of grams per 10 min.

[SOURCE: ISO 1133-1:2011, 3.1, modified - the second sentence in the NOTE has been deleted.]

3.4 Materials

3.4.1

crazing

microstructural phenomenon associated with the short-term application of tensile bending strain exceeding the material-related critical yield strain

3.5 Product stages

No additional definitions apply.

3.6 Service conditions

No additional definitions apply.