

---

---

**Plastics piping systems for renovation  
of underground drainage and  
sewerage networks under pressure —**

**Part 3:  
Lining with close-fit pipes**

*Systèmes de canalisations en plastique pour la rénovation des réseaux  
de branchements et de collecteurs d'assainissement enterrés sous  
pression —*

*Partie 3: Tubage par tuyau continu sans espace annulaire*

ISO 11297-3:2018

<https://standards.iteh.ai/catalog/standards/iso/c5616594-9272-43f6-ac2e-424d0ca57164/iso-11297-3-2018>



iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

ISO 11297-3:2018

<https://standards.iteh.ai/catalog/standards/iso/c5616594-9272-43f6-ac2e-424d0ca57164/iso-11297-3-2018>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
3.1 General.....	2
3.2 Techniques.....	3
3.3 Characteristics.....	3
3.4 Materials.....	3
3.5 Product stages.....	3
3.6 Service conditions.....	3
3.7 Joints.....	4
<b>4 Symbols and abbreviated terms</b> .....	<b>4</b>
4.1 Symbols.....	4
4.2 Abbreviated terms.....	5
<b>5 Pipes at the “M” stage</b> .....	<b>5</b>
5.1 Materials.....	5
5.1.1 Virgin material.....	5
5.1.2 Reprocessable and recyclable material.....	5
5.2 General characteristics.....	5
5.2.1 Appearance.....	5
5.2.2 Colour.....	5
5.3 Material characteristics.....	6
5.4 Geometric characteristics.....	6
5.5 Mechanical characteristics.....	6
5.6 Physical characteristics.....	6
5.7 Jointing.....	6
5.8 Marking.....	6
5.9 Regional requirements for pipes.....	7
<b>6 Fittings at the “M” stage</b> .....	<b>7</b>
6.1 Requirements.....	7
6.2 Marking.....	7
6.3 Regional requirements for fittings.....	7
<b>7 Ancillary components</b> .....	<b>7</b>
<b>8 Fitness for purpose of the installed lining system at the “I” stage</b> .....	<b>7</b>
8.1 Materials.....	7
8.2 General characteristics.....	7
8.3 Material characteristics.....	7
8.4 Geometric characteristics.....	8
8.5 Mechanical characteristics.....	8
8.6 Physical characteristics.....	9
8.7 Additional characteristics.....	9
8.8 Sampling.....	10
8.9 Regional requirements for the installed lining system.....	10
<b>9 Installation practice</b> .....	<b>10</b>
9.1 Preparatory work.....	10
9.2 Storage, handling and transport of pipes and fittings.....	10
9.3 Equipment.....	10
9.3.1 Butt fusion and debanding equipment.....	10
9.3.2 Reduction equipment.....	11
9.3.3 Pipe skids/rollers.....	11

9.3.4	Winching and rod-pulling equipment.....	11
9.3.5	Pipe entry guides.....	11
9.3.6	Reforming equipment.....	11
9.3.7	Electrofusion equipment.....	12
9.3.8	Inspection equipment.....	12
9.3.9	Lifting equipment.....	12
9.4	Installation.....	12
9.5	Process-related inspection and testing.....	13
9.6	Lining termination.....	13
9.7	Reconnection to existing manholes and laterals.....	13
9.8	Final inspection and testing.....	13
9.9	Documentation .....	13
<b>Annex A (normative) Factory-folded heat-reverted polyethylene (PE) pipe — Determination of memory ability.....</b>		<b>14</b>
<b>Bibliography .....</b>		<b>16</b>

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

ISO 11297-3:2018

<https://standards.iteh.ai/catalog/standards/iso/c5616594-9272-43f6-ac2e-424d0ca57164/iso-11297-3-2018>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 8, *Rehabilitation of pipeline systems*.

This second edition cancels and replaces the first edition (ISO 11297-3:2013), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [Figure 1](#) and [Clauses 1, 5.2.2, 5.5, 8.4, 9.3.4 and 9.4](#) have been technically revised;
- New sub-clauses [5.9, 6.3 and 8.9](#) specifying regional requirements for pipes, fittings and the installed system respectively, have also been added in accordance with the Vienna Agreement, to allow reference to European standards in countries where these are mandated by law in place of ISO standards of identical scope.

A list of all parts in the ISO 11297 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

This International Standard is a part of a system standard for plastics piping systems of various materials used for renovation of existing pipelines in a specified application area. System standards for renovation dealing with the following applications are either available or in preparation:

- ISO 11296, *Plastics piping systems for renovation of underground non-pressure drainage and sewerage networks*;
- ISO 11297, *Plastics piping systems for renovation of underground drainage and sewerage networks under pressure* (this document);
- ISO 11298, *Plastics piping systems for renovation of underground water supply networks*;
- ISO 11299, *Plastics piping systems for renovation of underground gas supply networks*.

These system standards are distinguished from system standards for conventionally installed plastics piping systems by the requirement to verify certain characteristics in the “as installed” condition, after site processing. This is in addition to verification of characteristics of plastics piping systems “as manufactured”.

Each of the System Standards comprises a:

- *Part 1: General*

and all applicable renovation technique family-related parts, which for non- drainage and sewerage networks under pressure include or potentially include the following:

- *Part 2: Lining with continuous pipes*
- *Part 3: Lining with close-fit pipes* (this document)
- *Part 4: Lining with cured-in-place pipes*
- *Part 5: Lining with discrete pipes*
- *Part 6: Lining with adhesive-backed hoses*

The requirements for any given renovation technique family are specified in Part 1, applied in conjunction with the relevant other part. For example, both ISO 11297-1 and this document together specify the requirements relating to lining with close-fit pipes. For complementary information, see ISO 11295. Not all technique families are pertinent to every area of application and this is reflected in the part numbers included in each System Standard.

A consistent structure of clause headings has been adopted for all parts to facilitate direct comparisons across renovation technique families.

[Figure 1](#) shows the common part and clause structure and the relationship between ISO 11297 and system standards for other applications.




Figure 1 — Format of the renovation system standards





# Plastics piping systems for renovation of underground drainage and sewerage networks under pressure —

## Part 3: Lining with close-fit pipes

### 1 Scope

This document, in conjunction with ISO 11297-1, specifies requirements and test methods for close-fit lining systems intended to be used for the renovation of underground drainage and sewerage networks under pressure.

It applies to pipes and fittings, as manufactured, as well as to the installed lining system. It is applicable to polyethylene (PE) pipes of either solid wall single layer or co-extruded layer construction, which is reduced in the factory or on site to provide a close-fitting independent or interactive pressure pipe liner, as well as associated fittings and joints for the construction of the lining system. It is not applicable to PE coated pipes having a peelable, contiguous, thermoplastic additional layer on the outside of the pipe.

It is applicable to PE pipes, fittings and assemblies intended to be used at an operating temperature of 20 °C as the reference temperature.

NOTE For applications operating at constant temperatures greater than 20 °C and up to 40 °C, see ISO 4427-1:2007, Annex A.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3, *Preferred numbers — Series of preferred numbers*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 4427-1:2007, *Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 1: General*

ISO 4427-2:2007, *Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 2: Pipes*

ISO 4427-3, *Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 3: Fittings*

ISO 4427-5:2007, *Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 5: Fitness for purpose of the system*

ISO 8772, *Plastics piping systems for non-pressure underground drainage and sewerage — Polyethylene (PE)*

ISO 9967, *Thermoplastics pipes — Determination of creep ratio*

ISO 11297-1:2018, *Plastics piping systems for renovation of underground drainage and sewerage networks under pressure — Part 1: General*

ISO 12176-1, *Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 1: Butt fusion*

ISO 12176-2, *Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 2: Electrofusion*

EN 12201-1, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 1: General*

EN 12201-2:2011, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 2: Pipes*

EN 12201-3, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 3: Fittings*

EN 12201-4, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 4: Valves for water supply systems*

EN 12201-5, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 5: Fitness for purpose of the system*

EN 12666-1, *Plastics piping systems for non-pressure underground drainage and sewerage — Polyethylene (PE) — Part 1: Specifications for pipes, fittings and the system*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 11297-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

#### 3.1 General

##### 3.1.1

##### **compound formulation**

clearly defined homogenous mixture of base polymer with additives, e.g. antioxidants, pigments, stabilizers and others, at a dosage level necessary for the processing and intended use of the final product

##### 3.1.2

##### **solid wall single layered pipe**

pipe with smooth internal and external surface, extruded from the same *compound formulation* (3.1.1) throughout the wall

##### 3.1.3

##### **pipe with co-extruded layers**

pipe with smooth internal and external surface, having co-extruded layers on either or both the outside and inside of the pipe, where all layers have the same MRS rating

##### 3.1.4

##### **close fit**

situation of the outside of the installed liner relative to the inside of the existing pipeline, which may either be an interference fit or include a small annular gap resulting from shrinkage and tolerances only

##### 3.1.5

##### **close-fit pipe**

continuous lining pipe of thermoplastic material reshaped or otherwise expanded after insertion to achieve a close fit to the existing pipeline