INTERNATIONAL STANDARD

ISO 11298-3

Second edition 2018-09

Plastics piping systems for renovation of underground water supply networks —

Part 3: Lining with close-fit pipes

Systèmes de canalisations en plastique pour la rénovation des réseaux enterrés d'alimentation en eau —

Partie 3: Tubage par tuyau continu sans espace annulaire

Document Preview

ISO 11298-3:2018

https://standards.iteh.ai/catalog/standards/iso/a641f4cf-6f09-4602-85ca-953188e78055/iso-11298-3-2018



iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 11298-3:2018

https://standards.iteh.ai/catalog/standards/iso/a641f4cf-6f09-4602-85ca-953188e78055/iso-11298-3-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents			
Fore	eword		v
Intr	oductio	on	vi
1	Scop	oe	1
2	Nori	native references	1
3	Terms and definitions		
3	3.1	General	
	3.2	Techniques	
	3.3	Characteristics	
	3.4	Materials	3
	3.5	Product stages	
	3.6	Service conditions	
	3.7	Joints	4
4	Sym	bols and abbreviated terms	4
	4.1	Symbols	
	4.2	Abbreviated terms	5
5	Pine	s at the "M" stage	5
	5.1	Materials	
		5.1.1 Virgin material	
		5.1.2 Reprocessable and recyclable material	5
	5.2	General characteristics	5
		5.2.1 Appearance	
		5.2.2 Colour	
	5.3	Material characteristics	
	5.4	Geometric characteristics MANIE MANI	
	5.5	Mechanical characteristics	
	5.6	Physical characteristics	
	5.7	Jointing	
	5.8 ₅ 5.9	Regional requirements for pipes	
6		ngs at the "M" stage	
	6.1	Requirements	
	6.2	Marking	
	6.3	Regional requirements for fittings	
7	Anci	llary components	7
8	Fitne	ess for purpose of the installed lining system at the "I" stage	7
	8.1	Materials	
	8.2	General characteristics	
	8.3	Material characteristics	
	8.4	Geometric characteristics	
	8.5	Mechanical characteristics	
	8.6	Physical characteristics	
	8.7 8.8	Additional characteristics	
	o.o 8.9	Sampling Regional requirements for the installed lining system	
0			
9		allation practice	
	9.1	Preparatory work	
	9.2 9.3	Storage, handling and transport of pipes and fittings	
	7.3	Equipment	
		9.3.2 Reduction equipment	
		9.3.3 Pipe skids/rollers	
		·	🚣 🚣

iii

ISO 11298-3:2018(E)

Bibliography			
Ann		ormative) Factory-folded heat-reverted polyethylene (PE) pipe — ermination of memory ability	14
	9.9	Documentation	13
	9.8	Final inspection and testing	
	9.7	Reconnection to the existing pipeline system	13
	9.6	Lining termination Reconnection to the existing pipeline system	13
	9.5	Process-related inspection and testing	12
	9.4	Installation	12
		9.3.9 Lifting equipment	12
		9.3.8 Inspection equipment	11
		9.3.7 Electrofusion equipment 9.3.8 Inspection equipment	11
		9.3.6 Reforming equipment	11
		9.3.5 Pipe entry guides	11
		9.3.4 Winching and rod-pulling equipment	11

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 11298-3:2018

https://standards.iteh.ai/catalog/standards/iso/a641f4cf-6f09-4602-85ca-953188e78055/iso-11298-3-2018

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, SC 8, *Rehabilitation of pipeline systems*.

This second edition cancels and replaces the first edition (ISO 11298-3:2010), which has been technically revised. ISO 11298-3:2018

The main changes compared to the previous edition are as follows: \$\frac{3188e78055/80-11298-3-2018}{2}\$

- <u>Figure 1</u> and <u>Clauses 1</u>, <u>3.4</u>, <u>3.6</u>, <u>5.8</u>, <u>8.4</u>, <u>8.5</u> and <u>9.3</u> to <u>9.8</u> have been technically revised.
- New sub-clauses 5.9, 6.3 and 8.9 specifying regional requirements for pipes, fittings and the installed lining system respectively, have also been added in accordance with the Vienna Agreement, to allow reference to European standards in countries where these are mandated by law in place of ISO standards of identical scope.

A list of all parts in the ISO 11298 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document is a part of a System Standard for plastics piping systems of various materials used for the renovation of existing pipelines in a specified application area. System Standards for renovation deal with the following applications:

- ISO 11296, Plastics piping systems for renovation of underground non-pressure drainage and sewerage networks;
- ISO 11297, Plastics piping systems for renovation of underground drainage and sewerage networks under pressure;
- ISO 11298, *Plastics piping systems for renovation of underground water supply networks* (this document):
- ISO 11299, Plastics piping systems for renovation of underground gas supply networks.

These System Standards are distinguished from those for conventionally installed plastics piping systems by the requirement to verify certain characteristics in the "as-installed" condition, after site processing. This is in addition to specifying requirements for plastics piping systems components "as manufactured".

Each of the System Standards comprises a:

— Part 1: General

and all applicable renovation technique family-related parts, which for water supply networks include or potentially include the following:

- Part 2: Lining with continuous pipes
- Part 3: Lining with close-fit pipes (this document)
- Part 4: Lining with cured-in-place pipes
- Part 5: Lining with discrete pipes dards/iso/a641f4cf-6f09-4602-85ca-953188e78055/iso-11298-3-2018
- Part 6: Lining with adhesive-backed hoses
- Part 10: Lining with sprayed polymeric materials
- Part 11: Lining with inserted hoses

The requirements for any given renovation technique family are specified in Part 1, applied in conjunction with the relevant other part. For example, ISO 11298-1 and this document together specify the requirements relating to lining with close-fit pipes. For complementary information, see ISO 11295. Not all technique families are pertinent to every area of application and this is reflected in the part numbers included in each System Standard.

A consistent structure of clause headings has been adopted for all parts of ISO 11298, in order to facilitate direct comparisons across renovation technique families.

<u>Figure 1</u> shows the common part and clause structure and the relationship between ISO 11298 and the System Standards for other application areas.




Figure 1 — Format of the renovation system standards

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 11208-3:2018

https://standards.iteh.ai/catalog/standards/iso/a641f4cf-6f09-4602-85ca-953188e78055/iso-11298-3-2018

Plastics piping systems for renovation of underground water supply networks —

Part 3:

Lining with close-fit pipes

1 Scope

This document, in conjunction with ISO 11298-1, specifies requirements and test methods for close-fit lining systems intended to be used for the renovation of water supply networks, which transport water intended for human consumption, including raw water intake pipelines.

It applies to pipes and fittings, as manufactured, as well as to the installed lining system. It is applicable to polyethylene (PE) pipes of either solid wall single layer or co-extruded layer construction, which is reduced in the factory or on site to provide a close-fitting independent or interactive pressure pipe liner, as well as associated fittings and joints for the construction of the lining system. It is not applicable to PE coated pipes having a peelable, contiguous, thermoplastic additional layer on the outside of the pipe.

It is applicable to PE pipes, fittings and assemblies intended to be used at an operating temperature of 20 °C as the reference temperature.

NOTE For applications operating at constant temperatures greater than 20 °C and up to 40 °C, see ISO 4427-1:2007, Annex A.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3126, Plastics piping systems — Plastics components — Determination of dimensions

ISO 4427-1:2007, Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 1: General

ISO 4427-2:2007, Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 2: Pipes

ISO 4427-3, Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 3: Fittings

ISO 4427-5:2007, Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 5: Fitness for purpose of the system

ISO 11298-1:2018, Plastics piping systems for renovation of underground water supply networks — Part 1: General

ISO 12176-1, Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 1: Butt fusion

ISO 12176-2, Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems — Part 2: Electrofusion

ISO 11298-3:2018(E)

EN 12201-1, Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 1: General

EN 12201-2:2011, Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 2: Pipes

EN 12201-3, Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 3: Fittings

EN 12201-4, Plastics piping systems for water supply — Polyethylene (PE) — Part 4: Valves

EN 12201-5, Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 5: Fitness for purpose of the system

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 11298-1:2018 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at https://www.iso.org/obp

3.1 General

iTeh Standards

3.1.1

compound formulation

clearly defined homogenous mixture of base polymer with additives, e.g. antioxidants, pigments, stabilizers and others, at a dosage level necessary for the processing and intended use of the final product

3.1.2

solid wall single layered pipe

pipe with smooth internal and external surface, extruded from the same *compound formulation* (3.1.1)

3.1.3

pipe with co-extruded layers

pipe with smooth internal and external surface, having co-extruded layers on either or both the outside and inside of the pipe, where all layers have the same MRS rating

3.1.4

close fit

situation of the outside of the installed liner relative to the inside of the existing pipeline, which can either be an interference fit or include a small annular gap resulting from shrinkage and tolerances only

3.1.5

close-fit pipe

continuous lining pipe of thermoplastic material reshaped or otherwise expanded after insertion to achieve a close fit to the existing pipeline

3.2 Techniques

No additional definitions apply.