
**Anodizing of aluminium and its
alloys — Accelerated test of light
fastness of coloured anodic oxidation
coatings using artificial light**

*Anodisation de l'aluminium et de ses alliages — Essai accéléré de
solidité à la lumière artificielle des couches d'oxydation anodique
colorées*

ITeH Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 2135:2017](https://standards.iteh.ai/catalog/standards/iso/3b1a17e0-877e-4b66-a1e5-30bd2fae2fa/iso-2135-2017)

<https://standards.iteh.ai/catalog/standards/iso/3b1a17e0-877e-4b66-a1e5-30bd2fae2fa/iso-2135-2017>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 2135:2017](https://standards.iteh.ai/catalog/standards/iso/3b1a17e0-877e-4b66-a1e5-30bd2fae12fa/iso-2135-2017)

<https://standards.iteh.ai/catalog/standards/iso/3b1a17e0-877e-4b66-a1e5-30bd2fae12fa/iso-2135-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
6 Test specimen	2
6.1 Sampling	2
6.2 Size	2
6.3 Treatment before testing	2
7 Procedure	2
7.1 Preparation of test specimen	2
7.2 Exposure conditions	2
7.3 Period of exposure	3
8 Expression of results	3
8.1 General	3
8.2 Visual assessment	3
8.3 Instrumental assessment	4
9 Test report	4
Annex A (normative) Various light sources	5
Bibliography	6

[ISO 2135:2017](https://standards.iteh.ai/catalog/standards/iso/3b1a17e0-877e-4b66-a1e5-30bd2fae2fa/iso-2135-2017)

<https://standards.iteh.ai/catalog/standards/iso/3b1a17e0-877e-4b66-a1e5-30bd2fae2fa/iso-2135-2017>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 2, *Organic and anodic oxidation coatings on aluminium*.

This fourth edition cancels and replaces the third edition (ISO 2135:2010), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the information on the test specimen has been added;
- the black panel temperature has been added;
- the instrumental assessment for colour change and gloss retention has been added;
- the specification of various light sources has been added as a new [Annex A](#).

Anodizing of aluminium and its alloys — Accelerated test of light fastness of coloured anodic oxidation coatings using artificial light

1 Scope

This document specifies an accelerated test method for assessing the fastness, using artificial light, of coloured anodic oxidation coatings on aluminium and its alloys.

For evaluating light fastness on exterior exposure, only outdoor exposure under conditions comparable with actual service is completely satisfactory.

Accelerated testing is suitable as a quality-control test of coloured anodic oxidation coatings whose light fastness number has already been established by means of outdoor exposure testing.

The method is applicable to coloured anodic oxidation coatings on aluminium and its alloys produced by any means and for any purpose.

However, the method is not suitable for the measurement of coloured coatings with a light fastness number already established by means of outdoor exposure testing and of less than 6.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to glass-filtered solar radiation, natural weathering or laboratory radiation sources* <https://standards.iteh.ai/>

ISO 7583, *Anodizing of aluminium and its alloys — Terms and definitions*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 7583 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

Exposure of coloured anodic oxidation coatings to artificial light, regular observations of any colour change by comparison with the grey scale in accordance with ISO 105-A02 and instrumental assessment.

The apparatus and light source are first calibrated by exposing parts of coloured cloth samples having a light fastness number of 6 on the European blue scale (in accordance with 8.2.1, NOTE, 8.2.2 and ISO 105-B01). The time of exposure is determined for these samples to show a colour change corresponding to grade 3 of the grey scale (about 25 % loss of colour). This length of time is defined as the exposure cycle for the apparatus (see 8.2.2, NOTE).

Coloured anodized test specimens of unknown light fastness are then exposed under the same conditions as the standard cloth samples until they also show a colour change corresponding to grade 3 of the grey scale. The number of exposure cycles required to produce this colour deterioration is used to assign the light fastness numbers of the specimens tested (see [8.2](#)).

5 Apparatus

For tests in artificial light, several types of apparatus fulfil the conditions stipulated in this document (see also [7.2](#)).

Suitable light sources shall be provided by a xenon-arc lamp, open-frame carbon-arc lamp or enclosed carbon-arc lamp (the specifications of which shall be in accordance with [Annex A](#)).

6 Test specimen

6.1 Sampling

The test specimen shall be taken from a significant flat surface of the product and shall not be taken from part of the edge because of possible distortion and/or non-uniformity.

Where it is impossible to test the product itself, a test specimen may be used. However, in this case, the test specimen used shall be one which is representative of the product and it shall be made from the same material and prepared under the same conditions of finishing as those used for the preparation of the product.

The aluminium alloy, the manufacturing conditions (kind and temper of the material) and the surface condition before treatment shall be the same as those of the product.

Pretreatment, anodizing, colouring and sealing shall be performed in the same baths and under the same conditions as the treatment of the product.

6.2 Size

The standard size of the test specimen should be about 150 mm × 70 mm. Other sizes may be used based on agreement between the interested parties.

6.3 Treatment before testing

The test specimen shall be clean, free from dirt, stains and other foreign matter. Any deposits or stains shall be removed with a clean, soft cloth or similar material which is wetted by water or an appropriate organic solvent such as ethanol. Organic solvent which can corrode the test specimens or generate protective films on the test specimens shall not be used.

7 Procedure

7.1 Preparation of test specimen

In order to detect colour changes, partly cover the exposed surface of the test specimen by means of an opaque mask.

7.2 Exposure conditions

Expose the test specimens in such a way that they are equidistant from the light source, around which they revolve slowly in order to ensure an identical distribution of light on each test specimen. If a flat bed type apparatus is used, this can be done by relocating test specimens.