



**Designation: ~~D226-06~~ Designation: D 226/D 226M – 09**

## Standard Specification for Asphalt-Saturated Organic Felt Used in Roofing and Waterproofing<sup>1</sup>

This standard is issued under the fixed designation D 226/D 226M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers asphalt-saturated organic felts, with or without perforations, intended to be used with asphalts conforming to the requirements of Specification D 312 in the construction of built-up roofs, and with asphalts conforming to the requirements of Specification D 449 in the construction of water proofing systems.

1.2 ~~The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only. The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.~~

1.3 The following safety hazards caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

D 70 Test Method for Density of Semi-Solid Bituminous Materials (Pycnometer Method)

D 146 Test Methods for Sampling and Testing Bitumen-Saturated Felts and Woven Fabrics for Roofing and Waterproofing

D 312 Specification for Asphalt Used in Roofing

D 449 Specification for Asphalt Used in Dampproofing and Waterproofing ~~D 727 Test Method for Kerosine Number of Roofing and Flooring Felt by the Vacuum Method~~

D 1079 ~~Terminology Relating to Roofing and Waterproofing~~ Terminology Relating to Roofing and Waterproofing

D 6136 Test Method for Kerosine Number of Unsaturated (Dry) Felt by Vacuum Method

### 3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology D 1079.

### 4. Classification

4.1 Asphalt-saturated felts covered by this specification are of two types:

4.1.1 *Type I*—Commonly called No. 15 asphalt felt.

4.1.2 *Type II*—Commonly called No. 30 asphalt felt.

### 5. Materials and Manufacture

5.1 In the process of manufacture a single thickness of dry felt shall be saturated with an asphaltic saturant.

5.2 The felt shall be produced principally from organic fibers. The surface of the felt shall be uniform and relatively smooth. Upon splitting or tearing on the bias, the felt shall appear reasonably free of lumps or particles of foreign substances.

### 6. Physical Requirements

6.1 The material shall conform to the physical requirements prescribed in Table 1 and the dimensions and masses prescribed in Table 2.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.04 on Felts and Fabrics.

Current edition approved July 15, 2006; 1, 2009. Published July 2006; 2009. Originally approved in 1925. Last previous edition approved in 2005; 2006 as D 226 – 056.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.