



Designation: ~~D3381-05~~ Designation: D 3381 – 09

Standard Specification for Viscosity-Graded Asphalt Cement for Use in Pavement Construction¹

This standard is issued under the fixed designation D 3381; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers asphalt cements graded by viscosity at 140°F (60°C) for use in pavement construction. Three sets of limits are offered in this specification. The purchaser shall specify the applicable table of limits. In the event the purchaser does not specify limits, Table 1 shall apply. For asphalt cements graded by penetration at 77°F (25°C) (see Specification D 946). If needed, volume corrections for asphalt cements should be made according to Practice D 4311.

2. Referenced Documents

2.1 *ASTM Standards:*²

D 5 Test Method for Penetration of Bituminous Materials

D 92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester

D 95 Test Method for Water in Petroleum Products and Bituminous Materials by Distillation

D 113 Test Method for Ductility of Bituminous Materials

D 140 Practice for Sampling Bituminous Materials

D 946 Specification for Penetration-Graded Asphalt Cement for Use in Pavement Construction

D 1754 Test Method for Effects of Heat and Air on Asphaltic Materials (Thin-Film Oven Test)

D 2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene

D 2170 Test Method for Kinematic Viscosity of Asphalts (Bitumens)

D 2171 Test Method for Viscosity of Asphalts by Vacuum Capillary Viscometer

D 2872 Test Method for Effect of Heat and Air on a Moving Film of Asphalt (Rolling Thin-Film Oven Test)

D 4311 Practice for Determining Asphalt Volume Correction to a Base Temperature

3. Manufacture

3.1 The asphalt cement shall be prepared from crude petroleum by suitable methods.

4. Physical Requirements

4.1 The asphalt cement shall be homogeneous, free from water, and shall not foam when heated to 347°F (175°C).

4.2 The asphalt cements shall conform to the requirements given in Table 1, Table 2, or Table 3, as specified by the purchaser.

5. Methods of Sampling and Testing

5.1 Sample and test asphalt cements in accordance with the following methods:

5.1.1 *Sampling*—Practice D 140.

5.1.2 *Water*—Test Method D 95.

5.1.3 *Viscosity at 140°F (60°C)*—Test Method D 2171.

5.1.4 *Viscosity at 275°F (135°C)*—Test Method D 2170.

5.1.5 *Penetration*—Test Method D 5.

5.1.6 *Flash Point, Cleveland Open Cup*—Test Method D 92 (see Table 1 and Table 2).

5.1.7 *Solubility in Trichloroethylene*—Test Method D 2042.

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.40 on Asphalt Specifications.

Current edition approved Dec. 1, 2005-2009. Published December 2005-2009. Originally approved in 1975. Last previous edition approved in 1999-2005 as D3381-92(1999)-D 3381 – 05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.