



SLOVENSKI STANDARD
oSIST prEN ISO 17225-2:2019
01-april-2020

Trdna biogoriva - Specifikacije goriv in razredi - 2. del: Razvrstitev lesnih peletov (ISO/DIS 17225-2:2020)

Solid biofuels - Fuel specifications and classes - Part 2: Graded wood pellets (ISO/DIS 17225-2:2020)

Biogene Festbrennstoffe - Brennstoffspezifikationen und -klassen - Teil 2: Klassifizierung von Holzpellets (ISO/DIS 17225-2:2020)

Biocombustibles solides - Classes et spécifications des combustibles - Partie 2: Classes de granulés de bois (ISO/DIS 17225-2:2020)

ITeh STANDARD PREVIEW
(standards.iteh.ai)
kSIST FprEN ISO 17225-2:2020
<https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-4d1b06e726f7ksist-fprEN ISO 17225-2:2020>

Ta slovenski standard je istoveten z: prEN ISO 17225-2

ICS:

75.160.40 Biogoriva Biofuels

oSIST prEN ISO 17225-2:2019 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[kSIST FprEN ISO 17225-2:2020](https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 17225-2

ISO/TC 238

Secretariat: SIS

Voting begins on:
2020-02-13Voting terminates on:
2020-05-07

Solid biofuels — Fuel specifications and classes —

Part 2: Graded wood pellets

*Biocombustibles solides — Classes et spécifications des combustibles —
Partie 2: Classes de granulés de bois*

ICS: 27.190; 75.160.40

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 17225-2:2020](https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020)<https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 17225-2:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 17225-2:2020](https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols and abbreviated terms	3
5 Specification of graded wood pellets	3
Bibliography	9

iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 17225-2:2020](https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020>

ISO/DIS 17225-2:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 238, Solid biofuels.

This second edition cancels and replaces the first edition (ISO 17225-2:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

- ash melting behaviour as normative and threshold values for DT temperature added for [Table 1](#)
- maximum value for bulk density added for [Table 1](#)
- particle density and fractioned pellets added as informative

A list of all parts in the ISO 17225 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The objective of the ISO 17225 series is to provide unambiguous and clear classification principles for solid biofuels; to serve as a tool to enable efficient trading of solid biofuels; to enable good understanding between seller and buyer as well as a tool for communication with equipment manufacturers. It also facilitates authority permission procedures and reporting.

This part of ISO 17225 supports the use of graded wood pellets for residential, small commercial and public buildings as well as industrial energy generation applications, which require classified pellet quality.

The residential, small and commercial and public building applications require higher quality fuel for the following reasons:

- Small-scale equipment does not usually have advanced controls and flue gas cleaning.
- Appliances are not generally managed by professional heating engineers.
- Appliances are often located in residential and populated districts.

NOTE 1 Pellets produced according to this part of ISO 17225 may be used in pellet stoves, which are tested according to European Standard EN 14785 [1], pellet burners tested according to EN 15270 [2] and pellet boilers or integrated-pellet burner systems tested according to EN 303-5 [3].

NOTE 2 For individual contracts, ISO 17225-1 can be used.

Although these product standards may be obtained separately, they require a general understanding of the standards based on and supporting ISO 17225-1. It is recommended to obtain and use ISO 17225-1 in conjunction with these standards.

[ksIST FprEN ISO 17225-2:2020](https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020)
<https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[kSIST FprEN ISO 17225-2:2020](https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/6d37d1d8-97e8-4864-a222-c4dbbc6c726f/ksist-fpren-iso-17225-2-2020>

Solid biofuels — Fuel specifications and classes —

Part 2: Graded wood pellets

1 Scope

This part of ISO 17225 determines the fuel quality classes and specifications of graded wood pellets for non-industrial and industrial use. This part of ISO 17225 covers only wood pellets produced from the following raw materials (see ISO 17225-1, Table 1):

- 1.1 Forest, plantation and other virgin wood;
- 1.2 By-products and residues from wood processing industry;
- 1.3.1 Chemically untreated used wood.

Thermally treated biomass pellets (e.g. torrefied pellets) are not included in the scope of this part of ISO 17225. Torrefaction is a mild pre-treatment of biomass at a temperature between 200 °C to 300 °C.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 14780, *Solid biofuels — Sample preparation*

ISO 16559, *Solid biofuels — Terminology, definitions and descriptions*

ISO 16948, *Solid biofuels — Determination of total content of carbon, hydrogen and nitrogen*

ISO 16968, *Solid biofuels — Determination of minor elements*

ISO 16993, *Solid biofuels — Conversion of analytical results from one basis to another*

ISO 16994, *Solid biofuels — Determination of total content of sulfur and chlorine*

ISO 17225-1, *Solid biofuels — Fuel specifications and classes — Part 1: General requirements*

ISO 17827-1, *Solid biofuels — Determination of particle size distribution for uncompressed fuels — Part 1: Oscillating screen method using sieves with apertures of 3,15 mm and above*

ISO 17828, *Solid biofuels — Determination of bulk density*

ISO 17829, *Solid Biofuels — Determination of length and diameter of pellets*

ISO 17830, *Solid biofuels — Particle size distribution of disintegrated pellets*

ISO 17831-1, *Solid biofuels — Determination of mechanical durability of pellets and briquettes — Part 1: Pellets*

ISO 18122, *Solid biofuels — Determination of ash content*

ISO 18125, *Solid biofuels — Determination of calorific value*

ISO/DIS 17225-2:2020(E)

ISO 18134-1, *Solid biofuels — Determination of moisture content — Oven dry method — Part 1: Total moisture — Reference method*

ISO 18134-2, *Solid biofuels — Determination of moisture content — Oven dry method — Part 2: Total moisture — Simplified method*

ISO 18135, *Solid Biofuels — Sampling*

ISO 18846-1, *Solid biofuels — Determination of fines content — Part 1: Reference method*

ISO 18846-2, *Solid biofuels — Determination of fines content — Part 2: Simplified method*

ISO 18847, *Solid biofuels — Determination of particle density of pellets and briquettes*

ISO 21404, *Solid biofuels — Determination of ash melting behaviour*

ISO 21945, *Solid biofuels — Simplified sampling method for small scale applications*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16559 and the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

wood pellet

densified biofuel made from woody biomass with or without additives usually with a cylindrical form, random length typically 5 to 40 mm and diameter up to 25 mm and broken ends

Note 1 to entry: The raw material for wood pellets is woody biomass in accordance with Table 1 of ISO 17225-1. Pellets are usually manufactured in a die, with total moisture content usually less than 10 % of their mass on wet basis.

Note 2 to entry: The woody biomass used as feedstock for pellet making is milled to size in accordance with customer specification. Determination of the particle size distribution of the constituents of pellets is done by ISO 17830.

3.2

additive

material which has been intentionally introduced into the fuel feed stock to improve quality of fuel (e.g. combustion properties), to reduce emissions or to make production more efficient

Note 1 to entry: Trace amounts of e.g. grease or other lubricants that are introduced into the fuel processing stream as part of normal mill operations are not considered as additives.

3.3

chemical treatment

any treatment with chemicals other than air, water or heat

EXAMPLE Glue and paint.

Note 1 to entry: Examples of chemical treatment are listed in ISO 17225-1.