

INTERNATIONAL STANDARD

ISO
2004

Sixth edition
2017-11

Natural rubber latex concentrate — Centrifuged or creamed, ammonia- preserved types — Specifications

*Latex concentré de caoutchouc naturel — Types centrifugés ou
crémés, préservés à l'ammoniaque — Spécifications*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 2004:2017](#)

<https://standards.iteh.ai/catalog/standards/iso/9bc01ade-095a-4aae-9c25-b002a2856e7a/iso-2004-2017>



Reference number
ISO 2004:2017(E)

© ISO 2017

iTeh Standards

(<https://standards.iteh.ai>)

Document Preview

[ISO 2004:2017](#)

<https://standards.iteh.ai/catalog/standards/iso/9bc01ade-095a-4aae-9c25-b002a2856e7a/iso-2004-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
5 Sampling	3

iTeh Standards

(<https://standards.iteh.ai>)

Document Preview

[ISO 2004:2017](#)

<https://standards.iteh.ai/catalog/standards/iso/9bc01ade-095a-4aae-9c25-b002a2856e7a/iso-2004-2017>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This sixth edition cancels and replaces the fifth edition (ISO 2004:2010), which has been technically revised.

[ISO 2004:2017](http://www.iso.org/iso/foreword.html)

The main changes compared to the previous edition are as follows:

- the dry rubber content in [Table 1](#) has been corrected from 60 % to 60,0 %, for type HA, LA and XA natural rubber latex concentrate;
- the coagulum content in [Table 1](#) has been reduced from 0,03 % to 0,02 %;
- the sludge content in [Table 1](#) has been reduced from 0,10 % to 0,06 %.