
**Fibre ropes for offshore
stationkeeping —**

**Part 2:
Polyester**

*Cordages en fibres pour le maintien en position des structures
marines —*

Partie 2: Polyester

ITeH Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 18692-2:2019](https://standards.iteh.ai/catalog/standards/iso/0afb27e8-e52e-4977-9e8d-9f5d72947d4a/iso-18692-2-2019)

<https://standards.iteh.ai/catalog/standards/iso/0afb27e8-e52e-4977-9e8d-9f5d72947d4a/iso-18692-2-2019>



iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO 18692-2:2019](https://standards.itih.ai/catalog/standards/iso/0afb27e8-e52e-4977-9e8d-9f5d72947d4a/iso-18692-2-2019)

<https://standards.itih.ai/catalog/standards/iso/0afb27e8-e52e-4977-9e8d-9f5d72947d4a/iso-18692-2-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Materials	1
5 Requirements — rope properties	1
5.1 Minimum breaking strength.....	1
5.2 Minimum core tenacity.....	2
5.3 Dynamic stiffness at end of bedding-in.....	2
5.4 Torque properties.....	2
5.5 Cyclic loading performance.....	2
5.6 Particle ingress protection.....	2
6 Requirements — Rope layout and construction	2
7 Rope testing	3
7.1 Type test.....	3
7.1.1 General.....	3
7.1.2 Sampling.....	3
7.1.3 Breaking strength, core tenacity and stiffness tests.....	3
7.1.4 Cyclic loading endurance test.....	3
7.1.5 Linear density test.....	3
7.1.6 Protective cover thickness.....	3
7.2 Testing of current production.....	3
8 Report	3
9 Certification	4
10 Marking, labelling and packaging	4
Annex A (normative) Fibre qualification and testing	5
Annex B (informative) Additional information and guidance	7
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

This first edition of ISO 18692-2, together with ISO 18692-1, cancels and replaces the first edition of ISO 18692:2007, which has been technically revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

A list of all parts in the ISO 18692 series can be found on the ISO website.

Fibre ropes for offshore stationkeeping —

Part 2: Polyester

1 Scope

This document specifies the main characteristics and test methods of new polyester fibre ropes used for offshore stationkeeping.

NOTE Additional information and guidance can be found in [Annex B](#).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1968, *Fibre ropes and cordage — Vocabulary*

ISO 18692-1:2018, *Fibre ropes for offshore stationkeeping — Part 1: General specification*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1968 and ISO 18692-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

4 Materials

The fibre used in the rope shall be high-tenacity polyester fibre, with an average tenacity not less than 0,78 N/tex and qualified and tested in accordance with [Annex A](#) and ISO 18692-1:2018, Annex A.

Rope cover material and other materials employed in rope assembly shall be in accordance with ISO 18692-1.

5 Requirements — rope properties

5.1 Minimum breaking strength

The minimum breaking strength of the rope, when tested according to ISO 18692-1, shall conform to [Table 1](#).

Table 1 — Minimum breaking strength (MBS)

Reference number ^a	Minimum breaking strength kN
106	3 140
118	3 920
132	4 900
150	6 180
160	6 960
170	7 850
180	8 830
190	9 810
200	11 000
212	12 300
224	13 700
236	15 700
250	17 700
265	19 600

^a The reference number corresponds to the approximate outer diameter of the rope, in millimetres (mm). Actual diameters may vary for a given reference number.

5.2 Minimum core tenacity

The rope minimum core tenacity shall be 0,47 N/tex, measured according to ISO 18692-1.

All samples tested shall conform with this minimum value.

5.3 Dynamic stiffness at end of bedding-in

The dynamic stiffness at the end of the bedding-in sequence, obtained according to ISO 18692-1, shall be between 18 and 28.

A different range may be specified by the purchaser.

5.4 Torque properties

Torque-neutral rope or torque-matched rope shall be as defined in ISO 18692-1.

5.5 Cyclic loading performance

The rope shall have demonstrated performance under cycling loading following the requirements of ISO 18692-1.

5.6 Particle ingress protection

Unless otherwise specified, the rope shall be constructed with a protection of the core against the ingress of particles in accordance with ISO 18692-1.

6 Requirements — Rope layout and construction

Rope layout and construction shall be in accordance with ISO 18692-1.