

---

**Dodajni materiali za varjenje - Oplaščene elektrode za obločno varjenje nelegiranih in drobnnozrnatih jekel - Razvrstitev (ISO/DIS 2560:2019)**

Welding consumables - Covered electrodes for manual metal arc welding of non-alloy and fine grain steels - Classification (ISO/DIS 2560:2019)

Schweißzusätze - Umhüllte Stabelektroden zum Lichtbogenhandschweißen von unlegierten Stählen und Feinkornstählen - Einteilung (ISO/DIS 2560:2019)

Produits consommables pour le soudage - Électrodes enrobées pour le soudage manuel à l'arc des aciers non alliés et des aciers à grains fins - Classification (ISO/DIS 2560:2019)

**Ta slovenski standard je istoveten z: prEN ISO 2560**

---

**ICS:**

25.160.20      Potrošni material pri varjenju    Welding consumables

**oSIST prEN ISO 2560:2019**

**en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 2560

ISO/TC 44/SC 3

Secretariat: ANSI

Voting begins on:  
2019-10-17Voting terminates on:  
2020-01-09

---

---

## Welding consumables — Covered electrodes for manual metal arc welding of non-alloy and fine grain steels — Classification

*Produits consommables pour le soudage — Électrodes enrobées pour le soudage manuel à l'arc des aciers non alliés et des aciers à grains fins — Classification*

ICS: 25.160.20

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 2560:2020

<https://standards.iteh.ai/catalog/standards/sist/adeacdc6-04d6-48d3-b8be-2d116776eb87/sist-en-iso-2560-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 2560:2019(E)

© ISO 2019

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 2560:2020

<https://standards.iteh.ai/catalog/standards/sist/adeacdc-b-04d6-48d3-b8be-2d116776eb87/sist-en-iso-2560-2020>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Foreword .....	iv
Introduction.....	vi
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions.....	2
4 Classification.....	2
5 Symbols and requirements .....	4
5.1 Symbol for the product/process .....	4
5.2 Symbols for strength and elongation of all-weld metal .....	4
5.3 Symbol for impact properties of all-weld metal.....	5
5.4 Symbol for the chemical composition of all-weld metal.....	5
5.5 Symbol for type of electrode covering.....	6
5.6 Symbol for condition of post-weld heat-treatment of all-weld metal .....	8
5.7 Symbol for nominal electrode efficiency and type of current.....	8
5.8 Symbol for welding position.....	9
5.9 Symbol for diffusible hydrogen content of deposited metal .....	9
6 Mechanical tests .....	10
6.1 Preheating and interpass temperatures.....	10
6.2 Pass sequence.....	13
7 Chemical analysis .....	14
8 Fillet weld test.....	17
9 Rounding procedure .....	19
10 Retests .....	19
11 Technical delivery conditions.....	19
12 Examples of designation .....	20
Annex A (informative) Classification systems.....	21
Annex B (informative) Description of types of electrode covering — Classification by yield strength and 47 J impact energy .....	24
Annex C (informative) Description of types of electrode covering — Classification by tensile strength and 27 J impact energy .....	26
Annex D (informative) Notes on diffusible hydrogen and the avoidance of cold cracking .....	29
Bibliography .....	30

## ISO/DIS 2560:2019(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

Official interpretations of TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

This fourth edition cancels and replaces the third edition (ISO 2560:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- draft updated to latest ISO template and styles, e.g. AC for a.c. and DC for d.c.
- all references updated to latest editions and titles
- Table 3B: alloy symbol “No symbol, –1, –P1 or –P2”, nominal level (% by mass) for Mn is now 1,3
- Table 4B: footnote “d” added to the “All” for symbol 45 to state: “Not including PF (vertical up)”
- Table 5A: Nominal electrode efficiency change to Electrode efficiency
- Table 10B: Maximum Si values have been changed for E4918 and E4918-1, E5516-3M3, E5516-N7
- Table 10B: Maximum Mo for E5516-N3 changed to N.S.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 2560:2020

<https://standards.iteh.ai/catalog/standards/sist/adeacdc8-04d6-48d3-b8be-2d116776eb87/sist-en-iso-2560-2020>

**ISO/DIS 2560:2019(E)****Introduction**

This document recognizes that there are two somewhat different approaches in the global market to classifying a given electrode, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both, where suitable) identifies a product as classified in accordance with this document. The classification in accordance with system A is mainly based on EN 499:1994. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim.

This Document provides a classification in order to designate covered electrodes in terms of the yield strength, tensile strength and elongation of the all-weld metal. The ratio of yield strength to tensile strength of weld metal is generally higher than that of parent metal. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Therefore, where the application requires matching tensile strength, selection of the consumable should be made by reference to column 3 of Table 1A or to Table 1B and Table 8B.

It should be noted that the mechanical properties of all-weld metal test specimens used to classify the electrodes vary from those obtained in production joints because of differences in welding procedure such as electrode size, width of weave, welding position, welding current, interpass temperature and parent metal composition.

STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 2560:2020

<https://standards.iteh.ai/catalog/standards/sist/adeacdc8-04d6-48d3-b8be-2d116776eb87/sist-en-iso-2560-2020>



# Welding consumables — Covered electrodes for manual metal arc welding of non-alloy and fine grain steels — Classification

## 1 Scope

This document specifies requirements for the classification of covered electrodes and deposited metal in the as-welded condition and in the post-weld heat-treated condition for manual metal arc welding of non-alloy and fine grain steels with a minimum yield strength of up to 500 MPa or a minimum tensile strength of up to 570 MPa.

This document is a combined specification providing for classification utilizing a system based upon the yield strength and the average impact energy of 47 J of all-weld metal, or utilizing a system based upon the tensile strength and the average impact energy of 27 J of all-weld metal.

- a) Clauses, subclauses and tables which carry the suffix letter “A” are applicable only to covered electrodes classified to the system based upon the yield strength and the average impact energy of 47 J of all weld metal in this Document.
- b) Clauses, subclauses and tables which carry the suffix letter “B” are applicable only to covered electrodes classified to the system based upon the tensile strength and the average impact energy of 27 J of all weld metal in this Document.
- c) Clauses, subclauses and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all covered electrodes classified in this Document.

<https://standards.iteh.ai/catalog/standards/sist/adeacdc6-04d6-48d3-b8bc-2d116776eb87/sist-en-iso-2560-2020>

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 2401, *Covered electrodes — Determination of the efficiency, metal recovery and deposition coefficient*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947, *Welding and allied processes — Welding positions*

ISO 13916, *Welding — Measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*. Amended by ISO 15792-1:2000/Amd 1:2011

ISO 15792-3:2011, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

**ISO/DIS 2560:2019(E)**

ISO 80000-1, *Quantities and units — Part 1: General*. Corrected by ISO 80000-1:2009/Cor 1:2011

**3 Terms and definitions**

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

**4 Classification**

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all, as is clear from the following subclauses. In most cases, a given commercial product can be classified in both systems. Then either or both classification designations can be used for the product.

The classification includes all-weld metal properties obtained with a covered electrode as given below. The classification is based on an electrode size of 4,0 mm, with the exception of the symbol for welding position, which is based on ISO 15792-3. Where the defined diameter has not been manufactured, the closest diameter to 4,0 mm shall be used for all-weld metal tests.

<https://standards.iteh.ai/catalog/standards/sist/adeacdc8-04d6-48d3-b8be-2d116776eb87/sist-en-iso-2560-2020>

#### 4A Classification by yield strength and 47 J impact energy

The classification is divided into eight parts:

- 1) the first part gives a symbol indicating the product/process to be identified;
- 2) the second part gives a symbol indicating the strength and elongation of all-weld metal (see Table 1A);
- 3) the third part gives a symbol indicating the impact properties of all-weld metal (see Table 2A);
- 4) the fourth part gives a symbol indicating the chemical composition of all-weld metal (see Table 3A);
- 5) the fifth part gives a symbol indicating the type of electrode covering (see 5.5A);
- 6) the sixth part gives a symbol indicating the nominal electrode efficiency and type of current (see Table 5A);
- 7) the seventh part gives a symbol indicating the welding position (see Table 6A);
- 8) the eighth part gives a symbol indicating the diffusible hydrogen content of the deposited metal (see Table 7).

In order to promote the use of this Document, the classification is split into two sections:

##### a) Compulsory section

This section includes the symbols for the type of product, the strength and elongation, the impact properties, the chemical composition and the type of covering, i.e. the symbols defined in 5.1, 5.2A, 5.3A, 5.4A and 5.5A.

##### b) Optional section

This section includes the symbols for the nominal electrode efficiency, the type of current, the welding positions for which the electrode is suitable, and the symbol for diffusible hydrogen content, i.e. the symbols defined in 5.7A, 5.8A and 5.9.

The designation (see Clause 12), compulsory section and any chosen elements of the optional section, shall be used on packages and in the manufacturer's literature and data sheets. See Figure A.1 for a schematic representation of the full designation of electrodes classified by yield strength and 47 J impact energy (system A). See Figure A.2 for a schematic representation of the full designation of electrodes classified by tensile strength and 27 J impact energy (system B).

#### 4B Classification by tensile strength and 27 J impact energy

The classification is divided into seven parts:

- 1) the first part gives a symbol indicating the product/process to be identified;
- 2) the second part gives a symbol indicating the strength of all-weld metal (see Table 1B);
- 3) the third part gives a symbol indicating the type of electrode covering, the type of current, and the welding position (see Table 4B);
- 4) the fourth part gives a symbol indicating the chemical composition of all-weld metal (see Table 3B);
- 5) the fifth part gives a symbol indicating the condition of post-weld heat treatment under which the all-weld metal test was conducted (see 5.6B);
- 6) the sixth part gives a symbol indicating that the electrode has satisfied a requirement for 47 J impact energy at the temperature normally used for the 27 J requirement;
- 7) the seventh part gives a symbol indicating the diffusible hydrogen content of the deposited metal (see Table 7).

In order to promote the use of this Document, the classification is split into two sections:

##### a) Compulsory section

This section includes the symbols for the type of product, the strength, the type of covering, the type of current, the welding position, the chemical composition and the condition of heat treatment, i.e. the symbols defined in 5.1, 5.2B, 5.4B, 5.5B and 5.6B.

##### b) Optional section

This section includes the symbol for the optional supplemental designator for 47 J impact energy, i.e. the symbol defined in 5.3B; and the symbol for diffusible hydrogen content, i.e., the symbol defined in 5.9.

## 5 Symbols and requirements

### 5.1 Symbol for the product/process

The symbol for the covered electrode used in the manual metal arc welding process shall be the letter E placed at the beginning of the designation.

### 5.2 Symbols for strength and elongation of all-weld metal

#### 5.2A Classification by yield strength and 47 J impact energy

The symbols in Table 1A indicate the yield strength, tensile strength, and elongation of the all-weld metal in the as-welded condition, determined in accordance with Clause 6.

#### 5.2B Classification by tensile strength and 27 J impact energy

The symbols in Table 1B indicate the tensile strength of the all-weld metal in the as-welded condition or in the post-weld heat-treated condition, determined in accordance with Clause 6. The yield strength and elongation requirements depend upon the specific chemical composition, heat treatment condition and coating type, as well as upon the tensile strength requirements, as given for the complete classification in Table 8B.

**Table 1A — Symbol for strength and elongation of all-weld metal**

(Classification by yield strength and 47 J impact energy)

Symbol	Minimum yield strength <sup>a</sup> MPa	Tensile strength MPa	Minimum elongation <sup>b</sup> %
35	355	440 to 570	22
38	380	470 to 600	20
42	420	500 to 640	20
46	460	530 to 680	20
50	500	560 to 720	18

<sup>a</sup> For yield strength, the lower yield strength ( $R_{eL}$ ) shall be used when yielding occurs, otherwise the 0,2 % proof strength ( $R_{p0,2}$ ) shall be used.

<sup>b</sup> The gauge length is equal to five times the specimen diameter.

**Table 1B — Symbol for strength of all-weld metal**

(Classification by tensile strength and 27 J impact energy)

Symbol	Minimum tensile strength MPa
43	430
49	490
55	550
57	570