
**Mineral and sapphire watch-glasses —
Part 4:
Anti-reflective treatment**

*Verres de montres minéraux et en saphir —
Partie 4: Traitements antireflet*

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[ISO 14368-4:2020](https://standards.iteh.ai/catalog/standards/sist/2fff8bd8-c3d5-48d2-b3b3-20825bdac399/iso-14368-4-2020)

<https://standards.iteh.ai/catalog/standards/sist/2fff8bd8-c3d5-48d2-b3b3-20825bdac399/iso-14368-4-2020>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14368-4:2020

<https://standards.iteh.ai/catalog/standards/sist/2fff8bd8-c3d5-48d2-b3b3-20825bdac399/iso-14368-4-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test methods and evaluation of results	2
4.1 General.....	2
4.2 Optical characterization.....	2
4.2.1 Luminous transmittance.....	3
4.2.2 Luminous reflectance and colour.....	3
4.2.3 Evaluation of results.....	4
4.3 Adhesive force.....	4
4.3.1 Test method.....	4
4.3.2 Evaluation of results.....	4
4.4 Humidity test.....	4
4.4.1 Test method.....	4
4.4.2 Evaluation of results.....	4
4.5 Thermal shock test.....	4
4.5.1 Test method.....	4
4.5.2 Evaluation of results.....	5
4.6 Salt spray test.....	5
4.6.1 Test method.....	5
4.6.2 Evaluation of results.....	5
4.7 Synthetic sweat test.....	5
4.7.1 Test method.....	5
4.7.2 Evaluation of results.....	5
4.8 Abrasion resistance.....	5
4.8.1 Sample preparation.....	5
4.8.2 Test method.....	5
4.8.3 Evaluation of results.....	5
4.9 Scratch resistance.....	5
4.9.1 Test method.....	5
4.9.2 Evaluation of results.....	6
4.10 Sunlight resistance.....	6
4.10.1 Test method.....	6
4.10.2 Evaluation of results.....	7
4.11 Cleaning test.....	7
4.11.1 Test method.....	7
4.11.2 Evaluation of results.....	7
Annex A (informative) Optical characterization of watch-glasses	8
Annex B (informative) Examples of test conditions parameters to sunlight	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 114, *Horology*, Subcommittee SC 13, *Watch-glasses*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Anti-reflective treatments are widely used in watch-glasses. Anti-reflective treatments are used to improve legibility of the watch dial by reducing light reflected from the watch-glasses.

When customers are wearing watches, the watches go through temperature variation, corrosion, scratch, sunlight and many other environmental conditions. The properties of the anti-reflective treatments may directly affect the appearance of the watch-glasses and the legibility of the dial, therefore this International Standard aims to clarify the test methods and the evaluations for the anti-reflective treatments.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 14368-4:2020](https://standards.iteh.ai/catalog/standards/sist/2fff8bd8-c3d5-48d2-b3b3-20825bdac399/iso-14368-4-2020)

<https://standards.iteh.ai/catalog/standards/sist/2fff8bd8-c3d5-48d2-b3b3-20825bdac399/iso-14368-4-2020>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 14368-4:2020

<https://standards.iteh.ai/catalog/standards/sist/2fff8bd8-c3d5-48d2-b3b3-20825bdac399/iso-14368-4-2020>

Mineral and sapphire watch-glasses —

Part 4: Anti-reflective treatment

1 Scope

This document specifies the terms and definitions, the test methods and the evaluation of results of watch-glasses with anti-reflective treatments.

The document is applicable to sapphire watch-glasses with anti-reflective treatments, and it can also be used as a reference for mineral watch-glasses with anti-reflective treatments.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3160-2:2015, *Watch-cases and accessories — Gold alloy coverings — Part 2: Determination of fineness, thickness, corrosion resistance and adhesion*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO/CIE 11664-1:2019, *Colorimetry — Part 1: CIE standard colorimetric observers*

ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants*

ISO 14368-3:2003, *Mineral and sapphire watch-glasses — Part 3: Qualitative criteria and test methods*

ISO 23160:2011, *Watch cases and accessories — Tests of the resistance to wear, scratching and impacts*

CIE 15:2018, *Colorimetry*

CIE 85:1989, *Solar Spectral Irradiance*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 luminous transmittance

ratio of the transmitted luminous flux to the luminous flux of the incident radiation

$$\tau_v = \frac{\int_0^\infty \tau(\lambda) \Phi_{e,\lambda}(\lambda) V(\lambda) d\lambda}{\int_0^\infty \Phi_{e,\lambda}(\lambda) V(\lambda) d\lambda}$$

where

- $\tau(\lambda)$ is the spectral transmittance of the sample;
- $\Phi_{e,\lambda}(\lambda)$ is the spectral radiant flux of the source;
- $V(\lambda)$ is the spectral luminous efficiency;

[SOURCE: ISO 80000-7:2019, 7-31.6, modified — The definition has been slightly reworded.]

3.2 luminous reflectance

ratio of the reflected luminous flux to the luminous flux of the incident radiation

$$\rho_v = \frac{\int_0^\infty \rho(\lambda) \Phi_{e,\lambda}(\lambda) V(\lambda) d\lambda}{\int_0^\infty \Phi_{e,\lambda}(\lambda) V(\lambda) d\lambda}$$

STANDARD PREVIEW
(standards.iteh.ai)

where

- $\rho(\lambda)$ is the spectral reflectance of the sample;
- $\Phi_{e,\lambda}(\lambda)$ is the spectral radiant flux of the source;
- $V(\lambda)$ is the spectral luminous efficiency;

[SOURCE: ISO 80000-7:2019, 7-31.4, modified — The definition has been slightly reworded.]

4 Test methods and evaluation of results

4.1 General

The following tests are all separate tests. Except for special instructions, each test is conducted with new samples, and no superposition test is conducted. The selection of test item and test plan can be determined by agreement between the contracting parties.

After the test, the anti-reflective treatment is evaluated by visual inspection and by comparison with referenced samples. The appearance shall be checked in accordance with ISO 14368-3:2003, Annex A. The evaluations of test results are checked according to the requirements given by each test item and, if required, higher acceptance criteria of the test results should be defined by agreement between the contracting parties.

4.2 Optical characterization

The spectral distribution of standard illuminant D65 as specified in ISO 11664-2 and the luminous efficiency of the average human eye for daylight vision ($V(\lambda)=\bar{y}(\lambda)$ for 2° observer) as specified in

ISO/CIE 11664-1:2019, 3.11, shall be used to determine the luminous transmittance τ_v or the luminous reflectance ρ_v .

The selection of the measurement geometry between transmittance and/or reflectance can be determined by agreement between the contracting parties.

4.2.1 Luminous transmittance

Parameters for the digital integration of the transmittance spectrum $\tau(\lambda)$ are: illuminant D65 and standard observer 2°, step width not exceeding 10 nm and range from 380 nm to 780 nm. The luminous transmittance factor is expressed in $\tau_v = Y$ as described in CIE 15:2018, Chapter 7.

$$\tau_v = \frac{\int_{380}^{780} \tau(\lambda) S(\lambda) \bar{y}(\lambda) d\lambda}{\int_{380}^{780} S(\lambda) \bar{y}(\lambda) d\lambda}$$

where

$S(\lambda)$ is the relative spectral power distribution of the illuminant D65;

$\bar{y}(\lambda)$ is one of the CIE colour matching function.

NOTE The measuring range between 380 nm to 780 nm can be truncated to another range (e.g. 360 nm to 740 nm) providing the result is not significantly changed (see CIE 15:2018, 7.2).

4.2.1.1 Apparatus with integration sphere

Use a spectrophotometer or a spectrophotometer with an integration sphere to obtain the transmittance spectrum with the Specular Component Included (SCI) according to a measuring geometry di:0° or 0°:di (see CIE 15:2018, Chapter 6).

4.2.1.2 Apparatus without integration sphere

Use a spectrophotometer or a spectrophotometer without integration sphere to obtain the transmittance spectrum according to a measuring geometry 0°:0° (see CIE 15:2018, Chapter 6). In this case, only the regular transmittance component is measured.

NOTE In case of a polarized light source (grating on the beam path) and due to the birefringent effect of the sapphire, it is recommended to align the optical axis of the sapphire with the polarization axis of the beam in order to minimize the fringes amplitude on the transmittance spectrum.

4.2.2 Luminous reflectance and colour

Parameters for the digital integration of the reflectance spectrum $\rho(\lambda)$ are: illuminant D65 and standard observer 2°, step width not exceeding 10 nm and range from 380 nm to 780 nm. Reflectance factor is expressed in $\rho_v = Y$ as described in CIE 15:2018, Chapter 7, and colour is expressed in $L^*a^*b^*$ values as described in CIE 15:2018, 8.2.

Use a spectrophotometer or a spectrophotometer with an integration sphere to obtain the reflectance spectrum in reflection mode with the Specular Component Included (SCI) according to a measuring geometry di:8° or 8°:di (CIE 15:2018, Chapter 6).

$$\rho_v = \frac{\int_{380}^{780} \rho(\lambda) S(\lambda) \bar{y}(\lambda) d\lambda}{\int_{380}^{780} S(\lambda) \bar{y}(\lambda) d\lambda}$$

where

$S(\lambda)$ is the relative spectral power distribution of the illuminant D65;

$\bar{y}(\lambda)$ is one of the CIE colour matching function.

NOTE 1 The measuring range between 380 nm to 780 nm can be truncated to another range (e.g. 360 nm to 740 nm) providing the result is not significantly changed (see CIE 15:2018, 7.2).

In order to measure the pure reflectance, only the light reflected by the watch-glass is collected by the detector. Particularly, light beams transmitted through the watch-glass and further reflected on a back support should not be included in the signal detected (see [Figure A.2](#)). It might be necessary to check if other light sources (ambient light, reflection on various support material or setting surface for example) do not affect the measurement in a significant manner.

NOTE 2 When colour parameters are measured, other colour spaces can be used such as L^*C^*h , xyY or $L^*u^*v^*$ (according to CIE 15:2018, Chapter 8).

4.2.3 Evaluation of results

Acceptance criteria of the test results should be defined by agreement between the contracting parties. Reference values of luminous transmittance, luminous reflectance and colour are given in [Annex A](#).

4.3 Adhesive force

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4.3.1 Test method

Use an adhesive tape with a peel adhesion of 2,9 N/cm to 3,3 N/cm. The tape is adhered to the treated surface, ensuring that bubbles between the tape and the treated surface are eliminated. After 10 s, tear the tape quickly with the force perpendicular to the treated surface. The tape used shall not leave any glue residues on the treated surface.

4.3.2 Evaluation of results

After the test, the anti-reflective treatment shall show no chap, bubble, delamination and peel-off.

4.4 Humidity test

4.4.1 Test method

The watch-glasses with anti-reflective treatments are placed in the constant temperature and humidity equipment. The temperature inside the chamber is set to 40 °C, with a tolerance of ± 2 °C. The relative humidity inside the chamber is set to 93 %, with a tolerance of ± 5 %. The test is carried out for at least 48 h.

4.4.2 Evaluation of results

After the test, the anti-reflective treatment shall show no chap, bubble, delamination and peel-off.

4.5 Thermal shock test

4.5.1 Test method

Place the samples in a thermal chamber stabilized at $70 \text{ °C} \pm 2 \text{ °C}$ without humidity contribution during 2 h. Then soak them immediately in deionized water at $5 \text{ °C} \pm 2 \text{ °C}$ during 30 s minimum. Repeat this cycle 5 times minimum. Samples shall be dried after each cycle.

4.5.2 Evaluation of results

After the test, the anti-reflective treatment shall show no chap, bubble, delamination and peel-off.

4.6 Salt spray test

4.6.1 Test method

According to ISO 9227, neutral salt spray test shall be carried out for at least 24 h. Then the adhesive force test specified in 4.3 is carried out.

4.6.2 Evaluation of results

After the test, the anti-reflective treatment shall show no chap, bubble, delamination, peel-off and obvious (dis)coloration.

4.7 Synthetic sweat test

4.7.1 Test method

According to ISO 3160-2:2015, 7.4, synthetic sweat test shall be carried out for at least 24 h. Then the adhesive force test specified in 4.3 is carried out.

4.7.2 Evaluation of results

After the test, the anti-reflective treatment shall show no chap, bubble, delamination, peel-off and obvious (dis)coloration.

4.8 Abrasion resistance

4.8.1 Sample preparation

The test samples, with flat surface, are made of the same material and the same anti-reflective treatment, and are produced using the same method as the watch-glass.

4.8.2 Test method

The samples (treated surface up) are cleaned and fixed on the friction testing machine. The friction head moves back and forth along the same path, and the distance between the two ends is twice the diameter of the friction head. After 100 times reciprocating friction, clean and check the samples by visual inspection. The friction head is a rubber whose diameter is 6,5 mm to 7,0 mm, and hardness is (75 ± 5) IRHD, with 6 to 8 layers dry degreasing cloth outside. The perpendicular stress applied on the friction head is (5 ± 1) N. The average rate of the test is $(1 \pm 0,1)$ cycle per second.

4.8.3 Evaluation of results

After the test, the anti-reflective treatment shall show no obvious scratch or wear.

4.9 Scratch resistance

4.9.1 Test method

The test method shall be in accordance with ISO 23160:2011, 5.2, 5.3 and 5.4.