INTERNATIONAL STANDARD

Second edition 2018-07

Adhesives — Determination of the solubility of water-soluble or alkali-soluble pressure-sensitive adhesives

Adhésifs — Détermination de la solubilité des adhésifs sensibles à la pression, solubles dans l'eau ou dans les alcalis

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 25179:2018</u> https://standards.iteh.ai/catalog/standards/sist/37c4a30b-e3f0-4d35-9bffa4601427d4d1/iso-25179-2018



Reference number ISO 25179:2018(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 25179:2018</u> https://standards.iteh.ai/catalog/standards/sist/37c4a30b-e3f0-4d35-9bffa4601427d4d1/iso-25179-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

Forew	ordiv	1		
1	Scope 1			
2	Normative references 1			
3	Terms and definitions 1			
4	Principle 1			
5	Apparatus2	,		
6	Solutions and materials 5	,		
7	Preparation of test specimens	;		
8	Procedure)		
9	Expression of results 7	,		
10	Test report 7	,		
Annex A (informative) Report form				
Bibliography 10				

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 25179:2018</u> https://standards.iteh.ai/catalog/standards/sist/37c4a30b-e3f0-4d35-9bffa4601427d4d1/iso-25179-2018

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

https://standards.iteh.ai/catalog/standards/sist/37c4a30b-e3f0-4d35-9bff-

This second edition cancels and replaces the first edition (ISO 25179:2010) of which it constitutes a minor revision. The main changes compared to the previous edition are as follows:

- definitions have been added in <u>Clause 3</u> for "pressure sensitive adhesive" and "solubility";
- <u>Annex A</u> has been revised to include columns for signature;
- a Bibliography has been added.

Adhesives — Determination of the solubility of watersoluble or alkali-soluble pressure-sensitive adhesives

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions. It is recognized that some of the materials permitted in this document may have a negative environmental impact. As technological advances lead to more acceptable alternatives for such materials, they will be eliminated to the greatest extent possible. At the end of the test, care should be taken to dispose of all waste in an appropriate manner.

1 Scope

This document specifies a test method for the determination of the solubility of a water-soluble pressure-sensitive adhesive in water or the solubility of an alkali-soluble pressure-sensitive adhesive in alkali by measuring the loss in mass of the adhesive when immersed in water or alkali. The solubility of the adhesive is one of the key factors in assessing the possibility of recycling products to which labels are fixed using a pressure-sensitive adhesive.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, Plastics — Standard atmospheres for conditioning and testing

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>

3.1

pressure sensitive adhesive

adhesive which in a dry state is permanently tacky at room temperature and adheres readily to surfaces under brief and light pressure

3.2

solubility

chemical property referring to the ability for a given substance, the solute, to dissolve in a solvent

Note 1 to entry: It is measured in terms of the maximum amount of solute dissolved in a solvent at equilibrium.

4 Principle

This method measures the solubility of a water-soluble or an alkali-soluble adhesive, coated on kraft paper, as a function of time by measuring the loss in mass of an adhesive-coated test specimen after shaking the specimen in water or alkali solution.

5 Apparatus

5.1 Orbital shaker, enclosed in a chamber capable of being heated by air at a temperature in the range 40 °C to 80 °C, accurate to within ± 2 °C, and having a motor capable of producing a shaking speed of 10 r/min to 100 r/min, for shaking the bottles (5.2) containing the test specimens (see Figure 1).



Key

shaker chamber

1 2

3	bottle	5	heater
4	shaker plate	6	motor

Figure 1 — Example of a shaker

5.2 Bottles, made of glass, with a volume of 500 ml and capable of being sealed with a cap to prevent the escape of any vapour.

NOTE The method uses two types of bottle cap, an ordinary bottle cap and a prepared bottle cap (see Figure 2) to which the test specimen holder (see Figure 3) is connected.

5.3 Test specimen holder, comprising a cylindrical drum, two specimen-clamping bars and a connecting rod made of AISI 316 stainless steel, as shown in <u>Figures 3</u>, <u>4</u> and <u>5</u>.

5.4 Drying oven, with forced-air convection, capable of being maintained at a temperature in the range from 50 °C to 120 °C to an accuracy of ± 2 °C.

5.5 Balance, capable of weighing the test specimen substrate and the coated test specimen to an accuracy of 0,000 1 g.



2 prepared bottle cap

Key 1

4 cylindrical drum of test specimen holder

Figure 2 — Examples of ordinary and prepared bottle caps



Кеу

Key

1

2

- 1 specimen-clamping bar
- test specimen

3

2 cylindrical drum



Dimensions in millimetres



Kev

- AISI 316 stainless steel, thickness 1,5 mm DARD PRE polytetrafluoroethylene (PTFE), thickness 1 mm 1 VIEW
- 2 (standards.iteh.ai)
- 3 fastening hole

Figure 5 — Example of a specimen-clamping bar

https://standards.iteh.ai/catalog/standards/sist/37c4a30b-e3f0-4d35-9bffa4601427d4d1/iso-25179-2018

6 Solutions and materials

6.1 **Distilled or deionized water**, for dissolving water-soluble adhesives.

6.2 **Aqueous alkali solution**, made by dissolving (1 ± 0.01) parts by mass of reagent-grade sodium hydroxide (NaOH) in (99 ± 1) parts by mass of water, for dissolving alkali-soluble adhesives.

Repulpable kraft paper, with a mass per unit area between 80 g/m² and 100 g/m², for use as the 6.3 test specimen substrate.

7 **Preparation of test specimens**

7.1 Cut from the kraft paper (6.3) a sheet measuring 400 mm in length and 300 mm in width.

7.2 Place the sheet on a clean glass plate and coat with the adhesive being tested, using a laboratoryscale coating machine to produce a wet-film thickness of about 40 µm.

7.3 Dry the coated sheet on the glass plate in the drying oven for 30 min at 80 °C. Then remove the sheet from the drying oven and allow to cool to room temperature.

Remove the coated sheet from the glass plate and cut from it 10 or more test specimens measuring 7.4 110 mm in length and 20 mm in width.