

ISO/TC 61/SC 2

Secretariat: KATS

Voting begins on:
2020-04-03

Voting terminates on:
2020-05-29

Plastics — Acquisition and presentation of comparable single-point data —

Part 2: Long-fibre-reinforced plastics

Plastiques — Acquisition et présentation de caractéristiques intrinseques comparables —

Partie 2: Plastiques renforcés par de longues fibres

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/FDIS 10350-2:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/8ced87b1-48bb-4dff-a440-f690bab0621d/iso-fdis-10350-2>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Specimen preparation and conditioning.....	3
5 Test requirements.....	4
6 Presentation of results.....	4
Bibliography.....	10

iTeh STANDARD PREVIEW
 (standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/8ced87b1-48bb-4df1-a440-f690bab0621d/iso-fdis-10350-2>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical behaviour*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 10350-2:2011), which has been technically revised. The main change compared to the previous edition are as follows:

- normative reference IEC 60250 has been cancelled and replaced by IEC 62631-2-1;
- normative reference IEC 60093 has been cancelled and replaced by either IEC 62631-3-1 or ISO 3915.

These changes were made previously for plastics in ISO 10350-1.

A list of all parts in the ISO 10350 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document has been prepared because users of long-fibre-reinforced plastics find that available data cannot always be readily used to compare the properties of similar materials, especially when the data have been supplied by different sources. Even when the same standard tests have been used, they can allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this document is to identify specific methods and conditions of test to be used for the acquisition and presentation of data in order that valid comparisons between materials can be made.

This document is concerned with tests employed to present “single-point” data on the limited range of properties commonly included in data sheets and used for the preliminary selection of materials. Such data represent the most basic approach to the specification of properties of materials and this document thus facilitates the first steps towards more efficient selection and use of plastics in the many applications to which they are suited.

Many properties of long-fibre-reinforced plastics are anisotropic. The test method standards for these properties have been produced with different procedures for specific types of reinforcement. In this document, use of the appropriate procedure is specified rather than the use of a specific specimen geometry as adopted in ISO 10350-1 for moulding materials. This is necessary for the recording of meaningful material property values.

Complementary International Standards (such as ISO 11403-1^[1], ISO 11403-2^[2] and ISO 11403-3^[3]) are concerned with the standardized acquisition and presentation of multipoint data, to demonstrate how properties vary with important factors such as time, temperature and the presence of particular natural and chemical environments. In these International Standards, some additional properties are included. Their use provides a more substantial database than one containing only single-point data, and so enables improved assessment of the fitness of a material for any particular application. In addition, ISO 11403-1, which deals with mechanical properties, assists predictions of the performance of components and ISO 11403-2, covering thermal and processing properties, aids predictions of melt-flow behaviour during manufacturing. ISO 11403-3 is concerned with environmental influences on properties, and other parts may be prepared to cover additional properties. The various parts of ISO 11403 were written primarily for moulding materials. The test methods and test conditions referred to might not therefore be ideally suited to the acquisition of data for all long-fibre-reinforced plastics.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/8ced87b1-48bb-4df1-a440-f690bab0621d/iso-fdis-10350-2>

Plastics — Acquisition and presentation of comparable single-point data —

Part 2: Long-fibre-reinforced plastics

1 Scope

ISO 10350 identifies specific test procedures for the acquisition and presentation of comparable data for certain basic properties of plastics. In general, each property is specified by a single experimental value, although in certain cases properties are represented by two values obtained under different test conditions or along different directions in the material. The properties included are those presented conventionally in manufacturers' data sheets.

This document applies to reinforced thermoplastic and thermosetting materials where the reinforcement fibres are either discontinuous with a fibre length prior to processing greater than 7,5 mm or continuous (e.g. fabric, continuous-strand mat or unidirectional).

ISO 10350-1 deals specifically with unreinforced and filled plastics, including those using fibres less than 7,5 mm in length.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-3, *Plastics — Determination of temperature of deflection under load — Part 3: High-strength thermosetting laminates and long-fibre-reinforced plastics*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites*

ISO 527-5, *Plastics — Determination of tensile properties — Part 5: Test conditions for unidirectional fibre-reinforced plastic composites*

ISO 1172, *Textile-glass-reinforced plastics — Prepregs, moulding compounds and laminates — Determination of the textile-glass and mineral-filler content — Calcination methods*

ISO 1183 (all parts), *Plastics — Methods for determining the density of non-cellular plastics*

ISO 1268 (all parts), *Fibre-reinforced plastics — Methods of producing test plates*

ISO 2577, *Plastics — Thermosetting moulding materials — Determination of shrinkage*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO/FDIS 10350-2:2020(E)

ISO 3915, *Plastics — Measurement of resistivity of conductive plastics*

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 6603-2, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing*

ISO 7822, *Textile glass reinforced plastics — Determination of void content — Loss on ignition, mechanical disintegration and statistical counting methods*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and step height*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 14125:1998, *Fibre-reinforced plastic composites — Determination of flexural properties*

ISO 14127, *Carbon-fibre-reinforced composites — Determination of the resin, fibre and void contents*

ISO 14130, *Fibre-reinforced plastic composites — Determination of apparent interlaminar shear strength by short-beam method*

ISO 15310, *Fibre-reinforced plastic composites — Determination of the in-plane shear modulus by the plate twist method*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electrical strength of insulating materials - Test methods - Part 1: Tests at power frequencies*

IEC 60296, *Fluids for electrotechnical applications - Unused mineral insulating oils for transformers and switchgear*

IEC 60695-11-10, *Fire hazard testing - Part 11-10: Test flames - 50 W horizontal and vertical flame test methods*

IEC 60695-11-20, *Fire hazard testing - Part 11-20: Test flames - 500 W flame test methods*

IEC 62631-2-1, *Dielectric and resistive properties of solid insulating materials - Part 2-1: Relative permittivity and dissipation factor - Technical Frequencies (0,1 Hz - 10 MHz) - AC Methods*

IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials - Part 3-1: Determination of resistive properties (DC methods) - Volume resistance and volume resistivity - General method*

IEC 62631-3-2, *Dielectric and resistive properties of solid insulating materials - Part 3-2: Determination of resistive properties (DC methods) - Surface resistance and surface resistivity*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

single-point data

data characterizing a plastics material by means of those property tests in which important aspects of performance can be described with single-value results

3.2

specimen coordinate axes

coordinate axes for a material in which the fibres are preferentially aligned in one direction

Note 1 to entry: Where the material contains a known axis of preferred fibre orientation, then this is defined as the “1”-axis (or “1”-direction). For materials prepared as a test plate, then the in-plane direction transverse to the “1”-axis is defined as the “2”-axis.

Note 2 to entry: Where the direction of preferred orientation is not known, the “1”-axis is taken as the production direction of the composite or the reinforcement (e.g. the warp direction for fabrics).

4 Specimen preparation and conditioning

Specimens shall be cut from test plates manufactured by the method given in the part of the ISO 1268 series appropriate to the material under test. Machining shall be performed in accordance with ISO 2818, as applicable, and the dimensions of the specimen shall comply with those for the appropriate specimen in [Table 2](#).

The moulding conditions stipulated in the ISO 1268 series, or other appropriate International Standard, shall be recorded with the single-point data for that material. Typical parameters are shown in [Table 1](#).

Table 1 — Moulding parameters

Moulding-material type	Manufacturing method and standard	Manufacturing parameters
Long-fibre-reinforced plastic	Test plate manufacture ISO 1268-1 to ISO 1268-11	Typical parameters given in the appropriate part of the ISO 1268 series covers: Temperatures (e.g. of mould, resin, preform, cure, post-cure) Pressures (e.g. of moulding, holding, resin transfer, vacuum level) Times, speeds and rates (e.g. curing times, speed of winding or pultrusion, quantity of glass and resin sprayed by unit of time)

For materials that have properties that are not significantly sensitive to any absorbed water, specimens shall be conditioned in accordance with the International Standard appropriate to the material concerned. If no materials standard is available, condition test specimens according to ISO 291. The preferred conditions are at (23 ± 2) °C and (50 ± 10) % RH for a minimum length of time of 88 h (see ISO 291).

For those materials having properties that are significantly dependent upon the concentration of any absorbed water, data shall be presented both for material that is dry and also for material that is in equilibrium with an atmosphere of 50 % RH at 23 °C but with the following exceptions (see [Table 2](#)).

- Rheological properties 1.1 to 1.6 dry only
- Thermal properties 3.1 to 3.8 dry only
- Surface resistivity and comparative tracking index 4.6 and 4.9 50 % RH only

For these materials, consult the relevant materials standard for procedures for conditioning specimens to achieve material that is dry or in equilibrium under 50 % RH. Following such conditioning, all test specimens shall be stored at (23 ± 2) °C for a minimum of 16 h before testing. The storage atmosphere shall then be either dry or at 50 % RH, depending upon the condition of the specimen.