
**Rigid cellular plastics — Thermal
insulation products for buildings —
Specifications**

*Plastiques alvéolaires rigides — Produits d'isolation thermique pour
bâtiments — Spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4898:2018](https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-6e88fa82104e/iso-4898-2018)

[https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-
6e88fa82104e/iso-4898-2018](https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-6e88fa82104e/iso-4898-2018)



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4898:2018

<https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-6e88fa82104e/iso-4898-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Sizes and dimensional-tolerance requirements	2
5 Physical-property requirements	3
5.1 Categories.....	3
5.2 Subcategories.....	3
5.3 Limiting quality values.....	4
5.4 Burning characteristics.....	4
6 Sampling	4
7 Conditioning	4
7.1 Sample panels.....	4
8 Test methods	4
8.1 Linear dimensions.....	4
8.2 Density.....	5
8.3 Compressive strength.....	5
8.4 Thermal conductivity.....	5
8.4.1 General.....	5
8.4.2 Initial thermal conductivity.....	5
8.4.3 Long-term thermal resistance.....	5
8.5 Dimensional stability.....	5
8.6 Compressive creep at elevated temperature.....	6
8.7 Water vapour permeability.....	6
8.8 Water absorption.....	6
8.9 Bending load at break.....	6
9 Conformity control	6
10 Labelling and marking of products	6
11 Reporting requirements	7
Annex A (normative) Amendments to ISO 12576-1	11
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 10, *Cellular plastics*.
ISO 4898:2018

<https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac->

This sixth edition cancels and replaces the fifth edition (ISO 4898:2010), of which it constitutes a minor revision.

The changes compared to the previous edition are as follows:

- product Category IV has been removed as this type of product is not made.

Rigid cellular plastics — Thermal insulation products for buildings — Specifications

1 Scope

This document specifies requirements and methods of testing for three categories of rigid cellular plastics thermal-insulation products for buildings. It covers rigid cellular plastics in the form of flat or profiled boards, with or without natural skins. They can also be faced or laminated with foil, plastic or metal films or sheets, mineral coatings, paper, cardboard or other materials.

This document is not applicable to materials used for the thermal insulation of pipes and vessels, for impact sound absorption or for acoustical insulation.

This document covers the following cellular materials used in the thermal insulation of buildings:

- PF based on phenolic polymer;
- EPS based on expanded polystyrene;
- XPS based on extruded polystyrene;
- PUR based on polyurethane.

The limiting quality values in this document are for use only in the specification of materials between purchaser and supplier, and are not intended to be used for design purposes.

Additional requirements for special applications can be added to those specified in this document by agreement between purchaser and supplier.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 844, *Rigid cellular plastics — Determination of compression properties*

ISO 845, *Cellular plastics and rubbers — Determination of apparent density*

ISO 1040, *Building construction — Modular coordination — Multimodules for horizontal coordinating dimensions*

ISO 1209-1, *Rigid cellular plastics — Determination of flexural properties — Part 1: Basic bending test*

ISO 1663, *Rigid cellular plastics — Determination of water vapour transmission properties*

ISO 1923, *Cellular plastics and rubbers — Determination of linear dimensions*

ISO 2796, *Cellular plastics, rigid — Test for dimensional stability*

ISO 2896, *Rigid cellular plastics — Determination of water absorption*

ISO 7616, *Cellular plastics, rigid — Determination of compressive creep under specified load and temperature conditions*

ISO 4898:2018(E)

ISO 7850, *Cellular plastics, rigid — Determination of compressive creep*

ISO 8301, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Heat flow meter apparatus*

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

ISO 11561, *Ageing of thermal insulation materials — Determination of the long-term change in thermal resistance of closed-cell plastics (accelerated laboratory test methods)*

ISO 12576-1:2001, *Thermal insulation — Insulating materials and products for buildings — Conformity control systems — Part 1: Factory-made products*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

EPS

rigid cellular plastics insulation material manufactured by moulding beads of expandable polystyrene or one of its copolymers and that has a substantially closed-cell structure, filled with air

[SOURCE: ISO 9229]

[ISO 4898:2018](https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-6e88fa82104e/iso-4898-2018)

3.2

XPS

rigid cellular plastics insulation material expanded and extruded with or without a skin from polystyrene or one of its copolymers and that has a closed-cell structure

[SOURCE: ISO 9229]

<https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-6e88fa82104e/iso-4898-2018>

3.3

PUR

rigid cellular plastics insulation material with a substantially closed-cell structure based on polyurethane or urethane/isocyanurate polymers

Note 1 to entry: For definitions of polyisocyanurate plastic, polyurethane and urethane plastic, see ISO 472.

3.4

PF

rigid cellular insulation foam, the polymer structure of which is made primarily from the polycondensation of phenol, its homologues and/or derivatives with aldehydes or ketones

Note 1 to entry: PF used for thermal-insulation purposes has a cellular structure consisting substantially of closed cells (subcategory A) or with a higher content of open cells (subcategory B) which affects the thermal conductivity.

[SOURCE: ISO 9229, modified – Note 1 to entry has been added.]

4 Sizes and dimensional-tolerance requirements

4.1 Board materials shall be supplied in dimensions agreed between purchaser and supplier or in accordance with ISO 1040. Boards shall be flat.

4.2 Dimensional tolerances for length, width and squareness shall conform to the requirements specified in [Table 1](#).

Table 1 — Tolerances for dimensions and squareness

Length or width mm	Tolerance on length or width ^a mm	Squareness tolerances based on differences in diagonal measurements ^{b c} mm
<1 000	±8	5
≥1 000	±10	5

a If more restrictive tolerances are required, these shall be agreed between purchaser and supplier.
b Tolerance categories for diagonal measurements are based on the board length (not width).
c Squareness may also be determined by equivalent methods such as the use of a rectangular pattern.

4.3 Dimensional tolerances for thickness shall conform to the requirements specified in [Table 2](#).

Table 2 — Tolerances for thickness

Thickness mm	Tolerance ^a mm
<50	±2
50 to 75 (incl.)	±3
>75 to 100 (incl.)	±3 ^b
>100	To be agreed between purchaser and supplier

a If more restrictive tolerances are required, these shall be agreed between purchaser and supplier.
b For EPS with natural skins, the thickness tolerance for this thickness category shall be ±4 mm.

5 Physical-property requirements

5.1 Categories

Physical-property requirements are organized into product categories to meet purchaser and supplier needs over a range of end-use applications.

Category I — Suitable for non-load-bearing applications such as wall and cavity insulation, vented roofs, cavity wall insulation and similar applications.

Category II — Suitable for limited load-bearing applications such as in built-up roofs, under floors and comparable applications, where elevated temperatures may be encountered and where compressive creep resistance is required. Products in this category may also be used for applications listed in category I.

Category III — Suitable for load-bearing applications such as in parking decks, floors of cold-storage areas and comparable applications requiring a higher level of compressive strength and compressive creep resistance. Products in this category may also be used for applications listed in categories I and II.

5.2 Subcategories

Product property categories I to III can be further divided into subcategories (A, B, C) on the basis of thermal-conductivity values. All thermal-conductivity specification values given for the subcategories in the tables are maximum values.

Thermal-conductivity values given in the tables shall be used only as limiting quality values for specification of materials between purchaser and supplier. They shall not be used for design purposes.

5.3 Limiting quality values

EPS materials shall conform to the limiting quality values for physical properties as specified in [Table 3](#).

XPS materials shall conform to the limiting quality values for physical properties as specified in [Table 4](#).

PUR materials shall conform to the limiting quality values for physical properties as specified in [Table 5](#).

PF materials shall conform to the limiting quality values for physical properties as specified in [Table 6](#).

5.4 Burning characteristics

It is recognized that there is a need to consider the burning characteristics of these materials in their intended application. Therefore, until such time as International Standards become available, individual national practice should be followed.

NOTE Due to compositional and processing parameters, some PF materials can exhibit smouldering combustion (punking).

6 Sampling

6.1 For density determinations, 10 full-size boards are required.

6.2 For all other physical-property determinations and for dimensional measurements, at least three full-size boards are required.

ISO 4898:2018

<https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-6e88fa82104e/iso-4898-2018>

7 Conditioning

7.1 Sample panels

All sample panels shall be conditioned under ambient conditions for a minimum of 28 days from the date of manufacture.

7.2 Specimens

Prior to dimensional measurements and physical-property testing, unless otherwise specified in the test method, the test specimens shall be conditioned, with all surfaces exposed, for a minimum of 24 h at

$(23 \pm 2) ^\circ\text{C}$ and $(50 \pm 10) \%$ relative humidity, or

$(23 \pm 5) ^\circ\text{C}$ and $(50_{-10}^{+20}) \%$ relative humidity, or

$(27 \pm 5) ^\circ\text{C}$ and $(65_{-10}^{+20}) \%$ relative humidity.

8 Test methods

8.1 Linear dimensions

The linear dimensions shall be measured in accordance with ISO 1923 for each of three boards. If the material has a surface facing, lamination or natural skin, the dimensions shall be determined without removing them.

A minimum of five measurements shall be made for each dimension. Each single value shall be within the tolerances specified in [4.2](#) and [4.3](#).

8.2 Density

Density measurement is optional for all materials in countries where a system of class identification has been established.

Density shall be determined in accordance with ISO 845 on each of 10 full-size boards and reported as the average of the 10 specimens. The average density of the 10 specimens shall be equal to or greater than the minimum required and no single specimen shall be less than 90 % of the minimum requirement.

When the natural skin of the material forms an integral part of the product in its end use, the surface skin shall not be removed prior to the determination of the density. For those materials with surface facing, lamination or coating, the density shall be determined for the core material after removing such facing, lamination or coating.

8.3 Compressive strength

The compressive strength or the compressive stress at 10 % deformation or yield, whichever occurs first, shall be determined in accordance with ISO 844. Specimens shall be tested with natural skin integral to the final product, surface facing, lamination or coating, unless surface irregularities require removal of such surfaces for uniform loading.

The compressive strength shall be measured in the direction normal to the surface of the board.

8.4 Thermal conductivity

8.4.1 General <https://standards.iteh.ai/catalog/standards/sist/9811056a-53f7-44b9-aaac-6e88fa82104e/iso-4898-2018>
ISO 4898:2018

The thermal conductivity shall be determined in accordance with ISO 8301 or ISO 8302 at a mean temperature of either 23 °C or 10 °C. Thermal-conductivity values measured at one of these mean temperatures may be used to calculate the mean value for the other temperature on the basis of a documented thermal conductivity versus mean temperature relationship. In cases of dispute, the thermal conductivity shall be determined at the mean temperature for which the value is reported.

8.4.2 Initial thermal conductivity

Cellular plastic insulation manufactured with the intent to not retain a blowing agent, other than air, for a period longer than 180 days shall be tested after conditioning for a minimum period of 28 days.

8.4.3 Long-term thermal resistance

All cellular plastic insulation manufactured with the intent to retain a blowing agent, other than air, for a period longer than 180 days shall have the long-term thermal resistance determined in accordance with ISO 11561. When measuring the thermal resistance, the temperature difference across the specimen shall be 23 °C.

8.5 Dimensional stability

Dimensional stability shall be determined at 70 °C for 48 h in accordance with ISO 2796, except that the thickness of the test specimen shall be equal to the thickness of the board as sold. Surface skins or facings shall not be removed.