



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 15792-2:2020**  
**01-januar-2020**

---

**Dodajni materiali za varjenje - Preskusne metode - 2. del: Priprava preskušancev za preskus enovarkovnega in dvovarkovnega varjenja jekel (ISO/DIS 15792-2:2019)**

Welding consumables - Test methods - Part 2: Preparation of single-run and two-run technique test specimens in steel (ISO/DIS 15792-2: 2019)

Schweißzusätze - Prüfverfahren - Teil 2: Vorbereitung eines Prüfstücks zur Prüfung von Einlagen- und Lage/Gegenlage-Schweißungen an Stahl (ISO/DIS 15792-2:2019)

Produits consommables pour le soudage - Méthodes d'essai - Partie 2: Préparation d'éprouvettes en une ou deux passes en acier (ISO/DIS 15792-2: 2019)

**Ta slovenski standard je istoveten z: prEN ISO 15792-2**

---

**ICS:**

25.160.20      Potrošni material pri varjenju    Welding consumables

**oSIST prEN ISO 15792-2:2020**

**en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 15792-2

ISO/TC 44/SC 3

Secretariat: ANSI

Voting begins on:  
2019-11-13Voting terminates on:  
2020-02-05

---

---

## Welding consumables — Test methods —

### Part 2: Preparation of single-run and two-run technique test specimens in steel

*Produits consommables pour le soudage — Méthodes d'essai —**Partie 2: Préparation d'éprouvettes en une ou deux passes en acier*

ICS: 25.160.20

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN ISO 15792-2:2020](https://standards.iteh.ai/catalog/standards/sist/1f16c771-df1f-42a6-a9c3-1a8cbd882d28/sist-en-iso-15792-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/1f16c771-df1f-42a6-a9c3-1a8cbd882d28/sist-en-iso-15792-2-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 15792-2:2019(E)

© ISO 2019

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 15792-2:2020

<https://standards.iteh.ai/catalog/standards/sist/1f16c771-df1f-42a6-a9c3-1a8cbd882d28/sist-en-iso-15792-2-2020>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 General requirements.....</b>	<b>1</b>
<b>5 Test plate material.....</b>	<b>1</b>
<b>6 Preparation of the test piece.....</b>	<b>2</b>
<b>7 Welding conditions.....</b>	<b>2</b>
<b>8 Heat treatment.....</b>	<b>2</b>
<b>9 Position of specimens, specimen dimensions and testing.....</b>	<b>2</b>
<b>10 Retests.....</b>	<b>3</b>
<b>11 Test report.....</b>	<b>6</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 15792-2:2020](https://standards.iteh.ai/catalog/standards/sist/1f16c771-df1f-42a6-a9c3-1a8cbd882d28/sist-en-iso-15792-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/1f16c771-df1f-42a6-a9c3-1a8cbd882d28/sist-en-iso-15792-2-2020>

## ISO/DIS 15792-2:2019(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

Official interpretations of TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

This second edition cancels and replaces the first edition (ISO 15792-2:2000), which has been technically revised.

A list of all parts in the ISO 15792 series can be found on the ISO website.

The main changes compared to the previous edition are as follows:

- To be completed before publication

## Introduction

Consumables for both submerged arc welding and metal arc welding with tubular cored electrodes can be suitable for welding by the single- or two-run technique and the methods for testing and classification are specified. When a welding consumable is offered for use by these techniques, it should be noted that all-weld metal test pieces may not be required by the consumable classification standard.

Test conditions prescribed and results required should not be considered to be requirements or expectations for a procedure qualification.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN ISO 15792-2:2020](https://standards.iteh.ai/catalog/standards/sist/1f16c771-df1f-42a6-a9c3-1a8cbd882d28/sist-en-iso-15792-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/1f16c771-df1f-42a6-a9c3-1a8cbd882d28/sist-en-iso-15792-2-2020>





# Welding consumables — Test methods —

## Part 2:

# Preparation of single-run and two-run technique test specimens in steel

## 1 Scope

This document specifies the preparation of butt weld test pieces and specimens. The purpose is to define test methods in order to determine strength and impact strength of the welded joint when testing welding consumables with single-run and two-run technique, not suitable for electro-slag or electro-gas welding.

This document is applicable to welding consumables for arc welding of steel.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4136:2012, *Destructive tests on welds in metallic materials — Transverse tensile test*

ISO 5178, *Destructive tests on welds in metallic materials — Longitudinal tensile test on weld metal in fusion welded joints*

ISO 9016:2012, *Destructive tests on welds in metallic materials — Impact tests — Test specimen location, notch orientation and examination*

ISO 13916, *Welding — Measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

## 3 Terms and definitions

No terms and definitions are listed in this document.

*The list below is always included after each option:*

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 General requirements

Welding consumables to be tested shall be representative of the manufacturer's products to be classified or tested. Test pieces shall be prepared as described below.

## 5 Test plate material

The material to be used shall be in accordance with the appropriate consumable classification standard.

## ISO/DIS 15792-2:2019(E)

### 6 Preparation of the test piece

The plates of the test piece shall be preset or restrained in such a way that a sufficiently flat test piece is produced for extraction of specimens. The welded test piece shall not be straightened. A suitable backing system for single-run technique may be used. Run-on and run-off plates may be used. See [Table 1](#).

### 7 Welding conditions

The test piece shall be welded in the flat position. Welding shall start at room temperature or after application of any preheating required by the welding consumable standard. The interpass temperature shall be in accordance with the welding consumable standard.

The preheating and interpass temperatures shall be measured using temperature indicator crayons, surface thermometers or thermocouples, see ISO 13916.

The welding conditions used, such as current, voltage, travel speed, weld bead size, shall be within the range recommended by the welding consumable manufacturer and where the test is performed for classification purposes in accordance with the limits specified in the relevant consumable standard.

### 8 Heat treatment

All heat treatments required for the butt weld, except hydrogen removal treatment shall be carried out on the completed test piece, or on sections thereof with a machining allowance.

The heat treatments are specified in standards relating to welding consumables.

Hydrogen removal treatment may be carried out on the test piece for tensile testing before or after final machining. The test piece may be held at a temperature not exceeding 250 °C for up to 16 h.

### 9 Position of specimens, specimen dimensions and testing

[Figure 1](#) and [Figure 2](#) show the position of the notched impact specimens, the transverse tensile test specimens and the all weld metal tensile test specimens as appropriate. The test piece must be divided by cutting (machining) or by thermal cutting. In the case of thermal cutting, machining allowances of 10 mm at least on either side shall be provided for subsequent machining of the specimens.

When applicable, the specimens for the impact test (see [Figure 1](#) and [Figure 2](#)) and testing shall be in accordance with ISO 9016. The impact specimen shall be in accordance with ISO 9016:2012, designation VWT 0/b. The position of the impact specimens shall be at the midline of the plate thickness for types 2.1, 2.2 and 2.6, and from the last welded run as shown in [Figure 2](#) for type 2.5. Impact specimens are not applicable for type 2.3 and 2.4.

The size of impact specimens shall be 10 mm ´ 10 mm. If impact testing is required for types 2.3 and 2.4 subsize specimens 5 mm ´ 10 mm shall be used.

The specimens for transverse tensile tests (see [Figure 1](#) a)) and testing shall be in accordance with ISO 4136. The specimen dimensions shall be in accordance with ISO 4136:2012, Table 2.

For type 2.6, the all weld tensile test specimen (see [Figure 1](#) b)) shall be in accordance with ISO 5178 and shall a nominal diameter of 6,0 mm. The reduced section of the longitudinal tensile specimen shall be located entirely within the weld.

Prior to the preparation of test specimens, it is recommended that the prepared and etched surface of the test piece be subjected to radiographic and/or macrographic examination to ascertain if there are any defects in the weld