
**Rubber — Comprehensive review of
the composition and nature of process
fumes in the rubber industry**

*Caoutchouc — Examen exhaustif de la composition et de la nature des
fumées de process dans l'industrie du caoutchouc*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 21275:2017](https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017)

<https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 21275:2017](https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017)

<https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Overview of the rubber industry	8
4.1 General.....	8
4.2 Rubber component production processes.....	8
4.3 Generic rubber types.....	11
4.4 Rubber chemicals and additives.....	12
4.5 Mechanistic chemistry of rubber vulcanization.....	13
4.5.1 Generality.....	13
4.5.2 Sulfur-accelerated cure systems.....	13
4.5.3 Peroxide-based cure systems.....	14
4.5.4 Metal oxides.....	14
4.5.5 Other vulcanizing systems.....	14
4.6 Effect of elevated temperature on rubbery polymers and rubber additives.....	15
5 Definition of rubber fumes	15
6 Nature and composition of rubber fumes	16
6.1 General.....	16
6.2 Key components of rubber fumes and their origin.....	16
6.3 Trapping and analysis of rubber fumes.....	17
6.3.1 General.....	17
6.3.2 Characterization studies carried out in factory environments.....	17
6.3.3 Characterization studies carried out under laboratory conditions.....	18
6.4 Changes in rubber technology that have influenced the nature and composition of rubber fumes and improved the protection of workers in the industry.....	19
6.4.1 General.....	19
6.4.2 Overall trend in rubber workers' exposure to total rubber fumes.....	19
6.4.3 Polyaromatic hydrocarbons.....	19
6.4.4 Nitrosamines.....	19
6.4.5 Silane coupling agents and resorcinol steel cord coating agent.....	19
7 Factors affecting the variability of rubber fumes	19
7.1 General.....	19
7.2 Influence of the rubber compound formulation on the composition of rubber fumes.....	20
7.3 Influence of different manufacturing processes on rubber fumes.....	20
7.4 Influence of different processing temperatures on the composition of rubber fumes.....	21
8 Review of literature on the composition and nature of rubber process fumes	22
8.1 Comprehensive literature search.....	22
8.1.1 General.....	22
8.1.2 Rubber fumes data obtained from factory atmospheres.....	22
8.1.3 Rubber fumes data obtained by laboratory studies.....	32
8.1.4 Research on sampling and analysis techniques for rubber fumes.....	36
8.1.5 Influence of rubber additives on the composition of rubber fumes.....	38
8.1.6 Work carried out at Rapra Technology Ltd.....	40
8.2 Other sources of information.....	41
8.2.1 General.....	41
8.2.2 Search strategy for external databases.....	42
8.2.3 Chemical abstracts results.....	42
8.2.4 General POLLUAB and NTSI database results.....	43

8.2.5	Search of industry-relevant publications, government publications and relevant websites.....	43
9	Summary of the finding of the literature review.....	44
10	Conclusions	45
Annex A (informative)	Abbreviated terms	47
Bibliography		49

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 21275:2017](https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017)

<https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*.

ISO/TR 21275:2017

<https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017>

Introduction

Fumes emitted during the rubber manufacturing processes were the topic of many studies. This comprehensive study was undertaken to compile and review published data with respect to rubber fume emissions in the workplace. This review has provided a comprehensive bank of technical data for dissemination and further debate. It has assessed literature regarding the chemical composition of rubber fumes in manufacturing from a comprehensive range of processes. It has been postulated that fume emissions from rubber compound vulcanization can be considered a single chemical entity, cited as posing a carcinogenic risk to human health. Although many studies have tried to characterize rubber fume emissions, there is no known concise study that provides a rational explanation for this conclusion. This study has tested this postulation and provided an insight as to whether it is a sound conclusion.

The aim of this project was to evaluate, on a basis of sound scientific literature, whether it is scientifically robust to consider “rubber fumes” as a homogeneous entity from a chemical point of view and, more importantly, in relation to measurement and control of occupational exposure risk for the rubber industry as a whole.

An extensive literature review aimed at providing a compilation of literature related to rubber fume emissions, this study has concentrated on the chemical compositional aspects of rubber fumes only and not on the toxicological or epidemiological aspects.

In addition, although rubber dust and rubber fumes are being considered by the EU for a potential incorporation in the scope of the Carcinogens Directive, this study has only considered rubber fumes.

This document provides detailed information on the study carried out, the results obtained from the literature reviews and the conclusions drawn from this information.

This document comprises two main parts; the first provides a general overview of the key areas of rubber technology and the second provides an extensive review of in-house and external literature on the composition and nature of rubber process fumes.

Natural rubber (NR) has been known to the civilized world since about 1493 when early European explorers found natives of Haiti playing with balls made from the exudates of a tree called “cau-uchu”. The term “rubber” was coined much later by the English chemist J.B. Priestly for its ability to erase lead pencil marks. The French scientist De La Condamine first introduced NR to Europe in 1736 and published his observations on the material in 1745. Industrial application of rubber only occurred after Charles Goodyear in 1841 discovered the process termed “vulcanization”, which converted the rubber to a more stable and useful material, that paved the way for the growth of the modern industry.

Synthetic rubbers were first produced in Germany in the 1930s, and during the Second World War when the supply of natural rubber was interrupted, methods were developed for the bulk production of synthetic rubbers. Styrene butadiene rubber (SBR) was one of the first synthetic rubbers to be developed and manufactured in high volume in the 1940s, mainly for the production of tyres and in an attempt to match the properties of natural rubber. Since that time, many different synthetic rubbers have been developed to allow the use of rubber in a very wide variety of environments and applications.

Over the years, the importance of rubber to modern life has constantly increased. This is not always immediately apparent because rubber components are often not colourful, eye catching or are used in applications where they are not readily visible. Natural and synthetic rubber compounds are used in a highly diverse range of rubber products which are manufactured throughout the world for various sectors of industry and for a variety of end users, including, but not exclusively, automotive, aerospace, medical/pharmaceutical, defence, commercial, general industrial and others.

Of the sectors where rubber is used, the automotive industry is of particular importance since tyre and tyre products account for approximately 60 % of the synthetic rubber and ~75 % of the natural rubber used today.

[Table 1](#) provides an overview of the diverse range of rubber components made from general manufacturing processes and dipped latex technology. The list of components is by no means exhaustive but helps highlight the diverse areas and products in which rubber is used.

Table 1 — Range of rubber components

Tyres	passenger cars, trucks, racing vehicles, cycles, off-road tyres, inner tubes, curing bladders
Conveyor/ Transmission belting	steel cord conveyor belting, repair material for conveyor belting, scrapers, mining conveyors, V-belts, flat belts, synchronous belts
Industrial hoses	water hoses, high-pressure hoses, welding hoses, hydraulic hoses, spiral hoses, offshore hoses, oil hoses, chemical hoses
Automotive products	coolant hoses, fuel hoses, seals and gaskets, anti-vibration mounts, hydraulic hoses, fuel injectors, timing belts, window and door channelling, transmission and engine components, wiper blades, exhaust hangers
General mouldings/ Sheeting	moulded seals and gaskets, anti-vibration products, floor coverings, sheeting, tube rings, roofing layers, subsoil water sheeting, roller coverings, protection linings, moulded micro-cellular products, composite profiles, rubberized fabric, micro-cellular rubbers/profiles, wire and cable jackets and insulations, glass sealants, pump impellers, roof membranes, pond liners, rail mounts, bridge bearings, military vehicle track pads
Medical/ Pharmaceutical products	surgical gloves, medical tubing, MDI valve gaskets, catheters, dialysis products, surgical implants, prostheses, contraceptives, soothers, baby feeding teats and breast caps, blood transfusion tubing and valves, medical and antistatic sheeting and membranes, masks and respirators
Clothing	boots/footwear, protective suits, household gloves, industrial gloves, footwear/boot heels and soles, cellular rubber soles, wet suits, diving suits, coated fabrics, sports footwear and clothing
Food contact products	food transportation (e.g. conveyor belts, hoses and tubing), food handling (gloves), pipe and machinery components (seals, gaskets, flexible connectors and diaphragm/butterfly valves), pumping system components (progressive cavity pumps, stators, diaphragm pumps), plate heat exchanger gaskets, seals/gaskets for cans, bottles and closures
Potable water products	pipe seals and gaskets, hoses, linings of pumps and valves, tap washers, membranes in pipes and filters, coatings on process plant, tank linings
Miscellaneous products	adhesives, rubberized asphalt, high vacuum and radiation components, carpet backing, latex thread, sealants and caulking, toys

It is important that the reader of this document concludes that the rubber material used to make any particular product is not a single entity but is a complex compounded material referred to as a “compound” or “formulation”, which may contain a large number of essential chemical ingredients. These ingredients will include the base rubber polymer(s), reinforcing and non-reinforcing particulate fillers, process oils, vulcanizing agents, protective agents, process aids, etc. (all of which are available in many types and grades from many suppliers and can be included at different levels). The company or individual who designs a rubber formulation for a specific product has a vast number of ingredients to choose from and as such, many formulations are therefore possible for a specific rubber product.

The processing route by which the majority of rubber components are manufactured includes mixing the ingredients together in a controlled manner to produce a rubber “compound” or “mix”, shaping of the mixed compound to give the desired shape or form, then “vulcanizing” (also known as “crosslinking” and “curing”) the compound to convert it to a condition where it has permanent properties and shape.

The type of rubber materials and manufacturing processes used will depend upon the individual product and are described in this document. Many of the manufacturing processes involve generating heat in the rubber compound where volatile species such as “fumes” can be released from it.

The large diversity in both the rubber formulations available and the manufacturing processes used can therefore potentially give rise to a highly diverse range of species evolved.

In order to assist the reader to understand the terminology associated with the rubber technology in this document, a glossary of terms is included in [Annex A](#).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 21275:2017](#)

<https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017>

Rubber — Comprehensive review of the composition and nature of process fumes in the rubber industry

1 Scope

This document, based on 95 publications, gives an overview of what is the composition of the fumes emitted during the rubber manufacturing processes. The results obtained confirm that rubber fumes are a complex and variable mix of chemicals which have a wide range of possible sources and origins, including chemicals generated from the chemical reactions occurring in the rubber compounds during processing and curing. Some of these chemical substances can be hazardous, others are not. This document demonstrates the need for International Standards to qualify and quantify the hazardous chemicals to which the operators in the factories producing rubber articles can be exposed to, allowing the identification and mitigation of potential health risks.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

accelerator

compounding ingredient used in small amounts with a vulcanizing agent to increase the speed of vulcanization and/or enhance the physical properties of the vulcanizate

[SOURCE: ISO 1382:2012, 2.5]

3.2

activator

compounding ingredient used in small proportions to increase the effectiveness of an accelerator

[SOURCE: ISO 1382:2012, 2.6]

3.3

ageing

<act of> exposure of a material to an environment for a period of time

[SOURCE: ISO 1382:2012, 2.13]

3.4

ageing

<effect of> irreversible change of material properties during exposure to an environment for a period of time

[SOURCE: ISO 1382:2012, 2.14]

**3.5
antidegradant**

compounding ingredient used to retard deterioration by ageing

Note 1 to entry: Antidegradant is a generic term for certain additives such as antioxidants, antiozonants, waxes and other protective materials.

[SOURCE: ISO 1382:2012, 2.21]

**3.6
antioxidant**

compounding ingredient used to retard deterioration caused by oxidation

[SOURCE: ISO 1382:2012, 2.24]

**3.7
autoclave**

pressurized vessel used for vulcanizing rubber in a vapour or gas

[SOURCE: ISO 1382:2012, 2.33]

**3.8
benzene**

C₆ H₆

simplest member of the aromatic series of hydrocarbons

Note 1 to entry: It is colourless liquid with a b.p. of 80 °C and is used in the manufacture of many organic compounds.

**3.9
blank**

piece of rubber compound of suitable shape and volume to fill the mould

[SOURCE: ISO 1382:2012, 2.44]

**3.10
bonding agent**

substance, usually in liquid form, coated onto another material and used to produce a good bond between the material and rubber

[SOURCE: ISO 1382:2012, 2.54, modified — Note 1 to entry has been deleted.]

**3.11
butadiene**

CH₂CHCHCH₂

buta-1,3-diene

gas used in the manufacture of polybutadiene rubber and as one of the copolymers in the manufacture of styrene-butadiene and nitrile rubbers

**3.12
calender**

machine with two or more essentially parallel rolls, operating at selected surface speeds, nips and temperatures, for such operations as sheeting, laminating, skim coating (topping) and friction coating of a product to a controlled thickness and/or controlled surface characteristics

[SOURCE: ISO 1382:2012, 2.65]

3.13**carbon black**

compounding ingredient consisting essentially of more than 95 % elemental carbon in the form of near-spherical particles with major diameters less than 1 µm, generally coalesced into aggregates

Note 1 to entry: Carbon black is produced by incomplete burning or thermal decomposition of hydrocarbons.

[SOURCE: ISO 1382:2012, 2.66]

3.14**chlorohydrin rubbers**

class of synthetic elastomers based on epichlorohydrin

3.15**chloroprene rubber**

CR

elastomeric materials composed of chloroprene

Note 1 to entry: It has fair to good resistance to petroleum-based fluids and good resistance to ozone and weathering.

[SOURCE: ISO 5598:2008, 3.2.96]

3.16**chlorosulfonated polyethylene**

CSPE

elastomer made by substituting chlorine and sulfonyl chloride groups into polyethylene

Note 1 to entry: The material is best known by the trade name Hypalon (DuPont).

3.17**compound**

intimate mixture of a rubber or rubbers or other polymer-forming materials with all the ingredients necessary for the finished product

Note 1 to entry: The term rubber is sometimes used to mean compound, but this use is deprecated.

[SOURCE: ISO 1382:2012, 2.96]

3.18**compounding**

development of rubber compounds which will effectively withstand the conditions under which the products made from them are to be used

Note 1 to entry: The mixes so developed must be capable of being processed in the factory without undue difficulty.

Note 2 to entry: The term is also applied to the assembling of elastomer and compounding ingredients ready for mixing.

3.19**compounding ingredient**

substance added to a rubber or rubber latex to form a mix

[SOURCE: ISO 1382:2012, 2.97]

3.20**compression moulding**

moulding process in which the blank is placed directly in the mould cavity and compressed to shape by closure of the mould

[SOURCE: ISO 1382:2012, 2.98]

3.21

conveyor belting

belting used mainly in the transmission of materials, although increasing use is being made of conveyor belting in the transportation of passengers

3.22

crosslinking

<act of> insertion of crosslinks between or within rubber chains to give a network structure

[SOURCE: ISO 1382:2012, 2.118]

3.23

curing

application of accelerators and temperature for the establishment of chemical crosslinks between macromolecules of rubber

Note 1 to entry: This term is synonymous with vulcanization only in case of mixes containing sulfur. Some other chemicals are also used to establish these crosslink, for example, peroxide.

Note 2 to entry: The word curing is generally paired with a specific method, e.g. press curing, open steam curing, cold curing.

3.24

dispersion

<act of> distribution of one or more ingredients into a rubber, a rubber blend or a continuum material, by the application of shearing forces, in order to confer optimum and uniform properties

[SOURCE: ISO 1382:2012, 2.147]

iteh STANDARD PREVIEW
(standards.iteh.ai)

3.25

double bond

bivalent gap

ethylenic linkage

bond in which two valency bonds link two atoms in a molecule

[ISO/TR 21275:2017](https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017)

<https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017>

Note 1 to entry: It is typical of compounds showing unsaturation, such as ethylene. A double bond does not indicate extra strength of the bond but rather chemical instability and reactivity.

3.26

elastomer

macromolecular material which returns rapidly to approximately its initial dimensions and shape after substantial deformation by a weak stress and release of the stress

[SOURCE: ISO 1382:2012, 2.161]

3.27

extender

organic material used as a replacement for a portion of the rubber required in a compound

[SOURCE: ISO 1382:2012, 2.171]

3.28

extruder

machine which, through the use of a screw or a hydraulic ram, continuously shapes a material by forcing it through a die or dies

[SOURCE: ISO 1382:2012, 2.176]

**3.29
filler**

solid compounding ingredient, in particulate form, which may be added in relatively large proportions to a rubber or rubber latex for technical or economic purposes

[SOURCE: ISO 1382:2012, 2.184]

**3.30
injection moulding**

moulding process in which a rubber compound is forced into a closed mould from a separate chamber, by a pressure which is independent of the mould clamping force

[SOURCE: ISO 1382:2012, 2.242]

**3.31
internal mixer**

machine with temperature controls containing one or more rotors operating in a closed cavity used to masticate and/or to incorporate and disperse compounding ingredients into the rubber

[SOURCE: ISO 1382:2012, 2.242]

**3.32
isoprene**

2-methyl-1,3-butadiene

$\text{CH}_2\text{C}(\text{CH}_3)\text{CHCH}_2$

liquid hydrocarbon with boiling point 34°C

Note 1 to entry: It is regarded as the unit molecule of natural rubber, which is *polyisoprene* (3.43). Synthetic polyisoprene is marketed under a variety of trade names.

**3.33
latex**

colloidal aqueous dispersion of a polymeric material

[SOURCE: ISO 1382:2012, 2.250]

**3.34
mill**

two-roll mill

machine with two counter-rotating rolls, frequently heated or cooled, usually driven at different speeds, and having an adjustable nip for mastication, mixing, blending, warm-up or sheeting

[SOURCE: ISO 1382:2012, 2.274]

**3.35
mix**

mixture of rubber in any form with other compounding ingredients

Note 1 to entry: The term can apply to an incomplete rubber compound.

[SOURCE: ISO 1382:2012, 2.278]

**3.36
mixer**

machine which, through the action of mechanical work (shear), incorporates and disperses compounding ingredients into rubber(s) to form a mix or compound

[SOURCE: ISO 1382:2012, 2.279]

3.37

moulding

<process> process of shaping a material in a mould by applying pressure and, usually, heat

[SOURCE: ISO 1382:2012, 2.288]

3.38

natural rubber

cis-1,4-polyisoprene obtained from the botanical source *Hevea brasiliensis*

[SOURCE: ISO 1382:2012, 2.295]

3.39

nitrile rubber

elastomer resulting from the copolymerization of butadiene and acrylonitrile

3.40

oil resistance

resistance of an elastomer to swelling and ultimate degradation due to contact with or immersion in an oil

3.41

open mill

mill in which the rolls are exposed, in contrast to those of an internal mixer

3.42

plasticizer

compounding ingredient used to enhance the flexibility of a rubber or product, especially at low temperature

[SOURCE: ISO 1382:2012, 2.333]

3.43

polyisoprene

polymerized isoprene

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 21275:2017](https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017)

<https://standards.iteh.ai/catalog/standards/sist/7d0fea83-e0f1-4696-a730-915d26a6b9d5/iso-tr-21275-2017>

Note 1 to entry: Naturally occurring polyisoprene are natural rubber (*cis*-form) and gutta percha (*trans*-form).

Note 2 to entry: The use of stereospecific catalysts has made possible the manufacture of synthetic *cis*-polyisoprene and *trans*-polyisoprene both of which are available commercially.

3.44

polymer

substance composed of molecules characterized by the multiple repetition of one or more species of atoms or groups of atoms (constitutional units) linked to each other in amounts sufficient to provide a set of properties that do not vary markedly with the addition or removal of one or a few of the constitutional units

[SOURCE: ISO 1382:2012, 2.341]

3.45

processing

variety of operations required to convert a raw elastomer into finished products

Note 1 to entry: Processing include calendering, *compounding* (3.18), *curing* (3.23), extrusion, mastication, mixing, spreading.

3.46

resin cure

vulcanization of elastomers effected by the incorporation in the compound of certain polymeric resins derived from the condensation of formaldehyde with 4-alkyl phenols

Note 1 to entry: Most frequently used with butyl and EPDM compounds for enhanced heat resistance.

3.47**retarder**

compounding ingredient used to reduce the tendency of a rubber compound to vulcanize prematurely

[SOURCE: ISO 1382:2012, 2.383]

3.48**rubber**

<products> family of polymeric materials which are flexible and elastic

Note 1 to entry: Rubber can be substantially deformed under stress, but recovers quickly to near its original shape when the stress is removed. It is usually made from a mixture of materials (solid or liquid), and in most products the base polymer is crosslinked by either chemical or physical links.

[SOURCE: ISO 1382:2012, 2.394]

3.49**rubber**

<raw material> natural or synthetic elastic polymer (elastomer) which forms the basis of the compound used in many rubber products

[SOURCE: ISO 1382:2012, 2.395]

3.50**rubber**

<rubber goods manufacturing> synonym for *compound* (the preferred term)

[SOURCE: ISO 1382:2012, 2.396]

3.51**silicone rubber**

polyorganosiloxane, having a backbone structure consisting of alternating silicone and oxygen atoms with organic groups, usually methyl, vinyl or phenyl radicals, attached to the silicone member

Note 1 to entry: It is an elastomer of the silicone family.

3.52**unsaturation**

<organic compounds> linking of some of the atoms of the molecule by more than one valency bond i.e., double or triple bonds

3.53**vulcanization****cure**

process, usually involving heat, in which rubber, through a change in its chemical structure (for example, crosslinking), is converted to a condition in which the elastic properties are conferred or re-established or improved or extended over a greater range of temperatures

Note 1 to entry: In some cases, the process is carried to a point where the substance becomes rigid, e.g. ebonite.

[SOURCE: ISO 1382:2012, 2.513]

3.54**vulcanizing agent****curative****curing agent**

compounding ingredient that produces crosslinking in rubber

[SOURCE: ISO 1382:2012, 2.515]