



SLOVENSKI STANDARD

oSIST prEN ISO 16964:2020

01-januar-2020

Plinske jeklenke - Gibljive cevi in sklopi - Specifikacija in preskušanje (ISO 16964:2019)

Gas cylinders - Flexible hoses assemblies - Specification and testing (ISO 16964:2019)

Gasflaschen - Flexible Schlauchleitungen - Spezifikation und Prüfung (ISO 16964:2019)

Bouteilles à gaz - Flexibles - Spécifications et essais (ISO 16964:2019)

Ta slovenski standard je istoveten z: prEN ISO 16964

ICS:

23.020.35	Plinske jeklenke	Gas cylinders
83.140.40	Gumene cevi	Hoses

oSIST prEN ISO 16964:2020

en,fr,de

INTERNATIONAL STANDARD

**ISO
16964**

Second edition
2019-01

Gas cylinders — Flexible hoses assemblies — Specification and testing

Bouteilles à gaz — Flexibles — Spécifications et essais

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN ISO 16964:2020](https://standards.iteh.ai/catalog/standards/sist/fl ea5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020)

<https://standards.iteh.ai/catalog/standards/sist/fl ea5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020>



Reference number
ISO 16964:2019(E)

© ISO 2019

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN ISO 16964:2020](https://standards.iteh.ai/catalog/standards/sist/fl ea5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020)

<https://standards.iteh.ai/catalog/standards/sist/fl ea5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
4.1 Production pressure tests.....	2
4.1.1 Strength test.....	2
4.1.2 Leak test.....	2
4.2 Type tests.....	2
4.2.1 General.....	2
4.2.2 Burst pressure test (3 samples per type).....	3
4.2.3 Pressure cycle test (3 samples per type).....	3
4.2.4 Oxygen compatibility test (3 samples per type).....	4
4.2.5 Acetylene compatibility test (3 samples).....	4
4.2.6 Gas material compatibility.....	4
4.2.7 Test of the safety cable (2 samples).....	4
4.2.8 Additional tests.....	5
5 Marking	6
Annex A (informative) Examples of kink test, side impact test and torsion test	7
Bibliography	14

Document Preview

[SIST EN ISO 16964:2020](https://standards.iteh.ai/catalog/standards/sist/fl5a5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020)

<https://standards.iteh.ai/catalog/standards/sist/fl5a5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020>

ISO 16964:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 58, *Gas cylinders*, Subcommittee SC 2, *Cylinder fittings*.

This second edition cancels and replaces the first edition (ISO 16964:2015), which has been technically revised.

The main changes compared to the previous edition are as follows:

- Test 1 for the safety cable has been clarified;
- the leak test has been corrected;
- the pressure cycle test has been clarified;
- the test apparatus for the torsion test, as shown in [Figures A.6](#) and [A.7](#) has been clarified.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Flexible hose assemblies are used to transfer industrial and medical gases into cylinders, bundles, MEGCs and trailers (battery vehicles), and also to supply such gases to user equipment.

There is a range of existing International Standards to be used for specific applications or hose construction:

- ISO 14113 which covers hoses made with internal rubber or plastics tubing and used to supply gases to customers for welding applications;
- ISO 21969 which covers hoses with an internal corrugated metallic liner and used to supply medical gases to customers;
- ISO 10380 which covers hoses with internal corrugated metallic liner for all applications including non-industrial and medical gases.

ISO 14113 and ISO 21969 cover only specific customer applications and are intended to be used accordingly, while ISO 10380 is general in its approach.

The intent of the document is to describe flexible hoses not defined in the specific applications documents mentioned above.

itech Standards
(<https://standards.itech.ai>)
Document Preview

[SIST EN ISO 16964:2020](https://standards.itech.ai/catalog/standards/sist/fl ea5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020)

<https://standards.itech.ai/catalog/standards/sist/fl ea5d7b-d0f2-4737-a129-f48d98721efa/sist-en-iso-16964-2020>

Gas cylinders — Flexible hoses assemblies — Specification and testing

1 Scope

This document provides specification and testing requirements for high pressure flexible hose assemblies intended to be connected to gas cylinders, bundles of cylinders or trailers (battery vehicles), and MEGCs for use when filling and emptying gas at production sites and also for customer use. This document applies to flexible hose assemblies with rated pressures up to 1 000 bar for use in the temperature range of $-40\text{ }^{\circ}\text{C}$ to $+65\text{ }^{\circ}\text{C}$.

This document is not applicable to:

- rubber and plastics flexible hose assemblies for welding, cutting and related processes up to 45 MPa (450 bar) for customer use (see ISO 14113);
- high pressure flexible hose assemblies for use with medical gas systems for customer use (see ISO 21969);
- low pressure hose assemblies for use with medical gases for customer use (see ISO 5359);
- rubber and thermoplastic low pressure hose assemblies for welding, cutting and related processes for customer use (see ISO 3821 or ISO 12170);
- flexible hose assemblies for cryogenic applications (see ISO 21012);
- flexible hose assemblies for liquid petroleum gas (LPG).

NOTE Flexible hose assembly designs which pass the type test approval described in this document can have a lower ratio of burst pressure to rated pressure than stated in other standards.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method*

ISO 10286, *Gas cylinders — Terminology*

ISO 10380, *Pipework — Corrugated metal hoses and hose assemblies*

ISO 14113:2013, *Gas welding equipment — Rubber and plastics hose and hose assemblies for use with industrial gases up to 450 bar (45 MPa)*

ISO 21969:2009, *High-pressure flexible connections for use with medical gas systems*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 10286 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>

ISO 16964:2019(E)

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1 rated pressure PR

pressure of a hose assembly equal to 1,25 PW, PW being the working pressure of the cylinder as defined in ISO 10286

Note 1 to entry: National and international design codes for pressure systems can specify a higher value of rated pressure.

Note 2 to entry: When cylinders are used (e.g. during filling or product withdrawal), the gas temperature can be higher than 15 °C. This is the reason why the rated pressure is higher than the cylinder working pressure.

3.2 burst pressure

highest pressure reached in a flexible hose assembly during a burst test

4 Requirements

4.1 Production pressure tests

4.1.1 Strength test

Each flexible hose assembly shall first be subjected to a strength test using oil-free water at a pressure at least equal to 1,5 times the rated pressure, PR, for a minimum of 3 min. There shall be no visible sign of leakage, permanent deformation or other sign of failure. Where hydraulic testing would result in unacceptable contamination of the flexible hose assembly, the hydraulic test may be replaced by a pneumatic test using a compatible medium such as dry oil-free air or nitrogen. Appropriate safety measures shall be taken to protect personnel and equipment during testing.

4.1.2 Leak test

Each hose or hose assembly shall be tested for leakage, e.g. by total immersion in water for 3 min at ambient temperature, at a test pressure equal to the PR, except for acetylene where the test pressure shall be no less than 300 bar.

Hose or hose assemblies to be used with hydrogen or helium shall be tested with helium. Hose or hose assemblies to be used with other gases shall be tested with a compatible medium such as dry oil-free air or nitrogen.

The leak rate shall be less than 15 cm³/h.

4.2 Type tests

4.2.1 General

All test samples shall be manufactured to the same design, material specification and from the same batch of raw material. Records of the tests performed are to be retained by the flexible hose assembly manufacturer.

To carry out the tests described in this document, it is recommended that the nominal length of hose between end fittings be 1 000 mm unless otherwise specified.

Before being type tested, all sample flexible hose assemblies shall be subjected to production pressure tests as specified in [4.1](#).

For hoses to be used in hydrogen or helium service, the leak test in [4.1.2](#) shall be carried out using helium.