INTERNATIONAL STANDARD

Second edition 2017-03

Plain bearings — Testing of bearing metals — Resistance to corrosion by lubricants under static conditions

Paliers lisses — Essai des matériaux antifriction — Résistance à la corrosion par des lubrifiants dans des conditions statiques

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 10129:2017</u> https://standards.iteh.ai/catalog/standards/sist/c13100c3-1cf9-4d63-a701d95230f13d5d/iso-10129-2017



Reference number ISO 10129:2017(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 10129:2017</u> https://standards.iteh.ai/catalog/standards/sist/c13100c3-1cf9-4d63-a701d95230f13d5d/iso-10129-2017



© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Page

Contents

Forew	ord		v
Introd	uction		v
1	Scope		1
2	Normative references		1
3	Terms and definitions		1
4	Health	and safety	1
5	Genera	al principles	1
6	Lubricants		2
7	Apparatus		2
8	Preparation of test samples		2
9	Test p	rocedure	3
10	Fynre	ssion of results	3
10	10.1	Mass change	3
	10.1	Changes in dimensions	3
	10.2	Surface changes	3
	10.4	Microstructural changes	4
	10.5	Type and nature of the corresion products PFVIFW	4
	10.6	Change of lubricant	4
	T .	(standards.iteh.ai)	Ì
11	Test re	eport (Scancar association)	4
Biblio	graphy	T&D 1013000	5
·	/	<u>IJU 10127.2017</u> https://standards.itah.ai/astalag/standards/sizt/a12100a2_1af0_4d62_a701	
		nups//statikiarus.iteri.a/catalog/statikiarus/stst/c15100c5-1019-4005-a/01-	

d95230f13d5d/iso-10129-2017

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants, their properties, characteristics, test methods and testing conditions*. https://standards.iteh.a/catalog/standards/sist/c13100c3-1c19-4d63-a/01-

This second edition cancels and replaces the first edition (ISO910129:2006), which has been technically revised.

Introduction

It is essential that certain properties of bearing materials combined within the tribological system remain unchanged or change only within a permissible range over a long period of time. It is on account of these properties that the materials are regarded as being especially suitable for the tribological system. As to the tribological system "plain bearing", the compatibility between the bearing materials and lubricant is of special interest and is dependent on chemical and mechanical actions.

The test established in this document determines the behaviour of plain bearing materials with respect to corrosion by lubricants (lubricating oils) under static conditions, i.e. without any mechanical action taking place simultaneously.

In order for such corrosion tests to be evaluated and compared, it is necessary that they be carried out in accordance with the conditions laid down in this document. Other conditions are to be indicated in detail.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 10129:2017</u> https://standards.iteh.ai/catalog/standards/sist/c13100c3-1cf9-4d63-a701d95230f13d5d/iso-10129-2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 10129:2017</u> https://standards.iteh.ai/catalog/standards/sist/c13100c3-1cf9-4d63-a701d95230f13d5d/iso-10129-2017

Plain bearings — Testing of bearing metals — Resistance to corrosion by lubricants under static conditions

1 Scope

This document establishes a test of the corrosion-resistance of bearing materials to lubricants. It also specifies the most important general principles for carrying out such corrosion testing.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

(standards.iten.ai)

- ISO Online browsing platform: available at http://www.iso.org/obp
- IEC Electropedia: available at <u>http://www.electropedia.org/</u>

3.1

corrosion

reaction of a bearing material to its environment causing a measurable change in the material and which can result in corrosion damage_{5230f13d5d/iso-10129-2017}

Note 1 to entry: In most cases, this reaction is of a chemical nature. It can, however, also involve chemical or mechanical processes. Material changes solely caused by or found only in combination with mechanical influences are not dealt with in this document. For a detailed explanation of the various causes of damage to plain bearings, see ISO 7146-1.

4 Health and safety

Resources, test pieces, test materials, test equipment and test procedures shall comply with the current health and safety regulations/laws of the country in which the test is carried out. Where equipment, materials and/or reagents that may be hazardous to health are specified, appropriate precautions in conformity with local regulations/laws shall be taken.

5 General principles

5.1 In general, corrosion tests are carried out as comparison tests, i.e. several materials and lubricants are compared with one another. However, it is also possible to include already known behaviour in the test reference materials or reference lubricants.

5.2 The duration of the test shall be chosen, and, if necessary, extended, so that at the end of the test, definite information on the corrosion behaviour of the material tested and, possibly, of the reference material can be obtained under the specified test conditions.

A value for a single material test is less informative, owing to a greater dispersion of the results, 5.3 which often occurs when determining an increase or decrease in mass.

Therefore, each result shall be given as a mean value from at least three tests.

6 Lubricants

The quantity of lubricant used shall be at least 10 ml/cm² of bearing material surface.

Specifications indicating the type and performance level of the oils are used to characterize the lubricants used for the tests.

However, in order to be able to draw conclusions concerning, for example, the additives used and their effect, it is recommended that the precise chemical and physical data be given, as follows:

- density at 15 °C, in grams per millilitre;
- flash point, in degree Celsius;
- neutralization value;
- saponification value;
- base number;
- kinematic viscosity at 40 °C, in square millimetres per second. IEW **DIA**
- kinematic viscosity at 100 °C, in square millimetres per second; (Standards.iten.ai)
- sulfate ash yield, as a percentage by mass;
 - ISO 10129:2017
- zinc content, as a percentage by mass; https://standards.iten.ai/catalog/standards/sist/c13100c3-1cf9-4d63-a701-
- phosphorus content, as a percentage by mass;
- barium content, as a percentage by mass;
- calcium content, as a percentage by mass;
- content of sulfur in corrosive forms, as a percentage by mass.

Apparatus 7

Beaker(s), of sufficient capacity to allow each test sample to be fully immersed. 7.1

Heating bath, preferably an oil bath, capable of maintaining the required temperature to 7.2 within ±2 °C.

The heating bath shall be large enough to allow the beaker to be immersed up to three quarters of its height to prevent overspill of heating bath fluid into the test beaker.

Preparation of test samples 8

8.1 The preferred test sample shall be a complete bearing. Where this is not possible, a test sample of bearing material shall be cut out from parts sufficiently large that any influences of strong mechanical cold-working and of high temperature rise at the edges of the cut are eliminated. Burrs shall be removed. **8.2** The surface of the bearing material shall not be less than 25 cm^2 in order to eliminate as far as possible the influence of irregularities. If one bearing surface area is less than 25 cm^2 , consider using more than one in the test vessel and combine the result.

8.3 The surface condition of test samples during the tests shall agree as far as possible with the surface condition of the bearing material in practice. The test sample shall be thoroughly cleaned and degreased. Suitable organic solvents (e.g. white spirit or methanol) should be used.

8.4 Test samples shall be clearly identified or could be marked. Marking methods which harm the mechanical strength of the bearing (e.g. electromechanical methods) shall be avoided.

9 Test procedure

Perform the following test procedure before testing.

- a) Record the mass, dimensions and roughness of the test samples.
- b) Place the bearing material test samples in the beakers (7.1) in such a way that they are completely covered by the lubricant in order to avoid the influence at the phase limit air/lubricant. Protect the beakers against dirt by means of a cover.
- c) In principle, test only samples of the same bearing material in one beaker in order to avoid any interaction. The atmosphere should be free from any substance which could interfere with the test.
- d) During the test, maintain the beakers at the specified test temperature to within ±2 °C. Recommended test temperatures are 80 °C, 100 °C, 120 °C, 150 °C and 180 °C.

The duration of the test shall be 20 days at least; it may be extended if necessary (see 5.2). Intermediate assessments shall be made after one week and after two weeks. Test temperatures and test times should be chosen to reflect operating conditions in the intended bearing application.

e) For the purpose of the intermediate and final assessments, clean the test samples by spraying using an appropriate solvent as one of the means. Dry them in a hot-air cabinet until a constant mass is attained. Record the mass, dimensions and roughness.

10 Expression of results

10.1 Mass change

Data concerning the mass changes of the samples are only really informative when the surface of the test samples is uniformly attacked.

The mass change of the samples (mass loss or increase in mass) shall be given as the mean value from at least three samples.

10.2 Changes in dimensions

Data concerning the dimensional changes of the samples are only really informative when the surface of the test samples is uniformly attacked.

The dimensional change of the samples (decrease or increase in dimensions) shall be given as the mean value from at least three samples.

10.3 Surface changes

During the intermediate and final assessments, check the surfaces of the test samples with regard to the frequency, extension and distribution of single corrosion points, as well as discolouration.