



Designation: D4707 – 09

Standard Test Method for Measuring Paint Spatter Resistance During Roller Application¹

This standard is issued under the fixed designation D4707; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the tendency of a paint to spatter when applied with a paint roller to a substrate.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D3924 Specification for Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials

D3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings

2.2 *Other Document:*

Pictorial Standards of Paint Roller Spatter³

3. Summary of Test Method

3.1 The test paint is applied to a black plastic panel by draw-down. The coated plastic panel is immediately mounted on an essentially vertical surface above a sheet of paper used to catch any spatter. A specially designed notched spool roller (see 5.1) is rolled through the film following a defined procedure, tending to generate spatter. Any spatter falls upon the spatter catch paper and, after drying, is rated against the pictorial standards.

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.42 on Architectural Coatings.

Current edition approved June 1, 2009. Published July 2009. Originally approved in 1987. Last previous edition approved in 2003 as D4707 - 97 (2003)¹. DOI: 10.1520/D4707-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Copies of the pictorial photographic reference standards are contained in *Pictorial Standards of Coatings Defects* and may be obtained from the Federation of Societies For Coatings Technology, 492 Norristown Rd., Blue Bell, PA 19422.

4. Significance and Use

4.1 Paint spatter generated by roller application is dependent on the properties of both the paint being applied and the paint roller cover used for the application. To eliminate the influence of the paint roller cover as a variable, and thus restrict the spatter-inducing variable to the paint under test only, the paint roller cover is replaced by a standard notched spool roller to generate spatter by a mechanism that simulates that of a paint-applying roller cover.

4.2 Although most of the development work to establish this test method was undertaken using latex paints, sufficient work was also done to show its applicability to solvent-reducible paints.

4.3 Tests during the development of this test method showed that the spattering properties of paints, like other physical properties, may in time change. Therefore, the results of this test are valid only for the time when the test is run.

5. Apparatus

5.1 *Notched Spool Test Roller* (Fig. 1).^{4,5}

5.2 *Glass Plate*—at least 230 by 485 mm (9 by 19 in.) by 6 mm (0.25 in.) thick.

5.3 *U-shaped Film Caster*,^{6,5} having a 175- μ m (7-mil) clearance by 135 mm (5.25 in.) wide.

5.4 *Metronome*, adjusted to 80 beats per min.

6. Materials

6.1 *Black Plastic Panels*,^{7,5} 165 by 430 mm (6.5 by 17 in.).


6.2 *Flannel Cloth*.

⁴ The sole source of supply for the notched spool test roller known to the committee at this time is Precision Gage and Tool Co., 28 Volkenand Ave., Dayton, OH 45410.

⁵ If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁶ The sole source of supply for the Dow film caster known to the committee at this time is BYK-Gardner, Inc., Gardner Laboratory, 2435 Linden Lane, Silver Spring, MD 20910.

⁷ The sole source of supply for the dull black plastic panels, Leneta P-121-10N, 6½ by 17 in. by 10 mil (production tolerance ± 1 mil) (165 by 430 by 250 μ m) in size known to the committee at this time is Leneta Company, 15 Whitney Rd., Mahwah, NJ 07430.



Dimensions

		in.	mm
A	Flange thickness	0.063 ± 0.005	1.60 ± 0.13
B	Space between flanges	0.343 ± 0.005	8.71 ± 0.13
C	Total diameter	1.600 ± 0.015	40.16 ± 0.38
D	Diameter under notches	1.400 ± 0.015	35.56 ± 0.38
E	Hole diameter	0.281 ± 0.005	7.14 ± 0.13

FIG. 1 Notched Spool Roller

6.3 Masking Tape, 25 mm (1 in.) wide.

6.4 Spatter Catch Paper, minimum size 190 by 240 mm (7.5 by 9.5 in.). This paper can be any convenient paper to which the spatter droplets will adhere and of a color to contrast that of the paint under test.

7. Sampling and Conditioning

7.1 Sample the material in accordance with Practice D3925.

7.2 Prior to testing, the samples shall be conditioned in accordance with the standard atmosphere described in Specification D3924. The testing shall take place under the same conditions.

8. Procedure

8.1 Clean the top of the glass plate and both sides of the black plastic panel to ensure that they are free of specks. Place the black plastic panel on the glass plate and tape the narrow end at the top to the glass plate. Smooth the panel along the plate to ensure a close fit.

8.2 Stir the paint under test thoroughly and strain to remove all skins and particles. Place the film caster with the 175-µm (7.0-mil) side down immediately below the taped portion of the black plastic panel. Turn on the metronome. Into the well formed by the film caster, pour sufficient paint that the well is filled from corner to corner. Draw down the paint the full

length of the black plastic panel until the film caster is fully beyond the far edge. The rate of application should be fairly slow, 3 to 4 seconds from end to end, to prevent pinholes or holidays in the paint film.

8.3 Immediately upon completion of the draw-down, remove the black plastic panel from the glass plate, keeping the masking tape intact, and tape, with the long direction vertical to a surface that is vertical or nearly vertical (within 5° of vertical, top sloping away from the operator) with the bottom of the black plastic panel about 25 mm (1 in.) above the laboratory bench or table (Fig. 2). It is desirable that the surface under the black plastic panel be firm but with a little resilience. A backing of 6-mm (¼-in.) thick fiberboard is ideal as very hard surfaces make proper performance of the test difficult. Center the spatter catch paper on the laboratory bench or table under the black plastic panel with the short side of the catch paper closest to the black plastic panel.

8.4 Using the clean, notched spool roller, start in one of the upper corners and roll downward and upward through the paint film. Always keep the notched spool in contact with the black plastic panel, not removing the roller from the film when changing directions. Make ten passes in each direction (20 passes total), 380 ± 15 mm (15 ± ½ in.) per pass, progressively moving sideways from one edge of the film to the other (Fig. 3). Each pass should coincide with a beat of the





FIG. 2 Test Set-Up Schematic



Dimensions		
	in.	mm
A Notched spool pass length	15 ± 1/2	380 ± 15
B Drawdown width (determined by blade)	5 1/4	140
C Panel width	6 1/2	165
D Panel length	17	430

FIG. 3 Test Pattern Schematic

metronome and the motion should be continuous, not jerky. Use the metronome for accurate timing since the speed of the rolling of the notched spool roller through the paint film has been found to be the only variable significantly affecting the results of the test. Make sure that all four flanges of the notched spool roller are within the draw-down area at all times. Use sufficient pressure to maintain constant contact between the notched spool roller and the black plastic panel. Note that as long as constant contact is maintained, pressure variations have not been found to affect the results noticeably.

8.5 Remove the spatter catch paper and lay it in a suitable place to dry.

8.6 Repeat the test with a second plastic panel after cleaning the apparatus.

9. Grading Procedure

9.1 Carefully cut an area 190 by 240 mm (7.5 by 9.5 in.) out of the front edge (edge nearest the paint) of the spatter catch paper. The shorter side will be the front edge. Center the area with respect to the spatter so a maximum of spatter is on this sheet (Fig. 4).

9.2 Compare the cut-out area to the pictorial standards. Assign the rating that most closely matches a standard, interpolating as needed for ratings (0—poor spatter resistance, 2, 4, 6, 8, and 10—no spatter).

NOTE 1—Figs. 5-9 are duplications thereof for sample purposes and are not meant to be used for test grading purposes.

FRONT (Edge nearest to the mounted panel during test.)




FIG. 4 Cutting Out Section of Spatter Catch paper for Evaluation

9.3 In rating the paints using the photographic standards, consider the population of spatter droplets of greater importance than the average size of the spatter droplets.

9.4 If the ratings of two tests do not agree within 1 unit, repeat until such precision is obtained.



FIG. 5 Paint Spatter Resistance to Roller Application Rating Standard No. 1