



Standard Test Method for Measurement of Coating Mass Per Unit Area on Anodically Coated Aluminum¹

This standard is issued under the fixed designation B 137; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers determination of the mass per unit area of coating on anodically coated aluminum and its alloys.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 1193 [Specification for Reagent Water](#)

3. Significance and Use

3.1 This test method is a destructive test procedure suitable for quality control within manufacturing operations for coating mass on anodically coated aluminum and aluminum alloys. The mass of the coating is an approximation of its thickness provided the conditions under which the coating was applied, or the density of the coating, are known. An anodic coating's protective value and amenability to coloring by dyeing or electrolytic methods are related to mass of coating per unit area.

4. Reagents

4.1 The test solution shall have the following makeup:

Chromic acid anhydride (CrO_3)	20 \pm 0.5 g
Orthophosphoric acid of 85 mass %, density 1.69	35 \pm 0.5 mL
Distilled or deionized water conforming with Type III Reagent Water of Specification D 1193, to make up to	1000 mL

NOTE 1—This solution is commonly referred to as a nondestructive “stripping solution” for anodic coatings. This solution dissolves the anodic coating with no significant attack of the substrate metal.

5. Test Specimen

5.1 Prepare a test specimen of known surface area, preferably a piece about 75 mm square. If the anodic coating is contaminated or impregnated with oil, grease, lacquer, etc., remove as much as possible of this material before determining the mass of the coating. It is not usually practicable to remove these materials from the pores of the coating, but surface films can frequently be removed by wiping the sample with a cloth wet with a suitable solvent.

5.2 In cases where it is required to measure the mass of coating on only one side of a specimen where both sides have anodic coatings, the following procedure may be used:

5.2.1 Prepare a specimen somewhat larger than required for 5.1.

5.2.2 Apply a suitable stop off around the edges of the specimen so that the area on the side of the specimen that is not to be

¹ This test method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.07 on Chromate Conversion Coatings.

Current edition approved Oct. 1, 2004; April 15, 2009. Published October 2004; July 2009. Originally approved in 1940. Last previous edition approved in 2000 as B 137 – 95 (2000).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.