



Designation: D1074 – 09

# Standard Test Method for Compressive Strength of Bituminous Mixtures<sup>1</sup>

This standard is issued under the fixed designation D1074; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope

1.1 This test method provides a method for measuring the compressive strength of compacted bituminous mixtures. It is for use with specimens weighed, batched, mixed, and fabricated in the laboratory, as well as for mixtures manufactured in a hot-mix plant.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[C136 Test Method for Sieve Analysis of Fine and Coarse Aggregates](#)

[C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)

[C702 Practice for Reducing Samples of Aggregate to Testing Size](#)

[D75 Practice for Sampling Aggregates](#)

[D140 Practice for Sampling Bituminous Materials](#)

[D979 Practice for Sampling Bituminous Paving Mixtures](#)

[D1075 Test Method for Effect of Water on Compressive Strength of Compacted Bituminous Mixtures](#)

[D2041 Test Method for Theoretical Maximum Specific Gravity and Density of Bituminous Paving Mixtures](#)

[D2726 Test Method for Bulk Specific Gravity and Density of Non-Absorptive Compacted Bituminous Mixtures](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.22 on Effect of Water and Other Elements on Asphalt Coated Aggregates.

Current edition approved July 1, 2009. Published August 2009. Originally approved in 1949. Last previous edition approved in 2002 as D1074 – 02. DOI: 10.1520/D1074-09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D3203 Test Method for Percent Air Voids in Compacted Dense and Open Bituminous Paving Mixtures](#)

[D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials](#)

[D4753 Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing](#)

[E4 Practices for Force Verification of Testing Machines](#)

[E2251 Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids](#)

2.2 *Federal Specification:*

[Standard Specifications for Construction of Roads and Bridges on Federal Highway Projects](#)<sup>3</sup>

## 3. Significance and Use

3.1 The compressive strength of specimens prepared and tested by this test method along with density and voids properties are used for laboratory mix design of bituminous mixtures. One approach is described in ASTM STP 252.<sup>4</sup>

3.1.1 This test method also describes the methods for molding, curing, and testing of specimens being evaluated by Test Method D1075.

3.1.2 When used in conjunction with other mixture physical properties, the compressive strength may contribute to the overall mixture characterization and is one factor determining its suitability for use under given loading conditions and environment as a highway paving material.

3.2 Typical values of minimum compressive strengths for design of bituminous mixtures by this test method for different traffic densities are given in Table 401-1 of the "Standard Specifications for Construction of Roads and Bridges on Federal Highway Projects."<sup>3</sup> Some state departments of transportation and federal agencies have specific requirements of their own based on their experience with this test method. The agencies should be consulted for their specific requirements if work is to meet their standards.

3.3 Reheated mixtures are permissible in this test method, but the resulting compressive strengths will be higher than for

<sup>3</sup> "Asphaltic Concrete Mix Requirements," *Standard Specifications for Construction of Roads and Bridges on Federal Highway Projects*, 1996, Federal Highway Administration, Washington, DC 20590, p. 233.

<sup>4</sup> Goode, J. F., "Use of the Immersion-Compression Test in Evaluating and Designing Paving Mixtures," *ASTM STP 252*, 1959, pp. 113–129.

newly prepared mixtures due to the change in the binder viscosity, an element of the compressive strength as measured under these loading conditions and temperature.<sup>5</sup>

NOTE 1—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Standard Practice D3666 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with D3666 alone does not completely assure reliable results. Reliable results depend on many factors; following the suggestions of D3666 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

#### 4. Apparatus

4.1 *Molds and Plungers*—The molds and plungers shall be in accordance with the following:

4.1.1 *Diameter Tolerances*—The mold shall have sufficient height to allow fabrication of a 4 by 4 in. (101.6 by 101.6 mm) specimen. It shall have an inside diameter of 4.000 to 4.005 in. (101.60 to 101.73 mm) and a nominal thickness of ¼ in. (6.4 mm).

4.1.2 The plungers shall pass through the mold freely and shall have a diameter within 0.050 in. (1.27 mm) of the mold inside diameter. The plungers may be solid, hollow, or other structure so long as the ends are at least 0.50 in. (12.7 mm) thick and are at a right angle to the mold wall. The bottom plunger shall be  $2 \pm \frac{1}{8}$  in. ( $50 \pm 4$  mm) high but the top plunger may be any suitable height.

4.1.3 *Specimens Other than 4 by 4 in. (101.6 by 101.6 mm)*—Molds and plungers for fabricating these size specimens are allowed in accordance with Section 6.

4.2 *Supports*—Temporary supports for specimen molds shall consist of two steel bars,  $1 \pm \frac{1}{8}$  in. ( $25.4 \pm 3.1$  mm) square and a minimum length of 3 in. (76.2 mm).

4.3 *Testing Machine*—The testing machine must be of any type of sufficient capacity that will provide a range of accurately controllable rates of vertical deformation. Since the rate of vertical deformation for the compression test is specified as 0.05 in./min-in. (0.05 mm/min-mm) of specimen height, and it may be necessary to test specimens ranging in size from 2 by 2 in. (50.8 by 50.8 mm) to perhaps 8 by 8 in. (203.2 by 203.2 mm) in order to maintain the specified minimum ratio of specimen diameter to particle size, the testing machine should have a range of controlled speeds covering at least 0.1 in. (2.5 mm)/min for 2-in. (50.8-mm) specimens to 0.4 in. (10.2 mm)/min for 8-in. (203.2-mm) specimens. The testing machine shall conform to the requirements of Practice E4. The testing machine shall be equipped with two steel bearing blocks with hardened faces, one of which is spherically seated and the other plain. The spherically seated block shall be mounted to bear on the upper surface of the test specimen and the plain block shall rest on the platen of the testing machine to form a seat for the specimen. The bearing faces of the plates shall have a diameter slightly greater than that of the largest specimens to be tested.

The bearing faces, when new, shall not depart from a true plane by more than 0.0005 in. (0.0127 mm) at any point and shall be maintained within a permissible variation limit of 0.001 in. (0.025 mm). In the spherically seated block, the center of the sphere shall coincide with the center of the bearing face. The movable portion of this block shall be held closely in the spherical seat, but the design shall be such that the bearing face can be rotated freely and tilted through small angles in any direction.

4.4 *Oven*—The oven used in the preparation of materials or reheating of mixtures shall be controllable within  $\pm 5^\circ\text{F}$  ( $\pm 3^\circ\text{C}$ ) of any specified temperature above ambient up to 392°F (200°C).

4.5 *Hot Plate*—A small hot plate equipped with a rheostat shall be provided for supplying sufficient heat under the mixing bowl to maintain the aggregate and bituminous material at the desired temperature during mixing.

4.6 *Hot Water Bath or Oven*—A water bath or oven sufficiently large to hold three sets of 4-in. (101.6-mm) molds and plungers. If the water bath does not have an internal temperature control, a hot plate of sufficient capacity with a control to maintain the water bath at a temperature just under the boiling point will be required. The oven shall be capable of maintaining a temperature of between 200 to 275°F (93.3 to 135°C).

4.7 *Air Bath*—The air bath shall be capable of either manual or automatic control for storing the specimens at  $77 \pm 1.8^\circ\text{F}$  ( $25 \pm 0.5^\circ\text{C}$ ) immediately prior to making the compression test.

4.8 *Balance*—Balances or scales and weights meeting the requirements of Specification D4753 shall be provided as appropriate for the sample or ingredient mass.

4.9 *Mixing Machine*—Mechanical mixing is preferable over hand-mixing. Any type of mixer may be used, provided it can be maintained at the required mixing temperature and will produce a well-coated, homogeneous mixture of the required size in two minutes or less, and further provided that it is of such design that fouling of the blades will be minimized and each individual batch can be retrieved in essentially its entirety including asphalt and fines. Hand-mixing is allowable, if necessary, but for hot mixtures the time required to obtain satisfactory coating is often excessive and generally the test results are less uniform than when machine mixing is employed.

4.10 *Spatulas*—A flexible spatula for scraping the mixing bowl and a stiff spatula for spading the specimen in the mold.

4.11 *Thermometers*—Calibrated liquid-in-glass thermometers of suitable range with a readability of 1°F (0.5°C) conform to the requirements of specification E2251 shall be used. (Thermometer ASTM No. S63F-03 or S63C-03, or equivalent). Alternately, another electronic thermometer may be used, for example resistance thermometer (RTD, PRT, IPRT) of equal or better accuracy.

#### 5. Preparation of Test Mixtures

5.1 Limit the size of the individual batches to the amount required for one test specimen.

<sup>5</sup> Welborn, J. Y., Halstead, W. J., and Olsen, R. E., "Relation of Absolute Viscosity of Asphalt Binders to Stability of Asphalt Mixtures," *Public Roads*, Vol. 32, No. 6, February 1963, FHWA, Washington, DC. (Also "Symposium on Fundamental Viscosity of Bituminous Materials" *ASTM STP No. 328*.)